ΝΟΤΙΟΕ

THIS DOCUMENT HAS BEEN REPRODUCED FROM MICROFICHE. ALTHOUGH IT IS RECOGNIZED THAT CERTAIN PORTIONS ARE ILLEGIBLE, IT IS BEING RELEASED IN THE INTEREST OF MAKING AVAILABLE AS MUCH INFORMATION AS POSSIBLE

This microfiche was produced according to **ANSI / AIIM Standards** and meets the quality specifications contained therein. A poor blowback image is the result of the characteristics of the original document.

P-14

NASA CASE NO. <u>MFS-28832-1</u> PRINT FIG. <u>#1</u>

NOTICE

The invention disclosed in this document resulted from research in aeronautical and space activities performed under programs of the National Aeronautics and Space Aoministration. The invention is owned by NASA and is, therefore, available for licensing in accordance with the NASA Patent Licensing Regulation (14 Code of Federal Regulations 1245.2).

To encourage commercial utilization of NASA-owned inventions, it is NASA policy to grant licenses to commercial concerns. Although NASA encourages nonexclusive licensing to promote competition and achieve the widest possible utilization, NASA will consider the granting of a limited exclusive license, pursuant to the NASA Patent Licensing Regulations, when such a license will provide the necessary incentive to the licensee to achieve early practical application of the invention.

Address inquiries and all applications for license for this invention to NASA/Marshall Space Flight Center, Patent Counsel, Mail Code CCO1, Marshall Space Flight Center, AL 35812. Approved NASA forms for application for nonexclusive or exclusive license are available from the above address.

Serial Number 08/158,331 FiJing Date November 29, 1993 NASA/MSFC (NASA-Case-MFS-28832-1) CHAMBER N94-29380 FREE FUSION WELDING ROOT SIDE PURGING METHOD AND APPARATUS Patent Application (NASA, Marshall Space Unclas Flight Center) 14 p

G3/26 0003650

CHAMBER FREE FUSION WELDING ROOT SIDE PURGING METHOD AND APPARATUS

The need for lighter and/or stronger materials has increased, particularly with regard to aerospace constructions, the interest in and the use of titanium and its alloys, likewise, has been increased. Although titanium and titanium alloy work pieces have the desired and needed characteristics of exceptional tensile strength and heat resistance, said work pieces are susceptible to atmospheric contamination during welding. Accordingly, in joining said work pieces by welding, it is generally necessary to weld the work pieces in a rigid chamber which has been purged of ambient air through use of inert gas. Use of the chamber requires enormous waste of time and waste of the purging inert gas used.

The instant invention permits the welding in an inert gas environment of work pieces of metal and metal alloys which are susceptible to atmospheric contamination during welding, without the use of either a rigid chamber or of shielding, inexpensively, quickly, and without the use of any undue loss of the inert gas used in the welding environment, either for purging or for welding.

FIGURE 1 is a side elevational view, in simplified pictorial and schematic form, partially fragmental of an embodiment of the invention showing inert gas being drawn to a weld seam by a plasma arc plume;

FIGURE 2 is a side elevational view in simplified form, and enlarged and not to scale, of a section of a porous metallic tubing which is shown in FIGURE 1 as a means for supplying an inert gas blanket to the weld seam;

FIGURE 3 is a perspective view of another embodiment of the invention, an open

view inert gas purging apparatus formed of porous metallic plates which provide an inert gas blanket in the weld seam zone.

ş

Inventors: William F. McGee and Daniel J. Rybicki

Application Serial No.: 08/158,331

:

Date Filed: November 29, 1993

- A CONTRACTOR OF A CONTRACTOR OF

.

Employer: Martin Marietta Manned Space Systems

MFS-28832

A second s

PATENT APPLICATION

5

19

15

CFAMBER FREE FUSION WELDING ROOT SIDE PURGING METHOD ANI APPARATUS

ORIGIN OF THE INVENTION

The invention described herein was made in the performance of work under a NASA contract and is subject to the provisions of Section 305 of the National Aeronautics and Space Act of 1958, Public Law 85-568 (72 Stat. 435, 42 U.S.C. 2457).

BACKGROUND OF THE INVENTION

FIELD OF THE INVENTION

20

The present invention relates to a chamber free gas purge method and apparatus for establishing an inert atmosphere zone at the root side of a weld seam. In another aspect, the invention relates to the concept of strategically providing an inert atmosphere to the root side of a weld joint through a porous medium whereby the jet-like thrust of a plasma arc draws the continuously supplied inert atmosphere into the path of the molten or high temperature solid weld zone. In yet another aspect, the invention relates to a chamber free provision of an inert atmosphere on the root side of a fusion welding which permits open view of the welding seam.

25

Ň

DESCRIPTION OF RELATED ART

Fusion welding of oxygen reactive materials such as aluminum-lichtum alloys, titanium and the like, requires that the molten weld zone and the local solid areas at high temperatures be shielded from the normal atmosphere or oxygen to prevent degradation of the welded area so as to avoid producing weld discontinuities and other potential defects. Full penetration welding of these reactive materials with a plasma arc welding process, in the "keyhole mode", requires that the root side of the joint be shielded with relative precision due to the additional implications brought on by the plasma arc thru ting to the root side of the weld seam. Most current root side welding methods involve encasing a section of or the entire length of the root side weld seam in a chamber which is purged with inert gas until the atmosphere contained within is relatively free of oxygen. These chambers may be fixed to the weld tooling or may be mobile and travel synchronously with the welding arc.

15 As the need for lighter and/or stronger materials has increased, particularly with regard to aerospace constructions, the interest in and the use of titanium and its alloys, likewise, has been increased. Although titanium and titanium alloy work pieces have the desired and needed characteristics of exceptional tensile strength and heat resistance, said work pieces are susceptible to atmospheric contamination during welding. Accordingly, in joining said work pieces by welding, it is generally necessary to weld the work pieces in a rigid chamber which has been purged of ambient air through use of inert gas. Use of the chamber requires enormous waste of time and waste of the purging inert gas used.

The above-described root side purging chamber utilization has further undesired aspects. The atmosphere contained within the chamber must be monitored for pressure and for oxygen content. The chambers, depending upon the configuration, will restrict viewing of the root side of the welding operation partially or fully, unless a fully transparent chamber is utilized. Viewing the root side of the plasma arc weld during full penetration is generally considered to be the best method of monitoring arc to seam alignment and penetration characteristics. The inert gas consumption requirement of these chambers is relatively large dus to requirements of maintaining a low oxygen level.

1

5

20

Several approaches have been utilized to modify the burden of the welding chamber such as by an inflatable, inert gas purged welding chamber assembly. The welding chamber of the assembly is defined by a collapsible, reusable inflatable member. In another approach, a purge gas unit establishes an enclosed zone for purge gas within tubes or pipes having portions which are to be joined by welding. The purge gas unit includes a first bladder positioned on one side of the welding location and a second bladder positioned on the other side of the location.

It is, therefore, readily apparent that what is needed in the art, and is not currently available, is an apparatus and method which eliminate the aforementioned disadvantages and which also permit the uncontaminated welding of titanium, titanium alloys, aluminum-lithium alloys and the like, and other work pieces of other metals and metal alloys which are reactive base materials in the presence of oxygen.

SUMMARY OF THE INVENTION

The instant invention permits the welding in an inert gas environment of work pieces of metal and metal alloys which are susceptible to atmospheric contamination during welding, without the use of either a rigid chamber or of shielding, inexpensively, quickly, and without the use of any undue loss of the inert gas used in the welding environment, either for purging or for welding.

These benefits can be achieved by the present invention which involves the concept of strategically providing an inert atmosphere to the root side of a weld joint through a porous 10 medium whereby the jet-like thrust of the plasma arc actually draws the continuously supplied inert atmosphere into the path of the molten or high temperature solid weld zone. Two mechanisms in accordance with the invention which share a common methodology are discussed under the appropriate terminology of sparge tube purging and open view purging. The sparge 15 tube purging mechanism and the open view purging device both utilize a porous medium through which inert gas is channeled. The porous medium is configured so it can be placed at the borders of the weld seam and parallel to the weld seam without restricting the view of the root side of the seam. The inert gas is dispersed evenly through the porous medium and across the weld seam at the point of arc penetration and in front of and behind the arc. The jet-like thrust 20 of the plasma arc creates a drawing action upon the inert gas and continuously provides an oxygen-free atmosphere to the molten and/or high temperature weld metal. With an adequate and continuous gas flow, the plasma arc can only draw in the inert blanket gases to form a true

purging or inert atmosphere. In addition, these apparatus do not require precise monitoring of pressure or oxygen content as these two variables are virtually eliminated. The apparatus according to the invention can be made relatively small and therefore will require a limited amount of inert gas flow to function successfully and they can be fashioned so that they are mobile and travel synchronously with the welding arc.

মানজন্ম হৈ য

The invention apparatus and methodology can also be adapted to other welding processes which are required for welding of reactive materials where intense heat from the welding process is transferred to the root side of the weld joint utilizing such processes where 10 the welding arc is not projected and open to the root side. Such utilization may require slight modifications of the inventive apparatus, however, the general concept would be available and sufficient to provide through a specifically configured directional flow mechanism which will ensure that full inert gas coverage is achieved.

15 The inventive apparatus and methodology would be applicable to all aerospace, defense related and commercially welded products fabricated from a reactive metal and where plasma arc welding is utilized as the joining process. Any plasma arc welding applications on products which have critical design, processing and inspection requirements would benefit from the root side purging apparatus. For example, the Space Shuttle external tank fabrication from aluminum is one primary candidate which would possibly use a new aluminum-lithium material requiring utilizing plasma arc welding.

5

These and other features and advantages of the present invention will become apparent to those skilled in the art upon reading of the following detailed description and when taken in conjunction with the drawings wherein there is shown and described various embodiments of the invention.

and a second second

5

BRIEF DESCRIPTION OF THE DRAWINGS

In the course of the following detailed description, reference will be made to the attached drawings wherein:

10

FIGURE 1 is a side elevational view, in simplified pictorial and schematic form, partially fragmental of an embodiment of the invention showing inert gas being drawn to a weld seam by a plasma arc plume;

15 FIGURE 2 is a side elevational view in simplified form, and enlarged and not to scale, of a section of a porous metallic tubing which is shown in FIGURE 1 as a means for supplying an inert gas blanket to the weld seam;

FIGURE 3 is a perspective view of another embodiment of the invention, an open view inert gas purging apparatus formed of porous metallic plates which provide an inert gas blanket in the weld seam zone.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

In the following description, like reference characters designate like and corresponding parts throughout the several views of the drawings.

5

10

16

The side elevational view of FIGURE 1 presents the sparge tube mechanism wherein plasma arc welding torch 2 provides a plasma arc 4 to the discontinuous first reactive metal segment 6 and second reactive metal segment 8 for welding joinder. The welded joint along weld joint 10 is accomplished through full penetration welding of the reactive metals with the plasma arc welding process in the "keyhole mode" which requires the weld joint root side 11 to be shielded with relative precision due to the addition 11 implications brough, on by plasma arc thrusting through to the root side of the weld seam. In fusion welding of oxygen reactive materials, the molten weld zone and local high temperature solid areas must be shielded from normal atmosphere to prevent degradation of the welded area to avoid producing weld defects.

15

The plasma arc plume 12 draws inert gas which flows from the porous metal tubes 14. The porous metal tubes 14 can be supplied with gas flow shrouds 16 which direct and economize the flow of inert gas in creating an inert gas blanket atmosphere in the region or zone of the weld. With such a supply of inert gas, the plasma arc plume 12 draws the gas to the weld zone, thus creating an enhanced inert blanketing gas atmosphere in front of, around and following the plasma arc plume 12.

In FIGURE 2, the porous metal tube 14 is presented in an enlarged not to scale side elevational view. A section of the porous metal tube 14 is presented having a porous metal tube cavity 18 and a porous metal tube wall 20. Such a porous metal tube 14 is shown in operative position in FIGURE 1 as a means for supplying inert gas atmosphere or blanket to the weld seam zone. The porous metal tubing 14 can be comprised of sintered metal which allows the permeability of gases through the tubing wall 20 either by the action of pressure in the porous metal tube cavity 18 and/or in combination with outside force such as that of the plasma arc plume 12 which has a jet-like thrust and draws inert gas to the weld seam zone. Such porous metal tubing 14 could be constructed with, for example, an inside diameter of 3/8" and an outside diameter of 1/2". Typically, multiple tubing within the environment of the invention is capable of supplying approximately 100 cubic feet per hour inert gas. Such dimensions obviously can be varied in order to accommodate multiple welding torches and/or reactive base material thicknesses and other welding variables.

15 A perspective view of another embodiment of the inventive anparatus is presented in FIGURE 3, the open view purging apparatus. The open view purging assembly 22 is comprised of a first porous metal plate 24 and a second porous metal plate 26 which are spaced apart to accommodate, for example, a plasma arc plume, while providing an inert gas atmosphere which can be enhanced by the jet-like thrust of the plasma arc plume. The first and second porous metal plates are porous on facing surfaces and can be porous along the thickness of the 20 plates which define chambers therein. The first porous metal plate 24 and the second porous metal plate 26 accommodate various numbers and sizes of plate pores 28 and 30 which

5

10

communicate to gas filled chambers defined within the two metal plates. These plate pores provide inert gas blanketing of the root side portion of the weld seam and can be controlled by internal pressure, number of pores, size of pores, spacing of the plates 24 and 26, as well as the plasma arc plume thrust. The first porcus metal plate 24 and the second porcus metal plate 26 are maintained at specific and yet adjustable spacing by mounting members 32 and 34. These mounting members are affixed to the first, porous metal plate 24 and second porous metal plate 26 by mounting member fasteners 36. The open view purging assembly 22 and first porous metal plate 24 and second porous metal plate 26 are provided with an inert gas outlet and inlet tubing 38 and 40.

10

15

5

The chamber free fusion welding root side purging method and apparatus presented in both the sparge tube purging apparatus and the open view purging assembly 22 utilize a common methodology and provide a porous medium through which inert gas is channeled. The porous medium can be placed along the borders of the weld seam and parallel to the weld seam without restricting the view of the root side of the seam while enhancing the inert gas blanket. The enhancement of the inert gas blanket is achieved through efficient localization of the inert gas which is further enhanced at the point of arc penetration, as well as in front of and behind the arc through the jet-like thrust of the plasma arc which creates a drawing action upon the inert gas and continuously provides an oxygen-free atmosphere to the molten and/or high temperature weld metal. Within the inert gas blanket provided by continuous gas flow, the plasma arc can 20 draw such blanket and focus or localize, i.e., concentrate the inert gas atmosphere to the zone of the weld. Such apparatus and methodology does not require inefficient amounts of inert gas

and eliminates the need for various controls row necessary for known systems. Furthermore, the ability of operator open viewing of the root side of plasma arc welding seams within the inert atmosphere avoids many, if not most, of the defects of weld seams occurring in presently used chambers. Not only can quick adjustments of the welding process be achieved, but avoidance of continuous defective weld seams is possible.

It is obvious that many embodiments may he made of this inventive concept and that many modifications may be made in the embourments hereinbefore described. Therefore, it is to be understood that all descriptive materials herein are to be interpreted merely as illustrative, exemplary and not in a limited sense. It is intended that the various modifications which might readily suggest themselves to those skilled in the art be covered by the following claims, as far as the prior arc permits.

10

5

 \mathbf{i}

ABSTRACT OF THE DISCLOSURE

A method and apparati are presented for non-chamber root side purging in fusion welding of oxygen reactive metals which require that the mether weld zone and local solid areas of the weld seam remaining at high temperatures be shielded from normal atmosphere to prevent degradation of the welded area. The apparati provide an inert atmosphere to the root side of a weld joint through a porous medium whereby the jet-like thrust of the plasma are actually draws the continuously supplied inert atmosphere into the path of the molten or high temperature solid weld zone. The porous medium is configured so it can be placed at the borders of the weld seam and substantially parallel to the seam without restricting the view of the root side of the seam. The inert gas is dispersed evenly through the porous media and across the weld seam, at the point of are penetration and in front of and behind the are. The apparati can be constructed so as to limit the amount of inert gas flow and can be mobile and travel synchronously with the welding are.

