

FLUX CREEP IN $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+x}$ SINGLE CRYSTALS

E.Agostinelli, G.Balestrino*, D.Fiorani, R.Muzi, P.Paroli+,
J.Tejada#, A.M.Testa

I.T.S.E., C.N.R., Area della Ricerca di Roma, P.B.10,
Monterotondo Stazione, Italy.

* Department of Physics, University of Salerno, Salerno, Italy

+ Department of Mechanical Engineering, University of Tor
Vergata, Rome, Italy

Departamento de Fisica Fonamental, Barcelona, Spain

The results of a magnetic study on a $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+x}$ single
crystal are reported. Low field susceptibility (DC and AC),
magnetization cycles and time dependent measurements have been
performed.

With increasing the temperature the irreversible regime of the
magnetization cycles is rapidly restricted to low fields,
showing that the critical current J_C becomes strongly field
dependent well below T_C . At 4.2 K the critical current in zero
field, determined from the remanent magnetization by using the
Bean formula for the critical state, is $J_C(//c) = 2 \cdot 10^5 \text{ Acm}^{-2}$.
The temperature dependence of J_C is satisfactorily described by
the phenomenological law $J_C = J_C(0) (1 - T/T_C)^n$, with $n=8$.

The time decay of the zero field cooled magnetization and of the
remanent magnetization has been studied at different temperatures
for different magnetic fields. The time decay has been found to
be logarithmic in both cases, at least at low temperatures.

At $T=4.2$ K for a field of 10 kOe applied parallel to the c axis,
the average pinning energy, determined by using the flux creep
model, is $U_0 = 0.010$ eV.