

# NASA Technical Memorandum

NASA TM-86553

EFFECTS OF EXTERNAL ENVIRONMENTS ON THE  
SHORT BEAM SHEAR STRENGTH OF FILAMENT WOUND  
GRAPHITE/EPOXY

(Center Director's Discretionary Fund Final Report)

By B. G. Penn and J. M. Clemons

Space Science Laboratory and  
Materials and Processes Laboratory  
Science and Engineering Directorate

July 1986

(NASA-TM-86553)	EFFECTS OF EXTERNAL ENVIRONMENTS ON THE SHORT BEAM SHEAR STRENGTH OF FILAMENT WOUND GRAPHITE/EPOXY	N86-32528
Center Director's Discretionary Fund Final Report (NASA)	14 p	Unclas
	CSCL 11D G3/24	44072



National Aeronautics and  
Space Administration

George C. Marshall Space Flight Center

1. REPORT NO. NASA TM -86553		2. GOVERNMENT ACCESSION NO.		3. RECIPIENT'S CATALOG NO.	
4. TITLE AND SUBTITLE Effects of External Environments on the Short Beam Shear Strength of Filament Wound Graphite/Epoxy (Center Director's Discretionary Fund Final Report)				5. REPORT DATE July 1986	
				6. PERFORMING ORGANIZATION CODE	
7. AUTHOR(S) B. G. Penn and J. M. Clemons*				8. PERFORMING ORGANIZATION REPORT #	
9. PERFORMING ORGANIZATION NAME AND ADDRESS  George C. Marshall Space Flight Center Marshall Space Flight Center, Alabama 35812				10. WORK UNIT NO.	
				11. CONTRACT OR GRANT NO.	
				13. TYPE OF REPORT & PERIOD COVERED  Technical Memorandum	
12. SPONSORING AGENCY NAME AND ADDRESS  National Aeronautics and Space Administration Washington, D.C. 20546				14. SPONSORING AGENCY CODE	
15. SUPPLEMENTARY NOTES Prepared by Space Science Laboratory and *Materials and Processes Laboratory, Science and Engineering Directorate.					
16. ABSTRACT  Filament wound graphite/epoxy samples were immersed in seawater, deionized water, and toluene at room temperature and 80°C for 5, 15, and 43 days, and in methanol at room temperature for 15 and 43 days. The percent weight gains and short beam shear strengths were determined after environmental exposure. Samples immersed in deionized water and seawater had higher percent weight gains than those immersed in toluene at room temperature and 80°C. The percent weight gains for samples immersed in methanol at room temperature were comparable to those of deionized water and seawater immersed samples. A comparison of percent decreases in short beam shear strengths could not be made due to a large scatter in data. This may indicate defects in samples due to machining or variations in material properties due to processing.  This research was sponsored by the Center Director's Discretionary Fund Project (No. 84-5, "Effects of External Environments on the Failure Mode and Mechanical Properties of an Epoxy and Graphite/Epoxy Composite System").					
17. KEY WORDS Composite materials, environmental effects, graphite/epoxy composite, seawater, deionized water, short beam shear strength, filament wound case			18. DISTRIBUTION STATEMENT  Unclassified - Unlimited		
19. SECURITY CLASSIF. (of this report) Unclassified		20. SECURITY CLASSIF. (of this page) Unclassified		21. NO. OF PAGES 13	22. PRICE NTIS

TABLE OF CONTENTS

	Page
INTRODUCTION .....	1
EXPERIMENTAL .....	1
Materials .....	1
Short Beam Shear Strength .....	2
Machining of Short Beam Shear Specimens .....	2
Environmental Testing .....	2
RESULTS AND DISCUSSION .....	2
Percent Weight Gains in the Liquid Environments .....	2
Analysis of Environmental Effects on the Short Beam Shear Strength...	2
CONCLUSION .....	3
REFERENCES .....	4

PRECEDING PAGE BLANK NOT FILMED

LIST OF TABLES

Table	Title	Page
1.	Composition of Seawater Salt Mixture According to Manufacturer .....	5
2.	Short Beam Shear Strength After 5 Days of Environmental Exposure .....	6
3.	Short Beam Shear Strength After 15 Days of Environmental Exposure .....	7
4.	Short Beam Shear Strength After 43 Days of Environmental Exposure .....	8
5.	Short Beam Shear Strength After Immersion in Methanol at Room Temperature .....	9

## TECHNICAL MEMORANDUM

### EFFECTS OF EXTERNAL ENVIRONMENTS ON THE SHORT BEAM SHEAR STRENGTH OF FILAMENT WOUND GRAPHITE/EPOXY

(Center Director's Discretionary Fund Final Report)

#### INTRODUCTION

Structural components fabricated from fiber reinforced polymers are finding wide applications in automobiles, commercial and military aircraft, and space systems because of their high strength, high stiffness, and low weight. In order to take advantage of these excellent properties, the effects of external environments during usage on the mechanical properties of composite materials need to be understood. This is especially true when material failure due to exposure to external environments can result in loss of life, injury, or high financial losses.

The effects of temperature, moisture, and various organic liquids on the mechanical properties of epoxy resin reinforced with graphite [1-7] have been studied. Degradation of mechanical properties most likely occurs due to debonding of the fiber and matrix and/or cracking of the matrix.

Short beam shear and flexural strength measurements have been used to examine the effect of environments on the mechanical properties of composite materials. For example, Rege and Lakkad [8] examined the effect of salt water and distilled water on carbon and graphite reinforced epoxy. Degradation in salt water was found to be more severe for the composite systems that were studied. Joshi [9] measured the short beam shear strengths of unidirectional carbon/epoxy samples immersed in boiling water. The shear strengths were found to decrease with an increase in the amount of absorbed moisture.

The purpose of this paper is to report preliminary results of a study directed at determining the effects of seawater, deionized water, methanol, and toluene on the short beam shear strengths of filament wound graphite/epoxy systems used in the Space Shuttle.

#### EXPERIMENTAL

##### Materials

The dry seawater salt mixture was purchased from Lake Product Co., St. Louis, Missouri. The composition of this mixture is shown in Table 1. The seawater was prepared by dissolving 41.95 g of salt mixture in 1000 ml of water as specified by the supplier.

The SRB-Filament Wound Case (FWC) segments were fabricated using an epoxy system composed of a mixture of Bisphenol A epoxy and 1,4 butanediol epoxy. The curing agent was a blend of methylene dianiline and m-phenylene diamine. The reinforcement was graphite fibers manufactured by Hercules and designated as A S4W-12K.

## Short Beam Shear Strength

The interlaminar shear strength was measured in accordance with ASTM-D 2344-76 short beam shear procedure. An Instron machine with a crosshead speed of 0.05 in./min was used. The size of the transverse specimens was 1.5 x 0.25 x 0.25 in.

### Machining of Short Beam Shear Specimens

Large pieces of specimens were cut from actual segments of the SRB-FWC and machined to dimensions of 1.5 x 0.25 x 0.25 in. This was carried out by cutting the large pieces of segment into 1.5-in. vertical strips. Each of these were then cut in the horizontal direction to give pieces having a length of 1.5 in. and width of 0.25 in. Samples with a thickness of 0.25 in. were prepared by cutting the necessary amount from the two remaining uncut faces. The machining process is illustrated in Figure 1.

### Environmental Testing

Samples machined to dimensions of 1.5 x 0.25 x 0.25 in. as described were immersed in deionized water, seawater, or toluene at room temperature and 80°C for 5, 15, and 43 days. In addition, samples were immersed in methanol at room temperature for the specified lengths of time. Control samples were also prepared and heated for the required amounts of time in a desiccator placed in an oven. After environmental exposure the samples were subjected to percent weight gain determination and short beam shear strength measurements.

## RESULTS AND DISCUSSION

### Percent Weight Gains in the Liquid Environments

The percent weight gains for filament wound graphite/epoxy samples immersed in deionized water, seawater, and toluene at room temperature and 80°C for 5, 15, and 43 days are summarized in Tables 2 through 4. The highest values were obtained for deionized water and seawater which had percent weight gain values ranging from 0.58 to 1.7 and 0.48 to 1.7, respectively. In comparison, the percent weight gain values ranged from 0.28 to 0.59 for toluene. Based on these results, deionized water and seawater are expected to degrade mechanical properties more than toluene.

The percent weight gains of samples immersed in methanol at room temperature are presented in Table 5. The percent weight gain values are 1.3 and 2.7 for 15 days and 43 days, respectively. This preliminary data indicate that methanol might have a significant effect on the degradation of mechanical properties since its percent weight gains are comparable to those of seawater and deionized water. This phenomenon will be further investigated in future projects.

### Analysis of Environmental Effects on the Short Beam Shear Strength

The effects on the short beam shear strengths of immersion in seawater, deionized water and toluene at room temperature and 80°C for 5, 15, and 43 days are summarized in Tables 2 through 4. Moreover, the effects of immersion in methanol

for 15 and 43 days at room temperature are presented in Table 5. The standard deviation values, which range from 179 to 615 for the controls and immersed samples, are too high and variable for determining the quantitative effects of the liquids on the short beam shear strengths. This trend in standard deviation values might be due to machining defects or variations in the properties of the composite samples. These prospective causes will be thoroughly examined in future programs.

## CONCLUSION

Graphite/epoxy samples machined from large segments, which were fabricated by the same process that will be used to make the SRB FWC, were immersed in deionized water, seawater, and toluene at room temperature and 80°C for 5, 15, and 43 days, and in methanol at room temperature for 15 and 43 days. The percent weight gains for samples immersed in toluene was less than those of samples immersed in deionized water and seawater. The percent weight gains for methanol exposed samples were comparable to those of seawater and deionized water immersed samples which suggest that the effects of alcohols and other polar liquid on the mechanical properties of this composite system should be further investigated.

A comparison of the percent decreases in short beam shear strengths was not attempted due to the wide data scatter and the small number of samples tested. The scatter in data might indicate the presence of defects in samples resulting from machining operations or there might have been variations in the properties of the filament wound segment. This investigation will continue using this study as a basis.

## REFERENCES

1. Browning, C. E., Husman, G. E., and Whitney, J. M.: Moisture Effects in Epoxy Matrix Composites. In Composite Materials: Testing and Design (Fourth Conference), ASTM STP 617, American Society for Testing, 1976, pp. 481-496.
2. Springer, G. S., Ed.: Environmental Effects on Composite Materials. Technomic Publishing Co., Inc., Westport, CT, 1981.
3. Browning, C. E.: Effects of Moisture on the Properties of High Performance Structural Resins and Composites. Proc. 28th Ann. Tech. Conf. Reinf. Plast./Com. Inst., SPI, 1973, Sec. 15A.
4. Hertz, J.: Investigation Into the High-Temperature Strength Degradation of Fiber-Reinforced Composites During Ambient Aging. Tech. Rept. GDCA-D 6B71-00403, Contract No. NAS8-27435, 1972.
5. Shen, D., and Springer, G. S.: J. Composite Materials, Vol. 11, 1977, p. 2.
6. Gillat, O., and Broutman, L. J.: Effects of External Stress on Moisture Diffusion and Degradation in a Graphite-Reinforced Epoxy Laminate. In Advanced Composite Materials-Environmental Effects, ASTM STP 658, J. R. Vinson, Ed., American Society for Testing and Materials, 1978, pp. 61-83.
7. Browning, C. E.: Polym. Eng. Sci., Vol. 18, No. 1, 1978, p. 16.
8. Rege, S. K. and Lakkad, S. C.: Fibre Science and Technology, Vol. 19, 1983, pp. 317-321.
9. Joshi, O. K.: Composites, Vol. 14, No. 3, 1983, pp. 196-200.






Figure 1. Machining of specimens for short beam shear strength measurements. Cutting of 1.5 in. dimension (a), 0.25 in. width (b), and 0.25 in. thickness (c).

TABLE 1. COMPOSITION OF SEAWATER SALT MIXTURE ACCORDING TO MANUFACTURER

Component	Percent Composition
NaCl	59.490
MgCl <sub>2</sub>	26.460
Na <sub>2</sub> SO <sub>4</sub>	9.750
CaCl <sub>2</sub>	2.765
KCl	1.645
NaHCO <sub>2</sub>	0.447
KBr	0.238
H <sub>3</sub> BO <sub>3</sub>	0.071
SrCl <sub>2</sub>	0.095
NaF	0.007

TABLE 2. SHORT BEAM SHEAR STRENGTH AFTER 5 DAYS OF ENVIRONMENTAL EXPOSURE

Environment	Property Measured	Room Temperature		Number of Samples Tested
		80°C	80°C	
Deionized Water	Short Beam Shear Strength (psi)	5266	5200	4
	Standard Deviation	345	510	
	Percent Weight Gain	0.58	0.80	
Seawater	Short Beam Shear Strength (psi)	5671	4723	4
	Standard Deviation	394	426	
	Percent Weight Gain	0.48	0.58	
Toluene	Short Beam Shear Strength (psi)	5043	4472	5
	Standard Deviation	544	382	
	Percent Weight Gain	0.28	0.32	
Control	Short Beam Shear Strength (psi)	5463	5192	4
	Standard Deviation	352	481	
	Percent Weight Gain	0.21	0	

TABLE 3. SHORT BEAM SHEAR STRENGTH AFTER 15 DAYS OF ENVIRONMENTAL EXPOSURE

Environment	Property Measured	Room Temperature		Number of Samples Tested
		80°C	80°C	
Deionized Water	Short Beam Shear Strength (psi)	5083	5222	4
	Standard Deviation	403	488	
	Percent Weight Gain	1.1	1.0	
Seawater	Short Beam Shear Strength (psi)	5146	4868	4
	Standard Deviation	348	477	
	Percent Weight Gain	1.2	1.0	
Toluene	Short Beam Shear Strength (psi)	5628	4119	5
	Standard Deviation	484	309	
	Percent Weight Gain	0.47	0.50	
Control	Short Beam Shear Strength (psi)	5330	5248	5
	Standard Deviation	186	519	
	Percent Weight Gain	0.24	0	

TABLE 4. SHORT BEAM SHEAR STRENGTH AFTER 43 DAYS OF ENVIRONMENTAL EXPOSURE

Environment	Property Measured	Room Temperature	80°C	Room Temperature	80°C	Number of Samples Tested
Deionized Water	Short Beam Shear Strength (psi)	5038	4929	5038	4929	4
	Standard Deviation	482	179	482	179	5
	Percent Weight Gain	1.5	1.7	1.5	1.7	4
Seawater	Short Beam Shear Strength (psi)	6283	5236	6283	5236	5
	Standard Deviation	368	518	368	518	5
	Percent Weight Gain	1.43	1.7	1.43	1.7	5
Toluene	Short Beam Shear Strength (psi)	5167	5310	5167	5310	4
	Standard Deviation	387	300	387	300	4
	Percent Weight Gain	0.59	0.52	0.59	0.52	4
Control	Short Beam Shear Strength (psi)	5103	5103	5103	5103	5
	Standard Deviation	315	615	315	615	5
	Percent Weight Gain	0.30	0	0.30	0	5

TABLE 5. SHORT BEAM SHEAR STRENGTH AFTER IMMERSION  
IN METHANOL AT ROOM TEMPERATURE

Environment	Property Measured	15 Days	43 Days
Methanol	Short Beam Shear Strength (psi)	5210	4863
	Standard Deviation	446	215
	Percent Weight Gain	1.30	2.7
	Number of Samples Tested	5	3
Control	Short Beam Shear Strength (psi)	5330	5103
	Standard Deviation	186	315
	Percent Weight Gain	0.24	0.30
	Number of Samples Tested	4	5

APPROVAL

EFFECTS OF EXTERNAL ENVIRONMENTS ON THE SHORT BEAM SHEAR  
STRENGTH OF FILAMENT WOUND GRAPHITE/EPOXY

(Center Director's Discretionary Fund Final Report)

By B. G. Penn and J. M. Clemons

The information in this report has been reviewed for technical content. Review of any information concerning Department of Defense or nuclear energy activities or programs has been made by the MSFC Security Classification Officer. This report, in its entirety, has been determined to be unclassified.

*E. Tandberg-Harrison*  
\_\_\_\_\_  
A. J. DESSLER  
Director, Space Science Laboratory