

NASA

AVRADCOM

Technical Memorandum 81431

Technical Report 80-C-3

(NASA-TM-81431) SOME LIMITATIONS IN  
APPLYING CLASSICAL EHD FILM-THICKNESS  
FORMULAE TO A HIGH-SPEED BEARING. (NASA)  
32 p HC A03/MF A01

N80-18409

CSCL 13I

Unclas

G3/37 47408

SOME LIMITATIONS IN APPLYING  
CLASSICAL EHD FILM-THICKNESS  
FORMULAE TO A HIGH-SPEED BEARING

John J. Coy

Propulsion Laboratory

AVRADCOM Research and Technology Laboratories

Lewis Research Center

and

Erwin V. Zaretsky

Lewis Research Center

Cleveland, Ohio



Prepared for the

International Lubrication Conference

cosponsored by the American Society of Mechanical Engineers

and the American Society of Lubrication Engineers

San Francisco, California, August 18-21, 1980

SOME LIMITATIONS IN APPLYING CLASSICAL EHD FILM THICKNESS

FORMULAE TO A HIGH-SPEED BEARING

by John J. Coy\*  
Propulsion Laboratory  
AVRADCOM Research and Technology Laboratories  
Lewis Research Center

and

Erwin V. Zaretsky†  
Lewis Research Center  
Cleveland, Ohio

ABSTRACT

Elastohydrodynamic film thickness was measured for a 20-mm ball bearing using the capacitance technique. The bearing was thrust loaded to 90, 448, and 778 N (20, 100, and 175 lb). The corresponding maximum stresses on the inner race were 1.28, 2.09, and 2.45 GPa (185 000, 303 000, and 356 000 psi). Test speeds ranges from 400 to 14 000 rpm. Film thickness measurements were taken with four different lubricants: (a) synthetic paraffinic, (b) synthetic paraffinic with additives, (c) neopentylpolyol (tetra) ester meeting MIL-L-23699A specifications, and (d) synthetic cycloaliphatic hydrocarbon traction fluid. The test bearing was mist lubricated. Test temperatures were 300, 338, and 393 K.

The measured results were compared to theoretical predictions using the formulae of Grubin, Archard and Cowking, Dowson and Higginson, and Hamrock and Dowson.

There was good agreement with theory at low dimensionless speed, but the film was much smaller than theory predicts at higher speeds. This was due to kinematic starvation and inlet shear heating effects. Comparisons

---

\*Member ASME.

†Fellow ASME.

with Chiu's theory on starvation and Cheng's theory on inlet shear heating were made.

## SYMBOLS

a	major semi-axis of Hertz contact, m (in.)
b	minor semi-axis of Hertz contact, m (in.)
E	reduced modulus of elasticity, $\frac{1}{E} = \frac{1}{2} \left( \frac{1 - \nu_1^2}{E_1} + \frac{1 - \nu_2^2}{E_2} \right)$
$E_1, E_2$	Young's modulus for body 1 and 2, GPa (psi)
F	normal applied load, N (lb)
G	materials parameter, $\alpha E'$
H	film thickness, $h/R_x$
h	film thickness, m (in.)
k	ellipticity ratio, $a/b$
$R_x$	equivalent radius in rolling direction, m (in.), $\frac{1}{R_x} = \frac{1}{R_{x1}} + \frac{1}{R_{x2}}$
U	speed parameter, $u\eta_0/E'R_x$
u	average surface speed, m/sec (in./sec)
W	load parameter, $F/E'R_x^2$
x	coordinate in rolling direction, m (in.)
y	coordinate in transverse direction, m (in.)
1	body 1
2	body 2
$\alpha$	pressure-viscosity exponent, $\text{GPa}^{-1}$ ( $\text{psi}^{-1}$ )
$\eta_0$	atmospheric viscosity, $\text{N-sec/m}^2$ ( $\text{lb-sec/in.}^2$ )
$\nu_1, \nu_2$	Poisson's ratio for body 1 and body 2

## INTRODUCTION

The elastohydrodynamic (EHD) lubrication of bearings has been investigated theoretically and experimentally for more than 30 years [1 to 16]. An EHD film is formed when non-conforming lubricated machine elements are pressed together in rolling and/or sliding contact. In essence, EHD film formation depends on the coupled effects of physical changes in the lubricant, which are caused by high pressures in the contact zone, and elastic changes in the shape of the contact zone which affect the pressure distribution. The high pressures in the EHD contact act to squeeze out the lubricant. However, the lubricant becomes thicker (more viscous) with increasing pressure and resists being squeezed out. The net result is the formation of a thin lubricant film that is beneficial in preventing seizure and rapid wear of contacting parts in motion.

Experimental measurement of EHD film thickness is very difficult because the film is generally less than a micrometer thick. Various methods have been developed and used to measure the EHD film thickness. These are the X-ray, optical and electrical capacitance and conductance methods [17]. X-ray measurements only are suited to measure film thickness between contacting disc rollers. This is because there must be a clear line of sight for the X-rays to pass through the EHD contact zone. Optical methods are generally applied to the case of a steel ball on a transparent disc. However, a recent application was made to a radial loaded roller bearing with a quartz window in the outer race [18]. In [19] it was concluded that film thickness measurement using the

conductance method is not practical. The capacitance technique was used to obtain the film thickness data presented in [20].

Operating EHD parameters of rolling-element contacts are conveniently arranged into dimensionless groupings. These are the load parameter  $W$ , the speed parameter  $U$ , the materials parameter  $G$ , and the film thickness,  $H$ . The speed parameter has a stronger effect on film thickness than the load parameter. Most experimental data which have been generated have been for speed parameters  $U$  less than  $10^{-10}$ .

Critical engineering design of mechanical components such as rollent-element bearings and gears requires that engineering data and theory on elastohydrodynamic (EHD) film formation be accurate and comprehensive. The research reported herein, which is based on the work reported in [20], was undertaken to experimentally investigate the elastohydrodynamic film thickness at speed parameter  $U$  values greater than  $10^{-10}$ . The primary objectives were to (a) experimentally measure the elastohydrodynamic film (EHD) thickness with four lubricants to speed parameter  $U$  values to  $10^{-8}$ , (b) compare the experimental EHD results with those obtained by other investigators and (c) compare EHD measured film thickness measurements with classical film thickness formulae to the practical situation of a 20-mm bore angular-contact ball bearing operating at high speed.

#### EHD TEST RIG

The experiments were conducted using the EHD film thickness test rig shown in figure 1 and initially described in [20]. The test rig consists of a rotating driveshaft supported by two bearings running

against a test bearing which is located in a vibration isolated housing. The shaft is driven with an air turbine. Shaft speed is sensed with a magnetic pickup. The speed is held constant during a test with an automatic controller. The load is applied pneumatically. The linear ball bushing allows the thrust load to be transmitted from the pneumatic loader through the shaft to the test bearing. The thrust load is determined from the air pressure acting on the loading cylinder.

The temperature of the test bearing is controlled by cartridge heaters which are located in the test bearing support block. The temperatures were held constant within approximately 3 K (5° F) during a test using an automatic controller on the heaters. Temperatures were sensed by thermocouples placed on the bearing outer race and in the inlet lubrication stream. The bearings were mist lubricated with separate systems for support bearings and test bearing. A separate heater allowed the inlet mist to the test bearing to be held equal to the bearing temperature.

#### Test Bearings

The test bearings for this experiment were 20-millimeter bore angular-contact bearings having three 7.15-millimeter (9/32-in.-) diameter balls. The bearing specifications are listed in table I. The bearing had a polyimide cage and the outer race was electrically isolated from the housing. The spring-loaded thermocouple at the outer race and the slip rings on the drive shaft provided electrical contact for measurements across the test bearing.

## Test Lubricants

Four different lubricants were used in the EHD film thickness experiments. The lubricant properties are given in table II. Lubricants A and B were experimental synthetic paraffinics with similar properties, but B had additives whereas A did not. Lubricant C was a 5-centistoke neopentylpolyol (tetra) ester. This is a type II lubricant, qualified to MIL-L-23699 as well as the lubricant specifications of most major aircraft-engine producers. Lubricant D is a synthetic cycloaliphatic hydrocarbon having a high coefficient of traction [21]. Lubricants C and D have similar temperature-viscosity properties. However, lubricant D has a larger pressure-viscosity exponent.

The elastohydrodynamic film thickness affects rolling-element fatigue life [22]. In general, the larger the film, the longer the life. Under given operating conditions, the film formed is a function of the initial ambient viscosity of the lubricant and the lubricant's pressure-viscosity coefficient. Comparative rolling-element fatigue tests were conducted with lubricants C and D [23,24]. No statistical life differences between these two fluids were exhibited. A synthetic paraffinic oil was also tested. However, this fluid had a lower viscosity than either lubricants A and B. The lower-viscosity synthetic paraffinic oil also exhibited no statistical life difference when compared to the tetraester fluid (lubricant C) [24]. A higher-viscosity paraffinic lubricant, such as the two of the current study, would be expected to have a larger EHD film thickness and, thus, result in longer fatigue life. Based upon previous research, no significant differences

would be expected in EHD film thickness [12] or rolling-element fatigue [25] for lubricants A and B since the only difference between these fluids is the presence of the additive package in lubricant B.

#### Test Procedure

The lubricant film thickness was measured using the electrical capacitance method as described in [3,6]. A schematic is shown in figure 2. The electrical capacitance between the inner and outer races of the test bearing is a function of the thickness of the lubricant film and the size of the Hertzian areas of contact (table III). The capacitance across the test bearing was measured with a capacitance bridge, and the film thickness was read from a calibration curve. During the tests the capacitance bridge balancing signal was observed on an oscilloscope. Any short circuiting of the test bearing capacitance could be observed. This short circuiting was an indication of asperity contact in the EHD zone. Further details of the measurement techniques used may be found in [20,26].

Test temperatures were 300, 338, and 393 K ( $80^{\circ}$ ,  $150^{\circ}$ , and  $250^{\circ}$  F). Thrust loads applied to the bearing were 90, 445, and 778 N (20, 100, and 175 lb). The shaft speed was adjusted at speeds from 400 to 15 000 rpm. In all cases the oil flow was approximately the same at 2 to 3 drops per minute, delivered by a mist.

The general test procedure was to begin at top speed and low load for a given temperature of operation. Then the loads were increased stepwise to the heaviest load, and held long enough to take a film thickness reading with the capacitance bridge. The test continued,



repeating the load sequence for each successive lower speed. During the loading sequence the shaft speed was held constant with an automatic controller. The temperature was controlled to within 3 K (5° F).

For the measurements with lubricant A the test bearing had approximately 20 to 30 hours of running time on it, which were accumulated during checkout and calibration of the test rig. For each of the remaining test lubricant sequences a new test bearing was used. The tests with the new bearings were carefully monitored to prevent continued operation in the asperity contact regime. The test sequence was stopped when it became clear that the lubricant film was breaking down. This occurred at the lower speeds and heavy loads.

## RESULTS AND DISCUSSION

### Effect of Load and Speed

The effect of speed and load on the elastohydrodynamic (EHD) film for the 20-mm bore angular-contact ball bearing using lubricant C is shown in figure 3. Figure 3 is a plot of the dimensionless film thickness  $H$  as a function of the dimensionless speed parameter  $U$ . The bearing was run at speeds ranging from 400 to 15 000 rpm, thrust loads of 90, 445, and 778 N (20, 100, and 175 lb) and at temperatures of 300, 338, and 393 K (80°, 150°, and 250° F). Measured film thicknesses ranged from 0.025 to 0.51  $\mu\text{m}$  (1 to 20  $\mu\text{in.}$ ). The results shown in figure 3 for lubricant C are representative of the other three lubricants.

Generally, the measured film thickness was more weakly dependent on speed than theory suggests. At lower temperatures where the lubricant was more viscous, film thickness was observed to be independent of speed, and film thickness even decreased at the higher speeds.

For the highest temperature and low speeds the film thickness speed dependence was closest to theoretical prediction.

The measured film thickness decreased slightly with load as predicted by EHD theory. However, in the cases where measured film thickness was independent of speed or decreased with the speed this was not true. In these cases, the measured film thickness increased slightly with load. It is shown later that the principal reason for deviation of the measured values from theory is lubricant starvation. Because of the insignificant difference of EHD film thickness with load, the data for the 90 N (20 lb) thrust load will be presented only in subsequent figures for purposes of clarity.

For synthetic paraffinic lubricants A and B, film thickness measurements were identical for the full range of test parameters. This was expected since lubricants A and B differ only in that B has additives whereas A does not. Thinner films were measured for the tetraester (lubricant C). This was expected since it is less viscous than lubricants A and B. Film thicknesses with the traction fluid (lubricant D) were comparable to those for the lubricants A and B. This is to be expected since the pressure-viscosity coefficient effectively raises the viscosity of this fluid in the contact zone.

#### Comparison to Classical Theories

The data for the 90 N (20 lb) load points are plotted on dimensionless coordinates in figure 4 and compared to some well known theoretical results. The theories chosen for comparison were those of Grubin [1], Dowson-Higginson [5], Archard and Cowking [4], and Hamrock and Dowson [16]. The respective formulae are as follows:

<u>Grubin's formula</u>	$H = 1.95 G^{0.73} U^{0.73} W^{-0.091}$
<u>Dowson-Higginson</u>	$H = 1.6 G^{0.6} U^{0.7} W^{-0.13}$
<u>Archard-Cowking</u>	$H = 2.04 \left( 1 + \frac{2R_x}{3R_y} \right)^{-0.71} G^{0.74} U^{0.74} W^{-0.74}$
<u>Hamrock-Dowson</u>	$H = 3.63(1 - e^{-0.68 k}) G^{0.49} U^{0.68} W^{-0.73}$

The above equations are plotted in figure 4 for three different values of materials parameter G which represent the maximum, minimum, and average values of G for the experimental conditions. In general there was fair agreement between measured and theoretical film thicknesses at dimensionless speeds less than  $10^{-10}$ . The differences between the film thicknesses calculated with the different EHD theories are less than the scatter in experimentally measured data. The significance of this is to show that some of the past refinements in film thickness prediction theory are unobservable in practice. At the higher speeds of U, between  $10^{-10}$  and  $10^{-8}$ , the correlation to classical isothermal, fully flooded inlet theory is not good.

#### Thermal Correction and Starvation

Thermal considerations in the inlet zone of the EHD zone [15] and kinematic starvation [27] have an effect on film reduction at higher speeds. Those theories are compared to the present data in figure 5.

A new dimensionless parameter designated "contact lubrication flow number" is introduced in this figure. This is the product of two dimensionless parameters, the materials parameter, G, and the speed parameter, U. This parameter is introduced for this figure because the data of [27] are in this form only.

Theoretical results by Cheng [15] for film thickness reduction

due to inlet shear heating are plotted in figure 5 for the synthetic paraffinic oil. Cheng's theory assumed  $G = 5000$  whereas the values of  $G$  for the test conditions range from 1980 to 7620. The average value of  $G$  was 3900. Figure 5 shows that inlet shear heating may account for part of the deviation between experiment and isothermal theory at the higher speeds. However, the data show the onset of the deviation at a lower speed, indicating that another mechanism of film thickness reduction is active.

A theoretical model for starvation in a rolling-element bearing was formulated by Y. P. Chiu [27]. Figure 5 shows the results from Chiu's analysis and experimental data [27] which are compared with the experimental data of figure 4. Based upon the correlation between the authors' experimental data and analytical predictions using Chiu's starvation theory, the authors conclude that starvation appears to be the primary cause of the deviation of the experimental data of figure 4 from classical EHD theory.

The lack of adequate lubricant in an EHD contact is affected by the mechanism of lubricant distribution. The mechanism of lubricant distribution was assumed to be any transverse lubricant flow on the rolling track [27]. This lubricant replenishment is aided by higher lubricant-air surface tension, increased ball spacing, and reduced viscosity. Other lubrication replenishment mechanisms are also possible, such as splashing, direct jet deposition, or flow from the cage to balls. All these depend on the particular geometric and kinematic conditions of the bearing [28]. The relative effectiveness of the Y. P. Chiu replenishment model compared to other possible replenishment mechanisms is unknown. However, it is probable that oil film replenishment was occurring due to centrifugal or

direct deposition effects. This is suggested by the continued thickness of oil film at  $GU > 10^{-6}$ .

#### Comparison to Other Experiments

Data from NASA sponsored experiments at the Battelle Memorial Institute [12,13] are compared to the Hamrock-Dowson formula and to the present experimental data in figure 6. In general, the NASA-BMI data which were taken using the X-ray film thickness measurement technique showed film thicknesses greater than theory suggests. The data of figure 4 showed film thicknesses less than theoretical. The total amount of scatter in the data from both methods of testing was approximately equal.

In a discussion to [16], Kunz and Weiner presented data for a steel ball sliding on a sapphire plate where film thickness was measured using the optical interferometry method for dimensionless speed parameters  $U$  less than  $10^{-11}$ . Figure 7 shows the comparison of their results to the experimental data of figure 4. Their data straddled the theoretically predicted film thickness and had about the same scatter as the present data. The similarity in scatter in film thickness measurements using X-ray, optical, and capacitance techniques suggests that the general accuracy of these methods is about the same.

#### Surface Condition

The bearing running tracks were examined using light and scanning electron microscopy techniques. In general, no evidence of wear or surface damage could be seen using light microscopy. However, scanning electron microscopy revealed many small induced surface defects in the

running track such as shown in figure 8 for lubricant B. The original grinding marks are clearly visible in the figure which would indicate that the bearing operated under mostly full EHD film conditions. No comparable surface defects could be detected on unrun bearing race surfaces. These defects were probably induced by wear particles which were generated during bearing operation and which passed through the ball-race contact zone.

There is a suggestion that the density of the induced defects is a function of the lubricant. Among lubricants B, C, and D, the density of the surface defects was highest for lubricant D. (The bearing used for lubricant A was run for a much longer period of time. Hence, no valid comparison could be made). The film thickness for a given operating condition was larger for lubricant D than lubricant C and equal to lubricant B. This would further suggest that surface defect density is not a function of EHD film thickness.

#### SUMMARY AND CONCLUSIONS

Film thicknesses were measured by the capacitance technique for a thrust loaded 20-mm bore ball bearing. The bearing was mist lubricated at a rate of 2 to 3 drops per minute. Test parameters were thrust loads of 90, 445, and 778 N (20, 100, and 175 lb) which gave maximum contact stresses of 1.28, 2.09, and 2.45 GPa (185 000, 303 000, and 356 000 psi) on the inner race, and speeds ranging from 400 to 15 000 rpm. Tests were conducted with four different lubricants at temperatures of 300, 338, and 393 K (80°, 150°, and 250° F). The lubricants were (a) synthetic paraffinic, (b) synthetic paraffinic with additives,

(c) a neopentylpolyol ester, and (d) a synthetic cycloaliphatic hydrocarbon traction fluid. The experimental results were compared to theoretical predictions for film thickness. The following results were obtained:

1. For dimensionless speed parameter,  $U$ , greater than  $10^{-10}$  there was gross thinning of the lubricant film. Kinematic starvation appears to be the primary cause of reduction in film thickness from classical EHD theory.

2. There was fair agreement between measured and theoretical film thickness at dimensionless speeds less than  $10^{-10}$  using isothermal, fully flooded inlet EHD theory.

3. The differences among the film thicknesses calculated with the different EHD theories are less than the scatter in experimentally measured data. The significance of this is to show that some of the past refinements in film thickness prediction theory are unobservable in practice.

4. The scatter in the experimental data using the capacitance technique was the same as for data taken by other methods. This means that the general accuracy and validity of measurements using X-ray, optical, and capacitance techniques are about the same.

#### REFERENCES

1. Grubin, A. N., "Fundamentals of the Hydrodynamic Theory of Lubrication of Heavily Loaded Cylindrical Surfaces," Chapter 2, Investigation of the Contact of Machine Components, Translation of Russian Book No. 30, Central Scientific Institute for Technology and Mechanical Engineering, Moscow, (1949), Ed., Ketova, Kh. F.  
(Available from Department of Scientific and Industrial Research,

- Great Britain, Trans., CTS-235 and Special Libraries Association, Trans. R-3554.)
2. Dowson, D. and Higginson, G. R., "A Numerical Solution to the Elastohydrodynamic Problem," J. Mech. Eng. Sci., 1, 1, pp 6-15 (1959).
  3. Dyson, A., Naylor, H., and Wilson, A. R., "The Measurement of Oil-Film Thickness in Elastohydrodynamic Contacts," Proc. Inst. Mech. Eng. (London), 180, pt. 3B, pp 119-134 (1965-66).
  4. Archard, J. F. and Cowking, E. W., "Elastohydrodynamic Lubrication at Point Contacts," Proc. Inst. Mech. Eng. (London), 180, pt. 3B, pp 47-56 (1965-66).
  5. Dowson, D. and Higginson, G. R., Elastohydrodynamic Lubrication, Pergamon Press, Inc., Elmsford, NY (1966).
  6. Allen, G. E., Peacock, L. A., and Rhoads, W. L., "Measurement of Lubricant Film Thickness in Hertzian Contacts," (SKF-AL68T075, SKF Industries, Inc., NASA Contract NAS3-7912) NASA CR-105378 (1968).
  7. Foord, C. A., Hammann, W. C., and Cameron, A., "Evaluation of Lubricants Using Optical Elastohydrodynamics," ASLE Trans., 11, 1, pp 31-43 (1968).
  8. Zaretsky, E. V. and Anderson, W. J., "EHD Lubrication," Mach. Des., 40, 7, pp 167-173 (1968).
  9. Cheng, H. S., "A Numerical Solution of Elastohydrodynamic Film Thickness in an Elliptical Contact," J. Lubr. Technol., 92, 1, pp. 155-162 (1970).
  10. Tallian, T. E., "Elastohydrodynamic Hertzian Contacts - Part 1," Mech. Eng., 93, 11, pp 14-18 (1971).



11. Tallian, T. E., "Elastohydrodynamic Hertzian Contacts - Part 2," Mech. Eng., 93, 12, pp 17-22 (1971).
12. Parker, R. J. and Kannel, J. W., "Elastohydrodynamic Film Thickness Between Rolling Disks with a Synthetic Paraffinic Oil to 589 K (600° F)," NASA TN D-6411 (1971).
13. Parker, R. J. and Kannel, J. W., "Elastohydrodynamic Film Thickness Measurements with Advanced Ester, Fluorocarbon, and Polyphenyl Ether Lubricants to 589 K (600° F)," NASA TN D-6608 (1971).
14. Kannel, J. W. and Bell, J. C., "Interpretations of the Thickness of Lubricant Films in Rolling Contact. 1 - Examination of Measurements Obtained by X-rays," J. Lubr. Technol., 93, 3, pp 478-484 (1971).
15. Cheng, H. S., "Isothermal Elastohydrodynamic Theory for the Full Range of Pressure-Viscosity Coefficient," J. Lubr. Technol., 94, 1, pp 35-43 (1972).
16. Hamrock, B. J. and Dowson, D., "Isothermal Elastohydrodynamic Lubrication of Point Contacts. Part III - Fully Flooded Results," J. Lubr. Technol., 99, 2, pp 264-276 (1977).
17. Seth, B. B. and Willis, T., "Techniques for Film Thickness Measurements in Elastohydrodynamic Lubrication," ASME Paper 76-DET-79 (September 1976).
18. Pemberton, J. C. and Cameron, A., "An Optical Study of the Lubrication of a 65 mm Cylindrical Roller Bearing," J. Lubr. Technol., 101, 3, pp 327-337 (1979).
19. Coy, J. J. and Sidik, S. M., "Two Dimensional Random Surface Model for Asperity Contact in Elastohydrodynamic Lubrication," Presented

- at the International Conference on Metrology and Properties of Engineering Surfaces, Leicester, England, Apr. 18-20 (1979). Also NASA TM-79006 (1979).
20. Coy, J. J., Gorla, R. S. R., and Townsend, D. P., "Comparison of Predicted and Measured Elastohydrodynamic Film Thickness in a 20-Millimeter Bore Ball Bearing," NASA TP-1542, also AVRADCOM TR-79-20 (1979).
  21. Green, R. L. and Langenfeld, F. L., "Lubricants for Traction Drives," Mach. Des., 46, 11, pp 108-113 (1974).
  22. Bamberger, E. N., et al., "Life Adjustment Factors for Ball and Roller Bearings - An Engineering Design Guide," American Society of Mechanical Engineers, New York (1971).
  23. Loewenthal, S. H. and Parker, R. J., "Rolling-Element Fatigue Life with Two Synthetic Cycloaliphatic Traction Fluids," NASA TN D-8124 (1976).
  24. Parker, R. J., "Rolling-Element Fatigue Lives of AISI 52100 Steel Balls with Several Synthetic Lubricants," Rolling Contact Fatigue: Performance Testing of Lubricants, Heyden & Son Ltd., London (1977), Eds. Tourret, R. and Wright, E. P., pp 281-295.
  25. Parker, F. J. and Zaretsky, E. V., "Effect of Lubricant Extreme - Pressure Additives on Rolling-Element Fatigue Life," NASA TN D-7383 (1973).
  26. Coy, J. J., "Correlation of Asperity Contact-Time Fraction with Elastohydrodynamic Film Thickness in a 20-Millimeter-Bore Ball Bearing," NASA TP-1547.

27. Chiu, Y. P., "An Analysis and Prediction of Lubricant Film Starvation in Rolling Contact Systems," ASLE Trans., 17, 1, pp 22-35 (1974).
28. McCool, J. I., et al., "Influence of Elastohydrodynamic Lubrication of the Life and Operation of Turbine Engine Ball Bearings - Bearing Design Manual," SKF AL75P014, SKF Industries, Inc. (1975). (AFAPL-TR-75-25, AD-A020500.)

TABLE I. - TEST BEARING SPECIFICATIONS

Material, balls and races . . . . .	AISI M-1
Inside diameter, mm (in.) . . . . .	20 (0.7874)
Outside diameter, mm (in.) . . . . .	47 (1.8504)
Width, mm (in.) . . . . .	14 (0.5512)
Pitch diameter, mm (in.) . . . . .	35.5 (1.4)
Nominal contact angle, deg . . . . .	17
Inner race curvature, % . . . . .	53
Outer race curvature, % . . . . .	54
Number of balls. . . . .	3
Ball diameter, mm (in.) . . . . .	7.15 (9/32)
Rockwell C hardness-inner race . . . . .	62-64
Rockwell C hardness-outer race . . . . .	62-64
Rockwell C hardness-balls . . . . .	62-64
Surface finish, rms-races, $\mu\text{m}$ ( $\mu\text{in.}$ ) . . . . .	0.15 (6)
Surface finish, rms-balls, $\mu\text{m}$ ( $\mu\text{in.}$ ) . . . . .	0.025-0.05 (1-2)
Tolerance specification. . . . .	ABEC-5

TABLE II. - LUBRICANT PROPERTIES

Lubricant	A	B	C	D
Type	Synthetic paraffinic	Synthetic paraffinic	Neopentylpolyol (tetra) ester	Synthetic cycloaliphatic hydrocarbon
Pour point, K	223	223	213	236
Flash point, K	544	544	535	435
Fire point, K	585	585	--	446
Autogenous ignition, K	677	677	699	599
Density, g/cc				
373 K	0.80	0.80	0.93	0.85
311 K	0.84	0.84	0.98	0.89
Pressure-viscosity exponent, $m^2/N$				
373 K	$1.51 \times 10^{-8}$	$1.36 \times 10^{-8}$	$1.00 \times 10^{-8}$	$1.70 \times 10^{-8}$
311 K	$1.99 \times 10^{-8}$	$1.81 \times 10^{-8}$	$1.37 \times 10^{-8}$	$3.11 \times 10^{-8}$
Kinematic viscosity, $cs$				
373 K	40	40	5.2	5.6
311 K	447	447	28	34
Surface tension, dyne/cm				
373 K	--	--	--	20
311 K	31	--	--	23
Specific heat, J/(kg)(K)				
	2890 at 473 K	--	2060 at 373 K	2140 at 373 K
	2650 at 423 K	--	1913 at 311 K	1860 at 311 K
Thermal conductivity, watt/(m)(K)				
373 K	--	--	0.152	0.102
311 K	--	--	0.162	0.104
Additives	No	Yes <sup>a</sup>	Yes <sup>b</sup>	Yes <sup>c</sup>

a Organic phosphonate, antiwear additive.

b Oxidation inhibitor, corrosion inhibitor, antiwear additive.


c Antiwear (zinc dialkyldithiophosphate), oxidation inhibitor, antifoam, VI improver (polymethacrylate).

TABLE III. - HERTZIAN CONTACT CONDITIONS AT INNER AND OUTER RACES FOR THREE THRUST LOADS

[Width of rolling track is determined by major axis width.]

Race	Contact condition	Thrust load, N (lbf)		
		90 (20)	445 (100)	778 (175)
Inner	Maximum Hertzian stress, GPa (ksi)	1.28 (185)	2.09 (303)	2.45 (356)
	Semimajor axis, cm (in.)	0.0510 (0.0200)	0.0840 (0.0330)	0.0990 (0.0390)
	Semiminor axis, cm (in.)	0.0066 (0.0026)	0.0110 (0.0043)	0.0130 (0.0051)
Outer	Maximum Hertzian stress, GPa (ksi)	1.13 (164)	1.85 (269)	2.19 (318)
	Semimajor axis, cm (in.)	0.0460 (0.0180)	0.0740 (0.0290)	0.0860 (0.0340)
	Semiminor axis, cm (in.)	0.0086 (0.0034)	0.0140 (0.0055)	0.0170 (0.0065)

OF 60000 000000  
 ORIGINAL 100000



CD-12313-15

Figure 1. - EHD film thickness measurement rig.

ORIGINAL PAGE IS  
OF POOR QUALITY




Figure 2. - Film thickness measurement schematic.






Figure 3. - Effect of speed and load on EHD film thickness. Experimental measurements for 20 mm angular contact bearing. Lubricant C.

	MATERIALS PARAMETER, G	LUBRI- CANT	TEMPER- ATURE, K (°F)
□	4920	A	300 (80)
○	4320	B	
◇	3300	C	
◊	7620	D	
□	4030	A	338 (150)
△	3660	B	
◇	2740	C	
◊	5640	D	
■	3070	A	393 (250)
●	2770	B	
◆	1980	C	
●	2770	D	

— THEORY OF GRUBIN [1]





Figure 4. - Comparison of isothermal EHD fully flooded inlet theories to EHD film thickness measurements for four lubricants. Bearing type, 20-mm bore angular contact; thrust load, 90 N (20 lbf).

	MATERIALS PARAMETER, G	LUBRI- CANT	TEMPER- ATURE, K (°F)
□	4920	A	300 (80)
◻	4320	B	
◇	3300	C	
○	7620	D	
◻	4030	A	338 (150)
◻	3660	B	
◇	2740	C	
○	5640	D	
■	3070	A	393 (250)
●	2770	B	
◆	1980	C	
●	2770	D	

— THEORY OF ARCHARD AND COWKING [4]





Figure 4. - Concluded.




Figure 5. - Theoretical effect of kinematic starvation and inlet shear heating on film thickness and comparison with experiment.

NASA BMI X-RAY DATA [12 AND 13]		THEORY (HAMROCK AND DOWSON) [16]
MATERIALS PARAMETER, G	LUBRICANT	
▲ 2440	SYNTHETIC PARAFFINIC	-----
■ 2440	TYPE II ESTER	-----
◆ 4200	POLYPHENYL ETHER	-----
● 5550	FLUOROCARBON	-----
○	EXPERIMENTAL DATA FROM FIG. 4	-----




Figure 6. - Comparison with X-ray film thickness measurements.

EXPERIMENT (KUNZ AND WEINER) [16]				THEORY (HAMROCK AND DOWSON) [16]
LOAD		MATERIALS PARAMETER, G	LUBRICANT	
$1.24 \times 10^{-6}$	$9.29 \times 10^{-6}$	4507	POLYALKYL AROMATIC	-----
		8874	SYNTHETIC HYDROCARBON	-----
		5107	MODIFIED POLYALKYL ETHER	-----




Figure 7. - Comparison with optical film thickness measurements under pure sliding.

ORIGINAL PAGE IS  
OF POOR QUALITY




Figure 8. - Scanning electron micrograph showing typical appearance of ball running track at conclusion of testing (lubricant B).

**ORIGINAL PAGE IS  
OF POOR QUALITY**

1. Report No. <b>NASA TM-81431</b> <b>AVRADCOM TR-80-C-3</b>		2. Government Accession No		3 Recipient's Catalog No.	
4 Title and Subtitle <b>SOME LIMITATIONS IN APPLYING CLASSICAL EHD FILM THICKNESS FORMULAE TO A HIGH-SPEED BEARING</b>				5 Report Date	
				6 Performing Organization Code	
7. Author(s) <b>John J. Coy and Erwin V. Zaretsky</b>				8 Performing Organization Report No. <b>E-198</b>	
9. Performing Organization Name and Address <b>NASA Lewis Research Center and AVRADCOM Research and Technology Laboratories Cleveland, Ohio 44135</b>				10. Work Unit No	
				11. Contract or Grant No	
12. Sponsoring Agency Name and Address <b>National Aeronautics and Space Administration Washington, D. C. 20546 and U. S. Army Aviation Research and Development Command, St. Louis, Mo. 63166</b>				13. Type of Report and Period Covered <b>Technical Memorandum</b>	
				14. Sponsoring Agency Code	
15 Supplementary Notes					
16. Abstract <p>Elastohydrodynamic film thickness was measured for a 20-mm ball bearing using the capacitance technique. The bearing was thrust loaded to 90, 448, and 778 N (20, 100, and 175 lb). The corresponding maximum stresses on the inner race were 1.28, 2.09, and 2.45 GPa (185 000, 303 000, and 356 000 psi). Test speeds ranged from 400 to 14 000 rpm. Film thickness measurements were taken with four different lubricants: (a) synthetic paraffinic, (b) synthetic paraffinic with additives, (c) neopentylpolyol (tetra) ester meeting MIL-L-23699A specifications, and (d) synthetic cycloaliphatic hydrocarbon traction fluid. The test bearing was mist lubricated. Test temperatures were 300, 338, and 393 K. The measured results were compared to theoretical predictions using the formulae of Grubin, Archard and Cowking, Dowson and Higginson, and Hamrock and Dowson. There was good agreement with theory at low dimensionless speed, but the film was much smaller than theory predicts at higher speeds. This was due to kinematic starvation and inlet shear heating effects. Comparisons with Chiu's theory on starvation and Cheng's theory on inlet shear heating were made.</p>					
17. Key Words (Suggested by Author(s)) <b>Lubrication Bearings Wear Measurement</b>			18 Distribution Statement <b>Unclassified - unlimited STAR Category 37</b>		
19. Security Classif. (of this report) <b>Unclassified</b>		20. Security Classif. (of this page) <b>Unclassified</b>		21. No. of Pages	22 Price*

\* For sale by the National Technical Information Service, Springfield, Virginia 22161



National Aeronautics and  
Space Administration

Washington, D.C.  
20546

Official Business  
Penalty for Private Use, \$300

SPECIAL FOURTH CLASS MAIL  
BOOK

Postage and Fees Paid  
National Aeronautics and  
Space Administration  
NASA-451



**NASA**

POSTMASTER: If Undeliverable (Section 158  
Postal Manual) Do Not Return

---