

NANO EXPRESS

Open Access

Surface plasma resonant effect of gold nanoparticles on the photoelectrodes of dye-sensitized solar cells

Teen-Hang Meen^{1*}, Jenn-Kai Tsai¹, Shi-Mian Chao², Yu-Chien Lin¹, Tien-Chuan Wu¹, Tang-Yun Chang¹, Liang-Wen Ji³, Walter Water¹, Wen-Ray Chen¹, I-Tsung Tang⁴ and Chien-Jung Huang^{5*}

Abstract

In this study, we prepared different shapes of gold nanoparticles by seed-mediated growth method and applied them on the photoelectrodes of dye-sensitized solar cells (DSSCs) to study the surface plasma resonant (SPR) effect of gold nanoparticles on the photoelectrodes of dye-sensitized solar cells. The analyses of field emission scanning electron microscopy show that the average diameter of the spherical gold nanoparticles is 45 nm, the average length and width of the short gold nanorods were 55 and 22 nm, respectively, and the average length and width of the long gold nanorods were 55 and 14 nm, respectively. The aspect ratio of the short and long gold nanorods was about 2.5 and 4, respectively. The results of ultraviolet-visible absorption spectra show that the absorption wavelength is about 540 nm for spherical gold nanoparticles, and the absorption of the gold nanorods reveals two peaks. One is about 510 to 520 nm, and the other is about 670 and 710 nm for the short and long gold nanorods, respectively. The best conversion efficiency of the dye-sensitized solar cells with spherical gold nanoparticles and short and long gold nanorods added in is 6.77%, 7.08%, and 7.29%, respectively, and is higher than that of the cells without gold nanoparticles, which is 6.21%. This result indicates that the effect of gold nanoparticles on the photoelectrodes can increase the conductivity and reduce the recombination of charges in the photoelectrodes, resulting in the increase of conversion efficiency for DSSCs. In addition, the long gold nanorods have stronger SPR effect than the spherical gold nanoparticles and short gold nanorods at long wavelength. This may be the reason for the higher conversion efficiency of DSSCs with long gold nanorods than those of the cells with spherical gold nanoparticles and short gold nanorods.

Keywords: Gold nanoparticles, Dye-sensitized solar cells, Seed-mediated growth method

Background

Recently, a new type of solar cell based on dye-sensitized nanocrystalline titanium dioxide has been developed by O'Regan and Grätzel [1]. The most attractive features of this technology are reduced production costs and ease of manufacture. Dye-sensitized solar cells (DSSCs) based on nanocrystalline TiO₂ electrodes are currently attracting widespread attention as a low-cost alternative to replace conventional inorganic photo voltaic devices [2-6].

The function of DSSCs is based upon the injection of electrons of photoexcited state of the sensitizer dye into the conduction band of the semiconductor. Constant researches attempt to achieve four goals: to promote the adsorption of dye, to harvest more solar light, to smoothen the progress of transport of photoexcited electrons, and to facilitate the diffusion of an electrolyte ion. A record of the cell convertible efficiency of 11% was achieved using N3 (RuL₂(NCS)₂, L = 2,2'-bipyridyl-4,4'-dicarboxylic acid) dye and the electrolyte containing guanidinium thiocyanate [7]. Grätzel et al. used DSSCs sensitized by N3 dye using guanidinium thiocyanate as self-assembly-facilitating agent, leading to improvement in efficiency [8-11]. Some of the cheaper dyes have also been used as sensitizers to improve the absorption in the

* Correspondence: thmeen@nfu.edu.tw; chien@nuk.edu.tw

¹Department of Electronic Engineering, National Formosa University, Hu-Wei, Yunlin 632, Taiwan

⁵Department of Applied Physics, National University of Kaohsiung, Kaohsiung, 811, Taiwan

Full list of author information is available at the end of the article

visible region [12-14]. Gold nanoparticles cannot only increase the conductivity, the different shapes will result to different intensities of the surface plasma resonance (SPR) [15]. Recent studies have shown that metal or metal ion-doped semiconductor composites exhibit shift in the Fermi level to more negative potentials. Such a shift in the Fermi level improves the energetics of the composite system and enhances the efficiency of interfacial charge-transfer process [16]. In addition, Chou et al. prepared TiO₂/nanometal composite particles by dry particle coating technique. This study shows that the power conversion efficiency η of the DSSCs with a film of TiO₂/Au (or TiO₂/Ag) on the working electrode always exceeds that of the conventional DSSCs due to the presence of the Schottky barrier [17]. In this study, we prepared different shapes of gold nanoparticles by seed-mediated growth method to apply on the photoelectrodes of the DSSCs. The gold nanoparticles and DSSCs were investigated by field emission scanning electron microscopy (FE-SEM), ultraviolet-visible (UV-vis) absorption spectra, current-voltage characteristics, electrochemical impedance spectroscopy (EIS), and incident photon conversion efficiency (IPCE) analyses to study the SPR effect of the gold nanoparticles on the photoelectrodes of the dye-sensitized solar cells.

Methods

Chemicals

Hydrogen tetrachloroaurate(III) trihydrate (HAuCl₄·3H₂O, 99.9%), hexadecyltrimethylammonium bromide (CTAB), silver nitrate (AgNO₃, 99.8%), ascorbic acid (AA, 99.7%), sodium borohydride (NaBH₄, 99.9%) were used as reactants. TiO₂ powder and 4-tert-butylpyridine were used as preparation paste of the photoelectrodes. The deionized (DI) water that was used throughout the experiments was purified using a Milli-Q system (Millipore Co., Billerica, MA, USA). Glassware was cleaned by soaking it in aqua regia and then washing it with DI water.

Synthesis of gold nanoparticles

We used seed-mediated growth method to prepare the gold nanoparticles. This method involves two main steps: (1) preparation of seed solution, where the gold seed solution was prepared by first combining (5 mL, 0.5 mM) and CTAB (5 mL, 0.2 M), followed by the addition of freshly made NaBH₄ (0.6 mL, 0.01 M) under vigorous stirring. Then, the mixture was left undisturbed, aged for 2 h at 25°C for further use. (2) The other is the preparation of a growth solution that consists of HAuCl₄·3H₂O (5 mL, 1 mM), 0.2 mL AgNO₃ (spherical and short and long rods are 0.01 and 0.04 M, respectively), and CTAB (5 mL, 0.2 M). AA (70 μ L, 0.0788 M) was then





Figure 1 TEM images of gold nanoparticles with different shapes. (a, d) Spherical nanoparticles. (b, e) Short nanorods (aspect ratio (AR) 2.5). (c, f) Long nanorods (AR 4).




added and followed by brief stirring (approximately 1 min). Finally, the spherical gold nanoparticles were synthesized, every 10 s, a drop for the short gold nanorods (aspect ratio of about 2.5), and every 1 min, a drop for the long gold nanorods (aspect ratio of about 4). Lastly, 25 μL of the seed solution was added to the growth solution. The mixture was allowed to react at 30°C. Centrifugation of the gold nanoparticles was carried out at 4,000 rpm for 20 min, and the supernatant was removed and then suspended with the same volume of deionized water. This process was repeated three times.

Assembling the DSSC

We used the scraper method to prepare the photoelectrode on fluorine-doped tin oxide glass substrate. The TiO_2 coatings were prepared from commercial TiO_2 particles (P25). The compositions of the TiO_2 paste were TiO_2 , 4-tert-butylpyridine, and deionized water. The concentration of the TiO_2 paste was 10 wt.%. The concentration of the gold nanoparticles added in the TiO_2 paste is about 1.5 wt.%. With the addition of gold nanoparticles, the TiO_2 film was scraped to the desired thickness on the substrate by scratching. After drying, we pressed the TiO_2 film by suitable pressure and annealed it at 450°C for 30 min to complete the photoelectrode. The size of the TiO_2 film electrodes used was 0.25 cm^2 (0.5 cm \times 0.5 cm). Finally, we kept the photoelectrode immersed in a mixture containing a 3×10^{-4} M solution of N3 dye and ethyl alcohol at 45°C for 1.5 h in the oven. The electrode was assembled into a sandwich-type open cell using platinum plate as a counter electrode.

Characterization

The surface morphology of the samples was observed using FE-SEM. The ultraviolet-visible absorption spectra of the samples were observed using a UV-vis spectrophotometer. The current-voltage characteristics and EIS of the samples were measured using Keithley 2400 source meter (Keithley Instruments Inc., Cleveland, OH, USA) and were determined under simulated sunlight with white light intensity, $P_L = 100 \text{ mW}/\text{cm}^2$. In the IPCE






Figure 4 Cross-section FE-SEM images of the photoelectrodes of dye-sensitized solar cells. (a) Without gold nanoparticles added. (b) With spherical gold nanoparticles added. (c) With short gold nanorods added. (d) With long gold nanorods added.

measurement, a xenon lamp (Oriel (Newport Corporation, Jiangsu, China), model 66150, 75 W) was used as the light source, and a chopper and lock-in amplifier were used for phase-sensitive detection.

Results and discussion

Figure 1a,d shows the TEM images of the gold nanoparticles, which are almost spherical and uniformly dispersed with a size of about 66 nm. Figure 1b,e shows the TEM images of the short gold nanorods. It is revealed that the short gold nanorods have an aspect ratio

of 2.5. Figure 1c,f shows the TEM images of the long gold nanorods. It indicates that the long gold nanorods have an aspect ratio of 4. The ultraviolet–visible absorption spectra of the gold nanoparticles are shown in Figure 2. The standard absorption wavelength is about 540 nm for the spherical gold nanoparticles. The short gold nanorods show the transverse SPR band at 510 nm and the longitudinal SPR band at 670 nm. The long gold nanorods show the transverse SPR band at 510 nm and the longitudinal SPR band at 710 nm. Figure 3 shows the FE-SEM images of the TiO₂ films without and with




Figure 5 The UV-vis absorption spectrum of TiO₂ films without and with gold nanoparticles added.




Figure 6 The *J-V* curves of DSSCs without and with gold nanoparticles added.

Table 1 The parameters of current–voltage characteristics for DSSCs without and with different shapes of gold nanoparticles

Type	J_m (mA/cm ²)	V_m (V)	J_{sc} (mA/cm ²)	V_{oc} (V)	F.F. (%)	η (%)
Without	14.12	0.44	16.72	0.63	58.90	6.21
Nanosphere	15.41	0.44	18.20	0.64	58.37	6.77
Nanorod (AR 2.5)	15.72	0.45	18.24	0.65	59.99	7.08
Nanorod (AR 4.0)	16.19	0.45	18.30	0.65	61.23	7.29

gold nanoparticles added. The films are all smooth, as shown in Figures 3 and 4. Figure 4 shows the cross-section FE-SEM images of the TiO₂ films without and with gold nanoparticles added. The thickness of these TiO₂ films was about 22 μ m.

Figure 5 shows the UV–vis absorption spectra of the TiO₂ films without and with gold nanoparticles added. It is found that the absorption spectrum of the TiO₂ film with gold nanoparticles added is better than that of the film without gold nanoparticles, and the film with gold nanorods has stronger SPR intensity than that with spherical gold nanoparticles at long wavelength. Figure 6 shows the current–voltage characteristics of the DSSCs without and with nanoparticles added. The parameters for the short-circuit current density (J_{sc}), the open circuit potential (V_{oc}), the fill factor (F.F.), and the overall conversion efficiency (η) are listed in Table 1. It is noted that the V_{oc} of the cell with long gold nanorods is higher than those cells with spherical gold nanoparticles and short gold nanorods. This result provides an evidence to prove the reports of Subramanian et al. [16] and Chou et al. [17] and may be due to the shift in the Fermi level to more negative potentials and the presence of the Schottky barrier. From the results of Table 1, it is found that the best conversion efficiency of the dye-

Table 2 Characteristic parameters of the DSSCs without and with gold nanoparticles

Type	K_{eff} (S ⁻¹)	τ_{eff} (S)	R_s (Ω)	R_{pt} (Ω)	R_k (Ω)
Without	5.901	0.169	5.843	4.317	10.25
Nanosphere	5.258	0.190	6.602	3.325	9.80
Nanorod (AR 2.5)	5.1944	0.193	6.805	3.674	9.52
Nanorod (AR 4.0)	4.804	0.208	6.425	5.864	8.16

sensitized solar cell with long gold nanorods added is 7.29%, which is the highest among the shapes. It is noted that the conversion efficiency of the DSSCs with long gold nanorods added is higher than that of the cells with spherical gold nanoparticles. It may be because long gold nanorods have stronger surface plasma resonance effect on the TiO₂ photoelectrodes than the spherical gold nanoparticles.

Figure 7 shows the spectra of EIS for the dye-sensitized solar cells without and with gold nanoparticles added. The simulation of the equivalent circuit is discussed in to the previous reports [18-20]. The parameter R_k , which is the charge transfer resistance related to the recombination of electrons, is also listed in Table 2. The value of R_k decreases from 10.25 to 8.16 Ω when the long gold nanorods are added. It indicates that the effect of the long gold nanorods added in TiO₂ film can improve the transport properties of TiO₂ photoelectrodes, resulting in the increase of conversion efficiency of DSSCs. From the results of the current–voltage characterization and EIS, the effect of the gold nanoparticles on the TiO₂ photoelectrodes can increase the conductivity and reduce the recombination of charges in the photoelectrodes, resulting in the increase of the conversion efficiency of the DSSCs. Furthermore, the long gold nanorods have stronger surface plasma resonance intensity than the spherical gold nanoparticles at long




Figure 7 The spectra of EIS for the dye-sensitized solar cells without and with gold nanoparticles added.




Figure 8 The IPCE spectra of DSSCs without and with gold nanoparticles added.

wavelength. This may be the reason why the conversion efficiency of the dye-sensitized solar cells with long gold nanorods is higher than those of the cells with spherical gold nanoparticles and short gold nanorods. Figure 8 shows the IPCE spectra of the DSSCs without and with gold nanoparticles added. The results of IPCE analysis indicate the number of incident photons inside the cells and their contribution to the efficiency. It is noted that all the IPCE spectra are similar in shape, and the IPCE value of the long gold nanorods is higher than those of the spherical gold nanoparticles and short gold nanorods in all wavelengths. It also provides an evidence that the conversion efficiency of DSSCs with long gold nanorods is higher than those of the cells with spherical gold nanoparticles and short gold nanorods.

Conclusions

In this study, we prepared different shapes of gold nanoparticles by the seed-mediated growth method to apply on the photoelectrodes of dye-sensitized solar cells. The diameter of the spherical gold nanoparticles is 45 nm, the length and width of the short gold nanorods are 55 and 22 nm, respectively, and the length and width of the long gold nanorods are 55 and 14 nm, respectively. The absorption spectrum of the TiO₂ film with gold nanoparticles added is better than that of the film without gold nanoparticles, and the film with gold nanorods has stronger SPR intensity than that with spherical gold nanoparticles at long wavelength. This SPR effect results in higher conversion efficiency of the dye-sensitized solar cells with long gold nanorods those with spherical gold nanoparticles and short gold nanorods.

Abbreviations

AA: Amino acid; AR: Aspect ratio; DI: Deionized; DSSC: Dye-sensitized solar cells; EIS: Electrochemical impedance spectroscopy; FE-SEM: Field emission scanning electron microscopy; IPCE: Incident photon conversion efficiency; UV-vis: Ultraviolet-visible absorption spectra.

Competing interests

The authors declare that they have no competing interests.

Authors' contributions

THM and JKT wrote this manuscript. SMC, YCL, and TYC carried out the preparation of the samples. TCW, LWJ, and WW carried out the current-voltage measurements. WRC, ITT and CJH carried out the EIS and IPCE measurements. All authors read and approved the final manuscript.

Acknowledgements

This research is supported by the National Science Council, Republic of China, under contract nos. NSC 101-2221-E-150-041 and NSC 100-2221-E-150-058.

Author details

¹Department of Electronic Engineering, National Formosa University, Hu-Wei, Yunlin 632, Taiwan. ²Department of Electrical Engineering, Hsiuping University of Science and Technology, Taichung 412, Taiwan. ³Institute of Electro-Optical and Materials Science, National Formosa University, Yunlin 632, Taiwan. ⁴Department of Greenery, National University of Tainan, Tainan 700, Taiwan. ⁵Department of Applied Physics, National University of Kaohsiung, Kaohsiung 811, Taiwan.

Received: 9 July 2013 Accepted: 4 September 2013

Published: 30 October 2013

References

1. O'Regan B, Grätzel M: A low-cost, high-efficiency solar cell based on dye-sensitized colloidal TiO₂ films. *Nature* 1991, **353**:737–740.
2. McFarland EW, Tang K: A photovoltaic device structure based on internal electron emission. *Nature* 2003, **421**:616–618.
3. Wei BY, Lin HM, Kao CC, Li AK: Effect of calcination on photocatalytic activity of TiO₂ nanopowders. *Mater Sci Eng* 2003, **35**(1):64–69.
4. Li Y, Hagen J, Schaffrath W, Otschik P, Haarer D: Titanium dioxide films for photovoltaic cells derived from a sol-gel process. *Sol Energ Mat Sol C* 1999, **56**:167–174.
5. Tachibana Y, Hara K, Takano S, Sayama K, Arakawa H: Investigations on anodic photocurrent loss processes in dye sensitized cells: comparison between nanocrystalline SnO₂ and TiO₂ films. *Chem Phys Lett* 2002, **364**:297–302.
6. O'Regan B, Schwartz DT, Zakeeruddin SM, Grätzel M: Electrodeposited nanocomposite n-p heterojunctions for solid-state dye-sensitized photovoltaics. *Adv Mater* 2000, **12**:1263–1267.
7. Grätzel M: Conversion of sunlight to electric power by nanocrystalline dye-sensitized solar cells. *J Photoch Photobio A* 2004, **164**:3–14.
8. Kuang D, Klein C, Snaith HJ, Baker RH, Zakeeruddin SM, Grätzel M: A new ion-coordinating ruthenium sensitizer for mesoscopic dye-sensitized solar cells. *Inorg Chim Acta* 2008, **361**:699–706.
9. Mende LS, Grätzel M: TiO₂ pore-filling and its effect on the efficiency of solid-state dye-sensitized solar cells. *Thin Solid Films* 2006, **500**:296–301.
10. Nazeeruddin MK, Klein C, Liska P, Grätzel M: Synthesis of novel ruthenium sensitizers and their application in dye-sensitized solar cells. *Coord Chem Rev* 2005, **249**:1460–1467.
11. Ito S, Murakami TN, Comte P, Liska P, Grätzel C, Nazeeruddin MK, Grätzel M: Fabrication of thin film dye sensitized solar cells with solar to electric power conversion efficiency over 10%. *Thin Solid Films* 2008, **516**:4613–4619.
12. Kay A, Grätzel M: Artificial photosynthesis: 1. Photosensitization of TiO₂ solar cells with chlorophyll derivatives and related natural porphyrins. *J Phys Chem* 1993, **97**:6272–6277.
13. Kay A, Humphry-Baker R, Grätzel M: Artificial photosynthesis. 2. Investigations on the mechanism of photosensitization of nanocrystalline TiO₂ solar cells by chlorophyll derivatives. *J Phys Chem* 1994, **98**:952–959.
14. Cherepy NJ, Smestad GP, Grätzel M, Zhang JZ: Ultra fast electron injection: implications for a photoelectrochemical cell utilizing an anthocyanin dye-sensitized TiO₂ nanocrystalline electrode. *J Phys Chem B* 1997, **101**:9342–9351.
15. Mock JJ, Barbic M, Smith DR, Schultz DA, Schultz S: Shape effects in plasmon resonance of individual colloidal silver nanoparticles. *J Chem Phys* 2002, **116**:6755–6759.
16. Subramanian V, Wolf EE, Kamat PV: Catalysis with TiO₂/gold nanocomposites. Effect of metal particle size on the Fermi level equilibration. *J Am Chem Soc* 2004, **126**:4943–4950.
17. Chou CS, Yang RY, Yeh CK, Lin YJ: Preparation of TiO₂/nano-metal composite particles and their applications in dye-sensitized solar cells. *Powder Technol* 2009, **194**:95–105.
18. Kern R, Sastrawan R, Ferber J, Stangl R, Luther J: Modeling and interpretation of electrical impedance spectra of dye solar cells operated under open-circuit conditions. *Electrochim Acta* 2002, **47**:4213–4225.
19. Han L, Koide N, Chiba Y, Islam A, Mitate T: Modeling of an equivalent circuit for dye-sensitized solar cells: improvement of efficiency of dye-sensitized solar cells by reducing internal resistance. *Comptes Rendus Chimie* 2006, **9**:645–651.
20. Adachi M, Sakamoto M, Jiu J, Ogata Y, Isoda S: Electron transport in dye-sensitized solar cells using electrochemical impedance spectroscopy. *J Phys Chem* 2006, **110**:13872–13880.

doi:10.1186/1556-276X-8-450

Cite this article as: Meen et al.: Surface plasma resonant effect of gold nanoparticles on the photoelectrodes of dye-sensitized solar cells. *Nanoscale Research Letters* 2013 **8**:450.