

Available online at [www.sciencedirect.com](http://www.sciencedirect.com)

ScienceDirect

journal homepage: [www.jfda-online.com](http://www.jfda-online.com)

## Review Article

# Nanotechnology in food science: Functionality, applicability, and safety assessment

Xiaojia He <sup>a,b</sup>, Huey-Min Hwang <sup>a,\*</sup><sup>a</sup> Department of Biology, Jackson State University, Jackson, MS, USA<sup>b</sup> Department of Marine Sciences, the University of Georgia, Athens, GA, USA

## ARTICLE INFO

## Article history:

Available online 16 July 2016

## Keywords:

food science  
 manufacturing  
 nanotechnology  
 packaging  
 safety assessment

## ABSTRACT

Rapid development of nanotechnology is expected to transform many areas of food science and food industry with increasing investment and market share. In this article, current applications of nanotechnology in food systems are briefly reviewed. Functionality and applicability of food-related nanotechnology are highlighted in order to provide a comprehensive view on the development and safety assessment of nanotechnology in the food industry. While food nanotechnology offers great potential benefits, there are emerging concerns arising from its novel physicochemical properties. Therefore, the safety concerns and regulatory policies on its manufacturing, processing, packaging, and consumption are briefly addressed. At the end of this article, the perspectives of nanotechnology in active and intelligent packaging applications are highlighted.

Copyright © 2016, Food and Drug Administration, Taiwan. Published by Elsevier Taiwan LLC. This is an open access article under the CC BY-NC-ND license (<http://creativecommons.org/licenses/by-nc-nd/4.0/>).

## 1. Introduction

Nanotechnology has become one of the most promising technologies to revolutionize conventional food science and the food industry. Nanotechnology-assisted processing and packaging has proved its competence in food systems [1]. Different preparation technology could produce nanoparticles with different physical properties; thus, they could be used in food [2]. However, not only is the public perception regarding this new technology uncertain [3], but also the regulation agencies have not yet reached an agreement on worldwide-applicable rules [4,5]. Despite significant debate over the necessity of establishing new regulations for nanotechnology, United States Environmental Protection Agency, National

Institute for Occupational Safety and Health, the Food and Drug Administration (FDA), the Health and Consumer Protection Directorate of the European Commission, International organizations such as the International Organization for Standardization and the Organization for Economic Cooperation and Development, as well as many regulatory bodies have issued multiple guidance documents with respect to the potential risks posed by nanomaterials.

- On August 5, 2015, U.S. FDA issued one final guidance document related to the use of nanotechnology in food for animals [6].
- On April 6, 2015, U.S. Environmental Protection Agency proposed one-time reporting and recordkeeping

\* Corresponding author. Biology Department, Jackson State University, Box 18540, 1400 Lynch Street, Jackson, MS 39217, USA.

E-mail address: [huey-min.hwang@jsums.edu](mailto:huey-min.hwang@jsums.edu) (H.-M. Hwang).

<http://dx.doi.org/10.1016/j.jfda.2016.06.001>

1021-9498/Copyright © 2016, Food and Drug Administration, Taiwan. Published by Elsevier Taiwan LLC. This is an open access article under the CC BY-NC-ND license (<http://creativecommons.org/licenses/by-nc-nd/4.0/>).

requirements under the Toxic Substances Control Act Section 8(a) [7].

- On June 24, 2014, U.S. FDA issued three final guidance documents related to the use of nanotechnology in regulated products, including cosmetics and food substances [8].
- In November 2007, The Working Party on Manufactured Nanomaterials of the Organization for Economic Cooperation and Development launched the Sponsorship Program for the Testing of Manufactured Nanomaterials (Testing Programme) [9].

The challenge remains for regulators that the lack of worldwide-accepted rules may ultimately fail to provide appropriate guidance in response to general public and occupational health risks associated with the manufacture, use, and disposal of nanomaterials.

Current scientific regulation of food nanotechnology is characterized by numerous uncertainties regarding risk characteristics. Functionality of food nanotechnology determines its range of applicability. Food nanotechnology can affect the bioavailability and nutritional value of food on the basis of its functions [10]. It is recognized that the biological properties (including toxicological effects) of nanomaterials are largely dependent on their physicochemical parameters [11–13]. In fact, the major links between nanotechnology and the food industry are enhancing food security, extending storage life, improving flavor and nutrient delivery, allowing pathogen/toxin/pesticide detection, and serving functional foods, as depicted in Figure 1. Achievements have been made in various areas of food systems, including foods and food packaging [14]. Most researches emphasize the regulation of

nanotechnology in food packaging and processing [15]. Unfortunately, there is no comprehensive review on the potential risks associated with the functionality and applicability of food nanotechnology yet.


In this review, we mainly focus on the aspects of the functionality and applicability of food nanotechnology, and the current progress in their regulation and risk/safety assessment. In particular, some nanomaterials are toxic to animals and humans; they act as oxidant scavengers or antimicrobial agents [16,17]. Moreover, depending on their applications in processing and packaging, and as actual food ingredients, nanocomposites may have completely different consequences. Therefore, a clear view of the potential hazards associated with their functionality and applicability is urgently demanded for providing further guidance on the safety of food nanotechnology.

## 2. Functionality and applicability of food nanotechnology

### 2.1. Protection against biological deterioration

#### 2.1.1. Antimicrobials

Microbial contamination has been leading to pathogenic infections and poor nutrition associated with weaning foods. Thus, dealing with bacterial deterioration is one of the most critical subjects in the production, processing, transport, and storing of food. Novel nanoantimicrobials have shown promising effects on safeguarding food deterioration, thereby extending the shelf life of food. A number of metal and metal oxide nanomaterials have long been suggested to be effective



**Figure 1** – Diagram showing the development of nanotechnology in food science/industry and its functionality, applicability, and safety assessments.

as antimicrobials. Their intrinsic physicochemical properties allow excessive formation of reactive oxygen species (ROS), leading to oxidative stress and subsequent cell damage [18,19]. Furthermore, the release of metal ions outside the cell, at the cell surface, or within the cell can alter cellular structure or function. Thus, metal/metal oxide-based nanocomposites have been utilized in food packaging and coating, or even as ingredients.

Silver nanoparticles and nanocomposites are one of the most widely used nanomaterials, as antimicrobials, in the food industry. A dozen silver-containing zeolites or other substances have been approved by the U.S. FDA for use as food contact materials for the purpose of disinfection [20]. Silver nanoparticles likely serve as a source of  $\text{Ag}^+$  ions, binding to membrane proteins, forming pits, causing other morphological changes [21], and catalyzing the generation of ROS in bacterial cells, subsequently leading to cell death through oxidative stress [22]. Nevertheless, multiple latest research studies suggested that silver nanocomposites are safe for food packaging, with no detectable or insignificant levels of silver nanoparticles that are released and migrated from impregnated containers into real food samples and food simulants [23,24].

Nanocomposites offer added stability, which is important for sustaining antimicrobial activity and reducing the likelihood of migration of metal ions into stored foods. Polymers are largely engineered to form nanocomposites with metal/metal oxide nanomaterials for food application. Among these polymers, low-density polyethylene (LDPE), gelatin, isotactic polypropylene, and polylactic acid are most widely used as part of nanocomposites. For instance, Ag/LDPE [25,26], CuO/LDPE [26],  $\text{TiO}_2$ /LDPE [27], and ZnO/LDPE [26,28], are reported to be used in food applications. In addition, ZnO/gelatin [29–31], Ag/OMt–LDPE [32], Ag/poly(3-hydroxybutyrate-co-18 mol%-3-hydroxyvalerate) [33], ZnO/polycarbonate [34], ZnO/isotactic polypropylene [35], ZnO/polylactic acid [36,37], and ZnO/graphene oxide/polylactic acid [38], are targeted specifically for food packaging applications. Earlier, chitosan, polystyrene, polyvinylprolidone, and poly(vinyl chloride) have also been reported as nanocomposite films that bind to Cu or ZnO nanomaterials to inactivate food pathogens [39–41].

### 2.1.2. Increasing bioavailability

The use of nanomaterials as delivery systems to improve the bioavailability of bioactive compounds as nutritional supplements has been reviewed in some studies [42,43]. Bioactives, such as coenzyme Q10 (CoQ10) [44], vitamins [44], iron [45], calcium [46], curcumin [47], etc., have been widely tested in nanodelivery systems. Nanodelivery vehicles such as association colloids (e.g., casein micelles) [48], lipid-based nanoencapsulators/nanocarriers [49], nanoemulsions [50], biopolymeric nanoparticles [51], nanolaminates [52], and nanofibers [53,54] are largely developed.

Generally, nanodelivery systems can increase the bioavailability of bioactives in various ways. It is noteworthy that the bioavailability of bioactive compounds can be evaluated quantitatively using the following equation and as illustrated in Figure 2:

$$BA = B^* \times A^* \times T^*$$


where BA is the oral bioavailability of bioactive compounds,  $B^*$  is bioaccessibility,  $A^*$  is absorption, and  $T^*$  is molecular transformation [43,55]. Thus, in order to maximize the bioavailability of bioactives, one can improve the bioaccessibility and absorption, and alter the molecular structure that might have occurred during digestion. By altering particle size, solubility can be improved through an increase of the surface area-to-volume ratio, leading to an increase in bioaccessibility. For instance, CoQ10 is lipophilic and has very low bioavailability due to its poor water solubility [56]. A novel lipid-free nano-CoQ10 system modified with different surfactants was formulated to improve the solubility and bioavailability of CoQ10 by oral administration [57]. In addition, gastrointestinal permeability can be enhanced by selecting appropriate formulation surfactants [49]. This can lead to an increase in absorption as well as bioaccessibility. For instance, hydrochloric acid has been used as a surfactant for the preparation of soy protein-stabilized acidic oil-in-water green tea catechin nanoemulsions, resulting in increased permeability [58]. Moreover, surface-modified nanodelivery systems have been developed to control their interactions with biologic milieu and therefore their bio-distribution. In fact, it is possible to modify the nanodelivery systems by chemical grafting of hydrophilic molecules. Among them poly(ethylene glycol) is the most known hydrophilic molecule [59]. By doing so, molecular transformation can be controlled in order to provide maximum bioaccessibility and absorption.

## 2.2. Protection against chemical ingredients

### 2.2.1. Antioxidants

Although some metal/metal oxide nanomaterials are known to cause oxidative stress via formation of ROS [13,60,61], less reactive nanomaterials are developed to act as antioxidant carriers. Polymeric nanoparticles are suggested to be suitable for the encapsulation of bioactive compounds (e.g., flavonoids and vitamins) and to release them in acidic environments (i.e., stomach) [62]. Similarly,  $\text{SiO}_2$ -gallic acid nanoparticles as novel nanoantioxidants are developed and tested based on its scavenging capacity of 2,2-diphenyl-1-picrylhydrazyl radicals [63].

Furthermore, application of antioxidant treatments in association with edible coating is the most common way to control browning of fresh-cut fruits [64]. It is well known that browning of fresh-cut fruits is an undesirable effect brought by the conversion of phenolic compounds into dark colored pigments in the presence of  $\text{O}_2$ , during storage and marketing [65]. However, there are only a few applications of nanomaterials directly as antibrowning agents. Nano-ZnO-coated active packaging has been reported to be a viable alternative to common technologies for improving the shelf-life properties of “Fuji” apples as a fresh-cut product [66]. In their study, the activities of polyphenol oxidase and pyrogallol peroxidase were significantly decreased in fruits stored in nano-ZnO packaging. Moreover, the initial appearance of fresh-cut Fuji



$$\text{Bioavailability} = \text{bioaccessibility} \times \text{absorption} \times \text{transformation}$$

**Figure 2** – Schematic diagram showing the delivery of bioactive components in food matrix. The overall oral bioavailability of bioactives is governed by three main factors: bioaccessibility, absorption, and transformation. GIT: gastro-intestinal tract. Reproduced with permission from “Excipient nanoemulsions for improving oral bioavailability of bioactives,” by L. Salvia-Trujillo, O. Martín-Belloso, D.J. McClements, 2016, *Nanomaterials*, 6, p. 17 [43].

apples was retained, and the browning index was prevented in fresh-cut fruits stored in nano-ZnO packaging, which was only 23.9, much lower than that of the control group (31.7) on day 12. Zambrano-Zaragoza et al [67] also reported that treatment of fresh-cut Red Delicious apples with nanocapsules containing DL- $\alpha$ -tocopherol with a poly- $\epsilon$ -caprolactone

biopolymer membrane significantly reduced the browning index.

#### 2.2.2. Flavors

As one of most important parts of the food system, flavors deliver sensory perception of taste and smell to enhance



the overall eating experience. Nanoencapsulation techniques have widely been used to improve flavor release and flavor retention, and to deliver culinary balance [68]. It has also been shown that SiO<sub>2</sub> nanomaterials can act as carriers of fragrances or flavors in food and nonfood products [69,70].

### 2.3. Enhancement of physical properties

#### 2.3.1. Color additives

As required by law, food color additives are subjected to approval by the Office of Cosmetics and Colors in the Center for Food Safety and Applied Nutrition, the U.S. FDA, and must be used only in compliance with the approved uses, specifications, and restrictions. With the advent of nanotechnology, a wide range of nanoscale color additives are being studied and manufactured. Certain nanomaterial products have currently been approved for use as food color additives, which have a vital role in the psychological appeal of consumer products. The U.S. FDA approved TiO<sub>2</sub> as a food color additive with the stipulation that the additive should not to exceed 1% w/w [71] and now are exempted from certification [72]. Color additive mixtures for food use made with TiO<sub>2</sub> may also contain SiO<sub>2</sub> and/or Al<sub>2</sub>O<sub>3</sub>, as dispersing aids—not more than 2% total. However, the use of carbon black as a food color additive is no longer authorized [73].

#### 2.3.2. Anticaking agents

SiO<sub>2</sub> is used mainly to thicken pastes, as an anticaking agent to maintain flow properties in powdered products, and as a carrier of fragrances or flavors in food and nonfood products. It has widely been applied in food products and registered within the EU as a food additive (E551). Recent research showed that in powdered food materials containing E551, at least a part of the SiO<sub>2</sub> is in the nanosize range [69,70]. Moreover, findings also suggest that, upon consumption of foods containing E551, the gut epithelium is most likely exposed to nanosized SiO<sub>2</sub> [74,75].

#### 2.3.3. Others

In addition to the abovementioned benefits, nanomaterials have also been constantly developed to enhance the physical and mechanical properties of packaging in terms of tensile strength, rigidity, gas permeability, water resistance, flame resistance, etc. Aimed at providing those aforementioned properties, polymer nanocomposites are the latest materials with a huge potential for application in the active food packaging industry [76]. Polymer nanocomposites with layered silicates were introduced in the 1990s [77,78]. As these new polymer nanomaterials are much stronger [79], more flame resistant [80], as well as having a potential role in UV-shielding applications [81], they are widely reported to have the potential to completely transform the food packaging industry [82]. Readers are encouraged to read the more extensive reviews listed in the reference section [83,84]. Notably, biodegradable polymer nanocomposites from renewable sources (biopolymers) are emerging as an alternative to synthetic plastic packaging materials, especially for use in short-term packaging and disposable applications [85,86].

## 3. Safety concerns

As the investigation into the application of nanotechnology in the food sector increases, the potential of nanotechnology in food science/industry also expands, and consequently so does the human exposure to these substances [87]. It is inevitable that human exposure to nanomaterials will increase in various ways, either intended or unintended. However, a few studies have focused on the potential toxicity of the presence of nanomaterials in foods, by analyzing food samples used in food additives/ingredients and food packaging. Little is known about the bioavailability, biodistribution, routes of nanomaterials, and the ultimate toxicity upon exposure to them. Most noticeably, nanomaterials, serving as food additives, come in direct contact with human organs. It may result in higher levels of exposure depending on their concentration in food and the amount of that food consumed. Increasing uses of nanomaterial substances in foods as flavor or color additives have attracted significant attention of public and government sectors [88]. A study on TiO<sub>2</sub> in sugar-coated chewing gum found that over 93% of TiO<sub>2</sub> in gum is of nanosize [89]. It is unexpectedly easy for TiO<sub>2</sub> to be released, be swallowed by a person chewing the gum, and be accumulated in the body gradually [89]. Similarly, the gut epithelium is most likely exposed to SiO<sub>2</sub> nanoparticles upon consumption of foods containing E551 [74,75].

In addition, nanoencapsulation also allows direct contact of nanomaterials with humans through oral intake. SiO<sub>2</sub> nanomaterials, one of the most used food nanomaterials, have been studied as carriers of fragrances or flavors in food products [69,70]. Lipid-based nanoencapsulation systems are also being developed to enhance the performance of antioxidants by improving their solubility and bioavailability [90], and entrap bioactives for targeted site-specific delivery and efficient absorption [91]. However, the safety of nanoencapsulation remains uninvestigated and calls for further risk assessment [92], particularly for long-term toxicity [88,93].

Nanoscale edible coatings have emerged as an attractive alternative to preserve food quality, extend storage life, and prevent microbial spoilage [94,95], allowing direct exposure of humans to nanomaterials. For instance, gelatin-based edible coatings containing cellulose nanocrystals [96], chitosan/nanosilica coatings [97], chitosan film with nano-SiO<sub>2</sub> [98], and alginate/lysozyme nanolaminate coatings have been reported to preserve the quality of fresh foods during extended storage [99]. In addition, another novel nanopacking method by blending polyethylene with nanopowder (nano-Ag, kaolin, anatase TiO<sub>2</sub>, and rutile TiO<sub>2</sub>) was also evaluated to assess its effect on preservation quality of strawberry fruits (*Fragaria ananassa* Duch. cv Fengxiang) [100]. However, none of them provided toxicological studies with respect to nanomaterial exposure.

In other cases, exposure may occur unintentionally via leaching from nanopackaging [101]. Nanoclay from food contact materials was found to migrate into food simulants [102]. It was observed that aluminum migrated into solutions both in dissolved form and as a part of nanoparticles, with a maximum migration value of 51.65 ng/cm<sup>2</sup> for the Aisaika bags and 24.14 ng/cm<sup>2</sup> for the Debbie Meyer bags [102].

Furthermore, it was found that migration of nanoclay from the multilayer film into food simulants increased with increasing contact time and temperature [103]. Moreover, inhalation of food packaging nanomaterials and their entrance through skin penetration is almost exclusively related to workers in the nanomaterial-producing industries [76]. Nevertheless, the number of tests on migration is still largely limited, and further investigation is needed before widely applying these materials.

It should be noted that the ultimate fate and toxicity of nanomaterials in foods and food packaging depend on physicochemical characteristics and dose [12,13]. Safe application of nanotechnology to the food industry requires thorough characterization and assessment *in silico* [104,105], *in vitro* [60], and *in vivo* [61]. Altogether, taking into consideration physical forces, osmotic concentration, pH, chemical factors, biological molecules, and commensal microbes, their absorption, distribution, metabolism, excretion, and ultimate toxicity could be quantified and evaluated for risk assessment [12,13,106,107].

Two major concerns, allergy and heavy metal release, of the adverse effects of nanomaterial exposure are briefly discussed in the following sections.

### 3.1. Allergies

Although nanotechnology is being developed to advance food-allergen management [108,109], one cannot ignore the fact that certain nanomaterials may promote allergic pulmonary inflammation [110–112]. A review of literature revealed promoted inflammatory response and increased ROS production to be common immune responses to nanomaterial exposure [112]. Literature indicates that SiO<sub>2</sub> nanoparticles can induce allergen-specific Th2-type allergic immune responses *in vivo*, as evident from a study of female BALB/c mice exposed to nanoparticles [110]. Intranasal exposure to ovalbumin (OVA) plus SiO<sub>2</sub> nanoparticles tended to induce a relatively high level of OVA-specific immunoglobulin (Ig) E, IgG, and IgG1 antibodies [110]. Exposure to Ag nanoparticles was also reported

to be able to induce nanoparticle-specific immune responses [113].

Moreover, carbon nanomaterials are well known to cause allergic inflammation. It has been reported that single- and multiwalled carbon nanotubes increased lung inflammation and allergen-specific IgE levels in mice sensitized to OVA egg allergen [114]. Ryman-Rasmussen et al [115] also reported that multiwalled carbon nanotubes with preexisting inflammation would increase airway fibrosis in mice with allergic asthma. Furthermore, the research group of Lefebvre et al [116] found that carbon black nanoparticles with a smaller particle size, a higher specific surface area, and higher purity were associated with the direct adjuvant effect on Th2 cells in this genetically susceptible model of OVA allergy. They reported that cocubation of OVA<sub>323–339</sub> peptide with 12 µg/mL of 22 nm carbon black nanoparticles enhanced gene expression of *interleukin-4* (IL-4), IL-10, and IL-13, all allergy-associated Th2 cytokines. In addition, cocubation of OVA<sub>323–339</sub> peptide with 12 µg/mL of 9 nm carbon black nanoparticles significantly enhanced IL-13 gene expression concurrent with the downregulation of the Th1-associated transcription factor *Stat4*.

### 3.2. Heavy metal release

Metal-based nanomaterials integrated with food contact polymers have been reported to enhance mechanical and barrier properties, prevent photodegradation of plastics, and serve as effective antimicrobials in the form of heavy metal ions [117]. It is well known that releases of heavy metals from nanomaterials are one of the major routes that lead to toxic outcomes [12,13]. Thus, one cannot ignore the possibility of the adverse effects of heavy metal releases into food simulants, particularly their long-term accumulation. Among metal-based nanomaterials, ZnO [118], Ag [119,120], and CuO [121] are three mostly reported metal-leaching nanomaterials. Most likely, the release of metal ions from those metallic nanomaterials is highly correlated to an increase of intracellular ROS level [118], further resulting in lipid peroxidation and DNA damage.




Figure 3 – Development of nanotechnology and its application in active and intelligent packaging. Reproduced with permission from “Nanotechnology development in food packaging: A review,” by S.D.F. Mihindukulasuriya, L.T. Lim, 2014, *Trends Food Sci Technol*, 40, p. 149–67 [131].

#### 4. Implication and perspectives

One should be cautious but not afraid, to embrace the development of nanotechnology and its application in food science and the food industry, along with its success in other various fields [12,122–124]. Although the fate and potential toxicity of nanomaterials are not fully understood at this time, it is evident that there have been significant advances in the application of novel nanotechnology in the food industry. In addition to the benefits we discuss in this review, nanotechnology can also assist in the detection of pesticides [125], pathogens [126,127], and toxins [128], serving in the food quality tracking–tracing–monitoring chain. Furthermore, nanotechnology has the potential to transform our future food packaging materials, as part of an active and intelligent packaging system [129–131], as described in Figure 3. However, the challenges to develop a healthy and sustainable food industry remain even with the advent of nanotechnology. The associated health, safety, and environmental impacts should be addressed and regulated at the forefront. To be successful in the long run, proper education of the public is also paramount in the introduction and development of nanotechnology in food system.

#### Conflicts of interest

All contributing authors declare no conflicts of interest.

#### Acknowledgments

This study was supported by the National Science Foundation-Centers of Research Excellence in Science and Technology program, with grant #HRD-157754 to Jackson State University.

#### REFERENCES

- [1] Weiss J, Takhistov P, McClements DJ. Functional materials in food nanotechnology. *J Food Sci* 2006;71:R107–16.
- [2] Feng T, Xiao Z, Tian H. Recent patents on nano flavor preparation and its application. *Recent Pat Food Nutr Agric* 2010;2:243–50.
- [3] Bieberstein A, Roosen J, Marette S, Blanchemanche S, Vandermoere F. Consumer choices for nano-food and nano-packaging in France and Germany. *Eur Rev Agric Econ* 2013;40:73–94.
- [4] Ravichandran R. Nanotechnology applications in food and food processing: innovative green approaches, opportunities and uncertainties for global market. *Int J Green Nanotechnol Phys Chem* 2010;1:P72–96.
- [5] Coles D, Frewer LJ. Nanotechnology applied to European food production—a review of ethical and regulatory issues. *Trends Food Sci Technol* 2013;34:32–43.
- [6] FDA issues guidance on the use of nanomaterials in food for animals. Division of Dockets Management, HFA-305, U.S. Food and Drug Administration; 2015. <http://www.fda.gov/AnimalVeterinary/NewsEvents/CVMUpdates/ucm457112.htm>, [accessed 18.07.16].
- [7] Control of Nanoscale Materials under the Toxic Substances Control Act. US Environmental Protection Agency; 2015. <https://www.epa.gov/reviewing-new-chemicals-under-toxic-substances-control-act-tsca/control-nanoscale-materials-under>, [accessed 18.07.16].
- [8] FDA issues guidance to support the responsible development of nanotechnology products. U.S. Food and Drug Administration; 2014. <http://www.fda.gov/NewsEvents/Newsroom/PressAnnouncements/ucm402499.htm>, [accessed 18.07.16].
- [9] Testing programme of manufactured nanomaterials. Organisation for Economic Co-operation and Development; 2007. <http://www.oecd.org/chemicalsafety/nanosafety/testing-programme-manufactured-nanomaterials.htm>, [accessed 18.07.16].
- [10] Srinivas PR, Philbert M, Vu TQ, Huang Q, Kokini JL, Saos E, Chen H, Peterson CM, Friedl KE, McDade-Ngutter C, Hubbard V, Starke-Reed P, Miller N, Betz JM, Dwyer J, Milner J, Ross SA. Nanotechnology research: applications in nutritional sciences. *J Nutr* 2010;140:119–24.
- [11] Hwang HM, Ray PC, Yu H, He X. Toxicology of designer/engineered metallic nanoparticles. In: Luque R, Varma RS, Clark JH, Kraus GA, editors. Sustainable preparation of metal nanoparticles: methods and applications. Cambridge, UK: Royal Society of Chemistry; 2012. p. 190–212.
- [12] He X, Aker WG, Huang M-J, Watts JD, Hwang H-M. Metal oxide nanomaterials in nanomedicine: applications in photodynamic therapy and potential toxicity. *Curr Top Med Chem* 2015;15:1887–900.
- [13] He X, Aker WG, Fu PP, Hwang H-M. Toxicity of engineered metal oxide nanomaterials mediated by nano-bio-eco-interactions: a review and perspective. *Environ Sci Nano* 2015;2:564–82.
- [14] Durán N, Marcato PD. Nanobiotechnology perspectives. Role of nanotechnology in the food industry: a review. *Int J Food Sci Technol* 2013;48:1127–34.
- [15] Chau CF, Wu SH, Yen GC. The development of regulations for food nanotechnology. *Trends Food Sci Technol* 2007;18:269–80.
- [16] Karakoti A, Singh S, Dowding JM, Sealac S, Self WT. Redox-active radical scavenging nanomaterials. *Chem Soc Rev* 2010;39:4422–32.
- [17] de Azeredo HMC. Antimicrobial nanostructures in food packaging. *Trends Food Sci Technol* 2013;30:56–69.
- [18] Wu H, Yin J-J, Wamer WG, Zeng M, Lo YM. Reactive oxygen species-related activities of nano-iron metal and nano-iron oxides. *J Food Drug Anal* 2014;22:86–94.
- [19] Fu PP, Xia Q, Hwang H-M, Ray PC, Yu H. Mechanisms of nanotoxicity: generation of reactive oxygen species. *J Food Drug Anal* 2014;22:64–75.
- [20] U.S. FDA. Environmental Decision Memo for Food Contact Notification No. 1569. Biologist, Regulatory Team 2, Division of Biotechnology and GRAS Notice Review (HFS-255); 2015.
- [21] Morones JR, Elechiguerra JL, Camacho A, Holt K, Kouri JB, Ramírez JT, Yacaman MJ. The bactericidal effect of silver nanoparticles. *Nanotechnology* 2005;16:2346–53.
- [22] Kim JS, Kuk E, Yu KN, Kim J-H, Park SJ, Lee HJ, Kim SH, Park YK, Park YH, Hwang CY, Kim YK, Lee YS, Jeong DH, Cho MH. Antimicrobial effects of silver nanoparticles. *Nanomed Nanotechnol Biol Med* 2007;3:95–101.
- [23] Addo Ntim S, Thomas TA, Begley TH, Noonan GO. Characterisation and potential migration of silver nanoparticles from commercially available polymeric food contact materials. *Food Addit Contam Part A* 2015;32:1003–11.



- [24] Metak AM, Nabhani F, Connolly SN. Migration of engineered Nanoparticles from packaging into food products. *LWT Food Sci Technol* 2015;64:781–7.
- [25] Becaro AA, Puti FC, Correa DS, Paris EC, Marconcini JM, Ferreira MD. Polyethylene films containing silver nanoparticles for applications in food packaging: characterization of physico-chemical and anti-microbial properties. *J Nanosci Nanotechnol* 2015;15:2148–56.
- [26] Beigmohammadi F, Peighambaroust SH, Hesari J, Azadmard-Damirchi S, Peighambaroust SJ, Khosrowshahi NK. Antibacterial properties of LDPE nanocomposite films in packaging of UF cheese. *LWT Food Sci Technol* 2016;65:106–11.
- [27] Bodaghi H, Mostofi Y, Oromiehie A, Ghanbarzadeh B, Hagh ZG. Synthesis of clay–TiO<sub>2</sub> nanocomposite thin films with barrier and photocatalytic properties for food packaging application. *J Appl Polym Sci* 2015;132:41764.
- [28] Esmailzadeh H, Sangpour P, Shahraz F, Hejazi J, Khaksar R. Effect of nanocomposite packaging containing ZnO on growth of *Bacillus subtilis* and *Enterobacter aerogenes*. *Mater Sci Eng C* 2016;58:1058–63.
- [29] Shankar S, Teng X, Li G, Rhim JW. Preparation, characterization, and antimicrobial activity of gelatin/ZnO nanocomposite films. *Food Hydrocoll* 2015;45:264–71.
- [30] Umamaheswari G, Sanuja S, John VA, Kanth SV, Umopathy MJ. Preparation, characterization and anti-bacterial activity of zinc oxide-gelatin nanocomposite film for food packaging applications. *Polym Polym Compos* 2015;23:199–204.
- [31] Arfat YA, Benjakul S, Prodpran T, Sumpavapol P, Songtipya P. Physico-mechanical characterization and antimicrobial properties of fish protein isolate/fish skin gelatin–zinc oxide (ZnO) nanocomposite films. *Food Bioprocess Technol* 2016;9:101–12.
- [32] Savas LA, Hancer M. Montmorillonite reinforced polymer nanocomposite antibacterial film. *Appl Clay Sci* 2015;108:40–4.
- [33] Castro-Mayorga JL, Fabra MJ, Lagaron JM. Stabilized nanosilver based antimicrobial poly (3-hydroxybutyrate-co-3-hydroxyvalerate) nanocomposites of interest in active food packaging. *Innov Food Sci Emerg Technol* 2016;33:524–33.
- [34] Dhapte V, Gaikwad N, More PV, Banerjee S, Dhapte VV, Kadam S, Khanna PK. Transparent ZnO/polycarbonate nanocomposite for food packaging application. *Nanocomposites* 2015;1:106–12.
- [35] Cimmino S, Duraccio D, Marra A, Pezzuto M, Romano I, Silvestre C. Effect of compatibilisers on mechanical, barrier and antimicrobial properties of iPP/ZnO nano/microcomposites for food packaging application. *J Appl Packag Res* 2015;7:6.
- [36] Marra A, Silvestre C, Duraccio D, Cimmino S. Polylactic acid/zinc oxide biocomposite films for food packaging application. *Int J Biol Macromol* 2016;88:254–62.
- [37] De Silva RT, Pasbakhsh P, Lee SM, Kit AY. ZnO deposited/encapsulated halloysite–poly (lactic acid) (PLA) nanocomposites for high performance packaging films with improved mechanical and antimicrobial properties. *Appl Clay Sci* 2015;111:10–20.
- [38] Huang Y, Wang T, Zhao X, Wang X, Zhou L, Yang Y, Liao F, Ju Y. Poly (lactic acid)/graphene oxide–ZnO nanocomposite films with good mechanical, dynamic mechanical, anti-UV and antibacterial properties. *J Chem Technol Biotechnol* 2015;90:1677–84.
- [39] Cárdenas G, Díaz J, Meléndrez M, Cruzat C, Cancino AG. Colloidal Cu nanoparticles/chitosan composite film obtained by microwave heating for food package applications. *Polym Bull* 2009;62:511–24.
- [40] Jin T, Sun D, Su JY, Zhang H, Sue H-J. Antimicrobial efficacy of zinc oxide quantum dots against *Listeria monocytogenes*, *Salmonella enteritidis*, and *Escherichia coli* O157:H7. *J Food Sci* 2009;74:M46.
- [41] Li X, Xing Y, Jiang Y, Ding Y, Li W. Antimicrobial activities of ZnO powder-coated PVC film to inactivate food pathogens. *Int J Food Sci Technol* 2009;44:2161–8.
- [42] Oehlke K, Adamiuk M, Behnsilian D, Gräf V, Mayer-Miebach E, Walz E, Greiner R. Potential bioavailability enhancement of bioactive compounds using food-grade engineered nanomaterials: a review of the existing evidence. *Food Funct* 2014;5:1341–59.
- [43] Salvia-Trujillo L, Martín-Belloso O, McClements DJ. Excipient nanoemulsions for improving oral bioavailability of bioactives. *Nanomaterials* 2016;6:17.
- [44] Wajda R, Zirkel J, Schaffer T. Increase of bioavailability of coenzyme Q10 and vitamin E. *J Med Food* 2007;10:731–4.
- [45] Pereira DI, Bruggraber SF, Faria N, Poots LK, Tagmount MA, Aslam MF, Frazer DM, Vulpe CD, Anderson GJ, Powell JJ. Nanoparticulate iron (III) oxo-hydroxide delivers safe iron that is well absorbed and utilised in humans. *Nanomed Nanotechnol Biol Med* 2014;10:1877–86.
- [46] Kim MK, Lee JA, Jo MR, Kim MK, Kim HM, Oh JM, Song NW, Choi S-J. Cytotoxicity, uptake behaviors, and oral absorption of food grade calcium carbonate nanomaterials. *Nanomaterials* 2015;5:1938–54.
- [47] Magro M, Campos R, Baratella D, Lima G, Holà K, Divoky C, Stollberger R, Malina O, Aparicio C, Zoppellaro G, Zbořil R, Vianello F. A magnetically drivable nanovehicle for curcumin with antioxidant capacity and MRI relaxation properties. *Chemistry* 2014;20:11913–20.
- [48] Sáiz-Abajo MJ, González-Ferrero C, Moreno-Ruiz A, Romo-Hualde A, González-Navarro CJ. Thermal protection of β-carotene in re-assembled casein micelles during different processing technologies applied in food industry. *Food Chem* 2013;138:1581–7.
- [49] Fathi M, Mozafari MR, Mohebbi M. Nanoencapsulation of food ingredients using lipid based delivery systems. *Trends Food Sci Technol* 2012;23:13–27.
- [50] Mason TG, Wilking JN, Meleson K, Chang CB, Graves SM. Nanoemulsions: formation, structure, and physical properties. *J Phys Condens Matter* 2006;18:R635.
- [51] Hu B. Biopolymer based nano-delivery systems for enhancing bioavailability of nutraceuticals. *Chin J Polym Sci* 2013;31:1190–203.
- [52] Hu M, Li Y, Decker EA, Xiao H, McClements DJ. Impact of layer structure on physical stability and lipase digestibility of lipid droplets coated by biopolymer nanolaminated coatings. *Food Biophys* 2011;6:37–48.
- [53] Sui X, Yuan J, Yuan W, Zhou M. Preparation of cellulose nanofibers/nanoparticles via electrospray. *Chem Lett* 2008;37:114–5.
- [54] Wongsasulak S, Patapeejumruswong M, Weiss J, Supaphol P, Yoovidhya T. Electrospinning of food-grade nanofibers from cellulose acetate and egg albumen blends. *J Food Eng* 2010;98:370–6.
- [55] McClements DJ. Utilizing food effects to overcome challenges in delivery of lipophilic bioactives: structural design of medical and functional foods. *Expert Opin Drug Deliv* 2013;10:1621–32.
- [56] Kommuru TR, Gurley B, Khan MA, Reddy IK. Self-emulsifying drug delivery systems (SEDDS) of coenzyme Q10: formulation development and bioavailability assessment. *Int J Pharm* 2001;212:233–46.
- [57] Zhou H, Liu G, Zhang J, Sun N, Duan M, Yan Z, Xia Q. Novel lipid-free nanoformulation for improving oral bioavailability of coenzyme Q10. *BioMed Res Int* 2014;2014:793879.



- [58] Bhushani JA, Karthik P, Anandharamakrishnan C. Nanoemulsion based delivery system for improved bioaccessibility and Caco-2 cell monolayer permeability of green tea catechins. *Food Hydrocoll* 2016;56:372–82.
- [59] van Vlerken LE, Vyas TK, Amiji MM. Poly (ethylene glycol)-modified nanocarriers for tumor-targeted and intracellular delivery. *Pharm Res* 2007;24:1405–14.
- [60] Pathakoti K, Morrow S, Han C, Pelaez M, He X, Dionysiou DD, Hwang HM. Photo-inactivation of *Escherichia coli* by sulfur and nitrogen-fluorine-codoped TiO<sub>2</sub> nanoparticles under solar simulated light and visible light irradiation. *Environ Sci Technol* 2013;47:9988–96.
- [61] He X, Aker WG, Hwang H-M. An in vivo study on the photo-enhanced toxicities of S-doped TiO<sub>2</sub> nanoparticles to zebrafish embryos (*Danio rerio*) in terms of malformation, mortality, rheotaxis dysfunction, and DNA damage. *Nanotoxicology* 2014;8(S1):185–95.
- [62] Pool H, Quintanar D, de Dios Figueroa J, Mano CM, Bechara JEH, Godínez LA, Mendoza S. Antioxidant effects of quercetin and catechin encapsulated into PLGA nanoparticles. *J Nanomater* 2012;2012:145380.
- [63] Deligiannakis Y, Sotiriou GA, Pratsinis SE. Antioxidant and antiradical SiO<sub>2</sub> nanoparticles covalently functionalized with gallic acid. *ACS Appl Mater Interfaces* 2012;4:6609–17.
- [64] Rojas-Graü MA, Soliva-Fortuny R, Martín-Belloso O. Edible coatings to incorporate active ingredients to freshcut fruits: a review. *Trends Food Sci Technol* 2009;20:438–47.
- [65] Zawistowski J, Biliaderis CG, Eskin NAM, editors. *Polyphenol oxidases*. London: Elsevier B.V.; 1991.
- [66] Li X, Li W, Jiang Y, Ding Y, Yun J, Tang Y, Zhang P. Effect of nano-ZnO-coated active packaging on quality of fresh-cut 'Fuji' apple. *Int J Food Sci Technol* 2011;46:1947–55.
- [67] Zambrano-Zaragoza ML, Mercado-Silva E, Gutiérrez-Cortez E, Cornejo-Villegas MA, Quintanar-Guerrero D. The effect of nano-coatings with  $\alpha$ -tocopherol and xanthan gum on shelf-life and browning index of fresh-cut "red delicious" apples. *Innov Food Sci Emerg Technol* 2014;22:188–96.
- [68] Nakagawa K. Nano- and microencapsulation of flavor in food systems. In: Kwak H-S, editor. *Nano- and microencapsulation for foods*. Chapter 10. Oxford, UK: John Wiley & Sons; 2014. p. 249–72.
- [69] Regulation (Ec) No. 1333/2008 of the European Parliament and of the Council of 16 December 2008 on Food Additives; 2008.
- [70] Dekkers S, Krystek P, Peters RJ, Lankveld DX, Bokkers BG, van Hoeven-Arentzen PH, Bouwmeester H, Oomen AG. Presence and risks of nanosilica in food products. *Nanotoxicology* 2011;5:393–405.
- [71] U.S. FDA. Listing of color additives exempt from certification. In: Office USGP, editor. *Code of federal regulations title 21—food and drugs*. Washington, DC: U.S. FDA; 2002.
- [72] U.S. FDA, CFR – Code of Federal Regulations Title 21. Food and Drug. Chapter I. Food and Drug Administration, Department of Health and Human Services. Part 73. Listing of color additives exempt from certification. Subpart A. Foods. Sec. 73.575. Titanium dioxide, <http://www.accessdata.fda.gov/scripts/cdrh/cfdocs/cfcfr/cfrsearch.cfm?fr=73.575>, [accessed 18.07.16]
- [73] U.S. FDA. Color additive status list. 2015. <http://www.fda.gov/ForIndustry/ColorAdditives/ColorAdditiveInventories/ucm106626.htm>, [accessed 18.07.16].
- [74] Peters R, Kramer E, Oomen AG, Herrera Rivera ZE, Oegema G, Tromp PC, Fokkink R, Rietveld A, Marvin HJ, Weigel S, Peijnenburg AA, Bouwmeester H. Presence of nano-sized silica during in vitro digestion of foods containing silica as a food additive. *ACS Nano* 2012;6:2441–51.
- [75] Athinarayanan J, Periasamy VS, Alsaif MA, Al-Warthan AA, Alshatwi AA. Presence of nanosilica (E551) in commercial food products: TNF-mediated oxidative stress and altered cell cycle progression in human lung fibroblast cells. *Cell Biol Toxicol* 2014;30:89–100.
- [76] Youssef AM. Polymer nanocomposites as a new trend for packaging applications. *Polym Plast Technol Eng* 2013;52:635–60.
- [77] Weibel M, Caseri W, Suter UW, Kiess H, Wehrli E. Preparation of polymer nanocomposites with "ultrahigh" refractive index. *Polym Adv Technol* 1991;2:75–80.
- [78] Giannelis EP. Polymer layered silicate nanocomposites. *Adv Mater* 1996;8:29–35.
- [79] Podsiadlo P, Kaushik AK, Arruda EM, Waas AM, Shim BS, Xu J, Nandivada H, Pumphlin BG, Lahann J, Ramamoorthy A, Kotov NA. Ultrastrong and stiff layered polymer nanocomposites. *Science* 2007;318:80–3.
- [80] Laoutid F, Bonnaud L, Alexandre M, Lopez-Cuesta JM, Dubois P. New prospects in flame retardant polymer materials: from fundamentals to nanocomposites. *Mater Sci Eng R Rep* 2009;63:100–25.
- [81] Lizundia E, Ruiz-Rubio L, Vilas JL, León LM. Poly (l-lactide)/ZnO nanocomposites as efficient UV-shielding coatings for packaging applications. *J Appl Polym Sci* 2016;133:42426.
- [82] Silvestre C, Duraccio D, Cimmino S. Food packaging based on polymer nanomaterials. *Prog Polym Sci* 2011;36:1766–82.
- [83] De Azeredo HM. Nanocomposites for food packaging applications. *Food Res Int* 2009;42:1240–53.
- [84] Arora A, Padua GW. Review: nanocomposites in food packaging. *J Food Sci* 2010;75:R43–9.
- [85] Rhim JW, Park HM, Ha CS. Bio-nanocomposites for food packaging applications. *Prog Polym Sci* 2013;38:1629–52.
- [86] Avella M, De Vlieger JJ, Errico ME, Fischer S, Vacca P, Volpe MG. Biodegradable starch/clay nanocomposite films for food packaging applications. *Food Chem* 2005;93:467–74.
- [87] Magnuson BA, Jonaitis TS, Card JW. A brief review of the occurrence, use, and safety of food-related nanomaterials. *J Food Sci* 2011;76:R126–33.
- [88] Jovanović B. Critical review of public health regulations of titanium dioxide, a human food additive. *Integr Environ Assess Manage* 2015;11:10–20.
- [89] Chen XX, Cheng B, Yang YX, Cao A, Liu JH, Du LJ, Liu Y, Zhao Y, Wang H. Characterization and preliminary toxicity assay of nano-titanium dioxide additive in sugar-coated chewing gum. *Small* 2013;9:1765–74.
- [90] Mozafari MR, Flanagan J, Matia-Merino L, Awati A, Omri A, Suntres ZE, Singh H. Recent trends in the lipid-based nanoencapsulation of antioxidants and their role in foods. *J Sci Food Agric* 2006;86:2038–45.
- [91] Ezhilarasi PN, Karthik P, Chhanwal N, Anandharamakrishnan C. Nanoencapsulation techniques for food bioactive components: a review. *Food Bioprocess Technol* 2013;6:628–47.
- [92] Borel T, Sabliov CM. Nanodelivery of bioactive components for food applications: types of delivery systems, properties, and their effect on ADME profiles and toxicity of nanoparticles. *Annu Rev Food Sci Technol* 2014;5:197–213.
- [93] McCracken C, Zane A, Knight DA, Dutta PK, Waldman WJ. Minimal intestinal epithelial cell toxicity in response to short-and long-term food-relevant inorganic nanoparticle exposure. *Chem Res Toxicol* 2013;26:1514–25.
- [94] Flores-López ML, Cerqueira MA, de Rodríguez DJ, Vicente AA. Perspectives on utilization of edible coatings and nano-laminate coatings for extension of postharvest storage of fruits and vegetables. *Food Eng Rev* 2015:1–14.

- [95] McClements DJ. Design of nano-laminated coatings to control bioavailability of lipophilic food components. *J Food Sci* 2010;75:R30–42.
- [96] F.M. Fakhouri, A.C.A. Casari, M. Mariano, F. Yamashita, L.I. Mei, V. Soldi, S.M. Martelli, Effect of a gelatin-based edible coating containing cellulose nanocrystals (CNC) on the quality and nutrient retention of fresh strawberries during storage, IOP Conference Series: Materials Science and Engineering, vol. 64, Conference 1, 2nd International Conference on Structural Nano Composites (NANOSTRUC 2014), 20–21 May 2014, Madrid, Spain
- [97] Shi S, Wang W, Liu L, Wu S, Wei Y, Li W. Effect of chitosan/nano-silica coating on the physicochemical characteristics of longan fruit under ambient temperature. *J Food Eng* 2013;118:125–31.
- [98] Yu Y, Zhang S, Ren Y, Li H, Zhang X, Di J. Jujube preservation using chitosan film with nano-silicon dioxide. *J Food Eng* 2012;113:408–14.
- [99] Medeiros BGdS, Souza MP, Pinheiro AC, Bourbon AI, Cerqueira MA, Vicente AA, Carneiro-da-Cunha MG. Physical characterisation of an alginate/lysozyme nano-laminate coating and its evaluation on 'Coalho' cheese shelf life. *Food Bioprocess Technol* 2014;7:1088–98.
- [100] Yang FM, Li HM, Li F, Xin ZH, Zhao LY, Zheng YH, Hu QH. Effect of nano-packing on preservation quality of fresh strawberry (*Fragaria ananassa* Duch. cv Fengxiang) during storage at 4°C. *J Food Sci* 2010;75:C236–40.
- [101] Han W, Yu Y, Li N, Wang L. Application and safety assessment for nano-composite materials in food packaging. *Chin Sci Bull* 2011;56:1216–25.
- [102] Echegoyen Y, Rodríguez S, Nerín C. Nanoclay migration from food packaging materials. *Food Addit Contam Part A* 2016;33:530–9.
- [103] Huang J-Y, Chieng YY, Li X, Zhou W. Experimental and mathematical assessment of migration from multilayer food packaging containing a novel clay/polymer nanocomposite. *Food Bioprocess Technol* 2015;8:382–93.
- [104] Pathakoti K, Huang M-J, Watts JD, He X, Hwang H-M. Using experimental data of *Escherichia coli* to develop a QSAR model for predicting the photo-induced cytotoxicity of metal oxide nanoparticles. *J Photochem Photobiol B* 2014;130:234–40.
- [105] Puzyn T, Rasulev B, Gajewicz A, Hu X, Dasari TP, Michalkova A, Hwang HM, Toropov A, Leszczynska D, Leszczynski J. Using nano-QSAR to predict the cytotoxicity of metal oxide nanoparticles. *Nat Nanotechnol* 2011;6:175–8.
- [106] He X, Aker WG, Leszczynski J, Hwang H-M. Using a holistic approach to assess the impact of engineered nanomaterials inducing toxicity in aquatic systems. *J Food Drug Anal* 2014;22:128–46.
- [107] He X, Hwang H-M. Engineered TiO<sub>2</sub> nanoparticles: their fate and effects in natural aquatic environments. *Chem Phys Res J* 2014;7:1–20.
- [108] Pilolli R, Monaci L, Visconti A. Advances in biosensor development based on integrating nanotechnology and applied to food-allergen management. *TrAC Trends Anal Chem* 2013;47:12–26.
- [109] Kumar S, Dilbaghi N, Barnela M, Bhanjana G, Kumar R. Biosensors as novel platforms for detection of food pathogens and allergens. *BioNanoScience* 2012;2:196–217.
- [110] Yoshida T, Yoshioka Y, Fujimura M, Yamashita K, Higashisaka K, Morishita Y, Kayamuro H, Nabeshi H, Nagano K, Abe Y, Kamada H, Tsunoda S, Itoh N, Yoshikawa T, Tsutsumi Y. Promotion of allergic immune responses by intranasally-administrated nanosilica particles in mice. *Nanoscale Res Lett* 2011;6:1–6.
- [111] Ilves M, Alenius H. Modulation of immune system by carbon nanotubes. In: Chen C, Wang H, editors. *Biomedical applications and toxicology of carbon nanomaterials*. Chapter 13. Weinheim, Germany: John Wiley & Sons; 2016. p. 397–428.
- [112] Syed S, Zubair A, Frieri M. Immune response to nanomaterials: implications for medicine and literature review. *Curr Allergy Asthma Rep* 2013;13:50–7.
- [113] Hirai T, Yoshioka Y, Ichihashi KI, Mori T, Nishijima N, Handa T, Takahashi H, Tsunoda SI, Higashisaka K, Tsutsumi Y. Silver nanoparticles induce silver nanoparticle-specific allergic responses (HYP6P. 274). *J Immunol* 2014;92(1 Suppl):118–9.
- [114] Nygaard UC, Hansen JS, Samuelson M, Alberg T, Marioara CD, Lovik M. Single-walled and multi-walled carbon nanotubes promote allergic immune responses in mice. *Toxicol Sci* 2009;109:113–23.
- [115] Ryman-Rasmussen JP, Tewksbury EW, Moss OR, Cesta MF, Wong BA, Bonner JC. Inhaled multiwalled carbon nanotubes potentiate airway fibrosis in murine allergic asthma. *Am J Respir Cell Mol Biol* 2009;40:349–58.
- [116] Lefebvre DE, Pearce B, Fine JH, Chomyszyn E, Ross N, Halappanavar S, Tayabali AF, Curran I, Bondy GS. In vitro enhancement of mouse T helper 2 cell sensitization to ovalbumin allergen by carbon black nanoparticles. *Toxicol Sci* 2014;138:322–32.
- [117] Llorens A, Lloret E, Picouet PA, Trbojevich R, Fernandez A. Metallic-based micro and nanocomposites in food contact materials and active food packaging. *Trends Food Sci Technol* 2012;24:19–29.
- [118] Fukui H, Horie M, Endoh S, Kato H, Fujita K, Nishio K, Komaba LK, Maru J, Miyauhi A, Nakamura A, Kinugasa S, Yoshida Y, Hagihara Y, Iwahashi H. Association of zinc ion release and oxidative stress induced by intratracheal instillation of ZnO nanoparticles to rat lung. *Chem Biol Interact* 2012;198:29–37.
- [119] Gliga AR, Skoglund S, Wallinder IO, Fadeel B, Karlsson HL. Size-dependent cytotoxicity of silver nanoparticles in human lung cells: the role of cellular uptake, agglomeration and Ag release. *Particle Fibre Toxicol* 2014;11:11.
- [120] McShan D, Ray PC, Yu H. Molecular toxicity mechanism of nanosilver. *J Food Drug Anal* 2014;22:116–27.
- [121] Karlsson HL, Cronholm P, Hedberg Y, Tornberg M, Battice LD, Svedhem S, Wallinder IO. Cell membrane damage and protein interaction induced by copper containing nanoparticles—importance of the metal release process. *Toxicology* 2013;313:59–69.
- [122] He X, Aker WG, Pelaez M, Lin Y, Dionysiou DD, Hwang H-M. Assessment of nitrogen–fluorine-codoped TiO<sub>2</sub> under visible light for degradation of BPA: implication for field remediation. *J Photochem Photobiol A Chem* 2016;314:81–92.
- [123] He X, Sanders S, Aker WG, Lin Y, Douglas J, Hwang H-M. Assessing the effects of surface-bound humic acid on the phototoxicity of anatase and rutile TiO<sub>2</sub> nanoparticles in vitro. *J Environ Sci* 2016;42:50–60.
- [124] Elgadir MA, Uddin MS, Ferdosh S, Adam A, Chowdhury AJK, Sarker MZI. Impact of chitosan composites and chitosan nanoparticle composites on various drug delivery systems: a review. *J Food Drug Anal* 2015;23:619–29.
- [125] Liu S, Yuan L, Yue X, Zheng Z, Tang Z. Recent advances in nanosensors for organophosphate pesticide detection. *Adv Powder Technol* 2008;19:419–41.
- [126] Nugen SR, Baeumner AJ. Trends and opportunities in food pathogen detection. *Anal Bioanal Chem* 2008;391:451–4.

- [127] Inbaraj BS, Chen BH. Nanomaterial-based sensors for detection of foodborne bacterial pathogens and toxins as well as pork adulteration in meat products. *J Food Drug Anal* 2015;24:15–28.
- [128] Palchetti I, Mascini M. Electroanalytical biosensors and their potential for food pathogen and toxin detection. *Anal Bioanal Chem* 2008;391:455–71.
- [129] Imran M, Revol-Junelles AM, Martyn A, Tehrany EA, Jacquot M, Linder M, Desobry S. Active food packaging evolution: transformation from micro- to nanotechnology. *Crit Rev Food Sci Nutr* 2010;50:799–821.
- [130] Pereira de Abreu DA, Cruz JM, Paseiro Losada P. Active and intelligent packaging for the food industry. *Food Rev Int* 2012;28:146–87.
- [131] Mihindukulasuriya SDF, Lim LT. Nanotechnology development in food packaging: a review. *Trends Food Sci Technol* 2014;40:149–67.