



Available online at www.sciencedirect.com

jmr&t

Journal of Materials Research and Technology

www.jmrt.com.br



Original Article

Quantification of the strengthening effect of rare earth elements during hot deformation of Mg-Gd-Y-Zr magnesium alloy



Hamed Mirzadeh

School of Metallurgy and Materials Engineering, College of Engineering, University of Tehran, Tehran, Iran

ARTICLE INFO

Article history:

Received 18 June 2014

Accepted 19 March 2015

Available online 19 April 2015

Keywords:

Magnesium alloys

Rare earth elements

Hot working

Constitutive equations

ABSTRACT

The flow stress of Mg-Gd-Y-Zr, Mg-Al-Zn, and Mg-Zn-Zr magnesium alloys during hot deformation were correlated to the Zener-Hollomon parameter through analyses based on the proposed physically-based and apparent approaches. It was demonstrated that the theoretical exponent of 5 and the lattice self-diffusion activation energy of magnesium (135 kJ/mol) can be set in the hyperbolic sine law to describe the peak flow stresses. As a result, the influence of rare earth elements, gadolinium (Gd) and yttrium (Y), upon the hot working behavior was readily characterized by the proposed approach, which was not possible by the conventional apparent approach. It was shown quantitatively that the rare earth addition exerts a profound effect on the hot strength and hence on the creep resistance.

© 2015 Brazilian Metallurgical, Materials and Mining Association. Published by Elsevier Editora Ltda. All rights reserved.

1. Introduction

Magnesium (Mg) alloys containing rare earth elements are promising structural materials due to their notable creep resistance and high specific strength at both ambient and elevated temperatures. The rare earth additions can remarkably improve the heat resistance of the Mg alloys due to solid solution strengthening and precipitation hardening effects [1–6]. Hot deformation processing is a suitable shaping method for polycrystalline Mg alloys due to the activation of additional slip systems at elevated temperatures and the possibility of structural refinement [7–12]. The understanding of the hot working behavior and the constitutive relations describing

material flow is one of the prerequisites for the implementation of shaping technology in the industry [13,14].

Heat resistant cast Mg alloy development includes three categories [3]: (1) alloying of Mg-Al based alloys with Ca (forming AX alloys), with Zn and Ca (forming AZX alloys), with Sr (forming AJ alloys), with Ca and Sr (forming AXJ alloys), with RE (forming AE alloys), with Si and Sb (forming ASS alloys), with Ca and RE (forming ACM alloys and MRI alloys), with Zn, Ca and RE (forming ZACE alloys), with Zn, Sn (forming ASZ alloys); (2) development of a new type of Mg-RE-Zr alloys, including Mg-Y-Nd-Zr (WE) alloys, Mg-Gd-Nd-Zr (GN), Mg-Dy-Nd-Zr (DN) and Mg-Gd-Y-Zr (GW) alloys; (3) development of Mg-RE-Zn (MEZ) alloys. Thanks to their magnificent room- and high-temperature strength, magnesium alloys containing rare

E-mail: hmirzadeh@ut.ac.ir

<http://dx.doi.org/10.1016/j.jmrt.2015.03.001>

2238-7854/© 2015 Brazilian Metallurgical, Materials and Mining Association. Published by Elsevier Editora Ltda. All rights reserved.

earth elements Gd and Y have been recently developed and extensively investigated [3].

In the current work, the constitutive behavior of Mg alloyed with Gd and Y will be compared with those of the high-strength Mg alloys, namely AZ91 (Mg-9Al-1Zn) [7,12] and ZK60 (Mg-6Zn-0.6Zr) [15,16], using a proposed method that utilizes the physically-based material's parameters, which makes it possible to conduct comparative studies.

2. Experimental details

The flow stress data of Mg-Gd-Y-Zr alloys with 9–10 wt% Gd, 2.7–4.8 wt% Y and 0.4–0.6 wt% Zr, hot compressed at deformation temperatures between 350 and 500 °C under strain rates of 0.001 to 10 s⁻¹, were taken from the literature [17–21]. Since the level of the peak flow stress did not show any considerable dependence on the small variation of Gd and Y among the considered research works, the flow data were combined together to determine the constitutive behavior of the Mg-Gd-Y-Zr alloy. The flow stress data for ZK60 (with 0.61 to 0.76 wt% Zr) and AZ91 were also taken from the literature [7,15,22–29]. The considered flow curves exhibited typical dynamic recrystallization (DRX) behavior [30,31] with a single peak stress (σ_p) followed by a gradual fall toward a steady state stress.

The well-known Zener-Hollomon parameter $Z = \dot{\varepsilon} \exp(Q/RT)$ can be related to flow stress in different ways. The power law description of stress ($Z = A' \sigma^n$) is preferred for relatively low stresses. Conversely, the exponential law ($Z = A'' \exp(\beta\sigma)$) is suitable for high stresses. However, the hyperbolic sine law ($Z = A[\sinh(\alpha\sigma)]^n$) can be used for a wide range of temperatures and strain rates. In these equations, A' , A'' , A (the hyperbolic sine constant), n' , n (the hyperbolic sine power), β and $\alpha \approx \beta/n'$ (the stress multiplier) are constants and Q is the hot deformation activation energy. In these equations, no strain for determination of flow stress is specified. As a result, characteristic stresses such as steady state stress, peak stress, or the critical stress for initiation of DRX may be used. Since the steady-state stress may not be precisely attained for all of the flow curves and obtaining the critical stress for initiation of DRX needs work-hardening rate analysis [31], it is usual to use the peak stress to find the values of A , n , α , and Q [32–35]. For each alloy, the selection criterion of the peak stress data from the literature was based on the consistency of stress level among the considered research works.

3. Results

Based on the power and exponential laws, the slopes of the plots of $\ln \dot{\varepsilon}$ against $\ln \sigma_p$ and $\ln \dot{\varepsilon}$ against σ_p can be used for obtaining the values of n' ($n' = [\partial \ln \dot{\varepsilon} / \partial \ln \sigma_p]_T$) and β ($\beta = [\partial \ln \dot{\varepsilon} / \partial \sigma_p]_T$), respectively. This is shown in Fig. 1a and b for the Mg-Gd-Y-Zr alloy and the subsequent linear regression of the data resulted in the average value $\alpha \approx 0.00973$ or simply $\alpha \approx 0.01 \text{ MPa}^{-1}$. The same average value of $\alpha \approx 0.01 \text{ MPa}^{-1}$ was also obtained for AZ91 [7] and ZK60 [15] alloys by similar type of analysis. Taking natural logarithm from the hyperbolic sine equation and subsequent partial differentiations at constant temperature and also at

constant strain rate together with algebraic operations results in $Q = R[\partial \ln \dot{\varepsilon} / \partial \ln \{\sinh(\alpha\sigma_p)\}]_T [\partial \ln \{\sinh(\alpha\sigma_p)\} / \partial (1/T)]_{\dot{\varepsilon}}$. It follows that the slopes of the plots of $\ln \dot{\varepsilon}$ against $\ln \{\sinh(\alpha\sigma_p)\}$ and $\ln \{\sinh(\alpha\sigma_p)\}$ against $1/T$ can be used for obtaining the value of Q . The representative plots are shown in Fig. 1c and d for the Mg-Gd-Y-Zr alloy. The linear regression of the data results in the average value of $Q = 199.83 \text{ kJ/mol}$ or simply 200 kJ/mol for the Mg-Gd-Y-Zr alloy. The average values of Q for the AZ91 and ZK60 alloy were determined as 136.27 and 140.30 kJ/mol, respectively. The values of hot deformation activation energy of 136.27 and 140.30 kJ/mol are close to that reported for the lattice self-diffusion activation energy of magnesium, which is about 135 kJ/mol [7,15]. Conversely, the value of 200 kJ/mol is effectively higher than 135 kJ/mol. Therefore, while AZ91 (Mg-9Al-1Zn) and ZK60 (Mg-6Zn-0.6Zr) alloys have relatively high amount of Al or Zn as alloying elements, the self-diffusion of Mg occurs rather easily during hot deformation of these alloys. However, the rare earth addition in Mg-Gd-Y-Zr alloy is very effective in hindering the self-diffusion that is a major factor in increasing creep rate [36].

Based on the hyperbolic sine law, the slope and the intercept of the plot of $\ln Z$ against $\ln \{\sinh(\alpha\sigma_p)\}$ can be used for obtaining the values of n and A . The corresponding plots are shown in Fig. 2a for all of the considered materials using the apparent values of Q . The linear regression of the data results in the following equations:

$$\begin{cases} \text{Mg-Gd-Y-Zr} \Leftrightarrow \dot{\varepsilon} \exp(200,000/RT) = 429^5 \{\sinh(0.01 \times \sigma_p)\}^{4.96} \\ \text{AZ91} \Leftrightarrow \dot{\varepsilon} \exp(136,270/RT) = 98.79^5 \{\sinh(0.01 \times \sigma_p)\}^{5.15} \\ \text{ZK60} \Leftrightarrow \dot{\varepsilon} \exp(140,300/RT) = 160.55^5 \{\sinh(0.01 \times \sigma_p)\}^{5.43} \end{cases} \quad (1)$$

Note that there is no possibility for elucidating the effects of alloying elements on the hot flow stress due to the differences in the values of Q and n .

4. Discussion

Recently, Mirzadeh et al. [37] have proposed an easy to apply approach that considers theoretical values of n and Q based




Fig. 1 – Plots used to obtain the values of the stress multiplier α and the deformation activation energy Q for the Mg-Gd-Y-Zr alloy.




Fig. 2 – Plots used to obtain the constants of the hyperbolic sine equations by consideration of (a) apparent values of Q and n and (b) $Q=135 \text{ kJ/mol}$ and $n=5$.

on the deformation mechanisms in the constitutive analysis. It was shown that when the deformation mechanism is controlled by the glide and climb of dislocations (climb-controlled), a constant exponent (n) of 5 and self diffusion activation energy can be used to describe the appropriate stress [1,7,15]. Based on the apparent values of n (near 5) and Q (near 135 kJ/mol) for the AZ91 and ZK60 alloys as indicated by Eq. (1), it seems that this assumption works perfectly for these materials. The apparent activation energy for hot deformation of Mg-Gd-Y-Zr alloy is $\sim 200 \text{ kJ/mol}$ due to the rare earth addition. However, the apparent value of n was determined as 4.96, which is close to the theoretical value of 5 and implies that the hot deformation of this alloy would also be climb-controlled if the lattice self-diffusion activation energy can be used in constitutive analysis. Therefore, it was investigated whether it is possible to consider the values of $Q=135 \text{ kJ/mol}$ with $n=5$ for this material and hence elucidating the effect of rare earth elements from the value of the hyperbolic sine constant (A). Therefore, the values of $Q=135 \text{ kJ/mol}$ and $n=5$ were considered in subsequent constitutive analysis for all of the investigated materials.

Again, based on the hyperbolic sine law, the intercept of the plot of $\ln Z$ (using $Q=135 \text{ kJ/mol}$) against $\ln(\sinh(\alpha\sigma_p))$ by setting the slope of $n=5$ can be used for obtaining the values of A . The corresponding plots are shown in Fig. 2b for all of the considered materials. The relatively good fit to experimental data justifies the consideration of $Q=135 \text{ kJ/mol}$ and $n=5$ for Mg-Gd-Y-Zr alloy. The linear regression of the data results in the following equations:

$$Z = \dot{\varepsilon} \exp \left(\frac{135,000}{RT} \right) = \begin{cases} 45.16^5 \{ \sinh(0.01 \times \sigma_p) \}^5 & \Leftrightarrow \text{Mg-Gd-Y-Zr} \\ 102.92^5 \{ \sinh(0.01 \times \sigma_p) \}^5 & \Leftrightarrow \text{AZ91} \\ 129.84^5 \{ \sinh(0.01 \times \sigma_p) \}^5 & \Leftrightarrow \text{ZK60} \end{cases} \quad (2)$$

The proposed approach in the present work considers theoretical values for n and Q in the constitutive analysis. This in turn brings about a possibility to study the constitutive behavior of materials based on the obtained values of A and α . Since the same value of $\alpha \approx 0.01 \text{ MPa}^{-1}$ was determined for all of

the considered materials, the difference in hot flow stress can be deduced from the values of A , which is the intercept of the plots of $\ln Z$ against $\ln\{\sinh(\alpha\sigma_p)\}$ by setting $n=5$ (Fig. 2b). Based on Eq. (2) and the intercepts of the plots shown in Fig. 2(b), the value of the hyperbolic sine constant A is significantly smaller in the case of Mg-Gd-Y-Zr alloy. According to the hyperbolic sine law, the flow stress of the material can be expressed as $\sigma_p = (1/\alpha)\{\sinh^{-1}(Z/A)^{1/n}\}$. Therefore, it is clear that by decreasing the value of A , at a given value of Z , the flow stress increases. This shows the magnificent effect of rare earth addition on the hot strength and hence on the creep resistance. This also implies that the used approach in the current work can be considered as a versatile tool in future hot working studies, especially in studies dedicated to alloy development.

5. Conclusions

A comparative study was carried out on the Mg-Gd-Y-Zr, AZ91, and ZK60 magnesium alloys in order to understand the effect of rare earth addition on the hot flow stress. A versatile approach was proposed in the current work, which considers the theoretical values of $n=5$ and the lattice self-diffusion activation energy of magnesium (135 kJ/mol) as the hot deformation activation energy (Q) in the constitutive analysis. This in turn brings about a possibility to study the constitutive behavior of materials based on the obtained values of A and α in the hyperbolic sine equation of the form $Z = A[\sinh(\alpha\sigma_p)]^n$. It was shown quantitatively that the rare earth addition exerts a profound effect on the hot strength and hence on the creep resistance.

Conflicts of interest

The author declares no conflicts of interest.

REFERENCES

- [1] Mirzadeh H, Roostaei M, Parsa MH, Mahmudi R. Rate controlling mechanisms during hot deformation of Mg-3Gd-1Zn magnesium alloy: dislocation glide and climb, dynamic recrystallization, and mechanical twinning. Mater Des 2015;68:228–31.
- [2] Zhang K, Li X, Lim Y, Ma M. Effect of Gd content on microstructure and mechanical properties of Mg-Y-RE-Zr alloys. Trans Nonferrous Metal Soc China 2008;18:12–6.
- [3] Yang Z, Li JP, Zhang JX, Lorimer GW, Robson J. Review on research and development of magnesium alloys. Acta Metall Sin 2008;21:313–28.
- [4] Yang Z, Guo YC, Li JP, He F, Xia F, Liang MX. Plastic deformation and dynamic recrystallization behaviors of Mg-5Gd-4Y-0.5Zn-0.5Zr alloy. Mater Sci Eng A 2008;485:487–91.
- [5] Hou QY, Wang JT. A modified Johnson-Cook constitutive model for Mg-Gd-Y alloy extended to a wide range of temperatures. Comput Mater Sci 2010;50:147–52.
- [6] Mirza FA, Chen DL, Li DJ, Zeng XQ. Effect of rare earth elements on deformation behavior of an extruded Mg-10Gd-3Y-0.5Zr alloy during compression. Mater Des 2013;46:411–8.

- [7] Mirzadeh H. Constitutive analysis of Mg-Al-Zn magnesium alloys during hot deformation. *Mech Mater* 2014;77:80–5.
- [8] Stanford N, Sabirov I, Sha G, La Fontaine A, Ringer SP, Barnett MR. Effect of Al and Gd solutes on the strain rate sensitivity of magnesium alloys. *Metall Mater Trans A* 2010;41:734–43.
- [9] Zhao X, Zhang K, Li X, Li Y, He Q, Sun J. Deformation behavior and dynamic recrystallization of Mg-Y-Nd-Gd-Zr alloy. *J Rare Earths* 2008;26:846–50.
- [10] Ma M, He L, Li X, Li Y, Zhang K. Hot workability of Mg-9Y-1MM-0.6Zr alloy. *J Rare Earths* 2011;29:460–5.
- [11] Chen Q, Xia X, Yuan B, Shu D, Zhao Z, Han J. Hot workability behavior of as-cast Mg-Zn-Y-Zr alloy. *Mater Sci Eng A* 2014;593:38–47.
- [12] Mirzadeh H. A comparative study on the hot flow stress of Mg-Al-Zn magnesium alloys using a simple physically-based approach. *J Magnes Alloys* 2014;2:225–9.
- [13] Mirzadeh H, Cabrera JM, Najafizadeh A, Calvillo PR. EBSD study of a hot deformed austenitic stainless steel. *Mater Sci Eng A* 2012;538:236–45.
- [14] Mirzadeh H, Cabrera JM, Najafizadeh A. Modeling and prediction of hot deformation flow curves. *Metall Mater Trans A* 2012;43:108–23.
- [15] Mirzadeh H. Constitutive behaviors of magnesium and Mg-Zn-Zr alloy during hot deformation. *Mater Chem Phys* 2015;152:123–6.
- [16] Friedrich HE, Mordike BL. *Magnesium technology*. Berlin: Springer; 2006.
- [17] Li L, Zhang X. Hot compression deformation behavior and processing parameters of a cast Mg-Gd-Y-Zr alloy. *Mater Sci Eng A* 2011;528:1396–401.
- [18] Zhou H, Wang QD, Ye B, Guo W. Hot deformation and processing maps of as-extruded Mg-9.8Gd-2.7Y-0.4Zr Mg alloy. *Mater Sci Eng A* 2013;576:101–7.
- [19] Yang Z, Li JP, Zhang JX, Guo YC, Wang BW, Xia F, et al. Effect of homogenization on the hot-deformation ability and dynamic recrystallization of Mg-9Gd-3Y-0.5Zr alloy. *Mater Sci Eng A* 2009;515:102–7.
- [20] Shao Z, Zhu X, Wang R, Wang J, Xu Y, Zhao B, et al. Hot deformation and processing map of as-homogenized Mg-9Gd-3Y-2Zn-0.5Zr alloy. *Mater Des* 2013;51:826–32.
- [21] Li HZ, Wang HJ, Li Z, Liu CM, Liu HT. Flow behavior and processing map of as-cast Mg-10Gd-4.8Y-2Zn-0.6Zr alloy. *Mater Sci Eng A* 2010;528:154–60.
- [22] Cerri E, Leo P, De Marco PP. Hot compression behavior of the AZ91 magnesium alloy produced by high pressure die casting. *J Mater Process Technol* 2007;189:97–106.
- [23] Ding H, Liu L, Kamado S, Ding W, Kojima T. Evolution of microstructure and texture of AZ91 alloy during hot compression. *Mater Sci Eng A* 2007;452–453:503–7.
- [24] Mu M, Zhi-min Z, Bao-hong Z, Jin D. Flow behaviors and processing maps of as-cast and as-homogenized AZ91 alloy. *J Alloys Compd* 2012;513:112–7.
- [25] Liu L, Ding H. Study of the plastic flow behaviors of AZ91 magnesium alloy during thermomechanical processes. *J Alloys Compd* 2009;484:949–56.
- [26] Galiyev A, Kaibyshev R, Gottstein G. Correlation of plastic deformation and dynamic recrystallization in magnesium alloy ZK60. *Acta Mater* 2001;49:1199–207.
- [27] Wang CY, Wang XJ, Chang H, Wu K, Zheng MY. Processing maps for hot working of ZK60 magnesium alloy. *Mater Sci Eng A* 2007;464:52–8.
- [28] Qin YJ, Pan QL, He YB, Li WB, Liu XY, Fan X. Modeling of flow stress for magnesium alloy during hot deformation. *Mater Sci Eng A* 2010;527:2790–7.
- [29] Yu H, Yu H, Min G, Park SS, You BS, Kim YM. Strain-dependent constitutive analysis of hot deformation and hot workability of T4-treated ZK60 magnesium alloy. *Metals Mater Int* 2013;19:651–65.
- [30] Mirzadeh H, Cabrera JM, Prado JM, Najafizadeh A. Hot deformation behavior of a medium carbon microalloyed steel. *Mater Sci Eng A* 2011;528:3876–82.
- [31] Mirzadeh H, Najafizadeh A. Prediction of the critical conditions for initiation of dynamic recrystallization. *Mater Des* 2010;31:1174–9.
- [32] Mirzadeh H, Najafizadeh A. Hot deformation and dynamic recrystallization of 17-4 PH stainless steel. *ISIJ Int* 2013;53:680–9.
- [33] Mirzadeh H, Najafizadeh A, Moazeny M. Hot deformation behaviour of precipitation hardening stainless steel. *Mater Sci Technol* 2010;26:501–4.
- [34] Mirzadeh H, Parsa MH, Ohadi D. Hot deformation behavior of austenitic stainless steel for a wide range of initial grain size. *Mater Sci Eng A* 2013;569:54–60.
- [35] Mirzadeh H, Parsa MH. Hot deformation and dynamic recrystallization of NiTi intermetallic compound. *J Alloys Compd* 2014;614:56–9.
- [36] Prasad YVRK, Rao KP, Gupta M. Hot workability and deformation mechanisms in Mg/nano-Al₂O₃ composite. *Compos Sci Technol* 2009;69:1070–6.
- [37] Mirzadeh H, Cabrera JM, Najafizadeh A. Constitutive relationships for hot deformation of austenite. *Acta Mater* 2011;59:6441–8.