

7-8

NASA CASE NO. LAR 14863-1-CUPRINT FIG. 1**NOTICE**

The invention disclosed in this document resulted from research in aeronautical and space activities performed under programs of the National Aeronautics and Space Administration. The invention is owned by NASA and is, therefore, available for licensing in accordance with the NASA Patent Licensing Regulation (14 Code of Federal Regulations 1245.2).

To encourage commercial utilization of NASA-owned inventions, it is NASA policy to grant licenses to commercial concerns. Although NASA encourages nonexclusive licensing to promote competition and achieve the widest possible utilization, NASA will provide the necessary incentive to the licensee to achieve early practical application of the invention.

Address inquiries and all applications for license for this invention to **NASA Patent Counsel, Langley Research Center, Code 143, Hampton, Virginia 23681-0001.**

Serial No.: 08/141,293
10/20/93

LaRC

(NASA-Case-LAR-14863-1-CU)
NON-RECTANGULAR TOWPREG
ARCHITECTURES Patent Application
(NASA, Langley Research Center)
8 p

N94-29485

Unclas

G3/24 0003673

AWARDS ABSTRACT

NON-RECTANGULAR TOWPREG ARCHITECTURES

NASA Case No. LAR 14863-1-CU

Ribbonized prepreg is used in the automated placement process where ribbons are robotically managed and continually fed onto a tool or part surface and adhered by application of heat and pressure. This automated placement process is particularly sensitive to ribbon material quality when considering low-flow matrix materials. The simultaneous assembly of adjacent ribbons (typically 4 to 34) offers significant advances in the lay-up of composite preregs. However, the low-flow matrix materials (which are often high performance) combined with lack of ribbon cross-sectional dimensional integrity, and most importantly, the existence of the standard rectangular cross-section, complicates the automated placement process frequently rendering poor results.

By the present invention, prepreg ribbons were made having a cross-sectional geometry which promotes intimate lateral contact between adjacent composite tows. Examples of this cross-sectional geometry include a triangle, a trapezoid, a parallelogram, and a polygon having more than 4 sides. Essentially, any shape will work provided that it is not rectangular or circular and allows for nesting on consolidation.

The novelty of this invention resides in the prepreg ribbon having a cross-sectional geometry which allows for intimate lateral contact or nesting between adjacent tows. The rectangular cross-sectional geometries of the prior art do not allow for nesting.

Inventors:	Donald A. Sandusky	Joseph M. Marchello
Address:	175 #8 Merrimac Trail Williamsburg, VA 23185 [REDACTED]	6 Rhoda Court Hampton, VA 23664 [REDACTED]
Employer:	Graduate Student College of William and Mary	Professor Old Dominion University

Robert M. Baucom
44 Cherbourg Dr.
Newport News, VA 23606
[REDACTED]
NASA LARC

Initial Evaluator: Terry L. St. Clair

Serial No.: 08/141,293
Filed: 10/20/93

NON-RECTANGULAR TOWPREG ARCHITECTURES

Cross-Reference to Related Applications

5 This application is related to co-pending patent application serial number _____, filed _____, entitled "Apparatus for Providing a Uniform, Consolidated, Unidirectional, Continuous, Fiber-Reinforced Polymeric Material and Method Relating Thereto".

Origin of the Invention

10 The invention described herein was made by an employee of the United States Government and two contract employees in the performance of work under NASA Grant Numbers NGT 51008 and NAG 1067 and is subject to the provisions of Public Law 96-517 (35 U.S.C. 202) in which the contractors have elected not to retain title.

15

Background of the Invention1. Field of the Invention

The present invention relates generally to prepreg ribbons. In particular, it relates to prepreg ribbon forms which have non-rectangular architectures.

20

2. Description of the Related Art

Ribbonized prepreg is used in the automated placement process where ribbons are robotically managed and continually fed onto a tool or part surface and adhered by application of heat and pressure. This automated placement process is particularly sensitive to ribbon material quality when considering low-flow matrix materials. The simultaneous assembly of adjacent ribbons (typically 4 to 34) offers significant advances in the lay-up of composite preregs. The low-flow matrix materials (which are often high performance) combined with lack of ribbon cross-sectional dimensional integrity, and most importantly, the

30

existence of the standard rectangular cross-section, complicates the automated placement process frequently rendering poor results. Although ribbons are bonded to their vertical neighbor (directly below) satisfactorily, the failure to make quality parts is generally attributed to the poor bonding of adjacent ribbons to each other. Low-flow thermoplastic parts made by using slit prepreg tapes are typically unconsolidated and exhibit excessive porosity and void content. High to moderate-flow matrix prepreg tapes and ribbons generally provide well consolidated, void-free parts. This contrast can be attributed to the correcting melt-flow nature of the high-flow matrix which allows for simultaneous congregation and filament intermingling of neighboring ribbons.

An object of the present invention is to provide a prepreg ribbon having a cross-sectional geometry which promotes intimate lateral contact between adjacent composite tows.

Another object of the present invention is to prepare a composite from the prepreg ribbons having the aforementioned geometry.

Summary of the Invention

The objects of the present invention were met by providing a prepreg ribbon having a cross-sectional geometry which promotes intimate lateral contact or nesting between adjacent tows. The cross-section has a plane of contact which provides intimacy of joining upon normal processing. Examples of such cross-section include a triangle, a trapezoid, a parallelogram, and a polygon having more than 4 sides. Essentially, any shape will meet the objectives of the invention as long as it is not rectangular or circular and allows for nesting of the ribbons upon consolidation.

Brief Description of the Drawings

Figure 1 is a diagram of the alternate prepreg ribbon architectures.

Figure 2 is a diagram of the grouping and alignment of the ribbons.

5

Description of the Preferred Embodiments

As a measure of the capabilities of the current technology, a low-flow hot-melt prepreg tape was slit into 1/4 inch rectangular ribbons and robotically placed onto a tool surface. Following a robotic in-situ manufacturing process known to those skilled in the art, a flat panel section was produced. The panel was placed into an autoclave and processed under vacuum, pressure and heat. The resulting panel contained adjacent ribbon tops and gaps. Mechanical testing proved this part was unacceptable.

15 A low-flow, 12K, powder coated towpreg was heated and shaped into a non-rectangular cross-sectional architecture. This was achieved by continuously pulling the powder coated towpreg through a forming means wherein the towpreg was consolidated and pre-shaped into a wide, flat, cross-sectional form. Upon exiting the forming means, the towpreg was consolidated into a malleable, wide, flat, cross-sectional form and passed into a shaping means. The shaping means reshaped the malleable, consolidated, flattened polymeric prepreg material into a towpreg having a non-rectangular cross-sectional architecture. Utilizing the same process as that which was disclosed for the slit tape, a composite part was fabricated. The part was well consolidated.


25


NON-RECTANGULAR TOWPREG ARCHITECTURES

Abstract of the Disclosure




5 A shaped towpreg ribbon having a cross-sectional geometry which promotes intimate lateral contact between adjacent composite tows was prepared. The cross-sectional geometry is non-rectangular and promotes intimate lateral contact between adjacent towpreg ribbons during normal processing.

FIG. 1





Roller Surface



Tool Surface

FIG. 2