PWA FR-4566 30 JUNE 1971

PROPERTIES OF MATERIALS IN HIGH PRESSURE HYDROGEN AT CRYOGENIC, ROOM, AND **ELEVATED TEMPERATURES**



ANNUAL REPORT

Contract NAS8-26191

Prepared for: George C. Marshall Space Flight Center National Aeronautics and Space Administration Marshall Space Flight Center, Alabama 35812

Prepared by: J. a. Harris, Jr.

Responsible Engineer

M C Yon Wonderham M. C. Van Wanderham **Program Manager**

Pratt & Whitney Aircraft DIVISION OF UNITED AIRCRAFT CORPORATION FLORIDA RESEARCH AND DEVELOPMENT CENTER BDX 2691, WEST PALM BEACH, FLORIDA 33402

CONTENTS

| SECTION | | PAGE |
|---------|--|--------------------------------------|
| | ILLUSTRATIONS | iv |
| | TABLES | LX |
| I | INTRODUCTION. | I-1 |
| II | CONCLUSIONS | II -1 |
| ш | MATERIALS AND SPECIMENS | III-1 |
| | A. Test Material B. Test Gases C. Test Specimens | III–1 III–3 III–4 |
| IV | LOW CYCLE FATIGUE | IV -1 |
| | A. Conclusions and Discussion | IV–1 IV–15 IV–19 |
| v | HIGH CYCLE FATIGUE | |
| | A. Introduction B. Conclusions and Discussion C. Test Procedure D. Results. | V-1 V-1 V-4 V-6 |
| VI | FRACTURE TOUGHNESS | VI-1 |
| | A. Introduction B. Conclusions and Discussion C. Test Procedure D. Test Results | VI–1 VI–1 VI–3 VI–6 |
| VII | CREEP RUPTURE | VII-1 |
| | A. Introduction B. Conclusions C. Test Procedure | VII-1 VII-1 VII-12 |
| VIII | TENSILE PROPERTIES | VIII-1 |
| | A. Introduction B. Conclusions C. Test Procedure D. Test Results | VIII-1 VIII-1 VIII-2 VIII-5 |

ILLUSTRATIONS

-

| FIGURE | | PAGE |
|----------------|---|-----------------|
| III-1 | Specimen Blank Preparation Prior to Welding | ПI – 3 |
| III - 2 | Typical Test Specimens Used To Determine Effect of High Pressure Gaseous Hydrogen on Mechanical Properties of Materials | III-4 |
| III-3 | Constant Strain Low Cycle Fatigue Specimen | III-6 |
| III-4 | Smooth Axial High Cycle Fatigue Specimen | III-7 |
| III–5 | Fracture Toughness Specimen (ASTM) | III - 8 |
| III-6 | Flat End Creep Rupture Specimen | III-9 |
| III-7 | Ambient-Cryogenic Tensile Specimen (Notch) | III -1 0 |
| III-8 | Ambient-Elevated Temperature Tensile Specimen (Smooth) | III- 11 |
| IV-1 | Typical Load-Strain Hysteresis Curve Obtained During a Specimen Low Cycle Fatigue Test | IV-1 |
| TV-2 | Low Cycle Fatigue Life of AMS 5666 (INCO 625) at 80°F | IV-3 |
| IV-3 | Effect of Gaseous Hydrogen and Strain Range on Low Cycle Fatıgue Lıfe of AMS 5666 (INCO 625) | IV-3 |
| IV - 4 | Effect of Heat Treatment on Microstructure of AMS 5662 (INCO 718) Heat BVTO | IV-5 |
| IV-5 | Low Cycle Fatigue Life of AMS 5662 at 80°F (INCO 718, 1750°F Solution Plus Age) | IV-6 |
| IV-6 | Low Cycle Fatigue Life of AMS 5662 at 1250°F (INCO 718, 1750°F Solution Plus Age) | IV-6 |
| IV-7 | Effect of Gaseous Hydrogen and Strain Range on Low Cycle Fatigue Life of AMS 5662 (INCO 718, 1750°F Solution Plus Arc) | 177.17 |
| IV-8 | Low Cycle Fatigue Life of AMS 5662 at 80°F (INCO 718, 1900°F Solution Plus Age) | IV-7 |
| IV-9 | Low Cycle Fatigue Life of AMS 5662 at -260°F (INCO 718, 1900°F Solution Plus Age) | IV-8 |
| IV-10 | Low Cycle Fatigue Life of AMS 5662 at 1250°F (INCO 718, 1900°F Solution Plus Age) | IV-8 |
| TV-11 | Effect of Gaseous Hydrogen and Strain Range on Low Cycle Fatigue Life of AMS 5662 (INCO 718, 1900°F Solution Plus Age) | IV-9 |
| IV-12 | Effect of Gaseous Hydrogen and Temperature on Low Cycle Fatigue Life of AMS 5662 (INCO 718, 1900°F Solution Plus Age) | IV-9 |

| FIGURE | | PAGE |
|--------------|--|-------|
| IV-13 | Low Cycle Fatigue Life of AMS 5754 (Hastelloy X) at 80°F | IV-10 |
| IV-14 | Effect of Gaseous Hydrogen and Strain Range on Low Cycle Fatigue Life of AMS 5754 (Hastelloy X) | IV-10 |
| IV-15 | Low Cycle Fatigue Life of AMS 4928 (T1 6-4) at 80°F | IV-11 |
| IV-16 | Low Cycle Fatigue Life of AMS 4928 (Ti 6-4) at 200°F | IV-11 |
| IV-17 | Effect of Gaseous Hydrogen and Strain Range on Low Cycle Fatigue Life of AMS 4928 (Ti 6-4) | IV-12 |
| IV-18 | Low Cycle Fatigue Life of AMS 4926 (A-110) at 80°F | IV-12 |
| IV-19 | Low Cycle Fatigue Life of AMS 4926 (A-110) at 200°F | IV-13 |
| TV-20 | Effect of Gaseous Hydrogen and Strain Range on Low Cycle Fatigue Life of AMS 4926 (A-110) | IV-13 |
| IV-21 | Low Cycle Fatigue Life of AMS 5735 (A-286) at 80°F | IV-14 |
| IV-22 | Low Cycle Fatigue Life of AMS 5735 (A-286) at 1250°F | IV-14 |
| IV-23 | Effect of Gaseous Hydrogen and Strain Range on Low Cycle Fatigue Life of AMS 5735 (A-286) | IV-15 |
| IV-24 | Low Cycle Fatıgue Life of AMS 5646 (AISI 347) at 80°F | IV-16 |
| IV-25 | High Pressure Gaseous Environment, Low Cycle Fatigue Test Vessel | IV-17 |
| IV-26 | Typical Load-Strain Hysteresis Curves for a High Pressure Gaseous Environment Low Cycle Fatigue Test (AMS 5646, 1.3% Total Strain Range, 80°F 5000-psig Hydrogen) | TV-18 |
| V-1 | Life of AMS 5662 at 80°F (INCO 718, | 14-10 |
| | 1750°F Solution Plus Age) | V-1 |
| V-2 | High Cycle Fatigue Life of AMS 5662 at 80°F (INCO 718, 1900°F Solution Plus Age) | V-2 |
| V - 3 | High Cycle Fatigue Life of AMS 5646 (AISI 347) at 80°F | V-2 |
| V-4 | High Cycle Fatigue Life of AMS 4926 (A-110) at 80°F • • • • • • • • • • • • • • • • • • • | V-3 |
| V-5 | High Cycle Fatigue Life of AMS 5662 (INCO 718) 1750°F Solution at 1250°F | V-3 |

-

| FIGURE | | PAGE |
|----------------|---|---------------|
| V-6 | High Cycle Fatigue Life of AMS 5662 (INCO 718) 1900°F Solution at 1250°F | - V-4 |
| V-7 | High Pressure Gaseous Environment High Cycle Fatigue Testing Equipment | V-5 |
| VI-1 | Engineering Ratio, K_{IC}/σ_{yS} or K_{IE}/σ_{yS} , for Alloys Tested in High Pressure Gaseous Environments | VI-3 |
| VI-2 | Tensile Machine, Test Environment Controls, and Data Acquisition Equipment Located in the Blockhouse | VI-4 |
| VI-3 | High Pressure Gaseous Environment Fracture Toughness Test Vessel Installed on Tensile Machine in the Test Cell | VI-5 |
| VI-4 | High Pressure Gaseous Environment Fracture Toughness Test Vessel With Outer Chamber Removed and Fracture Toughness Specimen With COD Gage Attached | VI-5 |
| VI-5 | Actual Load-Displacement Record for a Fracture Toughness Test Conducted in a High Pressure Gaseous Environment [AMS 4928 (6-4 Titanium), 5000-psig Hydrogen, 80°F] | VI-7 |
| VI-6 | Fracture Appearances | VI - 9 |
| VII-1 | Stress Rupture of AMS 5662 at 1250°F (INCO 718), 1750°F Solution Plus Age) | VII-2 |
| VII-2 | Stress Rupture of AMS 5662 at 1250°F (INCO 718, 1900°F Solution Plus Age) | VII-2 |
| VII-3 | Stress Rupture of AMS 5662 (INCO 625) at 1250°F | V ∏- 3 |
| VII-4 | Stress Rupture of AMS 5735 (A-286) at 1250°F | VII-3 |
| VП-5 | Stress Rupture of AMS 5646 (AISI 347) at 1250°F | VII-4 |
| VII-6 | Stress Rupture of AMS 4928 (Ti 6-4) at 200°F | V Ⅱ- 4 |
| VII-7 | Stress Rupture of AMS 4926 (A-110) at 200°F | V∏-5 |
| VII-8 | Creep-Stress-Time of AMS 5662 at 1250°F (INCO 718, 1750°F Solution Plus Age) | VII-6 |
| VⅡ-9 | Creep-Stress-Time AMS 5735 (A-286) at 1250°F | VII-6 |
| VII-10 | Creep-Stress Rupture of AMS 5662 at 1250°F (INCO 718, 1750°F Solution Plus Age) | VII-7 |
| VII -11 | Creep-Stress Rupture of AMS 5666 (INCO 625) at 1250°F | VII-7 |

| FIGURE | | PAGE |
|-----------------|--|------------------|
| VII - 12 | Creep-Stress Rupture of AMS 5735 (A-286) at 1250°F | VII-8 |
| VII-13 | Creep-Stress Rupture of AMS 5646 (AISI 347) at 1250°F | VII-8 |
| VII-14 | Creep-Stress Rupture of AMS 4928 (Ti 6-4) at 200°F | VII-9 |
| VII-15 | Creep-Stress Rupture of AMS 4926 (Ti A-110) at 200°F | VII-9 |
| VII-16 | Creep-Rupture Specimen of AMS 4926 (A-110) Showing Hydriding After Exposure to 5000-psig Hydrogen, 115,000-psi Stress and 200°F for 45 hr Until Rupture | VII-10 |
| VII-17 | Creep-Rupture Pressure Vessel Complete Assembly | VII-12 |
| VII-18 | Creep-Rupture Pressure Vessel With Chamber Wall Removed, Specimen, Extensometer, Universal Pin Joints and Half of Oven in Place | VII-13 |
| VII-19 | Typical Creep-Time Strip Chart Record for Creep-Rupture Test Conducted in High Pressure Gaseous Environment | VII - 14 |
| VIII -1 | Tensile Machine and Test Environment Controls and Data Acquisition Equipment | VIII-2 |
| VIII-2 | Various Views of Test Vessel | VIII-3 |
| VIII-3 | Test Vessel With Outer Chamber Removed Showing Specimen, Extensometer, and Half of Furnace in Place | VIII-4 |
| VIII-4 | Tensile Properties of AMS 5662 (INCO 718), 1750°F Solution in High Pressure Gaseous Environments | VII I-1 4 |
| VIII-5 | Tensile Properties of AMS 5662 (INCO 718), 1900°F Solution in High Pressure Gaseous | VIII-15 |
| VIII-6 | Tensile Properties of AMS 5666 (INCO 625) in High Pressure Gaseous Environments | VIII-16 |
| VIII-7 | Tensile Properties of AMS 5662 (INCO 718), 1900°F Solution Welds, and AMS 5666 (INCO 625) Welds, In High Pressure Gaseous Environments at Room Temperature (80°F) | VIII-17 |
| VIII-8 | Tensile Properties of AMS 5735 (A-286) in High Pressure Gaseous Environments | VIII-18 |

| FIGURE | | PAGE |
|---------|---|-----------|
| VIII-9 | Tensile Properties of AMS 5646 (AISI 347) in High_Pressure Gaseous Environments | VIII=19 - |
| VIII-10 | Tensile Properties of AMS 5754 (Hastelloy X) in High Pressure Gaseous Environments | VIII-20 |
| VIII-11 | Tensile Properties of AMS 4928 (T1 4–6) in High Pressure Gaseous Environments | VIII-21 |
| VIII-12 | Tensile Properties of AMS 4926 (A-110) in High Pressure Gaseous Environments | VIII-22 |

TABLES

| TABLE | | PAGE |
|---------------|--|---------|
| II -1 | Degree of Degradation of Various Alloys | II-2 |
| III-1 | Materials for Hydrogen Degradation Testing | III-1 |
| III-2 | Specimens Used to Determine Influence of Elevated Temperature on Metals in Gaseous Hydrogen | III–5 |
| IV-1 | Degradation of Alloys Due to High Pressure Hydrogen | IV-2 |
| IV-2 | Room Temperature Low Cycle Fatigue Properties of Materials in High Pressure Gaseous Environment | IV-20 |
| IV-3 | Cryogenic Temperature Low Cycle Fatigue Properties of Materials in High Pressure Gaseous Environment | IV-23 |
| IV-4 | Elevated Temperature Low Cycle Fatigue Properties of Materials in High Pressure Gaseous Environment | IV-24 |
| V-1 | Room Temperature High Cycle Fatıgue Properties of Materials in High Pressure Gaseous Environment | V-7 |
| V-2 | Elevated Temperature High Cycle Fatigue Properties of Materials in High Pressure Gaseous Environment | V-9 |
| VI-1 | Fracture Toughness of Materials in High Pressure Gaseous Environment | VI-8 |
| VII-1 | Creep-Rupture Properties of Materials in High Pressure Gaseous Environment | VII-11 |
| VⅢ - 1 | Room Temperature Tensile Properties of Materials in High Pressure Gaseous Environment | VIII-6 |
| VIII-2 | Cryogenic Temperature Properties of Materials in High Pressure Gaseous Environment | VIII-10 |
| VIII-3 | Elevated Temperature Tensile Properties of Materials in High Pressure Gaseous Environment | VIII-11 |

SECTION I INTRODUCTION

This report is submitted in accordance with the requirements of Contract NAS8-26191 and represents the first annual report covering the period 29 June 1970 to 29 June 1971. Experimental efforts in this program have consisted of mechanical property tests of nickel-base, titanium-base, and iron-base alloys in 5000-psig gaseous helium and hydrogen at various temperatures, and the comparison of test results to determine degradation of properties due to the hydrogen environment. The testing program for the first year's work under this contract is outlined below:

| Material | Temperature, °F | Low Cycle Fatigue, H ₂ /He ¹ | High Cycle Fatigue, H ₂ /H _e ¹ | Fracture Toughness, H ₂ /H _e ¹ | Creep Rupture, H ₂ /He ¹ | Notched Tensile, H ₂ /H _e 1 | Smooth Tensile, H ₂ /H _e ¹ |
|----------------------------------|--------------------|---|--|---|--|---|---|
| Inconel 718(2) | 80 1250 | 4/4 4/4 | 4/4 4/4 | 2/2 | 2/2 | 3/2 3/2 | 2/2 2/2 |
| Inconel 718 ⁽³⁾ | -260 80 1250 | 4/4 4/4 4/4 | 4/4 4/4 | 2/2 | 2/2 | 3/2 3/2 | 2/2 2/2 |
| Inconel 718 Welds ⁽³⁾ | 80 | | | 2/2 | | 3/2 | 2/2 |
| Inconel 625 | 80 1250 | 4 /4 | | 2/2 | 2/2 | 3/2 3/2 | 2/2 2/2 |
| Inconel 625 Welds | 80 | | | 2/2 | | 3/2 | 2/2 |
| A-286 | 80 1250 | 4/4 4 /4 | | 2/2 | 2/2 | 3/2 3/2 | 2/2 2/2 |
| AISI 347 | -260 80 1250 | 4/4 | 4/4 | 2/2 | 2/2 | 3/2 3/2 3/2 | 2/2 2/2 2/2 |
| Hastelloy X | 80 1250 | 4/4 | | | | 3/2 3/2 | 2/2 2/2 |
| Ti-6A1-4V | 80 200 | 4/4 4/4 | | 2/2 | 2/2 | 3/2 3/2 | 2/2 2/2 |
| T1-5A1-2.5 Sn | 80 200 | 4/4 4/4 | 4/4 | 2/2 | 2/2 | 3/2 3/2 | 2/2 2/2 |

(1) Numbers (X/X) are number of tests in hydrogen/helium.

(2) Anneal 1750 °F, 1 hour, air cool, plus aging at 1325 °F for 8 hours, furnace cool to 1150 °F, hold at 1150 °F for a total aging time of 18 hours, and air cool.

(3) Solution 1900 °F, 1 hour, air cool 50 °F/minute or faster, plus aging at 1325 °F for 8 hours, furnace cool to 1150 °F, hold at 1150 °F for total aging time of 18 hours, and air cool. PWA FR-4566

All testing was conducted on solid specimens exposed to external gaseous pressure. Specific mechanical properties determined and the testing methods used are summarized below:

- Low Cycle Fatigue Low cycle fatigue life was established - by constant-total-strain-testing using smooth specimens and total-strain closed-loop testing machines.
- High Cycle Fatigue High cycle fatigue life was established by load (stress) controlled tension-tension testing using smooth specimens and servo-actuated, closed-loop machines.
- Fracture Toughness Fracture toughness tests were conducted using single-edged, notched, fatigue-precracked, compact tensile specimens.
- Creep-Rupture Creep rate and time to failure were determined using smooth specimens and a standard creep-rupture machine equipped with a recording extensometer.
- Tensile Smooth and notched tensile tests were conducted on solid specimens using ASTM tensile testing techniques.

This report is arranged in sections, which cover the program conclusions, materials tested, and results and conclusions of the individual property tests.

This program has been conducted using the Program Manager - Project Group System by the Pratt & Whitney Aircraft, Florida Research and Development Center, Materials Development Laboratory under the cognizance of Mr. W. B. McPherson, Materials Division, Astronautics Laboratory, Marshall Space Flight Center.

Acknowledgement is given to the following personnel of the Project Group:

Mr. J. E. Bearden Mr. R. B. Bogard Mr. W. H. Carver Mr. J. E. Gies Mrs. A. Kirkpatrick Mr. P. E. Newett Mr. J. F. Schratt Mrs. C. B. Stevens Mr. C. T. Torrey Mr. B. H. Walker

- High Cycle Fatigue Testing
- Low Cycle Fatigue Testing
- Test Support, Rocket Test Facility
- Test Support, Rocket Test Facility
- Proposal and Report Efforts
- Tensile and Fracture Toughness Testing
- Creep-Rupture Testing
- Metallurgical Investigations
- Metallographic Investigations
- Tensile and Fracture Toughness Testing

3

SECTION II CONCLUSIONS

The following system is established to weigh the degree of degradation and serve as an aid in comparing the various alloys.

Extremely Degraded (ED) – Hydrogen reduced the property or life (in helium) greater than 50%

$$ED = \left(\frac{H_e - H_2}{H_e}\right) \quad X \text{ 100 is } > 50\%$$

Severely Degraded (SD) - Hydrogen reduced the property or life (in helium) greater than 25% but less than 50%

SD -=
$$\left(\frac{H_e - H_2}{H_e}\right)$$
 X 100 is > 25% but < 50%

Degraded (D) - Hydrogen reduced the property or life (in helium) greater than 10% but less than 25%

$$D = \left(\frac{H_e - H_2}{H_e}\right) \quad X \text{ 100 is } > 10\% \text{ but} < 25\%$$

Negligible Degradation (ND) - Hydrogen reduced the property or life (in helium) less than 10%

Using the above rating system, table Π -1 displays the degree of degradation of each alloy investigated with various tests.

| Material | Temperature °F | Fatıg <u>Low Cycle</u> Cyclıc Life 1%-2% Strain | ue High Cycle Cyclic Life | Fracture Toughness | Cree Ruptu: <u>Based</u> Life (hr) at 100 hr H ₂ | p re On Stress at 100 hr | Tensile |
|---|-----------------------|--|---------------------------------|-----------------------|--|---|----------------|
| Nickel Base | | | | | | | |
| INCO 625 AMS 5666 | 80° 1250° | ED | | ND | ED | D | ED D ¦ |
| INCO 625 Weld | 80° | | | ND | | | ND |
| INCO 718, 1900°F Solution Plus Age AMS 5662 | -260° 80° 1250° | ND* ED SD | $_{ m ED}$ | ND | ED | SD | SD ND |
| INCO 718, 1750°F Solution Plus Age AMS 5662 | 80° 1250° | ED SD | ED ED | ND | ED | SD | ED ND |
| INCO 718 (1900°) Weld | 80 ° | | | ND | | | ED |
| Hastelloy X AMS 5754 | 80° 1250° | ED | | | | | D ND |
| Titanium Base | | | | | | | |
| T1-A110 AMS 4926 | 80° 200° | ND ED | ND | ND | ED | ND | D SD |
| Ti-6-4 AMS 4928 | 80° 200° | ND SD | | ND | ED | D | ED SD |
| Iron Base | | | | | | | |
| A-286 AMS 5735 | 80° 1250° | ND ND | | ND | ED | SD | ND D |
| AISI 347 AMS 5646 | -260° 80° 1250° | ND | ND | ND | ND | ND | ND ND ND |
| *Not de | graded at -260°F | | | | | | |

Table II-1. Degree of Degradation of Various Alloys

•

Nickel Base Alloys

Tested were: INCO 718 (AMS 5662) 1750 °F Solution plus Age INCO 718 (AMS 5662) 1900 °F Solution plus Age INCO 625 (AMS 5666) Hastelloy X (AMS 5754)

The low-cycle and high-cycle fatigue life, both strain controlled and tensiontension load controlled, at 80°F was extremely degraded (ED) for all nickel base alloys tested in 5000-psig hydrogen. The degree of degradation of INCO 718 was less severe at 1250 °F (rated SD) and was not degraded at -260 °F.

The fracture toughness, K_{IC} or K_{IE} , was rated ND (Negligible Degradation) for all nickel base alloys.

The rupture life at 1250 °F in 5000-psig hydrogen, comparing H₂ life (hr) to H_e life (hr) at stress required for 100 hr H₂ life, is extremely degraded (ED) for INCO 625 and both heat treatments of INCO 718. However, making a comparison on a stress basis for 100 hr life, the degradation is rated severe for INCO 718 and degraded for INCO 625.

The tensile properties; 0.2% yield, ultimate, elongation and reduction in area for smooth specimens, and ultimate and reduction in area for notched specimens ($K_t = 8.0$), were all evaluated, and the degradation rating is based on any of these properties being degraded. INCO 718 (1750°F Solution Heat Treated), INCO 625, and GTA welded INCO 718 (1900°F Solution Heat Treated), were extremely degraded at 80°F in 5000-psig hydrogen. INCO 718 (1900°F Solution Heat Treated) was severely degraded at 80°F. GTA welded INCO 625 was not degraded at 80°F. Hastelloy X was rated as degraded at 80°F. Less degradation was noted on all alloys, INCO 718, INCO 625, and Hastelloy X, when tested at 1250°F.

Iron Base Alloys

| Tested were: | A-286 (AMS 5735) |
|--------------|---------------------|
| | AISI 347 (AMS 5646) |

These alloys as a class exhibited the least degradation of properties in hydrogen of all the materials tested. In fact, AISI 347 had negligible property degradation for all the tests and conditions investigated during this program. A-286 material, tested in the fully heat treated condition (AMS 5735) exhibited negligible property degradation at 80°F. At an elevated temperature of 1250°F, however, the creep rupture 100 hr life was extremely degraded and the stress level for 100 hr life was severely degraded. The elevated temperature tensile strength was also degraded. Low cycle fatigue life had negligible degradations.

Titanium Base Alloys

| Tested were: | Ti 6-4 (AMS 4928) |
|--------------|---------------------|
| | Ti A-110 (AMS 4926) |

A-110 and 6-4 titanium alloys were rated ND (Negligible Degradation) for fatigue and fracture toughness at 80°F. Low cycle fatigue and stress rupture lives, and tensile RA (reduction in area) of both A-110 and 6-4 Ti were either severely or extremely degraded at 200°F in 5000-psig hydrogen.

This program was established to determine degradation of specific material properties and to enable general observations in regard to the susceptibility of a particular material to hydrogen degradation. Certain tests did not indicate any conclusive degradation due to the hydrogen environment on materials known to be degraded. An example of this is the fracture toughness of INCO 718 with the 1750 °F Solution plus Age heat treatment. This test indicated negligible degradation of this material by the hydrogen environment. The low and high cycle fatigue, creep rupture, and tensile tests, however, indicated extreme hydrogen degradation.

. A-286 material exhibited negligible degradation at 80 °F in all tests. At elevated temperature, the creep-rupture test indicated severe to extreme degradation. This emphasizes the fact that no one test can be used as a basis for declaring a material to be free of hydrogen degradation. For this reason, a material should be subjected to several different tests in a high pressure hydrogen environment before a definite conclusion regarding the degree of hydrogen degradation can be made.

The experience of this program has been that creep-rupture and low cycle fatigue are the most severe tests of a material for hydrogen degradation, followed by high cycle fatigue, tensile and fracture toughness tests, in that order.

SECTION III MATERIALS AND SPECIMENS

A. TEST MATERIAL

The purpose of this contract is to determine the susceptibility of various alloys proposed for use in hydrogen-fueled rocket engines to hydrogen degradation. For this phase of the program, wrought nickel-, iron-, and titanium-base materials were tested. Table III-1 lists materials and conditions in which they were purchased.

| Name | Base | Purchasing Specification | P&WA Heat | As-Received Condition |
|-------------|--------|-----------------------------|--------------|---|
| INCO 718 | Nickel | AMS 5662 | BVTO | 0.750-in. diameter bar- stock, solution annealed at 1750°F only. |
| INCO 718 | Nickel | AMS 5662 | BZMK | 4.0-in. diameter barstock, solution annealed at 1750°F only. |
| INCO 625 | Nıckel | AMS 5666 | BZCV | 0.750-in. diameter bar- stock, annealed at 1800°F. |
| INCO 625 | Nıckel | AMS 5666 | BYAP | 4.250-in. diameter bar- stock, annealed at 1800°F. |
| A-286 | Iron | AMS 5735 | BZCU | 0.750-in. diameter bar- stock fully heat-treated, solution at 1800°F, age at 1350°F. |
| A-286 | Iron | AMS 5735 | BXOY | 4.500-in. diameter barstock fully heat treated, solution at 1800°F, age at 1350°F. |
| AISI 347 | Iron | AMS 5646 | BZCT | 0.750-in. diameter bar- stock, solution at 1875°F, cold finished. |
| A ISI 347 | Iron | AMS 5646 | BUJR | 4.250-in. diameter bar- stock, solution at 1875°F only. |
| Hastelloy X | Nickel | AMS 5754 | BZCR | 0.750-in. diameter bar- stock, solution at 2150°F only. |

Table III-1. Materials for Hydrogen Degradation Testing

| | , | , | | | | |
|----------------------------------|----------|-----------------------------|--------------|---|--|--|
| Name | Base | Purchasing Specification | P&WA Heat | As-Received Condition | | |
| Titanium 6A1–4V | Titanium | AMS 4928 | BZCR | 0.750-in. diameter bar- stock, annealed at 1375°F only. | | |
| Tıtanium 6A1–4V | Titanium | AMS 4928 | BZAX | 4.500-1n. diameter bar- stock, annealed at 1375°F only. | | |
| Tıtanium A-110 (5A1.2.5Sn) | Titanium | AMS 4926 | BZCW | 0.750-in. diameter bar- stock, annealed at 1200°F only. | | |
| Titanium A-110 (5A1-2.5Sn) | Titanium | AMS 4926 | BZMP | 4.500-in. diameter bar- stock, annealed at 1200°F only. | | |
| INCO 718 | Nıckel | AMS 5832 | | Weld wire, annealed. | | |
| INCO 625 | Nickel | AMS 5837 | | Weld wire, annealed. | | |

Table III-1. Materials for Hydrogen Degradation Testing (Continued)

Notes:

- 1. Specimens used to test tensile strength, low and high cycle fatigue, and creep rupture were made of 0.750-in. diameter barstock, of single heats.
- 2. Specimens used to test fracture toughness were made of larger diameter material (4.0 to 4.5 in.), and of heats other than those of the 0.750-in. diameter barstock.
- 3. Weld wire was from single heats.

Specimen blanks were cut and heat-treated as required. Only the INCO 718 and the A-286 materials were tested in a fully heat-treated condition. The A-286 material was received fully heat-treated (per AMS 5735), and no subsequent heat treatment was done. The INCO 718 material was received in the 1750°F annealed condition (per AMS 5662). It was heat-treated according to the two requirements of contract Work Statement as follows:

- 1. Anneal at 1750°F, 1 hour, air cool (as received); age at 1325°F, 8 hours, furnace cool to 1150°F; hold at 1150°F for total age time of 18 hours, air cool.
- 2. Anneal at 1750°F, 1 hour, air cool (as received); solution at 1900°F, 1 hour, air cool 50°F/min; age at 1325°F, 8 hours, furnace cool to 1150°F; hold at 1150°F for total age time of 18 hours, air cool.

All other materials were tested in the solution-annealed (as received) condition.

Blanks from which the welded specimens of INCO 718 and INCO 625 were machined were prepared as shown in figure III-1, and gas-tungsten-arc (GTA) welded. The INCO 718 blanks were welded using AMS 5832 as filler material; INCO 625 blanks were welded using AMS 5837 filler material. The INCO 718 welded blanks were then subjected to the heat treatment described in item 2 above. INCO 625 welded specimen blanks were subjected to an 1800°F, one hour, air cool, stress-relief cycle.



Figure III-1. Specimen Blank Preparation Prior To FD 51835 Welding

B. TEST GASES

Helium and hydrogen were used during the testing of specimens and nitrogen was used as a preliminary purge gas. Hydrogen was provided under Military Specification P-27201, which requires the gas to have an oxygen content of less than 1 part per million. Gas handling systems supplying the test vessels were equipped to enable sampling before and after specimen tests. Samples were analyzed using a modified gas chromatograph with accuracy in the parts per billion range. Typical oxygen content of hydrogen samples was found to be in the 1.3 to 1.5 parts per million. No appreciable difference was noted between pretest and posttest samples, indicating no gas contamination by the test rig and/or test itself. PWA FR-4566

C. TEST SPECIMENS

Surfaces of all specimens were machined¹ and finished to an average roughness of 16μ in. RMS or less except for one outer surface of the fracture toughness specimens, which was machined to a roughness of 32μ in. RMS in accordance with ASTM E-399T. Gage sections of specimens were polished prior to testing. The notch used for tensile specimens to obtain a stress concentration factor of 8.0 was designed according to Peterson² and was machined by grinding. Dimensions of the notch were checked optically (shadowgraph) several times during machining to ensure that the required 0.002-in. notch radius and the notch depth were obtained. Smooth tensile specimens had a gage section diameter of 0.251 in. minimum. A typical set of specimens is shown in figures III-2 and specimen prints are listed in table III-2 and shown in figures III-3 through III-7.



FE 108806A

FE 108806A

Figure III-2. Typical Test Specimens Used To Determine Effect of High Pressure Gaseous Hydrogen on Mechanical Properties of Materials

¹Test specimens were machined by both the Pratt & Whitney Aircraft Laboratory Machine Shop and outside vendors operating under Pratt & Whitney Materials Control Laboratory surveillance and control.

²R. E. Peterson, Stress Concentration Design Factors, John Wiley & Sons, Inc., New York, 1953.

Pratt & Whitney Aircraft PWA FR-4566



Figure IV-2. Low Cycle Fatigue Life of AMS 5666 DF 86830 (INCO 625) at 80°F



Figure IV-3. Effect of Gaseous Hydrogen and Strain DF 86831 Range on Low Cycle Fatigue Life of AMS 5666 (INCO 625)

IV-3

PWA FR-4566

3. INCO 718 (AMS 5662)

INCO 718 material was the most thoroughly investigated. Two heat treatments were applied to specimens from the same stock, differing only in solution temperature. The effect of 1750 and 1900°F solution temperatures upon microstructure is shown in figure IV-4. Both microstructures were fully recrystallized with the 1900°F solution temperature producing larger grain size. The 1900°F-solutioned material was slightly more degraded in hydrogen than the 1750°F-solutioned material, indicating microstructure affects LCF performance with small grain, recrystallized structures more desirable. Investigations by Harris and VanWanderham⁽¹⁾ have also described this relationship. Cyclic strain level and temperature also influence the degree of degradation (figure IV-5 through IV-11). The 1750°F-solutioned material has increasing degradation at increasing cyclic strain level. The 1900°F-solutioned material did not exhibit this trend. The most influential effect on LCF life resulted from temperature. Both materials were less susceptible (almost 65%) less) to life degradation at 1250°F than at 80°F. The 1900°F-solutioned material was tested at -260°F, 80°F, and 1250°F. A plot of degradation vs temperature (figure IV-12) indicates that degradation is most severe in the range of temperatures around 80°F, and with decreasing degradation with decreasing temperature. In fact, at a temperature of -260°F LCF life in hydrogen was significantly better than LCF life in helium at that temperature. The reason for this great improvement in LCF life at cryogenic temperature is not presently understood. It is believed that the 1750°F-solutioned material and perhaps other nickel-base alloys will also show similar influences of temperature. It is clear, however, that INCO 718 LCF life is most severely degraded in the room (80°F) temperature range. Additional testing at temperature ranges between -100 and 600°F would define the point of inflection in the temperature-degradation curve.

4. Hastelloy X

Hastelloy X (AMS 5754) was tested at 80°F only and exhibited the lowest average degradation of all the nickel-base alloys tested. Degradation of this alloy was strain level sensitive, with degradation inversely proportional to increasing cyclic strain level (figures IV-13 and IV-14).

5. Titanium-Base Alloys

The LCF life of the two titanium-base alloys tested, Ti 6-4 (AMS 4928) and A-110 (AMS 4926) was not as severely degraded as that of the nickel-base alloys. Both alloys showed an influence of cyclic strain level upon degree of degradation. The Ti 6-4 exhibited decreasing degradation with increasing cyclic strain level at both 80°F and 200°F (figures IV-15 through IV-17); whereas, the A-110 exhibited increasing degradation with increasing cyclic strain level at 200°F. This alloy (A-110) displayed no degradation at 80°F, however there was more scatter in the test data for this condition than for any other material tested(figures IV-18 through IV-20).

⁽¹⁾ VanWanderham, M., and J. A. Harris, Jr., "Low Cycle Fatigue of Metals in High Pressure Gaseous Hydrogen at Cryogenic, Ambient, and Elevated Temperatures," presented to the 1971 WESTEC Conference, Los Angeles, California.



Mag: 100X

1900°F Solution Plus Age Heat Treatment

Mag: 1000X

Figure IV-4. Effect of Heat Treatment on Microstructure of AMS 5662 (INCO 718) Heat BVTO



Figure IV-5. Low Cycle Fatigue Life of AMS 5662 DF 86832 at 80 °F (INCO 718, 1750 °F Solution Plus Age)



Figure IV-6. Low Cycle Fatigue Life of AMS 5662 at 1250°F (INCO 718, 1750°F Solution Plus Age)

DF 86833



Figure IV-9. Low Cycle Fatigue Life of AMS 5662 DF 86836 at -260°F (INCO 718, 1900°F Solution Plus Age)



Figure IV-10. Low Cycle Fatigue Life of AMS 5662 DF 86837 at 1250 °F (INCO 718, 1900 °F Solution Plus Age)



Figure IV-11. Effect of Gaseous Hydrogen DF 86838 and Strain Range on Low Cycle Fatigue Life of AMS 5662 (INCO 718, 1900°F Solution Plus Age)



Pratt & Whitney Aircraft PWA FR-4566

6-AI



Figure IV-13. Low Cycle Fatigue Life of AMS 5754 DF 86840 (Hastelloy X) at 80°F

Figure IV-14. Effect of Gaseous Hydrogen and Strain DF 86841 Range on Low Cycle Fatigue Life of AMS 5754 (Hastelloy X)



Figure IV-15. Low Cycle Fatigue Life of AMS 4928 DF 86842 (Ti 6-4) at 80°F



Figure IV-16. Low Cycle Fatigue Life of AMS 4928 DF 86843 (Ti 6-4) at 200°F

Figure IV-17, Effect of Gaseous Hydrogen and Strain DF 86844 Range on Low Cycle Fatigue Life of AMS 4928 (Ti 6-4)



Figure IV-18. Low Cycle Fatigue Life of AMS 4926 DF 86845 (A-110) at 80°F

•



Figure IV-19. Low Cycle Fatigue Life of AMS 4926 DF 86846 (A-110) at 200°F



Figure IV-20. Effect of Gaseous Hydrogen and Strain DF 86847 Range on Low Cycle Fatigue Life of AMS 4926 (A-110)

6. A-286

The A-286 (AMS 5735) iron-base material was not degraded at room temperature (80°F) and only slightly degraded (average of 9%) at 1250°F (figures IV-21 through IV-23). No definite trend is apparent in the degradation vs cyclic strain level plot at elevated temperature; however no-degradation-occurredat the maximum cyclic strain level tested (2.0%).



Figure IV-21. Low Cycle Fatigue Life of AMS 5735 DF 86848 (A-286) at 80°F



Figure IV-22. Low Cycle Fatigue Life of AMS 5735 DF 86849 (A-286) at 1250°F



Figure IV-23. Effect of Gaseous Hydrogen and Strain DF 86850 Range on Low Cycle Fatigue Life of AMS 5735 (A-286)

7. AISI 347

AISI type 347 stainless steel (AMS 5646) was tested at 80°F only and was not degraded at that temperature (figure IV-24).

B. TEST PROCEDURES

Smooth, round, solid specimens were used for the strain-controlled LCF tests discussed in this report. The test specimen used is described in Section III and detailed by print FML 95500B (figure III-3). The specimen configuration, which incorporates integral machined extensometer collars, was arrived at experimentally through the use of photoelastic and elastic-plastic strain analyses. A calibration procedure is established for each material to relate the maximum strain to collar deflection during both the elastic and plastic portion of the strain cycle. The specimen design and calibration procedure

have also been verified analytically through the use of finite element analyses technique and also mathematical model analyses.



Figure IV-24. Low Cycle Fatigue Life of AMS 5646 DF 86851 (AISI 347) at 80°F

After machining, specimen material was verified by either eddy current (Dermatron) or spectrographic techniques. Gage sections were then polished and dimensions measured. Prior to installation in the test rig, specimens were thoroughly cleaned with a nonchlorinated solvent.

Tests were conducted on a P&WA designed and built, closed loop type, hydraulically actuated test machine, located in an isolated test cell, utilizing the constant strain control mode. Specimen axial strain is measured and controlled by means of a proximity probe extensometer. A heavy walled pressure vessel made of AISI type 347 stainless steel was mounted on the upper platen of the test machine. This vessel (shown in figure IV-25) incorporates a Gray Loc type flange and seal because of the relative ease of assembly and the reliability of the seal in high pressure. The base of the vessel includes a pressure compensating device to eliminate the axial tensile load acting over the differential specimen and adapter areas. Both internal (to the pressure vessel) and external load cells are used, thus the effect of friction at the seals where the load rods enter the vessel is known and accounted for. During testing, load strain hysteresis curves, similar to figure IV-26, are plotted using the extensioneter and internal load cell outputs. Electrical connections to the load cell, extensioneter system, furnace (for elevated temperature tests only) and thermocouples are made through the vessel wall via high-pressure bulkhead connectors. Cryogenic temperatures are obtained by surrounding the test chamber with a liquid nitrogen bath. The test gas passes through a heat exchanger coil submersed in the liquid nitrogen bath and into the test chamber. Thermocouples attached to the specimen are used to monitor temperature during test.

Pratt & Whitney Aircraft PWA FR-4566



Specimen and Extensometer in Place



Specimen, Extensometer and Half Furnace in Place



Specimen, Extensometer and Furnace in Place



Closed Pressure Vessel, Cooling Jacket Not Shown

Figure IV-25. High Pressure Gaseous Environment, FD Low Cycle Fatigue Test Vessel

FD 53147



Figure IV-26. Typical Load-Strain Hysteresis Curves for a High Pressure Gaseous Environment Low Cycle Fatigue Test (AMS 5646, 1.3% Total Strain Range, 80°F, 5000-psig Hydrogen)

| . <u></u> | | Test Conditions | | | | Test Results | | |
|-------------|---------------------------|-----------------|-------------------|----------------------------|--------------------------------------|-------------------------|------------------------------|--|
| Material | Test Temperature °F | Environment | Pressure, psig | Total Stram Range, % | Cyclic Rate, Cycles/ Minute | Cycles to Failure | Plastic Strain Range, % * | |
| AMS 5662 | 80 | Helium | 5000 | 1.0 | 4 | 15,000 | 0.02 | |
| (INCO 718) | 80 | Helium | 5000 | 0.8 | 5 | 13,650 | 0.03 - 0.05 | |
| 1750°F Sol. | 80 | Helium | 5000 | 1.5 | 3 | 1,500 | 0.13 - 0.20 | |
| | 80 | Heluum | 5000 | 2.0 | ŝ | 1,220 | 0.35 - 0.54 | |
| | 80 | Hydrogen | 5000 | 1.0 | 4 | 6,310 | 0.07 - 0.08 | |
| | 80 | Hydrogen | 5000 | 1.0 | 4 | 6,080 | 0.05 - 0.08 | |
| | 80 | Hydrogen | 5000 | 1.5 | ŝ | 450 | 0.12 - 0.19 | |
| | 80 | Hydrogen | 5000 | $\frac{2}{2}, 0$ | 3 | 55 | 0.41 - 0.46 | |
| | 80 | Hydrogen | 5000 | 0.8 | 5 | 9,950 | 0.02 - 0.04 | |
| AMS 5662 | 80 | Helium | 5000 | 1.0 | 4 | 21,500 | 0.02 - 0.05 | |
| (INCO 718) | 80 | Helium | 5000 | 1.25 | 4 | 5,450 | 0.13 - 0.16 | |
| 1900°F Sol. | 80 | Helium | 5000 | 1.5 | 3 | 2,360 | 0.11 - 0.18 | |
| | 80 | Helium | 5000 | 2.1 | 3 | 900 | 0.60 - 0.70 | |
| | 80 | Hydrogen | 5000 | 1.0 | 4 | 2,220 | 0.03 | |
| | 80 | Hydrogen | 5000 | 1.3 | 4 | 760 | 0.04 - 0.09 | |
| | 80 | Hydrogen | 5000 | 1.5 | 3 | 460 | 0.18 - 0.22 | |
| | 80 | Hydrogen | 5000 | 2.0 | 3 | 300 | 0.33' - 0.49 | |
| AMS 5666 | 80 | Helium | 5000 | 0.8 | 5 | 15,200 | 0.06 | |
| (INCO 625) | 80 | Helium | 5000 | 1.4 | 4 | 4,160 | 0.36 - 0.42 | |
| | 80 | Helum | 5000 | 1.75 | 3 | 3,200 | 0.46 | |
| | 80 | Helium | 5000 | 2.0 | 3 | 2,730 | 0.62 - 0.72 | |
| | 80 | Hydrogen | 5000 | 1.0 | 4 | 1,890 | 0.06 - 0.09 | |
| | 80 | Hydrogen | 5000 | 1,25 | 4 | 970 | 0.14 - 0.16 | |
| | 80 | Hydrogen | 5000 | 1.5 | 3 | 360 | 0.39 - 0.46 | |
| | 80 | Hydrogen | 5000 | 2.0 | 3 | 340 | 0.58 - 0.62 | |

Table IV-2.Room Temperature Low Cycle Fatigue Properties of Materials in
High Pressure Gaseous Environment

| | Test Conditions | | | | Test Results | | | |
|---------------------------|--|--|---|---|--------------------------------------|---|---|--|
| Material | Test Temperature, °F | Environment | Pressure, psig | Total Strain Range, % | Cyclic Rate, Cycles/ Minúte | Cycles to Failure | Plastic Strain Range, %* | |
| AMS 5735 (A-286) | 80 80 80 80 80 80 80 80 | Helium Helium Helium Hydrogen Hydrogen Hydrogen Hydrogen | 5000 5000 5000 5000 5000 5000 5000 500 | 1.0 1.25 1.5 2.0 1.0 1.3 1.5 2.0 | 4 4 3 3 4 4 3 3 | $\begin{array}{c} 4,930\\ 4,012\\ 1,950\\ 870\\ 6,550\\ 4,030\\ 2,200\\ 700 \end{array}$ | $\begin{array}{c} 0. \ 12 \ - \ 0. \ 19 \\ 0. \ 20 \ - \ 0. \ 37 \\ 0. \ 36 \ - \ 0. \ 50 \\ 0. \ 93 \ - \ 0. \ 98 \\ 0. \ 12 \\ 0. \ 22 \ - \ 0. \ 31 \\ 0. \ 30 \ - \ 0. \ 42 \\ 0. \ 90 \ - \ 0. \ 95 \end{array}$ | |
| AMS 5646 (AISI 347) | 80 80 80 80 80 80 80 80 | Helium Helium Helium Helium Hydrogen Hydrogen Hydrogen Hydrogen | 5000 5000 5000 5000 5000 5000 5000 500 | $\begin{array}{c} 0.9\\ 1.25\\ 1.5\\ 1.7\\ 1.0\\ 1.5\\ 1.3\\ 2.0 \end{array}$ | 4 4 3 3 4 3 4 3 | $\begin{array}{c} \textbf{3, 100} \\ \textbf{1, 450} \\ \textbf{905} \\ \textbf{460} \\ \textbf{2, 200} \\ \textbf{1, 120} \\ \textbf{700} \\ \textbf{380} \end{array}$ | $\begin{array}{c} 0.\ 25 - 0.\ 29 \\ 0.\ 33 - 0.\ 39 \\ 0.\ 60 - 0.\ 77 \\ 0.\ 96 - 1.\ 05 \\ 0.\ 26 - 0.\ 33 \\ 0.\ 47 - 0.\ 58 \\ 0.\ 42 - 0.\ 54 \\ 0.\ 90 - 1.\ 10 \end{array}$ | |
| AMS 5754 (Hastelloy X) | 80 80 80 80 80 80 80 80 | Helium Helium Helium Hydrogen Hydrogen Hydrogen Hydrogen | 5000 5000 5000 5000 5000 5000 5000 500 | 1.5 1.4 1.85 2.0 1.0 1.25 1.5 2.0 | 3 4 3 4 4 3 3 | $\begin{array}{c} \textbf{3,500} \\ \textbf{3,300} \\ \textbf{1,720} \\ 200 \\ \textbf{3,050} \\ \textbf{1,964} \\ 810 \\ 405 \end{array}$ | $\begin{array}{c} 0.73 - 0.79 \\ 0.58 - 0.66 \\ 1.02 - 1.08 \\ 0.91 - 1.08 \\ 0.44 - 0.46 \\ 0.61 - 0.62 \\ 0.79 - 0.82 \\ 0.82 - 0.92 \end{array}$ | |

Table IV-2. Room Temperature Low Cycle Fatigue Properties of Materials in High Pressure Gaseous Environment (Continued)

Pratt & Whitney Aircraft PWA FR-4566

| T Material AMS 4928 (Ti 6-4) | Test Semperature, °F 80 | Environment | Pressure, psig | Total Strain | Cyclic Rate, Cycles/ | Cycles | 1 |
|---------------------------------------|----------------------------------|-------------|-------------------|-----------------|----------------------------|---------|------------------------------|
| AMS 4928 (Ti 6-4) | 80 | 1. | | Range, % | Minute | Failure | Plastic Strain Range, % * |
| (Ti 6-4) | 00 | Helium | 5000 | 1.6 | 3 | 2,370 | 0.05 - 0.10 |
| | 80 | Helium | 5000 | 1.9 | 3 | 950 | 0.21 - 0.26 |
| | 80 | Helium | 5000 | 2.25 | 3 | 360 | 0.28 - 0.37 |
| 80 80 | 80 | Hydrogen | 5000 | 1,4 | 4 | 4,850 | 0.09 - 0.10 |
| | 80 | Hydrogen | 5000 | 1.7 | 3 | 600 | 0.09 - 0.10 |
| | 80 | Hydrogen | 5000 | 1.7 | 3 | 2,940 | 0.04 - 0.05 |
| | 80 | Hydrogen | 5000 | 1.85 | 3 | 860 | 0.12 - 0.15 |
| | 80 | Hydrogen | 5000 | 1.2 | 4 | 5,130 | 0.035 - 0.04 |
| AMS 4926 | 80 | Helium | 5000 | 1.8 | 3 | 1,600 | 0.14 - 0.19 |
| (A-110) | 80 | Helium | 5000 | 1.6 | 3 | 1,620 | 0.18 |
| • | 80 | Helium | 5000 | 1.5 | 3 | 2,000 | 0.13 - 0.18 |
| 8 8 | 80 | Helium | 5000 | 1.0 | 4 | 9,050 | 0.015 - 0.04 |
| | 80 | Hydrogen | 5000 | 1.4 | 4 | 610 | 0.06 - 0.13 |
| | 80 | Hydrogen | 5000 | 1.85 | 3 | 500 | 0.20 - 0.31 |
| | 80 | Hydrogen | 5000 | 1.8 | 3 | 1,020 | 0.16 - 0.27 |
| | 80 | Hydrogen | 5000 | 1.0 | 4 | 17,500 | 0.02 - 0.04 |

Table IV-2. Room Temperature Low Cycle Fatigue Properties of Materials in High Pressure Gaseous Environment (Continued)
| | | Test Cond | litions | | Tes | t Results | |
|-------------|----------------------------|-------------|-------------------|-----------------------------|--------------------------------------|-------------------------|------------------------------|
| Material | Test Temperature, °F | Environment | Pressure, psig | Total Strain Range, % | Cyclic Rate, Cycles/ Minute | Cycles to Failure | Plastic Strain Range, % * |
| AMS 5662 | -260 | Helium | 5000 | 1.5 | 3 | 5,140 | 0.06 - 0.14 |
| (INCO 718) | -260 | Helium | 5000 | 2.0 | 3 | 1,630 | 0.41 - 0.61 |
| 1900°F Sol. | -260 | Helium | 5000 | 2.0 | 3 | 2,080 | 0.45 - 0.52 |
| | -260 | Helium | 5000 | 2.5 | 3 | 1,300 | 0.51 - 0.89 |
| | -260 | Hydrogen | 5000 | 1.5 | 3 | 22,300 | 0.04 - 0.07 |
| | -260 | Hydrogen | 5000 | 2.0 | 3 | 3,460 | 0.21 - 0.31 |
| | -260 | Hydrogen | 5000 | $2_{\bullet} 0$ | 3 | 3,580 | 0.15 - 0.32 |
| | -260 | Hydrogen | 5000 | 2.25 | 3 | 1,850 | 0.44 - 0.72 |
| | | | | | | | |

Table IV-3. Cryogenic Temperature Low Cycle Fatigue Properties of Materials in High Pressure Gaseous Environment

* Range includes strain hardening - softening effects.

4

t

| . <u> </u> | | Test Cond | litions | | Tes | t Results | 3 |
|---------------------------------------|--|--|---|--|--------------------------------------|---|---|
| Material | Test Temperature, °F | Environment | Pressure, psig | Total Strain Range, % | Cyclic Rate, Cycles/ Mınute | Cycles to Failure | Plastic Strain Range, %* |
| AMS 5662 (INCO 718) 1750°F | 1250 1250 1250 1250 1250 1250 1250 1250 | Helium Helium Helium Hydrogen Hydrogen Hydrogen Hydrogen | 5000 5000 5000 5000 5000 5000 5000 500 | $\begin{array}{c} 2.0\\ 1.45\\ 1.25\\ 1.0\\ 1.75\\ 1.50\\ 1.25\\ 1.0\\ 1.25\\ 1.0\\ \end{array}$ | 3 4 4 3 3 4 4 | $145 \\ 570 \\ 940 \\ 1,820 \\ 175 \\ 330 \\ 815 \\ 1,810$ | $\begin{array}{c} 0.59 - 0.72 \\ 0.15 - 0.28 \\ 0.04 - 0.16 \\ 0.026 - 0.10 \\ 0.45 - 0.59 \\ 0.21 - 0.39 \\ 0.05 - 0.18 \\ 0.05 \end{array}$ |
| AMS 5662 (INCO 718) 1900°F Sol. | 1250 1250 1250 1250 1250 1250 1250 1250 | Helium Helium Helium Helium Hydrogen Hydrogen Hydrogen Hydrogen | 5000 5000 5000 5000 5000 5000 5000 500 | 2.0 1.6 1.35 1.0 1.75 1.6 1.3 1.0 | 3 3 4 4 3 3 4 4 | $\begin{array}{c} 260 \\ 510 \\ 950 \\ 1,730 \\ 320 \\ 285 \\ 685 \\ 1,350 \end{array}$ | $\begin{array}{c} 0.\ 64 \ - \ 0.\ 85 \\ 0.\ 43 \ - \ 0.\ 52 \\ 0.\ 15 \ - \ 0.\ 28 \\ 0.\ 11 \ - \ 0.\ 22 \\ 0.\ 50 \ - \ 0.\ 67 \\ 0.\ 33 \ - \ 0.\ 48 \\ 0.\ 22 \ - \ 0.\ 39 \\ 0.\ 10 \ - \ 0.\ 17 \end{array}$ |
| AMS 5735 (A-286) | 1250 1250 1250 1250 1250 1250 1250 1250 | Helium Helium Helium Hydrogen Hydrogen Hydrogen Hydrogen Hydrogen | 5000 5000 5000 5000 5000 5000 5000 500 | 2.0 1.5 1.25 1.0 2.0 1.6 1.25 1.0 | 3 3 4 4 3 3 4 4 | $\begin{array}{r} 405\\ 1,000\\ 1,600\\ 2,290\\ 410\\ 650\\ 1,260\\ 2,050\end{array}$ | $\begin{array}{c} 0.82 - 0.89 \\ 0.31 - 0.42 \\ 0.08 - 0.14 \\ 0.05 - 0.15 \\ 0.70 - 0.89 \\ 0.39 - 0.57 \\ 0.057 - 0.063 \\ 0.03 - 0.14 \end{array}$ |

Table IV-4.Elevated Temperature Low Cycle Fatigue Properties of Materials in
High Pressure Gaseous Environment

| - | | Test Cond | itions | | Tes | t Results | |
|----------|----------------------------|-------------|-------------------|-----------------------------|--------------------------------------|-------------------------|------------------------------|
| Material | Test Temperature, °F | Environment | Pressure, psig | Total Strain Range, % | Cyclic Rate, Cycles/ Minute | Cycles to Failure | Plastic Strain Range, % * |
| AMS 4928 | 200 | Helium | 5000 | 1.25 | 4 | 11,270 | 0.033 - 0.047 |
| (T1 6-4) | 200 | Helium | 5000 | 1.6 | 3 | 2,130 | 0.03 - 0.08 |
| · · · · | 200 | Helium | 5000 | 1.8 | 3 | 1,650 | 0.14 - 0.19 |
| | 200 | Helium | 5000 | 2.15 | 3 | 1,050 | 0.45 - 0.56 |
| | 200 | Hydrogen | 5000 | 1.25 | 4 | 5,880 | 0.02 - 0.04 |
| | 200 | Hydrogen | 5000 | 1.5 | 3 | 3,020 | 0.043 |
| | 200 | Hydrogen | 5000 | 1.9 | 3 | 1,050 | 0.17 - 0.25 |
| | " 200 | Hydrogen | 5000 | 2.1 | 3 | 970 | 0.24 - 0.32 |
| AMS 4926 | 200 | Helium | 5000 | 1.25 | 4 | 5,300 | 0.04 - 0.07 |
| (A-110) | 200 | Helium | 5000 | 1.6 | 3 | 2,900 | 0.23 - 0.26 |
| | 200 | Helium | 5000 | 1.9 | 3 | 1,620 | 0.26 - 0.42 |
| | 200 | Helium | 5000 | 2.05 | 3 | 1,400 | 0.32 - 0.46 |
| | 200 | Hydrogen | 5000 | 1.0 | 4 | 14,200 | 0.03 - 0.036 |
| | 200 | Hydrogen | 5000 | 1.3 | 4 | 4,100 | 0.035 - 0.09 |
| | 200 | Hydrogen | 5000 | 1.6 | 3 | 215 | 0.14 - 0.24 |
| | 200 | Hydrogen | 5000 | 2.0 | 3 | 130 | 0.32 - 0.45 |

| Table IV-4. | Elevated Temperature Low Cycle Fatigue Properties of Materials in |
|-------------|---|
| | High Pressure Gaseous Environment (Continued) |

* Range includes strain hardening - softening effects.

Pratt & Whitney Aircraft PWA FR-4566

;

SECTION V HIGH CYCLE FATIGUE

A. INTRODUCTION

Tests were accomplished on nickel, iron, and titanium base alloys (INCO 718, AISI 347, and A-110, respectively) to evaluate the high cycle fatigue (HCF) behavior of these materials when subjected to high pressure gaseous helium and hydrogen atmospheres at ambient and elevated temperatures, and to establish the susceptibility of these alloys to hydrogen degradation.

High Cycle Fatigue (HCF) tests were conducted in 5000-psig gaseous helium and hydrogen at 80°F for all materials investigated and at 1250°F for the nickel base alloy, INCO 718. Results of the tests in helium provided a baseline for comparison with the hydrogen tests.

B. CONCLUSIONS AND DISCUSSION

Tests of the AMS 5662 (INCO 718) alloy with 1750°F and 1900°F solution plus age heat treatments at both 80°F and 1250°F in 5000-psig hydrogen indicated appreciable HCF life degradation for both heat treatments. Conclusions as to the degree of HCF degradation of this alloy by gaseous hydrogen are restricted due to data scatter inherent in this type of test, and because of the limited number of tests. Additional testing of a sufficient number of samples for a statistical analysis is required before definite conclusions as to the degree of hydrogen degradation can be made. The HCF life of the iron base alloy, AMS 5646 (AISI 347), and the titanium base alloy, AMS 4926 (A-110), which were tested at 80°F only, was not appreciably affected by 5000-psig hydrogen.

High cycle fatigue test results are presented graphically in figures V-1 through V-6.





Pratt & Whitney Aircraft PWA FR-4566



Figure V-3. High Cycle Fatigue Life of AMS 5646 DF 86854 (AISI 347) at 80 °F

V-2



Figure V-4. High Cycle Fatigue Life of AMS 4926 DF 86855 (A-110) at 80 °F



Figure V-5. High Cycle Fatigue Life of AMS 5662DF 86856(INCO 718) 1750 °F Solution at 1250 °F



Figure V-6. High Cycle Fatigue Life of AMS 5662 (INCO 718) 1900 °F Solution at 1250 °F

DF 86857

C. TEST PROCEDURE

Smooth, round specimens were used for the high cycle fatigue tests discussed in this report. The test specimen used is illustrated in Section III and detailed by print FML 95212B, also included in that section.

After machining, specimen material was verified, each specimen was inspected visually for any machining discrepancies, the minimum cross section was measured with a micrometer, and the specimen cleaned with acetone.

The HCF life data were established by a load (stress) controlled tensiontension test. A typical test cycle is a tensile load that varies sinusoidally about a constant tensile preload at a cyclic rate of 20 Hz. All specimens were tested at an R ratio (minimum stress/maximum stress) of 0.1.

Tests were conducted using a Pratt & Whitney Aircraft designed and fabricated closed-loop, servo-controlled, hydraulically actuated test machine located in an isolated test cell, figure V-7 (top). A heavy walled pressure vessel made of AISI 321 stainless steel was mounted on the upper platen of the test machine. The pressure vessel, shown in figure V-7 (bottom) is similar to those used for other testing under this contract.

Specimen load was measured and controlled by a strain gage load cell, integral with the specimen loading rod and inside the pressure vessel. Prior to the initial test and periodically throughout the test program, the load cell was calibrated (using an instrumented and calibrated specimen) at 5000-psig pressure so that axial tensile load on the specimen due to high pressure acting over differential specimen and loading rod areas could be eliminated. As the load cell was internal and was calibrated to give true specimen load, friction loss through the loading rod O-ring seals is of no consequence. Electrical connections to all internal strain gages, load cell, thermocouples and heating devices were made through the bottom of the pressure vessel via an instrumentation manifold and high pressure bulkhead connectors. During testing, the load cycle and number of cycles to failure were constantly monitored on a calibrated oscilloscope and electronic counter using the internal load cell output.



FC 23389 Test Machine Located in Isolated Test Cell



Test Vessel Open



Test Vessel Closed

Figure V-7. High Pressure Gaseous Environment High Cycle Fatigue Testing Equipment FD 53128

PWA FR-4566

Elevated temperature testing (1250°F) was accomplished using a dc power supply and a high power density, single zone furnace mounted inside the pressure vessel. Analysis of gas samples, before and after the specimen tests, indicated no oxygen contamination of the test media due to the heating device. Thermocouples attached to the specimen were used to monitor and control the specimen temperature during testing.

Test system shutdown was provided at the instant of specimen failure by a linear variable differential transformer (LVDT), which sensed load rod position, in combination with a meter relay. This proved an accurate means of determining the total number of test cycles to failure.

Test specimens were mounted in the pressure vessel load frame by threading the ends into tapped loading rods (top and bottom) and securing each end with locknuts. The specimen and the sealed pressure vessel were subjected to a purge cycle consisting of evacuation, nitrogen purge, two successive "pop" purges with the test media (helium or hydrogen), and final pressurization to test pressure (5000 psig).

D. RESULTS

Maximum stress level and cycles to failure data were obtained for each material and are listed in table V-1 for 80°F and table V-2 for 1250°F tests. These data were plotted graphically (figures V-1 through V-6) to obtain stress vs cycles to failure (S-N) curves for each material. The difference in the HCF curves for the helium and hydrogen tests represents the degradation of high cycle fatigue life caused by a high pressure hydrogen atmosphere.

| | | <u> </u> | Test | : Conditions | | | | |
|------------|--|-------------|-----------|--------------|----------|------------|--------------------|--|
| | Test | | | Stress | s Level* | Cvelie | | |
| | Temperature, | | Pressure, | Maximum, | Minimum, | Rate, | Cycle's to | |
| Material | <u> </u> | Environment | psig | ksi | ksi | cycles/sec | Failure | |
| AMS 5646 | 80 | Helium | 5000 | 90.0 | 9.0 | 20 | 100,000 + (Runout) | |
| (AISI 347) | 80 | Helium | 5000 | 100.0 | 10.0 | 20 | 70,800 | |
| (, | 80 | Helium | 5000 | 105.0 | 10.5 | 20 | 3,640 | |
| | 80 | Helium | 5000 | 110.0 | 11.0 | 20 | 700 | |
| | 80 | Hydrogen | 5000 | 95.0 | 9.5 | 20 | 100,000 + (Runout) | |
| | 80 | Hydrogen | 5000 | 100.0 | 10.0 | 20 | 20,600 | |
| | 80 | Hydrogen | 5000 | 105.0 | 10.5 | 20 | 1,620 | |
| | 80 | Hydrogen | 5000 | 115.0 | 11.5 | 20 | 100 | |
| AMS 4926 | 80 | Helium | 5000 | 120.0 | 12.0 | 20 | 196,600 (Runout) | |
| (A-110) | 80 | Helium | 5000 | 125.0 | 12.5 | 20 | 51,900 | |
| () | 80 | Helium | 5000 | 130.0 | 13.0 | 20 | 46,900 | |
| | 80 | Helium | 5000 | 135.0 | 13.5 | 20 | 17,500 | |
| | 80 | Hydrogen | 5000 | 130.0 | 13.0 | 20 | 73,600 | |
| | 80 | Hydrogen | 5000 | 132.5 | 13.25 | 20 | 17,200 | |
| | 80 | Hydrogen | 5000 | 135.0 | 13.5 | 20 | 3,200 | |
| | 80 | Hydrogen | 5000 | 140.0 | 14.0 | 20 | 5,300 | |
| *S | *Stress levels for R ratio $\left(\frac{\text{Minimum Stress}}{\text{Maximum Stress}}\right) = 0.1.$ | | | | | | | |

Table V-1.Room Temperature High Cycle Fatigue Properties of MaterialsIn High Pressure Gaseous Environment (Continued)

| · | | | Te | st Conditions | | | | | |
|------------|--|-------------|-------------------|-----------------|-----------------|---------------------|----------------------|--|--|
| | Test | | | Stres | s Level* | Cvelie | | | |
| Material | Temperature, °F | Environment | Pressure, psig | Maximum, ksi | Minimum, ksi | Rate. cycles/sec | Cycles to Failure | | |
| AMS 5662 | 1250 | Helium | 5000 | 140.0 | 14.0 | 20 | 10,200 | | |
| (INCO 718) | 1250 | Helium | 5000 | 145.0 | 14.5 | 20 | 13,400 | | |
| 1750°F | 1250 | Helium | 5000 | 150.0 | 15.0 | 20 | 2,400 | | |
| Solution | 1250 | Helium | 5000 | 137.5 | 13.75 | 20 | 8,400 | | |
| 001401011 | 1250 | Hvdrogen | 5000 | 115.0 | 11.5 | 20 | 6,100 | | |
| | 1250 | Hvdrogen | 5000 | 125.0 | 12.5 | 20 | 16,800 | | |
| | 1250 | Hvdrogen | 5000 | 130.0 | 13.0 | 20 | 4,900 | | |
| | 1250 | Hydrogen | 5000 | 135.0 | 13.5 | 20 | 800 | | |
| AMS 5662 | 1250 | Helium | 5000 | 140.0 | 14.0 | 20 | 9,600 | | |
| (INCO 718) | 1250 | Helium | 5000 | 142.5 | 14.25 | 20 | 4,530 | | |
| 1900°F | 1250 | Helium | 5000 | 150.0 | 15.0 | 20 | 100 | | |
| Solution | 1250 | Helium | 5000 | 160.0 | 16.0 | 20 | 20 | | |
| | 1250 | Hvdrogen | 5000 | 115.0 | 11.5 | 20 | 37,200 | | |
| | 1250 | Hvdrogen | 5000 | 125.0 | 12.5 | 20 | 6,500 | | |
| | 1250 | Hvdrogen | 5000 | 135.0 | 13.5 | 20 | 5,560 | | |
| | 1250 | Hydrogen | 5000 | 130.0 | 13.0 | 20 | 6,200 | | |
| | *Stress levels for R ratio $\left(\frac{\text{Minimum Stress}}{\text{Maximum Stress}}\right) = 0.1.$ | | | | | | | | |

Table V-2. Elevated Temperature High Cycle Fatigue Properties of Materials in High Pressure Gaseous Environment

Pratt & Whitney Aircraft PWA FR-4566

SECTION VI FRACTURE TOUGHNESS

A. INTRODUCTION

Fracture toughness tests were conducted in 5000 psig gaseous hydrogen at a temperature of approximately 80°F. For comparison, and to determine the degree of susceptibility to hydrogen degradation and/or embrittlement, similar tests were also conducted in 5000-psig helium. The materials tested (Section III) were AMS 5662 (INCO 718), AMS 5666 (INCO 625), AMS 5735 (A-286), AMS 5646 (AISI 347), AMS 4928 (Ti 6-4), and AMS 4926 (Ti A-110).

B. CONCLUSIONS AND DISCUSSION

The following conclusions were made from the results of this fracture toughness testing program and the metallographic investigations:

- 1. There was no severe hydrogen degradation in any of the materials tested. Only a slight sensitivity was evident in AMS 5662 (INCO 718), as indicated by slightly lower fracture toughness values and by the somewhat smoother fracture face when compared to results in helium.
- 2. Although there was no evidence of hydrogen degradation in fracture toughness values in AMS 4928 (Ti 6-4), the metal-lographic examination revealed a slight sensitivity to hydrogen in this material.
- 3. From the metallographic examinations, it was concluded that the most severely hydrogen embrittled alloy was AMS 5666 (INCO 625). This was not consistent with the obtained fracture toughness values, as if anything, they showed a slight increase in hydrogen.
- 4. A comparison of welded to parent material revealed a general decrease in magnitude of the fracture toughness values, but no susceptibility to hydrogen degradation. GTA-welded AMS 5662 (INCO 718) 1900 °F solution was less ductile than the parent material, as was evidenced by the appearance of the fracture face and the attained valid K_{IC} value. This was not the case with AMS 5666 (INCO 625) in that it remained very ductile and a valid K_{IC} was not attainable.
- 5. When comparing longitudinal to transverse fracture toughness values there was generally no difference, although there was a slight increase in magnitude in the transverse direction in both titanium materials tested.

Although the primary aim of this investigation was to determine the degree of susceptibility to high pressure hydrogen degradation, additional interpretation of the fracture toughness data is required for characterization of these alloys in terms of critical flaw size and stress level required for failure. Pelline, W. S.¹, and R. W. Judy, Jr., R. J. Goode, and C. N. Freed² have used Ratio Analysis Diagrams (RAD) to reduce the complex problem of interpretation of fracture toughness data. These diagrams have compared K_{IC} with Dynamic Test (DT) and Charpy V-notch (C_V) tests.

Correlation of engineering fracture toughness tests with K_{IC} provides the necessary information to express the fracture toughness, regardless of type of test, of materials in terms of critical flaw size and nominal stress level required for fracture. The equation:

$$\frac{\text{KIC}}{\sigma} = \frac{1.1 \sqrt{\pi a}}{\sqrt{Q}}$$

where:

| KIC | æ | Plane Strain Fracture Toughness, ksi 🗸 in. |
|---------|---|--|
| σ | = | Nominal Stress (ks1) |
| 1. 1/√Q | ŧ | Flaw Geometry Factor |
| a | = | Critical Crack Depth (in.) |

defines the critical flaw-stress conditions for plane strain conditions.

The ratio K_{IC}/σ ys, termed "engineering ratio," is the basic parameter in the equations used for calculating flaw size. Generalizing various K_{IC}/σ ys ratios as follows:

Ratios between 1 and 1.5 - Nominal stresses in excess of yield are required for fracture propagation.

Ratios between 0.5 and 1.0 - High elastic nominal stresses and detectable flaws required for fracture propagation.

Ratios below 0.5 - Low elastic nominal stresses and flaws that may be too small for reliable detectability are required for fracture propagation.

¹Pellini, W.S., "Advances in Fracture Toughness Characterization Procedures and in Quantitative Interpretations to Fracture-Safe Design for Structural Steels," Naval Research Laboratory, Washington, D.C., April 3, 1968.

²Judy, R.W., Jr. R.W. Goode, and C.N. Freed, "Fracture Toughness Characterization Procedures and Interpretations to Fracture-Safe Design for Structural Aluminum Alloys," Naval Research Laboratory, Washington, D.C., March 31, 1969.

These guidelines serve as a simple index for engineering assessment and/ or comparing materials.

In figure VI-1, INCO 718 (1900 °F solution) GTA-welded, Ti 6-4 and Ti A-110 tested in both 5000-psig gaseous helium and hydrogen are generally below the 0.5 ratio. INCO 718 (1900 °F solution) has a higher ratio than INCO 718 with 1750 °F solution with the hydrogen data lower than helium in both cases. INCO 625 and A-286 fall between ratios of 0.5 and 1.0. AISI 347 and GTA-welded INCO 625 have ratios of 1.0 or better.



Figure VI-1. Engineering Ratio, K_{IC}/σ_{ys} or DF 86788 K_{IE}/σ_{ys} , for Alloys Tested in High Pressure Gaseous Environments

C. TEST PROCEDURE

Longitudinal and transverse specimen blanks were cut from bar stock, heat treated if required, and machined per ASTM specifications for compact tension specimens. (See Print FML 95559C.) The specimens were all 0.750-in. thick. This thickness was chosen to stay within the load limits of the existing high pressure tensile testing rig. All specimens were precracked in tension - tension using a Sonntag fatigue machine, which operates at 1800 cpm. All precracking was conducted in air at approximately 80° F at load levels (K_f), which later were verified not to exceed 60% of K_O.

PWA FR-4566

1. Equipment

Fracture toughness testing was conducted on a 30,000-lb Tinius Olsen testing machine, equipped with a Pratt & Whitney designed pressure vessel. This equipment is shown in figures VI-2 and VI-3. The pressure vessel is shown open in figure VI-4 with a standard compact tension specimen and clip gage in place. The vessel is made of AISI 347 stainless steel and incorporates a high pressure Gray-Loc connector. An internal load cell is used, thus the effects of friction on the load rod are not recorded on the readout equipment. To make the necessary gas analyses, a gas sampling system is incorporated in the test cell.



Figure VI-2. Tensile Machine, Test Environment Controls, and Data Acquisition Equipment Located in the Blockhouse

FC 21272





Figure VI-3. High Pressure Gaseous Environment Fracture Toughness Test Vessel Installed on Tensile Machine in the Test Cell FC 21268

Figure VI-4.

High Pressure Gaseous Environment Fracture Toughness Test Vessel With Outer Chamber Removed and Fracture Toughness Specimen With COD Gage Attached FE 107942

Pratt & Whitney Aircraft

PWA FR-4566

2. Test Method

The following procedure is used during testing:

- 1. Specimen is precracked per tentative ASTM Designation E 399-70T for precracking compact tension specimens.
- 2. Chamber is opened, the prepared specimen installed, and the COD gage attached, as shown in figure VI-4.
- 3. Instrumentation continuity checks are conducted.
- 4. Chamber is closed, sealed, and evacuated.
- 5. Chamber is backfilled with nitrogen and purged.
- 6. Chamber is backfilled and "pop" purged twice in succession with the test gas.
- 7. Chamber is pressurized with test gas to 5000 psig.
- 8. Test is conducted. During the test, a load-displacement curve is plotted by an X-Y recorder from the output of a strain-gage-type internal load cell, and a crack opening displacement (COD) gage placed in the notch opening of the specimen.
- 9. After specimen failure, the chamber is vented and opened, and the failed specimen is removed.
- Fracture toughness values are calculated from the loaddisplacement curve per tentative ASTM Designation E 399-70T for compact tension fracture toughness specimens.

D. TEST RESULTS

The fracture toughness value is calculated from the load (P_Q) established by a 5% deviation from the linear portion of the recorded load-displacement curve, the specimen thickness (B), width (W), and crack length (a) after fracture by the equation:

$$K_{Q} = \frac{P_{Q}}{BW^{1/2}} \left[29.6 (a/W)^{1/2} -185.5 (a/W)^{3/2} +655.7 (a/W)^{5/2} -1017.0 (a/W)^{7/2} +638.9 (a/W)^{9/2} \right]$$

KQ is a valid K_{IC} (plain strain fracture toughness) value if both the specimen thickness (B) and the crack length (a) exceed 2.5 $(K_{IC}/\sigma_{ys})^2$, where σ_{ys} is the 0.2% offset yield strength of the material for the temperature of the test. In addition, there are requirements upon the precracking conditions and the shape of the fatigue precrack.

| | | Test Conditions | | Spec | imen Paramete | rs | Test Results | | | | | |
|--|--------------------------------|--|--|---|----------------------------------|----------------------------------|---------------------------------------|--|--|---|--------------------------------------|------------------------------|
| Material | Notch Orientation | Gaseous Environment | Load Rate K _I /min (ksi Vin./min) | Thickness "B" (in.) | Depth "W" (in.) | Crack Length (ln.) | Fracture Appearance (% Oblique) | $2 5 \left(\frac{K_Q}{\sigma_{ys}}\right)^2$ | Fractu Toughi (ksi√ K _{IE} | nre ness In.) K _{IC} | Yield Strength (ksi) | |
| AMS 5662 (INCO 718) 1750°F Sol | Long Trans Long Trans | Helium Helium Hydrogen Hydrogen | 80.0 80.0 80.0 80.0 80.0 | 0.750 0.745 0.751 0.740 | 1.501 1.502 1.500 1.496 | 0.852 0.785 0.855 0.848 | 3 3 3 3 | 0.686 0.881 0.613 0.620 | 95.5B | 84.0 76.2 76.7 | 160.4 160.4 154.1 154.1 | 0.52 0.59 0.49 0.50 |
| AMS 5662 (INCO 718) 1900°F Sol | Long Trans Long Trans | Hellum Hellum Hydrogen Hydrogen | 80.0 80.0 80.0 80.0 | 0.747 0.751 0.750 0.748 | 1.501 1.500 1.500 1.500 | 0.865 0.868 0.852 0.872 | 4 6 5 5 | 1.270 1.181 1.029 0.916 | 111.5 ^B 107.6 ^B 101.0 ^{AB} 95.2 ^B | | 156.4 156.4 157.4 157.4 | 0.71 0.69 0.64 0.61 |
| AMS 5662 (INCO 718) 1900°F Sol Welded | Long Trans Long Trans | Helium Helium Hydrogen Hydrogen | 80.0 80.0 80.0 80.0 | 0.752 0.753 0.748 0.751 | 1.503 1.499 1.498 1.503 | 0.852 0.915 0.868 0.885 | 3 2 2 3 | 0.660 0.503 0.550 0.531 | | 86.8 75.7 76.0 74.6 | 168.9 168.9 161.7 161.7 | 0.51 0.45 0.47 0.46 |
| AMS 5666 (INCO 625) | Long Trans Long Trans | Helium Helium Hydrogen Hydrogen | 80.0 80.0 80.0 80.0 80.0 | 0.751 0.749 0.748 0.747 | 1.509 1.504 1.500 1.500 | 0.855 0.975 0.885 0.862 | 15 14 10 8 | 0.954 1.142 0.888 0.731 | 51.8 ^B 56.6 ^{AB} 59.7 ^B 54.2 ^A | | 83.9 83.9 100.7 100.7 | 0.61 0.68 0.59 0.54 |
| AMS 5666 (INCO 625) Welded | Long Trans Long Trans | Hellum Hellum Hydrogen Hydrogen | 80.0 80.0 80.0 80.0 | 0.750 0.752 0.749 0.751 | 1.502 1.503 1.504 1.504 | 0.912 0.892 0.912 0.958 | 16 15 13 12 | 2,260 2,180 2,730 2,560 | 51.0B 49.8AB 55.0AB 53.4AB | | 53.6 53.6 52.7 52.7 | 0.95 0.92 1.04 1.0 |
| AMS 5735 (A-286) | Long Trans Long Trans | Helium Helium Hydrogen Hydrogen | 80.0 80.0 80.0 80.0 | 0.752 0.749 0.749 0.749 0.749 | 1.505 1.498 1.500 1.488 | 0.865 0.888 0.848 0.878 | 6 5 4 4 | 1.740 2.000 1.485 1.403 | 89.4 ^B 95.6 ^B 85.3 ^B 82.9 ^B | | 106.9 106.9 110.7 110.7 | 0.86 0.90 0.76 0.75 |
| AMS 5646 (AISI 347) | Long Trans Long Trans | Helium Helium Hydrogen Hydrogen | 80.0 80.0 80.0 80.0 | 0.749 0.750 0.750 0.747 | 1.499 1.500 1.497 1.498 | 0,872 0,925 0,902 0,686 | 12 13 9 10 | 0.925 0.582 0.559 0.815 | 40.7 ^B 37.7 ^{AB} | 32.2 31.2 | 30.0 30.0 30.0 30.0 30.0 | 1.36 1.07 1.04 1.27 |
| AMS 4928 (Tl 6-4) | Long Trans Long Trans | Helium Helium Hydrogen Hydrogen | 80.0 80.0 80.0 80.0 | 0.742 0.724 0.748 0.740 | 1.501 1.498 1.499 1.499 | 0,802 0,792 0 898 0,748 | 16 13 17 16 | 0.368 0.515 0.681 0.522 | 72.4 ^A | 56.0 66.4 75.7 | 146.1 146.1 144.9 144.9 | 0.38 0.45 0.52 0.50 |
| AMS 4926 (A-110) | Long Trans Long Trans | Helium Helium Hydrogen Hydrogen | 80.0 80.0 80.0 80.0 | 0.747 0.751 0.745 0.742 | 1.495 1.499 1.497 1.494 | 0.825 0.868 0.842 0.844 | 8 4 2 3 | 0.433 0.665 0.343 0.605 | | 51.2 63.5 47.0 62.6 | 122.9 122.9 127.3 127.3 | 0.42 0.52 0.37 0.49 |

Table VI-1. Fracture Toughness of Materials in High Pressure Gaseous Environment

A - Does not meet tentative ASTM designation E399-70T, paragraphs 7.2 3 and 7.2.4. B - Does not meet tentative ASTM designation E399-70T, paragraph 8.1.5.

All fatigue precracking done per tentative ASTM designation E399-70T, paragraphs 6.5.1 through 6.5.4.

VI-8



SECTION VII CREEP RUPTURE

A. INTRODUCTION

Creep rupture properties were evaluated under 5000-psig hydrogen and 5000-psig helium gaseous environments at either 200 °F or 1250 °F. Creep rate, rupture life, percent elongation and percent reduction of area were determined for two nickel, two iron, and two titanium base alloys.

B. CONCLUSIONS

Creep and rupture properties were degraded in 5000-psig hydrogen for all nickel, iron, and titanium base alloys tested except AISI 347 stainless steel. Degradation in rupture life is expressed as percent reduction of stress in hydrogen compared to helium to obtain identical rupture life (hr).

Degradation (%) for Life (hr) of:

| | H _e Stress - H ₂ S H _e Stres | $\frac{3 \text{tress}}{\text{s}}$ X 100 |
|---|--|---|
| Nickel Base | <u>10 hr</u> | <u>100 hr</u> |
| AMS 5662 (INCO 718) 1750 °F Solution + A AMS 5662 (INCO 718) 1900 °F Solution + A AMS 5666 (INCO 625) | ge 30% ge 26% 17% | 32% 28% 28% |
| Iron Base | | |
| AMS 5735 (A–286) AMS 5646 (AISI 347) | $ \begin{array}{c} \mathbf{16\%}\\ 0 \end{array} $ | 21% |
| Titanium | | |
| AMS 4928 (Ti 6-4) AMS 5926 (A-110) | * | * |

Stress rupture curves are shown in figures VII-1 through VII-7 for all alloys.

^{*}Results inconclusive for limited tests conducted.







(A-286) at 1250°F





Pratt & Whitney Aircraft

PWA FR-4566



Figure VII-7. Stress Rupture of AMS 4926 DF 86821 (A-110) at 200°F

Degradation was also quite evident in time required to obtain a given percent of creep. Limited available data (figures VII-8 and VII-9) for a constant stress level are given below.

| | | Time (h) | <u>c) to</u> | Creep | (%) of: | | |
|--|-----------------|----------|--------------|-------|------------------------------|--------|----|
| | Stress (ksi) | 0. | 1. | 0% | 2.0% | | |
| | | He | . <u>H2</u> | He | $\underline{\mathrm{H}_{2}}$ | He | H2 |
| AMS 5662 (INCO 718) 1750°F Solution + Age | 81 | >100 | 1 | >100 | 1.6 | 5 >100 | 2 |
| AMS 5735 (A-286) | 52 | 66 | 9 | 90 | 15 | 120 | 22 |

Generally, creep rates were greater in hydrogen for all alloys with the possible exception of AISI 347 stainless steel. This is evident in cases where it was possible to test in hydrogen and helium at same stress levels. Creep-rate curves are shown in figures VII-10 through VII-15.

The titanium base alloys were loaded to stress levels beyond the initial yield to obtain a desired stress rupture life between 10 and 100 hours. This did not allow a substantial margin between operating stress and ultimate stress. Hydrogen influence was visibly evident as a flaking off of surface material (figure VII-16). Metallographic analysis identified this as hydriding. All these factors combined to make results inconclusive for the limited tests conducted. Data are listed in table VII-1.



Figure VII-8. Creep-Stress-Time of AMS 5662 at 1250°F (INCO 718, 1750°F Solution Plus Age)





Figure VII-9. Creep-Stress-Time AMS 5735 (A-286) at 1250°F





Figure VII-11. Creep-Stress Rupture of AMS 5666 DF 86825 (INCO 625) at 1250°F



Figure VII-12. Creep-Stress Rupture of AMS 5735 DF 86826 (A-286) at 1250°F

Figure VII-13. Creep-Stress Rupture of AMS 5646 (AISI 347) at 1250°F



Figure VII-14. Creep-Stress Rupture of AMS 4928 DF 86828 (Ti 6-4) at 200°F



Figure VII-15. Creep-Stress Rupture of AMS 4926 (Ti A-110) at 200 °F

Pratt & Whitney Aircraft PWA FR-4566



Figure VII-16. Creep-Rupture Specimen of AMS 4926 (A-110) Showing Hydriding After Exposure to 5000-psig Hydrogen, 115,000-psi Stress and 200°F for 45 hr Until Rupture

FAC 21700

| | | Test | Conditions | | | | | | | |
|------------------------|------|-------------|------------|----------|--------|-----------|--------------|-----------------|----------|------|
| | | | | | Time | to Creep | (hr) | | | |
| | Test | | Pressure | Stress | | | | Time to Bunture | EL | RA |
| Material | (°F) | Environment | (psig) | (ksi) | 0.5% | 1.0% | 2.0% | (hr) | (%) | (%) |
| AND 5000 | 1250 | Helium | 5000 | 92.3 | < 0.2 | % Total (| Treep | 100.0 (1) | | |
| AMS 5002 (INCO 718) | 1250 | Helium | 5000 | 110.0 | 2.5 | 4.0 | 5.3 | 7.2 | 9.5 | 38.2 |
| 1750 °F | 1250 | Hydrogen | 5000 | 65.4 | 53.0 | 79.0 | 103.0 | 118.6 | 5.3 | 36.4 |
| Solution | 1250 | Hydrogen | 5000 | 85.2 | 0.1 | 0.15 | 0.25 | 0.4 | 7.8 | 48.8 |
| bolution | 1250 | Hydrogen | 5000 | 81.0 | 1.0 | 1.6 | 2.2 | 3.1 | 10.2 | 52.3 |
| AMS 5662 | 1250 | Helium | 5000 | 90.5 | 10.5 | 17.5 | 24.5 | 32.2 | 6.4 | 38.8 |
| (INCO 718) | 1250 | Helium | 5000 | 113.5 | < 0.3 | 1% Total | Creep | 0.3 | (2) | |
| 1900 °F | 1250 | Hydrogen | 5000 | 55.4 | < 0.1 | % Total | Creep | 100.0 (1) | | |
| Solution | 1250 | Hydrogen | 5000 | 70.4 | < 0.5 | % Total | Creep | 6.2 | 1.2 | 4.7 |
| | 1250 | Hydrogen | 5000 | 85.5 | Failed | on Load | ling | | (2) | |
| AMS 5666 | 1250 | Helium | 5000 | 53.5 | 0.6 | 1.0 | 1.6 | 4.0 (3) | 7.0 | 51.5 |
| (INCO 625) | 1250 | Helium | 5000 | 63.0 | 1.2 | 2.0 | 3.5 | 21.2 | 14.7 | 52.5 |
| (11100 020) | 1250 | Helium | 5000 | 63.0 | 0.45 | 0.7 | 1.2 | 25.7 | 39.2 | 52.4 |
| | 1250 | Hydrogen | 5000 | 45.4 | Failed | on Load | ling | | 18.9 | 76.7 |
| | 1250 | Hydrogen | 5000 | 45.6 | Failed | on Load | ling | | 17.6 | 78.4 |
| | 1250 | Hydrogen | 5000 | 38.0 | < 0.2 | 5% Total | Creep | 86.5 (1) | | |
| | 1250 | Hydrogen | 5000 | 41.5 (5) | 0.6 | 1.3 | 3 | 49.2 | 19.5 | 47.5 |
| AMS 5735 | 1250 | Helium | 5000 | 53.4 | 66.0 | 90.0 | 120.0 | 159.8 | 8.6 | 36.6 |
| (A-286) | 1250 | Helium | 5000 | 64.4 | 10.4 | 16.6 | 22.8 | 31.7 | 9,3 | 44.2 |
| | 1250 | Helium | 5000 | 64.4 | 3.5 | 6.5 | 9.8 | 22.8 | 27.5 | 27.8 |
| | 1250 | Hydrogen | 5000 | 57.5 | <0.1 | 0.1 | 0.13 | 0.25 | 10.8 | 55.5 |
| | 1250 | Hydrogen | 5000 | 52.5 | 9 | 15 | 22 | 35.6 | 7.4 | 26 |
| | 1250 | Hydrogen | 5000 | 64.4 | 1.75 | 2.8 | 4.2 | 8.6 | 12.1 | 40 |
| AMS 5646 | 1250 | Helium | 5000 | 40.4 | <0.1 | 0.15 | 0.2 | 0.3 | 8.7 | 48.3 |
| (AISI 347) | 1250 | Helium | 5000 | 19.4 | 3.0 | 9.0 | 16.5 | 24.5 | 8.5 | 43.7 |
| | 1250 | Hydrogen | 5000 | 11.8 | 60.0 | 115.0 | 187.0 | 187.0 (1) | | |
| | 1250 | Hydrogen | 5000 | 38.9 | Failed | on Load | ling | | 8.5 | 42.4 |
| | 1250 | Hydrogen | 5000 | 19.8 | 8.0 | 14.0 | 21.0 | 23.9 | 2.6 | 14.3 |
| AMS 4928 | 200 | Helium | 5000 | 140.0 | Failed | on Load | ling | | | |
| (Ti 6-4) | 200 | Helium | 5000 | 135.0 | 2.75 | 45.0 | 1. 13% Total | 140.3 (1) | 1 | 17.0 |
| | 200 | Hydrogen | 5000 | 140.0 | <0.1 | 0.3 | 0.67 | 0.67 | 4.2 (4) | 17.9 |
| | 200 | Hydrogen | 5000 | 135.0 | <0.1 | 0.6 | 1.7 | 1.7 | 3.16 (4) | 11.8 |
| AMS 4926 | 200 | Helium | 5000 | 118.0 | Failed | on Load | ling | 100 0 (1) | | |
| (A-110) | 200 | Helium | 5000 | 115.0 | 0.18 | 3.0 | 130.0 | 130.0(1) | E 1 /41 | 10 0 |
| | 200 | Hydrogen | 5000 | 115.0 | <0.1 | 0.35 | 3.6 | 45.3 | 5.1(4) | 20.0 |
| | 200 | Hydrogen | 5000 | 118.0 | <0.1 | 0.25 | 2.75 | 21.7 | 6.5 (4) | 20.9 |

Table VII-1. Creep-Rupture Properties of Materials in High Pressure Gaseous Environment

NOTES: 1. Test discontinued, no rupture.
2. Failure mode precludes accurate measurement.
3. Rig shutdown due to temperature loss, immediately prior to failure.
4. Includes initial yield.
5. Estimated from strip chart instantaneous elongation.

PWA FR-4566

C. TEST PROCEDURE

Creep-rupture tests were conducted on a 12,000 lb capacity Arcweld (Satec) Model JE creep-rupture machine modified and installed in a remote test cell. The loading frame and test vessel are explosion proofed and located in an enclosure exposed to atmospheric conditions. Controls and instrumentation readout are located in an adjacent block-house. The pressure vessel (figure VII-17) is made of AISI 321 stainless steel and incorporates a high pressure Gray-Loc connector. This vessel is suspended in the creep-rupture machine which is counterbalanced to maintain the load lever arm at a level position. The interior of the vessel is shown in figure VII-18 with specimen and extensometer in place and figure VII-19 with half of the furnace in place. The creep-rupture specimen was designed with integral collars for positive location and gripping of creep measuring extensometer heads. Ends of specimen were flat pin joints rather than the conventional threaded joints and acted as part of a two pin universal joint.



Figure VII-17. Creep-Rupture Pressure Vessel Complete Assembly

FC 21867

Pratt & Whitney Aircraft PWA FR-4566



Figure VII-18. Creep-Rupture Pressure Vessel With FC 21869 Chamber Wall Removed. Specimen, Extensometer, Universal Pin Joints and Half of Oven in Place



Figure VII-19. Typical Creep-Time Strip Chart Record for Creep-Rupture Test Conducted in High Pressure Gaseous Environment

FD 53127

Load rods and adapters also incorporate pin joints. This in effect puts a universal joint at the immediate ends of the specimen and eliminates alignment errors and resulting bending stresses upon the specimen.

As the specimen ends are exposed to the high pressure gas, a compensating technique is used to eliminate any effective load on the specimen due to pressure. The extensometer is inside the vessel and is of the averaging type. The output of the extensometer is recorded as elongation vs time (figure VII-19). Time run meter was used to validate rupture life indicated on strip chart.

Specimen heater was a resistance wire, split, clam shell configuration. Two zones were provided with independent control to minimize temperature gradient along gage length. Three chromel-alumel thermocouples were looped tight around gage section with ceramic beads. Split heater was positioned around specimen and extensometer heads. Pressure vessel was closed with Gray Loc clamps and connected to load rod adapters in creep-rupture machine.

Gas pressure lines, water cooling lines and electric power leads were connected. Low pressure leak check was performed with gaseous nitrogen. Pressure vessel was evaluated to 10-microns of mercury and pop-purged 10 times with test gas.

Vessel was pressurized to 4000-psig test gas and stabilized to check for high pressure leaks. Temperature was applied to specimen and allowed to stabilize by adjusting primary temperature controller. Temperature increased gas pressure which was vented as necessary to stabilize at 5000-psig. Stable temperature and pressure were obtained in 1-1/2 to 2 hr. Test load was applied by activating automatic lever arm leveling unit. Dead weights were lifted off rest pan to a position where lever arm was maintained level. Load was corrected for frictional losses by using the internal load cell to verify the stress on the specimen gage section. Test system was secured for automatic control and monitor. When specimen failed all control equipment was automatically deactivated. Specimen was removed and final gage length and diameter were measured and recorded to determine percent elongation and percent reduction of area.

SECTION VIII TENSILE PROPERTIES

A. INTRODUCTION

Tensile properties were investigated in 5000-psig hydrogen and helium gaseous environments at temperatures of -260°F, 80°F and 200°F or 1250°F. Both smooth and notched ($K_t = 8.0$) tests were conducted on nickel, iron, and titanium base alloys.

B. CONCLUSIONS

Both solution heat treatments of AMS 5662 (INCO 718) tested were degraded in hydrogen at room temperature, as evidenced by a severe decrease in ductility. The 1750 °F solution had a 75% decrease in ductility as compared to helium, while the 1900 °F solution had a 20% decrease. However, at 1250 °F there was no hydrogen degradation in either solution heat treatment, with the smaller grained 1750 °F solution material having the better tensile properties.

Of the nickel-base alloys tested in this study (INCO 718, INCO 625, and Hastelloy X) only AMS 5754 (Hastelloy X) experienced no hydrogen degradation at ambient ($80^{\circ}F$) or elevated temperature ($1250^{\circ}F$). AMS 5666 (INCO 625) was degraded, as evidenced by the 50% decrease in ductility as compared to helium at room temperature ($80^{\circ}F$). However, at elevated temperatures ($1250^{\circ}F$) there was only a 12% decrease in ductility as compared to helium.

Although AMS 5662 (INCO 718) is degraded in hydrogen at ambient temperatures, at elevated temperatures the 1750°F solution heat treatment demonstrated the best tensile properties of the nickel-base alloys.

Comparing welded AMS 5662 (INCO 718 1900°F solution) to welded AMS 5666 (INCO 625) reveals INCO 718 to be superior in strength, but not in ductility, to INCO 625. GTA-welded INCO 718 was degraded by hydrogen, as evidenced by a decrease in ductility, while welded INCO 625 was not degraded. Comparing welded to parent material, INCO 718 maintained strength but lost ductility, while INCO 625 lost strength but experienced only a small loss in ductility.

The iron-base alloys AMS 5735 (A-286) and AMS 5646 (AISI 347) experienced no degradation in tensile properties in high pressure hydrogen. AISI 347 demonstrated superior tensile properties at cryogenic temperatures, but decreased significantly in strength with increasing temperature.

Both titanium-base alloys AMS 4928 (Ti 6-4) and AMS 4926 (A-110) experienced hydrogen degradation, as was evidenced by a 20% decrease in ductility as compared to helium. At temperatures of 200°F both alloys experienced severe hydrogen degradation, as evidenced by the 45% decrease in percent reduction of area as compared to helium.

Pratt & Whitney Aircraft

PWA FR-4566

C. TEST PROCEDURE

Specimen blanks were cut from 0.750-inch diameter bar stock, heat-treated if required, and machined as per ASTM Designations E8-69 for smooth and notched tensile specimens. (See Section III Prints FML 95224B and FML 95620B.) All smooth round tensile specimens have a 0.252-inch gage diameter and a gage length of 1.00 inch. Notched specimens (K_t of 8.0) have a large diameter of 0.500 inch and a notch diameter of 0.315 inch machined in the center of the specimen gage at a 60-degree angle with a 0.002-inch radius at the apex of the notch.

Tensile testing was done with a Tinius Olsen 30,000-lb capacity tensile machine equipped with a P&WA-designed pressure vessel. All controls and instrumentation readout equipment are located inside the adjacent block house. This equipment is shown in figures VIII-1 and VIII-2a. The pressure vessel is shown open in figure VIII-2b with a notched specimen in place and in figure VIII-2c with a smooth specimen and room temperature extensometer in place. The vessel is made of AISI 347 stainless steel and incorporates a high pressure Gray-Loc connector. A special compensating device built into the base of the vessel compensates for any blowoff load resulting from specimen failure. Both internal and external load cells are used, thus the effect of friction on the load rods passing through the seals is known and accounted for.



Figure VIII-1. Tensile Machine and Test Environment Controls and Data Acquisition Equipment

FC 21272
Pratt & Whitney Aircraft

PWA FR-4566



a) Test Vessel Installed on Tensile Machine in Remote Test Cell

Attached



 FC 21572
b) Test Vessel Open With Notch Tensile Specimen in Place



 FC 21573
FE 107940
c) Test Vessel Open With Smooth Specimen in Place and Room Temperature Extensometer

Figure VIII-2. Various Views of Test Vessel

FD 53125

To conduct cryogenic tests, the pressure vessel was modified by the addition of an insulated jacket placed over the upper portion. (See figure VIII-2d.) This jacket has provisions for flowing LN₂, thus providing cryogenic temperature inside the pressure vessel. To enhance cooling, the hydrogen gas passes through a heat exchanger coil located inside the LN₂ jacket before passing into the pressure vessel.

To conduct elevated temperature tests, a two-zone furnace and separate control systems for each zone were prepared to minimize any heat gradient due

Pratt & Whitney Aircraft

PWA FR-4566

to the high conductivity of the gases. The upper zone uses a Research Incorporated Model 625 temperature-power controller, while the lower zone uses a Barber Colman Model 477P proportional controller. The high temperature extensometer system, developed by P&WA, is shown attached in place with thermocouples on a smooth tensile specimen in figure VIII-3. This extensometer system uses conventional linear differential transformers to measure specimen strain at elevated temperatures.



Figure VIII-3. Test Vessel With Outer Chamber Removed Showing Specimen, Extensometer, and Half of Furnace in Place

To make the necessary gas analyses, a gas sampling system is incorporated in the test cell. All the controls for the gas sampling system are operated by remote control inside the block house.

FE 107943

| | | Test Conditions | | | | | | | Test Results | | | |
|---------------|---------------------|-----------------------------------|-------------|-------------------|--------------------|----------------------|---------------|------------------|-------------------------|--------------------|--|--|
| | | | | | Load in/n | Rate ain | Stre | ength | , Duc | tility | | |
| Material | Test Temp, °F | Stress Concentration Factor | Environment | Pressure, psig | 0 Load to Yield | Yield to Ultimate | Yıeld, ksi | Ultimate, ksi | EL, ⁽¹⁾ % | RA, ⁽²⁾ | | |
| AMS 5735 | 80 | Smooth | Hydrogen | 5000 | 0.050 | 0.100 | 110.2 | 155.8 | 28, 5 | 46.4 | | |
| (A-286) | 80 | Smooth | Hydrogen | 5000 | 0.050 | 0.100 | 111.2 | 155.6 | $27_{i^*}0$ | 45.8 | | |
| (Cont'd) | 80 | 8.0 | Hydrogen | 5000 | | 0.100 | | 225.4 | | 8.1 | | |
| | 80 | 8.0 | Hydrogen | 5000 | | 0.100 | | 224.3 | , | 8.6 | | |
| | 80 | 8.0 | Hydrogen | 5000 | | 0.100 | | 225.4 | | 7.2 | | |
| AMS 5646 | 80 | Smooth | Helium | 5000 | 0.050 | 0.100 | 69.7 | 102.0 | 38.0 | 70.1 | | |
| (ÅISI 347) | 80 | Smooth | Helium | 5000 | 0.050 | 0.100 | 63.9 | 99.4 | 36.5 | 70.5 | | |
| • • | 80 | 8.0 | Helium | 5000 | | 0.100 | | 170.0 | I. | 20.7 | | |
| | 80 | 8.0 | Helium | 5000 | | 0.100 | | 173.3 | | 20.1 | | |
| | 80 | Smooth | Hydrogen | 5000 | 0.050 | 0.100 | 64.6 | 109.7 | 41.5 | 71.1 | | |
| | 80 | Smooth | Hydrogen | 5000 | 0.050 | 0.100 | 67.4 | 108.3 | 39:0 | 70.4 | | |
| | 80 | 8.0 | Hydrogen | 5000 | | 0.100 | | 166.8 | | 18.3 | | |
| | 80 | 8.0 | Hydrogen | 5000 | | 0.100 | | 172.1 | | 18.0 | | |
| | 80 | 8.0 | Hydrogen | 5000 | | 0.100 | | 127.8 | , | 19.5 | | |
| AMS 5754 | 80 | Smooth | Helium | 5000 | 0.050 | 0.100 | 48.6 | 106.7 | 54.0 | 63.0 | | |
| (Hastellov X) | 80 | Smooth | Helium | 5000 | 0.050 | 0.100 | 44.6 | 103.0 | 53.5 | 62.8 | | |
| () | 80 | 8.0 | Helium | 5000 | | 0.100 | | 127.7 | | 17.2 | | |
| | 80 | 8.0 | Helium | 5000 | | 0.100 | | 163.8 | 1 | 18.3 | | |
| | 80 | Smooth | Hydrogen | 5000 | 0.050 | 0,100 | 48.6 | 105.5 | 51.5 | 60.5 | | |
| | 80 | Smooth | Hydrogen | 5000 | 0.050 | 0.100 | 50.1 | 105.3 | 54,5 | 66.4 | | |
| | 80 | 8.0 | Hydrogen | 5000 | | 0.100 | | 124.0 | , | 13.5 | | |
| | 80 | 8.0 | Hydrogen | 5000 | | 0.100 | | 125.5 | | 9.2 | | |
| | 80 | 8.0 | Hydrogen | 5000 | | 0.100 | | 130.8 | | 19.4 | | |

Table VIII-1. Room Temperature Tensile Properties of Materials in High Pressure Gaseous Environment (Continued)

.

| <u>.</u> | Test Conditions | | | | | | | Test Results | | | |
|-------------|---------------------|-----------------------------------|-------------|-------------------|--------------------|----------------------|---------------|------------------|-------------------------|-------------------------|--|
| | | | | | Load 10/1 | Rate nin | Stre | ngth | Duct | Ductility | |
| Material | Test Temp, °F | Stress Concentration Factor | Environment | Pressure, psig | 0 Load to Yield | Yield to Ultimate | Yield, ksi | Ultımate, ksi | EL, ⁽¹⁾ % | RA, ⁽²⁾ % | |
| AMS 4928 | 80 | Smooth | Helium | 5000 | 0.050 | 0.100 | 145.4 | 151,1 | 15.0 | 45.4 | |
| (T1 6A1-4V) | 80 | Smooth | Helium | 5000 | 0.050 | 0.100 | 146.7 | 151.0 | 15.0 | 44.0 | |
| . , | 80 | 8.0 | Helium | 5000 | | 0.100 | | 205.3 | | 4.3 | |
| | 80 | 8.0 | Helium | 5000 | | 0.100 | | 209.5 | | 3.0 | |
| | 80 | Smooth | Hydrogen | 5000 | 0.050 | 0.100 | 144.1 | 147.8 | 13.5 | 34.0 | |
| | 80 | Smooth | Hydrogen | 5000 | 0.050 | 0.100 | 145, 7 | 152.7 | 13.5 | 37.8 | |
| | 80 | 8.0 | Hydrogen | 5000 | | 0.100 | | 189.7 | | 2.1 | |
| | 80 | 8.0 | Hydrogen | 5000 | | 0.100 | | 183.5 | | 1.2 | |
| | 80 | 8.0 | Hydrogen | 5000 | | 0.100 | | 178.8 | | 1.0 | |
| AMS 4926 | 80 | Smooth. | Helium | 5000 | 0.050 | 0.100 | 115.6 | 132.5 | 20.0 | 44.6 | |
| (A-110) | 80 | Smooth | Helium | 5000 | 0.050 | 0.100 | 130, 3 | 133.1 | 18.5 | 43.9 | |
| | 80 | 8.0 | Helium | 5000 | | 0.100 | | 204,9 | | 2.0 | |
| | 80 | 8.0 | Helium | 5000 | | 0.100 | | 197.2 | | 3.1 | |
| | 80 | Smooth | Hydrogen | 5000 | 0.050 | 0.100 | 121.0 | 134.8 | 14.5 | 35.4 | |
| | 80 | Smooth | Hydrogen | 5000 | 0.050 | 0.100 | 133.6 | 138.9 | 16.5 | 31.4 | |
| | 80 | 8.0 | Hydrogen | 5000 | | 0.100 | | 158.2 | | 1.4 | |
| | 80 | 8.0 | Hydrogen | 5000 | | 0.100 | | 173.3 | | 2.3 | |
| | 80 | 8.0 | Hydrogen | 5000 | | 0.100 | | 167.1 | | 2.3 | |

Table VIII-1. Room Temperature Tensile Properties of Materials in High Pressure Gaseous Environment (Continued)

(1) Elongation in 1 inch.

VIII-9

(2) Reduction of Area.

| | Test Conditions | | | | | | Test Results | | | | |
|------------------------|---|--|--|---|----------------------------------|---|-------------------------------|---|------------------------------|--|--|
| | | | | | Load Rate, in/min | | d Rate, Stro /min | | ngth | Ductility | |
| Material | Test Temp, °F | Stress Concentration Factor | Environment | Pressure, psig | 0 Load to Yield | Yield to Ultimate | Yield, ksi | Ultimate, ksi | EL, ⁽¹⁾ % | RA, ⁽²⁾ % | |
| AMS 5646 (AISI 347) | $\begin{array}{r} -260 \\ -260 \\ -260 \\ -260 \\ -260 \\ -260 \\ -260 \\ -260 \\ -260 \\ -260 \end{array}$ | Smooth Smooth Smooth Smooth 8.0 8.0 8.0 8.0 8.0 8.0 8.0 8.0 | Helium Helium Hydrogen Hydrogen Helium Helium Hydrogen Hydrogen Hydrogen | 5000 5000 5000 5000 5000 5000 5000 500 | 0.050 0.050 0.050 0.050 | 0.100 0.100 0.100 0.100 0.100 0.100 0.100 0.100 0.100 | 99.8 109.0 96.5 96.0 | 196.9 202.4 190.0 177.2 230.4 227.4 221.3 225.9 222.6 | 43.5 42.5 42.5 43.5 | 64.0 64.6 62.8 11.6 12.1 11.9 13.1 11.9 | |
| (1) Elongat | uon in 1 incl | b- | | | | | | | | | |

Table VIII-2. Cryogenic Temperature Properties of Materials in High Pressure Gaseous Environment

TT-10

(2) Reduction of area.

1

| | | | Test C | Conditions | Test Re | | | | esults | | |
|------------|---------------------|-----------------------------------|-------------|-------------------|--------------------|----------------------|---------------|-----------------|--------------------|-------------------------|--|
| | | | | | Load in/i | Rate min | Str | ength | Duc | tılity | |
| Material | Test Temp, °F | Stress Concentration Factor | Environment | Pressure, psig | 0 Load to Yield | Yield to Ultimate | Yield, ksi | Ultımate ksi | EL, ⁽¹⁾ | RA, ⁽²⁾ % | |
| AMS 5662 | 1250 | Smooth | Helium | 5000 | 0.050 | 0.100 | 136.7 | 155.9 | 20.0 | 19.7 | |
| (INCO 718) | 1250 | Smooth | Helium | 5000 | 0.050 | 0.100 | 131.3 | 154.3 | 25.0 | 47.5 | |
| 1750°F Sol | 1250 | 8.0 | Helium | 5000 | - | 0.100 | | 202.5 | | 3.3 | |
| | 1250 | 8.0 | Helium | 5000 | | 0.100 | | 210.5 | | 4.6 | |
| | 1250 | Smooth | Hydrogen | 5000 | 0.050 | 0.100 | 137.5 | 150.3 | 22.0 | 46.8 | |
| | 1250 | Smooth | Hydrogen | 5000 | 0.050 | 0.100 | 136.0 | 155.5 | 21.5 | 34.9 | |
| | 1250 | 8.0 | Hydrogen | 5000 | | 0.100 | | 187.5 | | 4.6 | |
| | 1250 | 8.0 | Hydrogen | 5000 | | 0.100 | | 196.5 | | 3.3 | |
| | 1250 | 8.0 | Hydrogen | 5000 | | 0.100 | | 199.1 | | 5.3 | |
| AMS 5662 | 1250 | Smooth | Helium | 5000 | 0.050 | 0.100 | 134.9 | 150.3 | 17.5 | 31.8 | |
| (INCO 718) | 1250 | Smooth | Helium | 5000 | 0.050 | 0.100 | 141.3 | 150.4 | 11.5 | 18.0 | |
| 1900°F Sol | 1250 | 8.0 | Helium | 5000 | | 0.100 | | 190.0 | | 5.4 | |
| | 1250 | 8.0 | Helium | 5000 | | 0.100 | | 196.6 | | 4.0 | |
| | 1250 | Smooth | Hydrogen | 5000 | 0.050 | 0.100 | 133.3 | 150.3 | 17.0 | 27.0 | |
| | 1250 | Smooth | Hydrogen | 5000 | 0.050 | 0.100 | 134.5 | 151.8 | 15.5 | 19.6 | |
| | 1250 | 8.0 | Hydrogen | 5000 | | 0.100 | | 176.2 | | 3.9 | |
| | 1250 | 8.0 | Hydrogen | 5000 | | 0.100 | | 174.7 | | 6.5 | |
| | 1250 | 8.0 | Hydrogen | 5000 | | 0.100 | | 180.8 | | 4.7 | |
| AMS 5666 | 1250 | Smooth | Helium | 5000 | 0.050 | 0.100 | 75.3 | 116.9 | 62.5 | 70.4 | |
| (INCO 625) | 1250 | Smooth | Helium | 5000 | 0.050 | 0.100 | 71.7 | 120.8 | 59.0 | 66.2 | |
| | 1250 | 8.0 | Helium | 5000 | | 0.100 | | 150.0 | | 15.3 | |
| | 1250 | 8.0 | Helium | 5000 | | 0.100 | | 135.8 | | 17.0 | |
| | 1250 | Smooth | Hydrogen | 5000 | 0.050 | 0.100 | 72.7 | 119.1 | 57.5 | 64.2 | |
| | 1250 | Smooth | Hydrogen | 5000 | 0.050 | 0.100 | 77.4 | 127.4 | 52.5 | 55.9 | |
| | 1250 | 8.0 | Hydrogen | 5000 | | 0.100 | | 146.0 | | 19.5 | |
| | 1250 | 8.0 | Hydrogen | 5000 | | 0.100 | | 147.4 | | 13.2 | |
| | 1250 | 8.0 | Hydrogen | 5000 | | 0.100 | | 148.0 | | 14.9 | |

Table VIII-3. Elevated Temperature Tensile Properties of Materials in High Pressure Gaseous Environment

VIII-11

| | | | Test C | onditions | | | Test Results | | | | |
|---------------------------|--|---------------------------------------|--|--|--------------------|--|----------------|---|--------------------|--------------------------------------|--|
| | | | | | Load in/r | Rate nin | Stre | ngth | Duc | tility | |
| Material | Test Temp, °F | Stress Concentration Factor | Environment | Pressure, psig | 0 Load to Yield | Yield to Ultimate | Yield, ksi | Ultımate, ksi | EL, ⁽¹⁾ | RA, ⁽²⁾ % | |
| AMS 5735 (A–286) | 1250 1250 1250 1250 1250 | Smooth Smooth 8.0 8.0 | Helium Helium Helium Helium | 5000 5000 5000 5000 | 0.050 0.050 | 0.100 0.100 0.100 0.100 | 104.6 104.0 | 119.0 122.4 166.5 182.0 | 25.5 29.0 | 52.1 54.5 9.6 12.5 | |
| | 1250 1250 1250 1250 | Smooth Smooth 8.0 8.0 | Hydrogen Hydrogen Hydrogen Hydrogen | 5000 5000 5000 5000 | 0.050 0.050 | 0.100 0.100 0.100 0.100 | 106.7 122.3 | 118.9 109.3 173.5 184.5 | 22.0 25.0 | 44.6 46.6 6.7 9.6 | |
| AMS 5646 (AISI 347) | 1250 1250 1250 1250 | 8.0 Smooth Smooth 8.0 | Hydrogen Helium Helium Helium | 5000 5000 5000 5000 | 0.050 0.050 | 0.100 0.100 0.100 0.100 | 57.8 57.4 | 60.4 59.6 104.0 | 24.5 25.0 | 7.2 66.3 68.1 19.7 | |
| | 1250 1250 1250 1250 1250 | 8.0 Smooth Smooth 8.0 8.0 | Hellum Hydrogen Hydrogen Hydrogen Hydrogen | 5000 5000 5000 5000 5000 | 0.050 0.050 | $\begin{array}{c} 0.100\\ 0.100\\ 0.100\\ 0.100\\ 0.100\\ 0.100\\ 0.100 \end{array}$ | 54.7 60.3 | 102.7 58.8 64.2 101.4 100.0 | 25.5 25.0 | 18.1 68.3 66.7 15.0 16.5 | |
| AMS 5754 (Hastelloy X) | 1250 1250 1250 1250 1250 | Smooth Smooth 8.0 8.0 | Helium Helium Helium Helium | 5000 5000 5000 5000 5000 | 0.050 0.050 | 0.100 0.100 0.100 0.100 0.100 | 35.2 33.1 | 82.1 77.5 90.2 91.2 | 53.0 53.0 | 57.5 57.6 18.1 18.3 | |
| | 1250 1250 1250 1250 1250 1250 | Smooth Smooth 8.0 8.0 8.0 | Hydrogen Hydrogen Hydrogen Hydrogen Hydrogen | 5000 5000 5000 5000 5000 5000 | 0.050 0.050 | 0.100 0.100 0.100 0.100 0.100 0.100 | 33.9 34.1 | 80.8 80.3 88.6 90.8 91.0 | 51.5 51.0 | 58.2 48.9 20.2 17.6 18.8 | |

Table VIII-3.Elevated Temperature Tensile Properties of Materials in
High Pressure Gaseous Environment (Continued)

| | | | Test C | Conditions | | | Test Results | | | |
|----------------------|--|---|--|---|----------------------------------|--|----------------------------------|--|------------------------------|--|
| | | | | | Load Rate in/min | | Strength | | Ductility | |
| Material | Test Temp, °F | Stress Concentration Factor | Environment | Pressure, psig | 0 Load to Yield | Yield to Ultimate | Yield, ksi | Ultımate, ksı | EL, ⁽¹⁾ % | ra, ⁽²⁾ % |
| AMS 4928 (Ti 6-4) | 200 200 200 200 200 200 200 200 200 200 | Smooth Smooth 8.0 8.0 8.0 Smooth Smooth Smooth 8.0 8.0 8.0 8.0 | Helium Helium Helium Helium Hydrogen Hydrogen Hydrogen Hydrogen Hydrogen | 5000 5000 5000 5000 5000 5000 5000 500 | 0.050 0.050 0.050 0.050 | $\begin{array}{c} 0.100\\ 0.100\\ 0.100\\ 0.100\\ 0.100\\ 0.100\\ 0.100\\ 0.100\\ 0.100\\ 0.100\\ 0.100\\ 0.100\\ 0.100\\ 0.100\\ 0.100\\ 0.100\\ 0.100\\ 0.100\\ 0.100\\ 0.00$ | 138.3 139.2 141.0 138.5 | 152.5 147.6 207.5 206.5 146.3 144.7 209.0 184.4 183.3 | 15.0 16.0 10.5 12.0 | $\begin{array}{c} 46.6\\ 47.0\\ 3.6\\ 5.0\\ 4.7\\ 22.6\\ 31.4\\ 3.7\\ 4.2\\ 4.2\\ 4.2 \end{array}$ |
| AMS 4926 (A-110) | 200 200 200 200 200 200 200 200 200 200 | Smooth Smooth 8, 0 8, 0 8, 0 Smooth Smooth 8, 0 8, 0 8, 0 8, 0 | Helium Helium Helium Helium Hydrogen Hydrogen Hydrogen Hydrogen Hydrogen | 5000 5000 5000 5000 5000 5000 5000 500 | 0.050 0.050 0.050 0.050 | 0.100 0.100 0.100 0.100 0.100 0.100 0.100 0.100 0.100 0.100 0.100 | 111.8 113.6 114.4 112.5 | 127.6 132.7 190.5 185.3 187.0 126.0 130.0 160.2 168.0 175.5 | 20.5 17.5 14.0 17.0 | 45.4 46.6 3.5 5.0 3.5 20.8 31.9 3.0 2.7 2.3 |

Table VIII-3. Elevated Temperature Tensile Properties of Materials in High Pressure Gaseous Environment (Continued)

(1) Elongation in 1 inch.

(2) Reduction of Area.



Figure VIII-4. Tensile Properties of AMS 5662 (INCO 718), 1750°F Solution in High Pressure Gaseous Environments

FD 53124



Figure VIII-5. Tensile Properties of AMS 5662 (INCO 718), 1900°F Solution in High Pressure Gaseous Environments

FD 53123



Figure VIII-6. Tensile Properties of AMS 5666 (INCO 625) in High Pressure Gaseous Environments









\$

Figure VIII-8. Tensile Properties of AMS 5735 (A-286) in High Pressure Gaseous Environments

FD 53120





FD 53119



Figure VIII-10. Tensile Properties of AMS 5754 (Hastelloy X) in High Pressure Gaseous Environments FD 53118



Figure VIII-11. Tensile Properties of AMS 4928 (Ti 4-6) in High Pressure Gaseous Environments

FD 53117





Figure VIII-12. Tensile Properties of AMS 4926 (A-110) in High Pressure Gaseous Environments



Welded specimens were machined from blanks prepared as previously dis-.cussed; manual GTA welding was done on oversized blanks to ensure specimen finished dimensions. Both the root pass and the finished weld were X-ray inspected and judged radiographically sound. Prior to finish machining, specimens were given a light etch to define weld location. After finish machining, all specimens were polished to produce desired surface finish.

| Name | Print Number | Figure |
|---|-------------------------------|----------------|
| Constant Strain Low Cycle Fatigue Specimen | FML 95500B | III - 3 |
| Smooth Ax1al Fatigue Specimen (High Cycle Fatigue) | FML 95212B | III-4 |
| Fracture Toughness Specimen | $\mathbf{FML}95559\mathrm{C}$ | ПІ – 5 |
| Flat End Creep Rupture Specimen | FML 95623B | III-6 |
| Ambient-Cryogenic Tensile Specimen (notch) | FML 95620B | III-7 |
| Ambient-Elevated Temperature Tensile Specimen (Smooth) | FML 95224B | III-8 |

Table III-2. Specimens Used to Determine Influence of Elevated Temperature on Metals in Gaseous Hydrogen



Figure III-3. Constant Strain Low Cycle Fatigue Specimen



Figure III-4. Smooth Axial High Cycle Fatigue Specimen

FML 95212B

Pratt & Whitney Aircraft

PWA FR-4566

PWA - 10000 REV - 2 45

Figure III-5. Fracture Toughness Specimen (ASTM)

FML 95559C

Figure III-6. Flat End Creep Rupture Specimen

FML 95623B

PWA 10000 - REV - 8-68

Figure III-7. Ambient-Cryogenic Tensile Specimen (Notch)

FML 95620B

4

Figure III-8. Ambient-Elevated Temperature Tensile Specimen (Smooth)

FML 95224B

SECTION IV LOW CYCLE FATIGUE

Low cycle fatigue tests were conducted under this contract to determine the gaseous hydrogen degradation of various nickel-base, iron-base, and titanium-base alloys. Comparison of results of axial constant strain tests in a high pressure hydrogen environment to results of similar tests in a helium environment establishes the degradation due to the hydrogen environment. The low cycle fatigue tests performed under this contract have been of the straincontrolled type with the material cycling through a constant total (elastic plus plastic) strain range (figure IV-1) until complete specimen fracture.

Figure IV-1. Typical Load-Strain Hysteresis Curve FD 48672 Obtained During a Specimen Low Cycle Fatigue Test

A. CONCLUSIONS AND DISCUSSION

1. Summary

Except for AMS 5646 (AISI type 347, tested at 80°F only) materials tested in general exhibited degradation in LCF life due to high pressure hydrogen of at least one of the conditions tested. This degradation appears to be dependent upon both temperature and strain range. The nickel-base alloys were most susceptible to hydrogen effects, followed by the titanium-base alloys with the iron-base alloys the least susceptible. Table IV-1 summarizes the test findings; materials are listed in decreasing order of degree of hydrogen degradation based upon average degradation for tests in the range of 1.0 to 2.0% cyclic strain for the temperatures tested.

To fully characterize the LCF performance of these materials in hydrogen, testing should be conducted at additional temperatures.

| | | Average D | egradation | 1 |
|---------------------------------------|--------------|-----------|------------|--------|
| Material | -260°₽ | - 80°F | 200°F | 1250°F |
| Nickel Base AMS 5666 (INCO 625) | NT | 85% | NT | NT |
| AMS 5662 (INCO 718, 1900°F Sol.) | 0* | 82% | NT | 29% |
| AMS 5662 (INCO 718, 1750°F Sol.) | NT | 80% | NT | 28% |
| AMS 5754 (Hastelloy X) | NT | 66% | NT | NT |
| Tıtanium Base AMS 4926 (A-110) | NT | 0 | 74% | NT |
| AMS 4928 (Ti 6-4) | NT | 0 | 26% | NT |
| Iron Base AMS 5735 (A-286) | NT | 0 | NT | 9% |
| AMS 5646 (AISI 347) | NT | 0 | NT | NT |
| NT – Not Tested * – See specific | conclusions. | | | |

| Table IV-1. | Degradation of | Alloys | Due to | High | Pressure | Hydrogen |
|-------------|----------------|--------|---------------|------|----------|----------|
|-------------|----------------|--------|---------------|------|----------|----------|

2. INCO 625 (AMS 5666)

INCO 625 material was tested at 80°F only, and exhibited the most severe degradation of all alloys tested at that temperature, ranging from 80 to almost 90% over total strain levels of 1.0 to 2.0%. Some influence of strain level on degree of degradation was observed (figures IV-2 and IV-3), but even extrapolation of the LCF curves into the elastic range indicates degradation would occur at very low strain levels.