



**DEVELOPMENT OF COST-OPTIMIZED INSULATION  
SYSTEM FOR USE IN LARGE SOLID ROCKET MOTORS**

**Volume I: Task I - Survey and Screening**

by: *T-3626*

**Dr. B. A. Simmons, Manager, Space Booster Department  
and**

**D. L. Nachbar, Project Manager, LMISD Program**

**AEROJET-GENERAL CORPORATION**

**Prepared for:**

**NATIONAL AERONAUTICS AND SPACE ADMINISTRATION**

**NASA Lewis Research Center  
Contract NAS3-11224  
J. J. Pelouch, Jr., Project Manager**



**AEROJET-GENERAL CORPORATION**

**SACRAMENTO, CALIFORNIA**

NOTICE

This report was prepared as an account of Government-sponsored work. Neither the United States, nor the National Aeronautics and Space Administration (NASA), nor any person acting on behalf of NASA:

- A.) Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately-owned rights; or
- B.) Assumes any liabilities with respect to the use of, or for damages resulting from the use of, any information, apparatus, method or process disclosed in this report.

As used above, "person acting on behalf of NASA" includes any employee or contractor of NASA, or employee of such contractor, to the extent that such employee or contractor of NASA or employee of such contractor prepares, disseminates, or provides access to any information pursuant to his employment or contract with NASA, or his employment with such contractor.

FINAL REPORT

Development of Cost-Optimized Insulation  
System for Use in Large Solid Rocket Motors  
Volume I: Task I - Survey and Screening

by:

Dr. B. A. Simmons, Manager, Space Booster Department  
and  
D. L. Nachbar, Project Manager, LMISD Program

Aerojet-General Corporation  
Propulsion Division, Solid Rocket Operations  
Sacramento, California

Prepared for:

National Aeronautics and Space Administration

August 1969

Contract NAS3-11224

NASA Lewis Research Center  
Cleveland, Ohio  
J. J. Pelouch, Jr., Project Manager  
Chemical Propulsion Office

FOREWORD

The insulation development work described herein, which was conducted by the Solid Rocket Division of Aerojet-General Corporation, was performed under NASA Contract NAS3-11224. The work was accomplished under the management of the NASA Project Manager, Mr. J. J. Pelouch, Jr., Chemical Propulsion Division, NASA-Lewis Research Center.

Special acknowledgements for work accomplished in Task I are accorded to Messrs. A. A. Stenerson and W. Bradley, Material Technology Department, for material property analyses, and to Messrs. C. J. Rogers, P. L. Smith, and R. F. Russ, Propellant Development Department, for material processing analyses.

TABLE OF CONTENTS

	<u>Page</u>
I. Summary	1
II. Introduction	6
A. Purpose of Report	6
B. Program Background	6
C. Program Objectives	7
D. Scope of Effort	7
E. Program Schedule	8
III. Material Survey	8
IV. Phase I - Material Property Measurements	11
A. Mechanical Properties	12
B. Density	12
C. Heat Capacity, Heat of Combustion, Thermal Conductivity, and Thermal Diffusivity	13
D. Bond Line Tensile and Shear Strength	13
E. Pot Life	13
F. Viscosity	13
G. Thermogravimetric Analysis	14
H. Water Absorption	14
V. Phase II - Material Thermal Tests	15
A. Insulation Test Motor Design	15
B. Insulation Test Motor Processing	17
C. Test Results	18
D. Motor S/N I-3 Malfunction	21
VI. Phase III - Preliminary Evaluations	24

FIGURE LIST

	<u>Figure</u>
Contract Progress Schedule	1
Reference List of Reports Reviewed on Large Rocket Motor Insulation	2
Sample Letter Distributed to Insulation Suppliers	3
Large Rocket Motor Case Insulation Materials Recommended by Suppliers	4
Summary of Insulation Material Property Data Received from Suppliers	5
Use History of Supplier Recommended Insulation Materials	6
Intermediate List of 30 Insulation Materials Applicable to Large Rocket Motors	7
List of 20 Insulation Materials Selected for Evaluation in Task I	8
Task I Insulation Material Procurement	9

FIGURE LIST (cont)

	<u>Figure</u>
Property Measurement Data Summary	10
Typical Stress-Strain Diagrams for Insulation Materials	11
Density of Insulation Materials	12
Thermal Diffusivity-vs-Temperature	13
Thermal Conductivity-vs-Temperature	14
Heat Capacity-vs-Temperature	15
Viscosity Buildup Curves for Trowelable Materials	16
Viscosity Buildup Curves for Castable Materials	17
Viscosity Buildup Curves for Sprayable Materials	18
Thermogravimetric Analysis of Insulation Materials	19
LMISD Test Motor Configuration	20
Stress Analysis of LMISD Test Motor	21
Contour Measurement Method Comparison	22
Setup for Layout of Test Motor Closure Insulation Specimens	23
Aft Closure Insulation Specimen Processing Setup	24
Specimen Location in Nozzle S/N I-1	25
Specimen Location in Nozzle S/N I-2	26
Specimen Location in Nozzle S/N I-3A	27
Pressure-vs-Time Performance, Motor S/N I-1	28
Pressure-vs-Time Performance, Motor S/N I-2	29
Pressure-vs-Time Performance, Motor S/N I-3A	30
Summary of Insulation Specimen Posttest Profiles, Motor S/N I-1	31
Summary of Insulation Specimen Posttest Profiles, Motor S/N I-2	32
Summary of Insulation Specimen Posttest Profiles, Motor S/N I-3A	33
Summary of Insulation Specimen Erosion Data, Motor S/N I-1	34
Summary of Insulation Specimen Erosion Data, Motor S/N I-2	35
Summary of Insulation Specimen Erosion Data, Motor S/N I-3A	36
Thickness Loss Rate-vs-Initial Mach Number, Motor S/N I-1	37
Thickness Loss Rate-vs-Initial Mach Number, Motor S/N I-2	38
Thickness Loss Rate-vs-Initial Mach Number, Motor S/N I-3A	39
Pressure-vs-Time Performance, Motor S/N I-3	40
Relative Listing of Materials with Respect to Erosion, Cost, Physical, Thermal, Chemical, and Adhesive Properties	41

FIGURE LIST (cont)

	<u>Figure</u>
Summary of Material Ratings	42
Recommended Materials for Further Evaluation in Tasks II and III	43
Recommended Tasks II and III Material Selection and Evaluation Plan	44

APPENDICES

Appendix I	Test Procedures for Material Property Measurements
Appendix II	Engineering Drawings for LMISD Test Motor
Appendix III	Individual Insulation Material Specimen Pre- and Posttest Profiles for Motors S/N I-1, I-2, and I-3A

ABSTRACT

A program to develop a cost-optimized insulation system for large solid rocket motors was conducted by Aerojet-General Corporation under Contract NAS3-11224. Four tasks were derived to accomplish the program objective: Task I, Survey and Screening; Task II, Process Demonstration; Task III, Material Performance Determination; and Task IV, Preparation of 260-in.-dia full-length motor insulation system Design and Process Plan. Task I, which has been completed and is the subject of this report, was accomplished in three phases. Initially, a literature survey revealed thirty firms or facilities engaged in research, development, and production of insulation materials which were applicable to large rocket motors. Of the forty-six materials recommended by potential suppliers, twenty materials, including four pressure-cured, six trowelable, five castable, and five sprayable, were selected for evaluation in Task I. In Phase I of Task I, the selected twenty materials were subjected to a series of property measurements; these measurements included composite tensile strength/modulus, density, ambient pot life, viscosity build-up, bond line tensile/shear, water absorption, thermal diffusivity, thermal conductivity, heat capacity, heat of combustion, and thermogravimetric analysis. The objective of this Task I phase was to establish which of the candidate materials exhibit properties most applicable to large solid-rocket motors. Three 20-in.-dia heavyweight motor tests were conducted in Phase II to determine the relative erosion resistance of the candidate materials. The motors operated at 640 psia over a web burning duration of 17.6 sec. A malfunction, caused by improper propellant cartridge installation, occurred in the third motor and necessitated a fourth motor test. Six candidate material specimens, plus V-44 and V-61 control specimens, were evaluated in each motor. Initial Mach numbers and material thickness losses were obtained from pre- and posttest profile measurements. Plots of material thickness loss rates as a function of Mach numbers provided a comparison of the erosion resistance of each material relative to the erosion performance of the V-44 control. A tradeoff rating using data from Phases I and II yielded a recommendation of ten materials, plus the specified V-44 control, for further evaluation in Tasks II and III of the program. Approval of the material recommendations by the NASA-LeRC Project Manager concluded the Task I effort.

NASA report numbers and corresponding volume numbers are as follows:

CR-72581	Volume I
CR-72582	Volume II
CR-72583	Volume III
CR-72584	Volume IV



I. SUMMARY

The objective of the Large Motor Insulation System Development (LMISD) Program is to evaluate low-cost insulation materials which are applicable to large solid-propellant rocket motors. Four tasks were derived to accomplish the planned objective. Task I, which is completed and the subject of this report, involved a survey of available materials applicable to large motors; selection of twenty candidate materials, including Gen-Gard V-44 and V-61 as controls; measurement of candidate material physical, chemical, mechanical, thermal, and adhesive properties; evaluation of material erosion resistance in three solid-propellant motor tests; evaluation of property measurement and motor test data; and selection of twelve materials, including V-44 and V-61 controls, for further evaluation in Tasks II and III. Task II will be a process demonstration, in which candidate materials selected in Task I are installed into a 54-in.-dia motor chamber. Task III will include material performance determinations in five solid-propellant motor tests. Task IV will be the preparation of a 260-in.-dia full length motor cost-optimized insulation system design and process plan, using materials selected on the basis of data obtained from Tasks II and III. This report summarizes in detail the Task I effort.

The Task I materials survey consisted of two parts: a literature survey and supplier consultations. The literature survey concentrated on insulation materials and processes developed and evaluated in 100-, 120-, 156-, and 260-in.-dia motors. From this survey, a list of thirty firms or facilities engaged in research, development, and production of insulation materials was prepared. Letters requesting material recommendations and current data on pressure-cured, trowelable, castable, and sprayable insulators were sent to thirty suppliers. Forty materials were recommended by eighteen of the thirty suppliers contacted; of these forty materials, twenty-two were of the pressure-cured group, nine were trowelable, nine were castable, and six were sprayable. Only one phenolic/crepe-paper material was not applicable to specified material categories. Material data received from the various suppliers were collated and evaluated. Following intensive review, the following twenty materials were recommended for Task I evaluation:

Pressure-Cured

Gen-Gard V-44 (Control)	General Tire & Rubber Co.
Orco 9250	Ohio Rubber Co.
USR 3800	Uniroyal, Inc.
USR 3804	Uniroyal, Inc.

I. Summary (cont)

Trowelable

Gen-Gard V-61 (Control)	General Tire & Rubber Co.
IBT-100	Aerojet-General Corp.
IBT-106	Aerojet-General Corp.
LPL-44	Lockheed Propulsion
TI-H704B	Thiokol Chemical Corp.
Gen-Gard V-4011	General Tire & Rubber Co.

Castable

IBC-101	Aerojet-General Corp.
40SD-80	American Poly-Term Co.
Castable Carbon	Atlantic Research Corp.
RTV-511	General Electric Corp.
Avcoat 8021	AVCO Corp.

Sprayable

IBS-107	Aerojet-General Corp.
IBS-108	Aerojet-General Corp.
IBS-109	Aerojet-General Corp.
Avcoat II	AVCO Corp.
PR-1933	Products Research & Chem. Corp.

The foregoing material recommendations were approved by the NASA-LeRC Project Manager. This concluded the materials survey portion of Task I.

Material procurement was initiated for Phase I property measurements and Phase II solid-propellant motor tests; Phase I and Phase II of Task I were accomplished concurrently. Lockheed Propulsion Company's LPL-44 trowelable, PBAA insulation could not be procured within the allotted expenditure. As a result, 93-104 castable silicone rubber, manufactured by Dow Corning, was substituted for LPL-44; the NASA-LeRC Project Manager concurred with this substitution. One other material change was made later in the Task I effort. During processing of candidate materials into the test motors, an acceptable specimen of castable carbon could not be obtained because of its viscosity and cure characteristics. As a result, a specimen of IBC-111 was used instead. IBC-111,

## I. Summary (cont)

manufactured by Aerojet-General Corporation, was a castable version of trowelable, PBAN-epoxy IBT-100, and was developed originally as an exit cone liner for the M-1 liquid engine program. IBC-111 contains Refrasil (high purity silica) in place of carbon black and asbestos.

In the Phase I effort, the twenty candidate materials selected from the survey were subjected to the following physical, chemical, mechanical, thermal, and adhesive property measurements:

Composite Tensile Strength Modulus	Thermal Diffusivity
Density	Thermal Conductivity
Pot Life/Viscosity Build-Up	Thermogravimetric Analysis
Bondline Tensile/Shear Strength	Heat Capacity
Water Absorption	Heat of Combustion

The objective was to establish which of the candidate materials possess properties most applicable to 260-in.-dia motor operating requirements. The data from the property measurement are summarized in this report.

Phase II included the design and manufacture of a 20-in.-dia solid-propellant insulation test motor; requirements for the test motor were as follows:

Throat Diameter, in.	1.8
Operating Pressure, psia	600 $\pm$ 25
Burning Duration, sec	19
Specimen Exposure Environment	Mach zero to 0.3
Propellant	ANB-3254

The aft closure/nozzle configuration included a dual entrance section. A 45-degree approach was used from the attachment flange to an area ratio of approximately 4:1. From this area ratio to the throat a 10-degree nozzle approach was used to expand the desired zero to 0.3 Mach region.

Government-furnished propellant cartridges were used. The 20-in.-dia by 20-in.-long pressure-vessel was fabricated from an ASTM A235 steel forging. The aft closure was ASTM A36 steel. Six candidate material specimens, plus V-44 and V-61 control specimens, were installed into the aft closure. Pre- and posttest insulation specimen profiles were measured and recorded using a Portage Layout Machine; profile measurements were used to determine initial Mach numbers at the specimen surfaces and the material thickness loss.

I. Summary (cont)

Three Task I insulation test motors, identified as S/N's I-1, I-2, and I-3, were test fired on 18 October, 31 October, and 22 November 1968, respectively. The attempt to test fire motor S/N I-3 resulted in a 1.9 sec hangfire, after which time the motor chamber pressure increased abruptly to over 1000 psia, causing failure of the aft flange joint bolts and ejection of the closure. Neither the motor pressure-vessel nor the aft closure were damaged significantly. This malfunction was attributed to improper installation of the propellant cartridge. The S/N I-3 components were repaired, rehabilitated, and reassembled; the motor, reidentified as S/N I-3A, was test fired successfully on 20 December 1968.

The following is a summary of the insulation material specimens tested in each motor:

<u>Motor S/N I-1</u>	<u>Motor S/N I-2</u>	<u>Motor S/N I-3A</u>
V-44	V-44	V-44
V-61	V-61	IBT-100 <sup>(3)</sup>
IBT-100	40 SD-80	Orco 9250
IBT-106	RTV-511	USR 3800
IBC-101	IBC-111 <sup>(1)</sup>	USR 3804
IBS-107	Avcoat II	TI-H704B/V-61
IBS-108	PR 1933	4011
IBS-109	TBS-758 <sup>(2)</sup>	Avcoat 8021

Notes: (1) Replacement material for castable carbon.  
 (2) Used in place of 93-104.  
 (3) Used in place of 93-104 specimen.

The following is a summary of motor performance:

	<u>S/N I-1</u>	<u>S/N I-2</u>	<u>S/N I-3</u>	<u>S/N I-3A</u>
Web Average Pressure, psia	640	641	1.9 sec	634
Maximum Pressure, psia	680	668	Hangfire	662
Web Duration, sec	17.6	17.7	Closure Ejected	17.6

I. Summary (cont)

Following each test, the motor was visually inspected, the char layer was removed, and posttest profiles were obtained. Using pre- and posttest profiles, each material thickness loss was measured at specified locations normal to the specimen surfaces; gas flow Mach numbers at the specimen surfaces were calculated. Thickness loss rates were calculated, and a visual comparison of each candidate material performance relative to V-44 was obtained by plotting the thickness loss rate as a function of Mach number, then drawing the most representative line through the data points for each material. Material performance relative to V-44 are summarized as follows:

- |              |                   |   |
|--------------|-------------------|---|
| 1. USR-3800  | 8. V-44 (control) | 15. IBS-108   |
| 2. Orco 9250 | 9. IBS-109        | 16. Avcoat II   |
| 3. V-61      | 10. V-4011        | 17. RTV-511   |
| 4. IBT-100   | 11. USR-3804      | 18. PR-1933   |
| 5. IBS-107   | 12. 40SD-80       | 19. TBS-758   |
| 6. IBC-111   | 13. IBC-101       | Avcoat 8021 - No meaningful data - 93-104 and Castable Carbon not tested. |
| 7. IBT-106   | 14. TI-H704B      |   |

The objective of Phase III preliminary evaluation was to review the data obtained from Phases I and II, and, on the basis of this data, select eleven materials, including V-44 control for further evaluation in Tasks II and III. Independent trade-off evaluations were made based on the following characteristics: performance; cost; compatibility with propellant/liner/steel; thermal, physical, chemical, mechanical, and adhesive properties; and ease of repair/removal. A significance factor was applied to each characteristic, with major significance placed on performance and cost. The silicone rubber materials, 93-104, RTV-511, and PR-1933, were eliminated from further consideration because of their poor erosion resistance and bonding characteristics with SD 850-2 liner. An unacceptable, short pot life was the reason for eliminating V-61 and V-4011; V-4011 also experienced poor bonding to SD-850-2 liner. The following materials were recommended for Task II and III evaluation:

<u>Pressure-Cured</u>	<u>Task II</u>	<u>Task III</u>
Gen-Gard V-44	No demonstration	Control specimen
USR-3800	No demonstration	1 motor test
<u>Trowelable</u>		
IBT-100	Demonstrate as head insulator	1 motor test
IBT-106	Demonstrate as head/sidewall insulation	1 motor test
TI-H704B	Demonstrate as head sidewall insulation	1 motor test

I. Summary (cont)

	<u>Task II</u>	<u>Task III</u>
<u>Castable</u>		
IBC-101	No demonstration	1 motor test
IBC-111	Demonstrate as head insulator	1 motor test
40SD-80	Demonstrate as head insulator	1 motor test
<u>Sprayable</u>		
IBS-107	Demonstrate as sidewall insulator/propellant boot	1 motor test
IBS-109	Demonstrate as sidewall insulator/propellant boot	1 motor test
Avcoat II	Demonstrate as sidewall insulator	1 motor test

The approval of the foregoing material recommendations by the NASA-LeRC Project Manager concluded the Task I effort of the LMISD Program.

II. INTRODUCTION

A. PURPOSE OF REPORT

This document is the first volume in a series of final reports dealing with the major tasks of the Large Motor Insulation System Development (LMISD) Program, Contract NAS3-11224. This series of reports constitutes the LMISD Program final report. This report summarizes in detail the Task I effort for the LMISD Program.

B. PROGRAM BACKGROUND

In the design of the insulation system for Motors 260-SL-1, S1-2, and SL-3, which were test fired successfully at the Aerojet-Dade Division, Florida, the main emphasis was placed on reliability, so that the insulation system essentially was zero-risk to the program. For this reason, Gen-Gard V-44 rubber was selected as the insulating material because of its demonstrated reliability and predictable performance in numerous prior rocket motor programs. V-44 rubber insulation components were vulcanized on mandrels to the required configuration at high temperature and pressure. These cured components were transported to the motor processing facility and secondarily

## II. B. Program Background (cont)

bonded into the motor chamber interior. This technique, although highly reliable, involved the use of substantial tooling and labor, both at the rubber component manufacturing facility and at the motor processing facility.

As the 260-in.-dia motor demonstration program had been completed successfully, it was now possible to consider cost optimization of the large motor insulation system using Gen-Gard V-44 material properties, processing techniques, and performance as comparative baselines. Several materials showed potential for large solid motor applications at a cost savings through reduction in raw materials, processing, tooling, and labor. Previous work accomplished under Contract AF 04(611)-11609, Investigation of Insulation Materials for Multiple Restart Applications, and Contract NAS3-12083, Preparation of Insulation Material Monograph, identified low cost material previously thought to be unsuitable for large motor applications.

Analytical and experimental investigation of candidate materials followed by selective screening and design definition, using common ground rules, was the necessary first step toward the qualification of a cost-optimized insulation system for 260-in.-dia motors. The development program described herein was derived to accomplish this first step.

## C. PROGRAM OBJECTIVES

The objectives of the LMISD Program are to evaluate insulation materials applicable to large solid-propellant motors, select the best materials based on cost, processing capability, and performance, and relate the selected materials to an insulation system design for a 260-in.-dia full-length motor. Four tasks were derived to accomplish the program objectives. Task I, which is the subject of this report, involved a survey of available materials, selection of twenty candidate materials, evaluation of candidate material properties and thermal performance, and selection of twelve materials for further evaluation in Tasks II and III. Task II was the process demonstration, in which the candidate materials selected in Task I were installed into a 54-in.-dia motor chamber. Task III included candidate material performance determinations in five solid-propellant motor test firings. Task IV was the preparation of a design and process plan for a 260-in.-dia full-length motor cost-optimized insulation system using materials and processes selected from Tasks II and III.

## D. SCOPE OF EFFORT

This report volume summarizes in detail the Task I effort for the LMISD Program. The following work was accomplished:

1. A survey of insulation materials applicable to large solid rocket motors.

II.D. Scope of Effort (cont)

2. Consultation with insulation material suppliers regarding availability of candidate materials.
3. Selection of twenty materials for evaluation in Task I.
4. Determination of physical, chemical, thermal, mechanical, and adhesive properties of twenty candidate materials.
5. Design, manufacture, and test of three solid-propellant motors to evaluate thermal performance of twenty candidate insulation materials.
6. Evaluation of the properties and thermal performance of candidate materials.
7. Selection of twelve materials for further evaluation in Tasks II and III for the LMISD Program.

E. PROGRAM SCHEDULE

A program schedule is shown in Figure 1.

III. MATERIAL SURVEY

The materials survey consisted of two parts: a literature survey and supplier consultations. Materials applicable to the following categories were investigated:

Chemical Groups

synthetic rubber and synthetic rubber/filler combinations  
phenolic filler, phenolic/natural rubber/filler, and  
phenolic/synthetic rubber/filler combinations

Physical Groups

pressure cured components secondarily bonded into place  
ambient cured or vacuum cast components secondarily bonded  
into place  
room or elevated temperature cured materials troweled or  
cast into place  
room or elevated temperature cured materials sprayed into  
place



III. Material Survey (cont)

Primary emphasis was placed on the investigation of trowelable, castable, and sprayable materials, preferably those capable of being processed at the motor manufacturing facility. Only those materials meeting the following requirements were considered:

the material must have no previous unreliable usage history in solid-propellant motors

suppliers of any given material must be able to manufacture the material in quantities necessary for large motor applications without extensive facility modifications; assumed motor production rate was 4 units per year

supplier's quality control capability must be adequate for the intended material use.

A literature survey on insulation materials and processes developed and evaluated in large motor programs, 100-, 120-, 156-, and 260-in.-dia motors, was conducted. A list of the reports reviewed in the literature survey are shown in Figure 2. Based on this survey, a list of principal suppliers and firms or facilities engaged in research, development, and production of all types of insulation materials was prepared. Letters requesting current data on pressure-cured, trowelable, castable, and sprayable insulation materials which met the foregoing requirements, were sent to the following suppliers:

General Tire & Rubber Co.	U. S. Naval Ordnance Laboratory
Lockheed Propulsion Co.	Hercules, Inc., Allegany Ballistics Lab.
Thiokol Chemical Corp.	Dow Corning Corp.
United Technology Center	General Electric Co.
American Poly-Therm Co.	Union Carbide Corp.
Kirkhill Rubber Co.	Insulation Technology, Inc.
Ohio Rubber Co.	H. I. Thompson Fiberglass Co.
Atlantic Research Corp.	B. F. Goodrich Co.
Uniroyal, Inc.	Goodyear Tire & Rubber Co.
West American Rubber Co.	Arrowhead Products
U. S. Polymeric, Inc.	Narmco Materials Division
AVCO Corp.	Garlock, Inc.
Ferro Corp.	Product Research Co.
Raybestos Manhattan	Minnesota Mining & Manufacturing Co.
Fiberite West Coast Corp.	Aerojet-General Corporation

## III. Material Survey (cont)

A sample of the letter which was sent to each supplier is shown in Figure 3. The data requested included available quantities; delivery time; raw material cost for various quantities; processing characteristics; adhesive bonding data; use history; and mechanical, physical, chemical, and adhesive properties. Personal contacts were made with responding suppliers whose material or process was directly applicable to large motor insulation systems.

Forty-six materials were recommended by eighteen of thirty suppliers contacted. Of the forty-six materials recommended, twenty-two were of the pressure-cured group, nine were trowelable, nine were castable, and six were sprayable. Figure 4 is a summary of insulation materials recommended by responding suppliers. Only FM-5272, a phenolic/crepe-paper material recommended by U. S. Polymeric, was not applicable to the specified material categories. Material data received from suppliers are summarized in Figures 5 and 6.

The forty-six recommended insulation materials were reduced to the thirty materials shown in Figure 7. In general, one material was selected from each of the pressure-cured group classes shown in Figure 4, plus the Gen-Gard V-44 control. Only one material from the butyl, SBR-phenolic, and isoprene classes were recommended and available for selection. The lower cost material was selected from each of the NBR, NBR-phenolic, and phenolic-carborazole classes. The two supplier recommended materials from the newly developed ethylene-propylene class were selected. Also, since six silicone rubber materials were recommended by suppliers, two materials from this class were included with the thirty materials. All nine of the supplier recommended trowelable materials were included in Figure 7. Of the nine castable materials recommended, five were selected. Two of the polyurethane materials recommended by American Poly-Therm, 40SA-2 and 40SA-40, were eliminated because of their high cost. Also, one of the silicone rubber materials recommended by Dow Corning, 93-073, was excluded because of its similarity to 93-104. Five of the six recommended sprayable materials were selected. IBS-105 was eliminated because of its chemical and physical property similarity to IBS-109.

The reduction of thirty materials down to twenty materials recommended for evaluation in the Task I property measurements and thermal tests was accomplished strictly on a cost basis. Since the LMISD program was directed toward trowelable, castable, and sprayable groups, the recommended twenty materials included a minimum of five materials from these material groups. The list of the twenty materials selected for Task I evaluation is shown in Figure 8.

Only three materials other than V-44 control were selected from the selected from the pressure-cured group. Orco 9250 (NBR class), USR 3804 (EPR class), and USR 3800 (NBR-phenolic class) were the lowest cost materials. Six trowelable materials were recommended for further evaluation. The cost

### III. Material Survey (cont)

differential between the silicone class and the other classes made the selection clear. Gen-Gard 4011 is a relatively new trowelable material being developed by GT&R for low temperature applications. Although there currently is no low temperature application involved in large motor insulation systems, 4011 potentially offered processing and ablative potential and was worth evaluation in this program. The higher cost DC 93-104 was eliminated from the castable group. Only five sprayable materials were available from the thirty materials; thus, those five materials were recommended for further evaluation.

The recommendation of the twenty materials shown in Figure 8 was approved by the NASA-LeRC Project Manager, thus completing the material survey portion of the Task I effort.

### IV. PHASE I - MATERIAL PROPERTY MEASUREMENTS

In this phase of the Task I effort, the twenty materials selected from the materials survey (Figure 8) were subject to the following physical, chemical, mechanical, thermal, and adhesive property measurements:

- Composite tensile strength and modulus
- Density
- Pot life and viscosity
- Bond line tensile and shear strength
- Water absorption
- Thermal diffusivity
- Thermal conductivity
- Thermogravimetric analysis
- Heat capacity
- Heat of combustion

The objective of this task was to establish which of the candidate materials possess properties most applicable to 260-in.-dia motors. Property measurement test procedures are described in Appendix I.

Insulation material procurement for the Phase I property measurements and Phase II thermal test were initiated concurrently. Suppliers of the twenty materials shown in Figure 8 were contacted and arrangements were made to procure approximately 25 lb of each material for all of the Task I tests. A material procurement summary is shown in Figure 9. Five materials were received as free samples. V-44 and V-61 materials were available as residual

## IV. Phase I - Material Property Measurements (cont)

from the 260-SL-3 motor program. Raw materials for the IBT, IBC, and IBS formulations were available from Aerojet's overhead stock at the cost shown in Figure 5. Only 6 lb of TI-H704B material was received, necessitating the use of a small specimen in the test motor. A problem was encountered concerning procurement of Lockheed Propulsion Company's LPL-44 trowelable, PBAA insulation; a firm quotation of \$6200 was received for 25 lb of this material, which amounted to \$248/lb. Since the cost was beyond their advertised price and beyond the allotted expenditures for material procurement, a request was made to substitute Dow Corning 93-104 castable silicone rubber material for the LPL-44. The NASA-LeRC Project Manager concurred with this substitution and DC-93-104 material was procured.

Results of the property measurements are summarized in Figure 10. The following paragraphs summarize the pertinent results of each test.

## A. MECHANICAL PROPERTIES

Tensile strength, elongation, modulus, and Shore A hardness values for 19 insulation materials are shown in Figure 10. Typical stress-strain curves are shown in Figure 11. Tensile strength values ranged from a high of 3332 psi for Avcoat 802, to a low of 82 psi for RTV-511. The basic requirement for insulation material is that its tensile strength must be equal to or greater than the propellant tensile strength. Measured tensile strength values of 260-SL motor propellants, ANB-3105 and ANB-3254 were as follows:

<u>Propellant</u>	<u>Average Tensile Strength, psi</u>	<u>Motor</u>
ANB-3105	118/101	260-SL-1/SL-2
ANB-3254	90	260-SL-3

RTV-511 silicone rubber was the only material that exhibited a tensile strength less than the maximum propellant strength of 118 psi, all other material tensile strengths were equal to or greater than 118 psi.

Modulus and Shore A hardness values ranged from a high of 35,958 psi and 90 for Avcoat 8021 to a low of 132 psi and 21 for PR 1933.

## B. DENSITY

Measured density values at 100, 200, and 300°F are included in Figure 10; these data are presented graphically in Figure 12. There is no specific requirement regarding material density for large motor applications. However, density is a factor in the insulation design thickness versus total motor weight tradeoff.

## IV. Phase I - Material Property Measurements (cont)

## C. HEAT CAPACITY, HEAT OF COMBUSTION, THERMAL CONDUCTIVITY, AND THERMAL DIFFUSIVITY

Measured values for these four material properties are included in Figure 10; thermal diffusivity, thermal conductivity and heat capacity values are plotted versus temperature in Figures 13, 14, and 15, respectively. These properties are a measure of the capability of the material to resist thermal degradation. Previous insulation development work, Reference 21 in Figure 2, found that material thermal properties were related to ablation resistance.

## D. BOND LINE TENSILE AND SHEAR STRENGTH

Bond line tensile and shear strength specimen test results are included in Figure 10. Because these were composite specimens (steel, primer, adhesive, insulation, liner, and propellant), the values shown reflect, for the most part, the propellant tensile and shear strengths. Previous values obtained in similar 260-SL-3 motor program tests were 150 psi tensile and 104 psi shear. Poor bonding between insulation and liner were experienced with the silicone rubber materials, RTV-511, 93-104 and PR1933, and with 4011 and Avcoat II. Bonding problems with the silicone rubber materials also were experienced during processing of insulation specimens into the test motor aft closure. Some reduction in strength values were recorded for the IBS-108 and -109 specimens; for these materials, failure occurred in the insulation-to-propellant interface.

## E. POT LIFE

Material pot life and working consistency data, included in Figure 10, were recorded during processing of the test motor aft closure specimens.

## F. VISCOSITY

Viscosity build-up curves for candidate trowelable, castable, and sprayable materials are shown in Figures 16, 17, and 18, respectively. The pot life of 4011 and V-61 were so short (<30 minutes) that meaningful viscosity data could not be obtained. As previously reported, only 6 lb of TI-H704B material were received; for this reason, there was insufficient material available for the extrusion tube rheometer viscosity measurement.

## IV. Phase I - Material Property Measurements (cont)

## G. THERMOGRAVIMETRIC ANALYSIS

Curves showing the thermogravimetric analysis conducted at a heating rate of 20°C/min are shown in Figure 19. These TGA curves showed that the castable carbon and the DC-93-104 materials were far superior to the other materials in thermal stability. Avcoat 8021 and 40SD-80 material decomposed rapidly in a temperature range from 300 to 400°C.

The TGA data were used in conjunction with a computer program to determine chemical kinetic rate constants required for the preparation of the Insulation Thermal Behavior Model in Task III. The kinetic rate constants required included the order of reaction, the frequency factor, and the activation energy.

## H. WATER ABSORPTION

Results of the water absorption test series are included in Figure 10. Materials that previously exhibited unsatisfactory bondline tensile and shear strengths, 93-104, RTV-511, PR 1933, and 4011, were not subjected to the moisture absorption tests. In general, there appeared to be no significant degradation in the bond strengths after exposure to 50 and 90% RH, except for the IBS, IBC, and IBT materials. During the tensile/shear bond line strength tests conducted as part of the water absorption evaluation, the IBT, IBC, and IBS materials experienced propellant-to-insulator breaks after both 180°F drying and extended exposure to 50 and 90% RH. IBS-108 and IBS-109 experienced propellant-to-liner breaks also on the "as-received" specimens. The reasons for these propellant-to-liner breaks were due either to oxidation or post cure of the insulation surface during 180°F drying or to poor adhesive qualities in the propellant used for this test series. Bond line tensile/shear values are repeated in the following table for clarity of discussion.

	Tensile Shear, psi			
	"As-Processed"	After 180°F Drying	After 50% RH Exposure	After 90% RH Exposure
IBS-107	93/107 a	73/77 b	85/88 c	77/62 d
IBS-108	127*/71* a	63*/38* b	61*/42* c	56*/31* d
IBS-109	125*/82* a	86*/59* b	46*/32* c	74*/40* d
IBT-100	167/105 a	59*/53* b	32*/35* c	40*/69* d
IBT-106	161/108 a	104*/66* b	84*/92 c	59*/80 d
IBC-101	131/105 a	64*/63* b	61*/74* c	83*/69* d
IBC-111	96/189 b	103*/109* d	75/89 e	84/103 e

\*Break at propellant-to-liner bond.

a, b, c, d, e, - Sequence of propellant batches used in this test series.

## IV.H. Water Absorption (cont)

At first, the propellant used in specimen preparation was suspected of having potentially poor adhesive properties. This propellant was obtained from batches processed for the Propellant Improvement Program being conducted under NASA-LeRC Contract NAS3-12002. Relating tensile/shear values to the various propellant batches in the foregoing table showed no correlation between a specific propellant batch and propellant-to-liner breaks. Batches a, c, and d gave consistently high tensile/shear values (~170/130 psi), whereas batches b and e produced lower values (~100/150 psi). From this data, it was concluded that the propellant-to-liner breaks in the IBX materials were caused by surface oxidation or post-cure during the 180°F drying cycle. Apparently serious consideration must be given to using the SD 850-2 liner system with the IBX materials, particularly if the "as installed" insulation experiences long term storage or temperatures in excess of +135°F. However, the necessity for drying temperatures above 135°F appears remote, since the weight gain for the IBX PBAN-epoxy and CTPB materials was only 0.30 to 0.42% after prolonged exposure to a 50% RH environment. During Task III processing operations, additional double-plate specimens will be prepared to investigate the effect of an SD 850-2 liner system on the bond line tensile/shear strength values of IBX materials. One preliminary test was made during the moisture absorption evaluation series. Fresh SD 850-2 liner was applied to one of the IBC-111 specimens following 90% RH exposure. The measured tensile strength value was 108 psi; this value was significantly higher than the 84 psi value obtained for IBC-111 specimens without liner (see Note 10, Figure 10, Sheet 4).

Measured moisture weight gain values were as expected. Percent weight gain for the PBAN-epoxy, CTPB, and PBAA materials ranged from 0.30 to 0.42% after prolonged exposure to a 50% RH environment. USR 3804 ethylene-propylene material exhibited the lowest weight gain (0.36%) of the pressure-cured materials. USR 3800 and V-61 materials, which contain significant quantities of boric acid, experience higher weight gains of 1.51 and 1.65%, respectively. There was no apparent bond strength degradation for pressure-cured, 40-SD80, V-61, and TI-H704B materials after 180°F drying and prolonged exposure to 50 and 90% RH environments.

V. PHASE II - MATERIAL THERMAL TESTS

## A. INSULATION TEST MOTOR DESIGN

Relative performance of the twenty insulation materials selected from the survey was measured in subscale solid-propellant motor tests. Requirements for the insulation test motor were as follows:

## V.A. Phase II - Material Thermal Tests (cont)

Throat Diameter, in.	1.8 minimum
Operating Pressure, psia	600 $\pm$ 25
Burning Duration, sec	19 minimum
Specimen Exposure Environment	Mach 0 to 0.3
Propellant	ANB-3254

The insulation test motor configuration is shown in Figure 20. Detailed engineering drawings for the insulation test motor are shown in Appendix II. Three Task I motor tests were planned. Each test motor aft closure contained six candidate insulation specimens, plus a V-44 and V-61 specimen for control. A stress analysis summary of LMISD test motor components is shown in Figure 21.

The most difficult part of the Phase I Thermal Test (also Task III, Phase I, Material Performance Determination) was to obtain accurate insulation erosion data at the higher Mach number regions in a motor with a small nozzle size. Gas velocities from Mach 0.1 to 0.3 occurred in a relatively small region close to the motor throat. A 10-degree nozzle approach was used to expand this Mach number region. The observed thicknesses loss rate (TLR) of V-44 at Mach 0.3 in large motors is approximately 0.065 in./sec. At Mach 0.1, this is reduced to only 0.01 in./sec. This means that within 2.0 in., which is the true distance between the Mach 0.1 and the Mach 0.3 regions on the insulation surface the erosion rate differed by a factor of 6.5. The concern was that the region between Mach 0.1 and sonic flow (Mach 1.0) was so narrow that, for 20 sec of exposure, erosion at the higher Mach number regions would influence and distort erosion upstream at the lower Mach number regions. To ensure that usable erosion data were obtained from the motor tests, V-44 rubber specimens were included in each of the motor tests as a control. In this way, V-44 erosion was compared to the data currently available so that any distortions caused by the proximity of the high and low Mach number regions were identified. The erosion occurring in other candidate insulation materials was compared with V-44 rubber performance, and at least comparative information was available. To achieve this material comparison, it was necessary to establish an accurate means of inspecting pre- and posttest insulation specimen contours. Several methods of obtaining insulation contour measurements were investigated and evaluated for use on the LMISD Program; the methods investigated are summarized in Figure 22. The most accurate method appeared to involve the use of the Sheffield CORDAX 300 automatic coordinate measurement machine. However, limited access to the aft closure nozzle entrance section severely restricted the use and accuracy of this equipment. Re-evaluation of various inspection methods led to the selection of a Portage layout machine for measuring insulation specimen profiles. The inspection setup for layout of the test motor aft closure insulation specimen profiles is shown in Figure 23. Twenty-two measurements were made at each 45-degree radial location. The 0 degree index was the approximate centerline of the V-44 rubber control specimen.



## V.A. Phase II - Material Thermal Tests (cont)

Only one fabrication problem was encountered which affected the insulation test motor design. Fabrication of the chamber (P/N 1145905-9) involved welding ASTM A36 steel plate flanges to each end of a 24-in.-O.D., Schedule 40, ASTM A53 seamless steel pipe. Upon completion of welding prior to final machining, the supplier reported that visual and radiographic inspection revealed unacceptable welds. The supplier was given the option of repairing the existing chamber or fabricating another. The supplier chose to fabricate a new chamber, and requested permission to fabricate the component from a rolled forging rather than chance another weld rejection. The forging approach was approved, and, after consultation with structural analysis personnel, ASTM A235, Class C-1 steel was selected. Hydrotest of the completed pressure-vessel was successful.

## B. INSULATION TEST MOTOR PROCESSING

The test motor pressure-vessel cap and chamber were insulated with 0.2-in.-thick cured sheets of Gen-Gard V-44 rubber; the sheets were cut from residual cylindrical section insulation from the 260-SL-3 motor program ANB-3254 propellant cartridges were insulated with 0.2-in.-thick sheet of V-44, then bonded to the forward cap. The insulated chamber was assembled to the loaded cap. Polyethylene sheet was applied to the inside surface of the chamber, then the annulus between the chamber and insulated propellant cartridges were filled with SD-793 urethane potting material. The polyethylene sheet served as a release to simplify posttest disassembly.

Processing of insulation specimens into the test motor aft closure presented some processing problems due to limited access and a wide variety of material viscosity, pot life, and cure temperature characteristics. The castable, sprayable, and trowelable material specimens were installed into the first two closures; the third closure contained most of the pressure-cured specimens. The method selected for specimen processing is shown in Figure 24. An IBC-101 plug with eight plexiglass dividers was installed in the 10-degree nozzle entrance section. Sprayable and castable materials were injected into alternate sections through a Semco cartridge. After cure, the plug was removed and trowelable and pressure-cured materials were installed. Because there was some concern about the erosion resistance of RTV-511 and PR-1933, these materials were installed into the aft nozzle section over a 0.5-in. ply of V-44. This backup ply served to protect the closure in the event of severe erosion, as was experienced in the second closure. As previously mentioned in Section IV of this report, only 6 lb of Thiokol TI-H704B material were received. As a result, a 1.5-in.-wide by 1.5-in.-thick bar was cast and cured, then installed into the nozzle entrance section and potted into place with IBT-106 trowelable insulation material.

## V.B. Insulation Test Motor Processing (cont)

TBS-758 and IBC-111 material specimens tested in the second motor were not on the original list of twenty materials. During processing of the second closure, attempts to bond Dow Corning 93-104 castable silicone rubber material specimen to an adjacent PR-1933 specimen were unsuccessful. Since no other specimens had been prepared, the Aerojet Project Manager approved substitution of General Electric TBS-758 silicone rubber material, so that the assembly and test schedule of the second motor would not be delayed. It was discovered later that the bonding problem was not due to the DC 93-104 material, but rather to the PR-1933; DC 93-104 was to be evaluated in the third motor test.

IBC-111 castable, PBAN-epoxy material was substituted for castable carbon. After numerous unsuccessful attempts to process an acceptable specimen in the aft closure, castable carbon was eliminated as a candidate insulation material. Its very short pot-life and cure hardness present processing problems totally undesirable for a large motor insulation system. IBC-111 is a castable version of IBT-100, and was developed as an exit cone liner for the M-1 liquid engine program. IBC-111 formulation is the same as that for IBT-100, except that the 20% carbon black and asbestos in IBT-100 is replaced with Refrasil (high purity silica). IBC-111 has exhibited good erosion resistance in the previous test program, and its potential was worth evaluating in the current program.

## C. TEST RESULTS

The three Task I insulation test motors, identified as S/N's I-1, I-2, and I-3, were test fired on 18 October, 31 October, and 22 November, respectively. An attempt to test fire motor S/N I-3 on 22 November resulted in a 1.9 sec hangfire, after which time the motor chamber pressure increased abruptly to over 1000 psia, causing failure of the aft closure-to-chamber bolts. As will be described in detail in Section V.D. of this report, the S/N I-3 motor components were repaired, rehabilitated, and reassembled. The motor, reidentified as S/N I-3A, was test fired successfully on 20 December 1968.

The following is a summary of the insulation material specimens tested in each motor:

## V.C. Test Results (cont)

<u>Motor S/N I-1</u>	<u>Motor S/N I-2</u>	<u>Motor S/N I-3A</u>
V-44	V-44	V-44
V-61	V-61	IBT-100
IBT-100	40SD-80	Orco 9250
IBT-106	RTV-511	USR 3800
IBC-101	IBC-111	USR 3804
IBS-107	Avcoat II	TI-H704B/V-61
IBS-108	PR 1933	4011
IBS-109	TBS-758	Avcoat 8021

The specimen locations for each motor are shown in Figures 25, 26, and 27.

The pressure-vs-time performance curves are shown in Figures 28, 29, and 30. The following is a summary of motor performance:


	<u>S/N I-1</u>	<u>S/N I-2</u>	<u>S/N I-3</u>	<u>S/N I-3A</u>
Web Average Pressure, psia	640	641	1.9 sec	634
Maximum Pressure, psia	680	668	Hangfire	662
Web Duration, sec	17.6	17.7	Closure Ejected	17.6

The 1128714-1, ANB-3254 propellant cartridges were cast from batch B-473 during 260-SL-3 motor propellant production at the Aerojet-Dade Division, Homestead, Florida. Liquid strand burning rate for propellant batch B-473 was 0.692 in./sec at 600 psia; the burning rate and exponent specified by NASA-LeRC for use in the LMISD Program was 0.692 in./sec at 600 psia and 0.35, respectively. The reported ANB-3254 burning rate for Motor 260-SL-3 was 0.729 in./sec at 600 psia. The 0.73 in./sec burning rate apparently applied to batch B-473, as evidenced by the higher than predicted web average pressures and shorter web burning durations.

The fired motors were returned to the processing area, disassembled, and visually inspected. Char thickness on all specimens except IBS-107 was approximately 0.1 in.; residual char thickness on the IBS-107 specimen was approximately 0.13 to 0.20-in., very similar to V-61 charring. Unusual erosion and charring patterns were evident in the PR 1933 and TBS-758 specimens. Also, an unusual erosion pattern was experienced by the Avcoat 8021 specimen in the Motor S/N I-3A. The Avcoat 8021 specimen was prepared by bonding two 0.25-in.-thick cured sheets together with Epon 921. A 2-in.-thick by 1-in.-wide block

V.C. Test Results (cont)

was cut from the material and bonded into the motor aft closure; IBT-106 was troweled around the specimen as shown previously in Figure 27. The Epon 921 bond line between the two 0.25-in.-thick plies was oriented perpendicular to the closure shell and essentially parallel to the closure center line. As shown in the following sketch, severe erosion occurred in the bond line, thus negating any meaningful performance data.



Cross Section of Avcoat 8021 Specimen

Following visual inspection, the char was removed from the specimens and posttest profiles were measured.

Pre- and posttest specimen profiles for each motor are summarized in Figures 31, 32, and 33. Individual specimen profiles for each material in each motor are presented in Appendix III. As previously noted, the objective of the Phase II motor tests was to obtain insulation material performance data for each of the materials relative to V-44 and relative to each other. Specific material thickness loss rates versus area ratio or gas flow Mach number were not possible because of the significant, non-linear variation in the area ratio over the 17 sec burning duration. The profile summaries of Figures 31, 32 and 33 were prepared by using the V-44 specimen pretest profile as the initial surface; then each material erosion profile was plotted relative to the V-44 surface.

## V.C. Test Results (cont)

Using the pre- and posttest profiles recorded in Appendix III, each material thickness loss was measured at the 22 specified locations normal to the specimen surface. The initial area ratio ( $A/A^*$ ) and initial Mach number at each of the 22 locations in each closure were calculated from the recorded profiles. Thickness loss rates were calculated by dividing the measured thickness loss at each location by the web burning duration for each motor. Initial area ratios, initial Mach numbers at the specimen surface, thickness losses, and calculated thickness loss rates are summarized in Figures 34, 35, and 36.

Again, in an effort to compare visually the relative erosion resistances of the candidate materials, the measured thickness loss rates are plotted as a function of the initial Mach number at the specimen surface for each motor in Figures 37, 38, and 39. These graphs are not intended as a material design guide, but only to show the relative performance of each specimen, and were prepared by plotting the TLR-vs-Mach number data summarized in Figures 34, 35, and 36, then drawing the most representative line through the data points for each material. Material performance relative to V-44 are summarized as follows:

- |                   |  |
|-------------------|--|
| 1. USR 3800       | 11. USR-3804   |
| 2. Orco 9250      | 12. 40SD-80  |
| 3. V-61           | 13. IBC-101  |
| 4. IBT-100        | 14. TI-H704B   |
| 5. IBS-107        | 15. IBS-108  |
| 6. IBC-111        | 16. Avcoat II  |
| 7. IBT-106        | 17. RTV-511  |
| 8. V-44 (Control) | 18. PR 1933  |
| 9. IBS-109        | 19. TBS-758  |
| 10. 4011          | Avcoat 8021 - No meaningful data. 93-104 and Castable Carbon - Not tested. |

## D. MOTOR S/N I-3 MALFUNCTION

1. Performance Analysis

An attempt to test fire Motor S/N I-3 on 22 November 1968 resulted in a 1.9 sec hangfire, after which time the motor chamber pressure increased abruptly to over 1000 psia. The nuts on the 48 aft closure-to-chamber joint bolts failed, and the closure and burning propellant cartridge were ejected. The insulated chamber and forward cap were undamaged; bolts in the

V.D. Motor S/N I-3 Malfunction (cont)

cap-to-chamber joint had yielded and were loose after the test. The insulated aft closure impacted on a revetment approximately 35 feet west of the W-1 test stand. Damage to the closure included a 3.0-in.-long depression on the outer circumference of the 25-in.-dia flange, substantial unbonding of DC93-104 specimen, and some superficial gouges in the forward face of several insulation specimens.

A pressure-vs-time performance curve for Motor S/N I-3 is shown in Figure 40. The igniter functioned normally for approximately 0.2 sec, attaining a maximum pressure of 158 psia at 0.08 sec. The calculated maximum pressure of a 300 gram boron-potassium nitrate pellet igniter fired in this test motor free-volume is 152 psia. The LMISD igniter output is much greater than the design requirements, shown as follows:

<u>Characteristics</u>	<u>LMISD Igniter</u>	<u>Design Requirements</u>
Induced Pressure, psia	158	20, minimum
Heat-flux, cal/cm <sup>2</sup> -sec	1480	70, minimum
Total available energy, cal/cm <sup>2</sup>	312	40, minimum

It is evident that the igniter used in Motor S/N I-3 functioned as designed and delivered sufficient energy for propellant ignition. This conclusion can be substantiated further by the fast, reproducible, ignition performance observed in Motors S/N I-1 and I-2, and subsequently in Motor S/N I-3A.

Having concluded that igniter performance was not the cause of the hangfire, the next logical suspect area was the exposed propellant grain surface. Two possibilities exist; either the propellant surface was contaminated or the propellant cartridge was installed so that the restricted face rather than the propellant face was exposed.

As previously stated, the test motor cap and chamber were undamaged; the only rehabilitation required was replacement of the 48 bolts and nuts. Major sections of the cartridge plastic sleeve and insulation were found in the vicinity of the test bay. The most significant item found was the 0.25-in.-thick, SD850-2 propellant face restrictor. The restrictor (17-in.-dia) was in one piece, and was charred on both sides. The fact that this propellant restriction was found outside of the motor and essentially intact indicated that the propellant cartridge either was improperly bonded or was improperly installed.

Close inspection of the aft closure after cleaning revealed a 17-in.-dia indentation in the insulation. The full diameter indentation was 0.06 to 0.12-in.-deep, depending upon the material specimen hardness.

V.D. Motor S/N I-3 Malfunction (cont)

Apparently the 17.5-in.-O.D. propellant cartridge was unbonded. As pressure built up at the forward end, most likely due to burning at the forward face, the cartridge was forced at high pressure against the aft closure insulation, thus causing the indentation.

In summary, the following facts are known:

- the igniter functioned as designed.
- the 230,000 psi/sec rate of pressure rise was caused by unplanned exposure of additional propellant burning surface (~130 in.<sup>2</sup>) a temporarily plugged nozzle, or a temporary plugged pressure tap.
- the 17.5-in.-dia indentation in the aft closure insulation, ejection of the propellant cartridge, and recovery of the restrictor indicated an inadequate or non-existent bond existed between the propellant cartridge and the forward cap.

The S/N I-3 malfunction apparently was caused in incorrect installation of the propellant cartridge.

2. Remedial Action

The fired motor was returned to the processing area for dis-assembly and further inspection. Only minor clean-up of the insulated cap and chamber was required. The aft closure was cleaned and dimensionally inspected. Inspection results showed that the forward flange flatness and roundness were within original design tolerance. The following action was taken to repair and rehabilitate the aft closure:

- repair machining included removal of not more than 0.06 in. of material from the 24-in.-dia forward flange face to remove surface irregularities resulting from the impact and to obtain the original 125 finish for an O-ring seal.
- the exterior surface was magnetic particle inspected; no defects were found.
- damaged or unbonded insulation specimens were repaired; this included replacing the unbonded 93-104 specimen with IBT-100, removing damaged insulation at the forward face of the closure and replacing with IBT-100, and replacing damaged material and superficial surface depressions with new material.
- the pretest profiles of the repaired insulation specimens were measured.

## V.D. Motor S/N I-3 Malfunction (cont)

Several changes to the motor processing procedures were made. First, 100% project surveillance of all processing operations were initiated. Second, the cartridge propellant surface was scaped prior to final assembly to remove any foreign material, glaze, or fuel rich material. Last, only 3.0-in. of SD-793 urethane potting were installed. The rehabilitated motor was identified as S/N I-3A.

VI. PHASE III - PRELIMINARY EVALUATIONS

The objective of the preliminary evaluation phase of Task I was to review the data obtained, and, on the basis of this data, select twelve materials, including V-61 and V-44 controls, for further evaluation in Tasks II and III. The selected twelve materials were to include no less than two materials each from the trowelable, castable, and sprayable groups.

A summary listing the material in their relative standing for performance (erosion), cost, density, thermal properties, and moisture absorption is presented in Figure 41. Figure 41 also shows the materials which are acceptable, marginal, or unacceptable with regard to mechanical properties, ambient pot life, and bond line tensile/shear strengths. Independent trade-off evaluations were made by personnel from Department 0720, Material Technology, Department 3810, Propellant Development, and the Project Manager. The individual material ratings, summarized in Figure 42, were based on the following characteristics:

<u>Characteristic</u>	<u>Approximate Significant Weight, %</u>
Performance (test motors)	20
Cost (raw material, processing)	25
Compatibility with propellant, liner and motor case steel	10
Physical properties	10
Mechanical properties	10
Chemical properties	10
Adhesive properties	10
Ease of repair/removal	<u>5</u>
	100



## VI. Phase III - Preliminary Evaluations (cont)

Materials recommended and approved for further evaluation in Tasks II and III are shown in Figure 43.

The silicone rubber materials, 93-104, RTV-511, PR 1933, were eliminated from further consideration because of their poor relative erosion resistance and their poor bonding characteristics, particularly with SD850-2 liner. An unacceptable, short ambient pot life was the reason for eliminating V-61 and V-4011 from further evaluation; V-4011 also exhibited poor bond strength characteristics with SD850-2 liner. It was interesting to note that the foregoing materials (93-104, RTV-511, PR1933, V-61, and V-4011) also were the higher cost materials, as shown in Figure 41, Sheet 1, Column 2. Castable carbon was eliminated earlier in the program because an acceptable specimen could not be installed into the test motor closure. Processing complexity certainly prohibited the use of castable carbon as a large motor insulator.

Elimination of the foregoing materials left thirteen materials, plus V-44, available for selection. Pressure-cured materials, USR 3800, USR 3804, and Orco 9250 all exhibited good erosion resistance, reasonable cost, and good thermal properties. USR 3800 was selected as the best low cost pressure-cured material. Orco 9250 was the alternative material in the event that USR 3800 was unavailable. Only three trowelable materials were available; IBT-100, IBT-106, and TI-H704B. IBT-100 and IBT-106 each rated high in all characteristics evaluated. Although its erosion performance was poorer than that of the V-44 control, TI-H704B exhibited satisfactory properties in other categories to warrant its evaluation in Tasks II and III. Four castable materials were available: IBC-101, IBC-111, 40SD-80 and Avcoat 8021. IBC-111, a replacement material for castable carbon, was not included in the original twenty materials approved for Task I evaluation; as a result, thermal property data were not obtained. However, a good performance relative low cost, and properties similarity to IBC-101 indicated IBC-111 was worth further evaluation. Avcoat 8021 was not selected because the supplier would not furnish the material in the uncured condition as would be required for the Task II demonstration. The sprayable materials selected were IBS-107, IBS-109, and Avcoat II. IBS-108 was not selected because of its close chemical similarity to IBS-109. Avcoat II exhibited only fair erosion performance, but showed good density and thermal properties at relatively low cost.


Figure 44 is a brief Task II and III material demonstration and performance evaluation plan. V-44 will be included as a control in each of the five motor tests, but will not be demonstrated in Task II. USR-3800, which rated high in performance, cost, and thermal properties, will be evaluated in one of the Task III motor tests, but as a pressure-cured material, will not be demonstrated in Task II.

VI. Phase III - Preliminary Evaluations (cont)

IBT-100 and IBT-106 will be included in one of the Task III motor tests and will be demonstrated primarily as a forward/aft head insulator in Task II. TI-H704B will be tested in Task III and demonstrated as a sidewall-head insulator in Task II.

IBC-111, IBC-101, and 40SD-80 will be included in the Task II motor tests, but only IBC-111 and 40SD-80 will be demonstrated in Task II. Bottom-casting of IBC-101 was demonstrated previously in the fabrication of inert slivers for Motor 260-SL-3.

IBS-107 and IBS-109 will be tested in Task III and will be demonstrated for both sidewall and propellant boot applications in Task II. Avcoat II will be tested in Task III and demonstrated in Task II as a sidewall insulator.



Contract Progress Schedule

Figure 1

Report NASA CR-72581

1. Report AFRPL-TR-64-167, Vol. 1, "156-In.-Dia Motor Jet Tab TVC Program," LPC, 29 January 1965.
2. Report NASA-CR-72228, 260-SL-3 Motor Program, Vol. 1: "260-SL-3 Motor Internal Insulation System," AGC, 28 April 1967.
3. Report NASA-CR-54930, 260-IN.-Dia Motor Feasibility Demonstration Program, Vol. IV: "260-SL Motor Internal Insulation System," AGC, 8 April 1966.
4. Report AFRPL-TR-67-104, W. Bradley, "Investigation and Evaluation of Motor Insulation for Multiple Restart Application," Second Phase Report, AGC, April 1967.
5. Report No. 0314-3, W. P. Whelan, Jr., et al, "Improved Insulators for Rocket Motors," Quarterly Progress Report, U.S. Rubber Co., Contract NOW 66-0314-C, June 1966.
6. Contract NAS3-10283, "Design Criteria Monograph for Solid Rocket Motor Insulation," AGC, November 30, 1967.
7. NASA Technical Memorandum X-1277, "Casting and Spraying Techniques for Fabricating Filled Elastomeric Ablation Materials," R. C. Clark and R. T. Magee, Langley Research Center, September 1966.
8. Technical Note No. RPL-TDR-64-58, "260-In. Motor Demonstration and 156-in. Motor Nozzle Test Program," Thiokol Chemical Corp., 31 March 1964.
9. Report AFRPL-TR-65-4, "156-In.-Dia Motor Movable Nozzle Program, Vol. II - Subscale Motor Development," Thiokol Chemical Corp., 20 August 1965.
10. Report AFRPL-TR-66-109, "156-In.-Diameter Motor Liquid Injection TVC Program, Vol. II - Test Results, Motor 156-5," Lockheed Propulsion Co., July 1966.
11. Report No. AFRPL-TR-65-108, "156-In.-Dia Motor Jet Tab TVC Program," Lockheed Propulsion Co., July 1965.
12. Report No. AFRPL-TR-65-212, "156-In.-Dia Motor Jet Tab TVC Program," Lockheed Propulsion Co., December 1965.
13. Report No. AFRPL-TR-64-147, "Final Report, 156-In.-Dia Motor Jet Tab TVC Program," January 1965.
14. Report ER-UTC-65-99, Test Evaluation Report (Ground Test), U.A. 1205-15 United Technology Center, 15 June 1965.

Reference List of Reports Reviewed  
on Large Rocket Motor Insulation

15. Report No. RTD-PBR-63-2, "Research, Design, and Demonstration of Advanced Components for Large Solid-Propellant Motors," United Technology Center, May 1962.
16. "UTC Reliability and Quality Assurance Program Status Report," Quarterly Report No. 13, Contract AF 04(695)-156, United Technology Center, October - December 1965.
17. "260-SL Subscale Nozzle Verification Program," Contract NAS3-6285, Thiokol Chemical Corp., January 1966.
18. Report BSD-TR-66-207, Final Report, "High Performance Large Motor Demonstration Test Firing Program," Thiokol Chemical Corp., August 1966.
19. Report No. AFRPL-TR-66-331, "156-In. Fiberglass Case LITVC Motor Program," Thiokol Chemical Corp., January 1967.
20. Report AFRPL-TR-65-2, "260-In. Motor Demonstration and 156-In. Motor Nozzle Test Program," Thiokol Chemical Corp., 31 December 1964.
21. Report AFRPL-TR-67-287, "Investigation and Evaluation of Motor Insulation for Multiple Restart Application," Aerojet-General Corporation, November 1967.

Reference List of Reports Reviewed  
on Large Rocket Motor Insulation



# AEROJET - GENERAL CORPORATION

SACRAMENTO

CALIFORNIA

## SACRAMENTO PLANT

Gentlemen:

The Aerojet-General Corporation has recently been awarded a contract entitled "Development of Cost-Optimized Insulation System for Use in Large Solid Rocket Motors", Contract NAS 3-11224. The initial phase of this contract is to conduct a literature and supplier survey to investigate potential candidate insulation materials applicable to large solid propellant motor cases. We would like to receive up-to-date information on the availability, cost and properties of your \_\_\_\_\_ material(s), selected as tentative candidate(s) for evaluation in this program and also on other materials you may have that are suitable for this application. In order to evaluate the applicability of the available insulation materials, NASA has submitted the following directives as a guideline:

### 1. Material Categories

The types of materials to be considered include the following categories:

- a. Chemical Groups
  - (1) Synthetic rubber and SR/filler combinations.
  - (2) Phenolic/filler, phenolic/NR/filler, and phenolic/SR/filler combinations
- b. Physical Groups
  - (1) Pressure cured components secondarily bonded into place.
  - (2) Ambient or vacuum cast components secondarily bonded into place.
  - (3) Room or elevated temperature cured materials troweled or cast into place.
  - (4) Room or elevated temperature cured materials sprayed into place.

Sample Letter Distributed to Insulation Suppliers

Figure 3, Sheet 1 of 3

Primary emphasis is to be placed on the investigation of trowelable, castable, and sprayable materials, preferably materials that can be processed at the motor processing facility.

2. Material Requirements

The specific requirements imposed on the insulation materials are as follows:

- a. The material must have no unreliable usage history in solid rocket motors.
- b. The supplier must be able to manufacture the materials in quantities necessary for large solid motor applications without extensive facility modifications. Assumed motor production rates shall be four units per year.
- c. The supplier's quality control capability must be adequate for the intended use of the material.

On the basis of the assumed motor production rate of four units per year, it is estimated that as much as 25,000 lbs of material may be required per quarter year with a total of 100,000 lbs per year providing a single material is selected for insulation of all parts of the motor case. However, materials available in smaller quantities also will be considered as one material may be selected for insulation of the sidewall, another material for insulation of the forward and aft end of the motor case and a third material for the boots. The selection of candidate materials of the various categories, as outlined in the NASA directive, will be based on a number of factors of different significance values. The essential data to be considered are as follows:

Availability: 100,000 lbs per year (25,000 lbs per 3 months)  
 25,000 lbs per year (5,000 lbs per 3 months)  
 10,000 lbs per year (2,000 lbs per 3 months)

Delivery Time: Weeks, Days

Raw Material Cost: \$/lb for quantities 25,000; 5,000; 2,000; 200 lbs.

Processing Characteristics: Curing condition (time, temperature, pressure)  
 Also, viscosity and potlife for the castable, trowelable and sprayable materials.

Mechanical Properties: Tensile strength, elongation, modulus, hardness.

Physical Properties: Density, thermal conductivity, specific heat, water absorption.

Bonding to Motor Case and other insulation materials: Primer-adhesive system recommended, shear and peel strength data.

Sample Letter Distributed to Insulation Suppliers

**Ablative Properties:** Ablation and erosion rates in oxyacetylene torch and plasma arc tests, subscale and/or full scale motor evaluations.

**Use History:** Rocket motors in which the material is or has been used or evaluated. (Reference to reports.)

We would appreciate receiving data on your materials as outlined in the directives, as much of the property data as are currently available, and other information that may be of significance, as soon as possible and no later than June 5, 1968. Test methods should be included along with the property data. The materials are to be identified by trade name or designation, basic binder structure and basic filler ingredient(s). Applicable specifications also should be listed.

AEROJET-GENERAL CORPORATION  
P.O. Box 15847  
Sacramento, California 95813  
*A. A. Stenersen*  
A. A. Stenersen  
Dept. 0726/Bldg. 2015  
Telephone: 355-6061, Area Code 916



<u>Pressure-Cured Group</u>	<u>Chemical Group</u> <u>(Elastomer)</u>	<u>Pigment</u> <u>Filler</u>	<u>Fiber</u> <u>Filler</u>	<u>Supplier</u>
<u>NBR (1) Class</u>				
Gen-Gard V-44 (Control)	NBR	Silica	Asbestos	General Tire & Rubber Co.
Hitco 6520	NBR	Silica	Asbestos	H.I. Thompson Fiberglass Co.
Orco 9250	NBR	Silica	Asbestos	Ohio Rubber Co.
5031-1	NBR	Silica	Asbestos	West American Rubber Co.
<u>EPR Class</u>				
USR 3804	Ethylene-Propylene	Silica	Asbestos	Uniroyal, Inc.
Gen-Gard 4010	Ethylene-Propylene	Asbestos	Asbestos	General Tire & Rubber Co.
<u>Butyl Class</u>				
SMR-81-8	Butyl	Silica	Asbestos	West American Rubber Co.
<u>NBR-Phenolic Class</u>				
USR 3800	NBR-Phenolic	Boric Acid		Uniroyal, Inc.
N-356	NBR-Phenolic	Inorganic Hydrate		B. F. Goodrich Co.
<u>SBR (2) -Phenolic Class</u>				
Gen-Gard V-62	SBR-Phenolic	Silica		General Tire & Rubber Co.
Carborazole 10	Phenolic/Carborazole	Cork		Fiberite Corp.
Carborazole 18	Phenolic/Carborazole	Silica Tape		Fiberite Corp.
Carborazole 26	Phenolic/Carborazole	Silica Fabric		Fiberite Corp.

(1) Acrylonitrile-butadiene rubber  
 (2) Styrene-butadiene rubber

Large Rocket Motor Case Insulation Materials Recommended by Suppliers

Figure 4, Sheet 1 of 5

<u>Pressure-Cured Group</u>	<u>Chemical Group (Elastomer)</u>	<u>Pigment Filler</u>	<u>Fiber Filler</u>	<u>Supplier</u>
<u>Phenolic Class</u>				
FM 5272	Phenolic		Crepe Paper	U.S. Polymeric
<u>Isoprene Class</u>				
LPL 4B	Polyisoprene/ NBR	Carbon Black	Asbestos	Lockheed Propulsion Co.
<u>Silicone Class</u>				
S-2048	Phenyl-Methyl Silicone Rubber			Dow Corning Corp.
X-30-724	Phenyl-Methyl Silicone Rubber			Dow Corning Corp.
SE-557	Silicone Rubber			General Electric Co.
K-1213	Silicone Rubber			Union Carbide
K-1255	Silicone Rubber			Union Carbide
K-1305W	Silicone Rubber			Union Carbide
<u>Epoxy Class</u>				
Guardian	Modified Epoxy		Asbestos	Atlantic Research Corp.
<u>Trowelable Group</u>				
<u>Epoxy-Polysulfide Class</u>				
Gen-Gard V-61 (Control)	Epoxy-Polysulfide NBR		Asbestos	General Tire & Rubber Co.

Large Rocket Motor Case Insulation Materials Recommended by Suppliers

<u>Trowelable Group</u>	<u>Chemical Group (Elastomer)</u>	<u>Pigment Filler</u>	<u>Fiber Filler</u>	<u>Supplier</u>
<u>PBAN (1) Epoxy Class</u>				
IBT-100	PBAN-Epoxy	Sb <sub>2</sub> O <sub>3</sub> -Carbon Black	Asbestos	Aerojet-General Corp.
IBT-106	PBAN-Epoxy	Sb <sub>2</sub> O <sub>3</sub> -Carbon Black	Asbestos	Aerojet-General Corp.
<u>PBAA (2) Class</u>				
LPL-44	PBAA		Asbestos	Lockheed Propulsion Co.
TI-H704B	PBAA	Carbon Black	Asbestos	Thiokol Chemical Co.
Gen-Gard 4011	Hydroxyl-Terminated Polybutadiene		Asbestos	General Tire & Rubber Co.
<u>Silicone Class</u>				
93-083	Silicone Rubber			Dow Corning Corp.
TBS-542	Silicone Rubber			General Electric Co.
PR-1955	Silicone Rubber			Products Research & Chemical Corp.

- (1) Terpolymer of polybutadiene, acrylonitrile and acrylic acid
- (2) Polybutadiene-acrylic acid copolymer

Large Rocket Motor Case Insulation Materials Recommended by Suppliers

<u>Castable Group</u>	<u>Chemical Group (Elastomer)</u>	<u>Pigment Filler</u>	<u>Fiber Filler</u>	<u>Supplier</u>
<u>PBAN-Epoxy Class</u>				
IBC-101	PBAN-Epoxy	Sb <sub>2</sub> O <sub>3</sub> -Carbon Black	Asbestos	Aerojet-General Corp.
IBC-111	PBAN-Epoxy		Refrasil	Aerojet-General Corp.
<u>Urethane Class</u>				
40 SA 2	Polyurethane		Silica	American Poly-Therm Co.
40 SA 40	Polyurethane		Silica	American Poly-Therm Co.
40 SD 80	Polyurethane			American Poly-Therm Co.
<u>Silicone Class</u>				
93-073	Silicone Rubber			Dow Corning Corp.
93-104	Silicone Rubber			Dow Corning Corp.
RTV-511	Silicone Rubber			General Electric Corp.
<u>Carbon Class</u>				
Castable Carbon	Furanepolymer	Carbon		Atlantic Research Corp.
<u>Epoxy-Polyamide Class</u>				
Avcoat 8021	Epoxy-Polyamide			Avco Corp.

Figure 4, Sheet 4 of 5

Large Rocket Motor Case Insulation Materials Recommended by Suppliers

<u>Sprayable Group</u>	<u>Chemical Group (Elastomer)</u>	<u>Pigment Filler</u>	<u>Fiber Filler</u>	<u>Supplier</u>
<u>PBAN-Epoxy Class</u>				
IBS-105	PBAN-Epoxy	Sb <sub>2</sub> O <sub>3</sub> -Carbon Black	Asbestos	Aerojet-General Corp.
IBS-108	PBAN-Epoxy	Sb <sub>2</sub> O <sub>3</sub> -Carbon Black	Asbestos	Aerojet-General Corp.
IBS-109	PBAN-Epoxy	Sb <sub>2</sub> O <sub>3</sub> -Carbon Black	Asbestos	Aerojet-General Corp.
<u>CTPB Class</u>				
IBS-107	Carboxy-terminated Polybutadiene	Sb <sub>2</sub> O <sub>3</sub>	Silica	Aerojet-General Corp.
<u>Epoxy-Polyamide Class</u>				
Avcoat II	Epoxy-Polyamide			AVCO Corp.
<u>Silicone Class</u>				
PR-1933	Silicone Rubber			Product Research & Chemical Corp.

Figure 4, Sheet 5 of 5

Large Rocket Motor Case Insulation Materials Recommended by Suppliers

Material	Thermal Conductivity		Specific Heat		Thermal Expansion		Modulus		Elongation		Tensile Strength		Compression Strength		Shore Hardness		Ablation Rate in Oxidative Test		Ablation Rate in Plasma Arc Test		Raw Material Cost		Typical Curing Cond.		Mooney Scorch, hr. 212 F min.
	GH/cc	BTU-in/hr-ft <sup>2</sup> -F	BTU-in/hr-ft <sup>2</sup> -F	BTU-in/hr-ft <sup>2</sup> -F	BTU-in/hr-ft <sup>2</sup> -F	BTU-in/hr-ft <sup>2</sup> -F	BTU-in/hr-ft <sup>2</sup> -F	BTU-in/hr-ft <sup>2</sup> -F	BTU-in/hr-ft <sup>2</sup> -F	BTU-in/hr-ft <sup>2</sup> -F	BTU-in/hr-ft <sup>2</sup> -F	BTU-in/hr-ft <sup>2</sup> -F	BTU-in/hr-ft <sup>2</sup> -F	BTU-in/hr-ft <sup>2</sup> -F	BTU-in/hr-ft <sup>2</sup> -F	BTU-in/hr-ft <sup>2</sup> -F	BTU-in/hr-ft <sup>2</sup> -F	BTU-in/hr-ft <sup>2</sup> -F	BTU-in/hr-ft <sup>2</sup> -F	BTU-in/hr-ft <sup>2</sup> -F	BTU-in/hr-ft <sup>2</sup> -F	BTU-in/hr-ft <sup>2</sup> -F	BTU-in/hr-ft <sup>2</sup> -F	BTU-in/hr-ft <sup>2</sup> -F	
V-44	1.269	2.266	0.433	0.016	1.331	430	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
HITCO 6520	1.28	---	---	---	2500	550	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
ORCO 9250	1.28	1.47	0.46	---	1125/1700	650/700	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
5031-1	1.27	---	0.36	9.092	800/1250	175/175	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
USR 3804	1.119	---	0.418	---	1200	400	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
4010	1.09	1.188	0.493	---	2003	797	5300	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
SMR 81-8	1.35	1.770	0.478	---	934	350	2200	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
USR 3800	1.15	1.230	0.514	---	1200	325	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
N-356	1.204	1.740	0.511	---	800	200	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
V-62	1.063	1.204	0.454	---	675	740	1789	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
Carborazole 10	0.64	0.6	0.5	---	400	40	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
Carborazole 18	0.64	0.65	0.3	---	400/900	2/5	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
Carborazole 26	1.28	1.3	0.28	---	3000/6000	0.6/25	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
FM 5272	1.34	---	---	---	7110	0.9	9 x 10 <sup>5</sup>	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
IFL-4B	1.30	---	0.31	---	400/700	50	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
S-2018	1.30	1.76	0.29	---	850	300	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
X-30-724	1.57	---	---	---	840	110	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
SE-557	1.68	---	---	---	1100	600	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
K-1213	1.16	---	---	---	1100	850	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
K-1215	1.23	---	---	---	1100	700	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
K-1305W	1.16	---	---	---	1050	400	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
Quart. in	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---

Summary of Insulation Material Property Data Received from Suppliers

Figure 5, Sheet 1 of 3

Material	Specific Gravity, GM/cc	Thermal Conduct. Btu-in/ft <sup>2</sup> -hr-F	Specific Heat @ 250°F, Btu-lb/F	Specific Moisture Absorption, %	Elongation at Max. Tensile Strength, %	Modulus, psi	Shore Hardness	Ablation Rate in			Raw Material Cost, \$/lb	Leak Time, Weeks	Viscosity @ 77°F, Centi-poise	Pot Life @ 77°F, Hr.	Curing Conditions Temp., F	Time, Hr.				
								Oxy-acetylene Torch Test	Plasma Arc Test, mls/sec	Flame Arc Test, 100 Btu 225 Btu 50 Btu										
<u>Trowable</u>																				
V-61	1.308	1.443	0.433	---	900	---	20	1.4	1.91	3.65	3.98	4.45	4.15	3.48	13	0.5	75/120	144/6		
IBF-100	1.39	1.618	0.382	0.5	866	3900	---	---	1.29	2.60	3.65	0.65(2)	0.65(2)	0.65(2)	8-12	---	4-6	135	48	
IBF-106	1.40	---	---	0.5	1640	11,500	---	---	---	---	---	0.60(2)	0.60(2)	0.57(2)	8-12	---	8-10	135	48	
LPL-44	1.30	---	0.34	---	884	---	85	---	---	---	---	4.63	3.48	2.78	8	---	12	77/160	---	
TI-HY04B	1.30	---	0.325	---	175	---	---	---	---	---	---	2.02	1.90	1.87	6-8	---	5-6	135	72/120	
4011	1.10	---	---	---	975	---	82	1.7	---	---	---	6.25	6.25	6.25	6	---	2	75	24/120	
93-083	1.75	4.1	---	---	275	---	65	---	---	---	---	8.00	8.00	6.00	4-6	---	2	77	24	
TBS-542	1.34	---	0.36	---	450	---	---	---	---	---	---	12.00	12.00	7.00	4-6	---	80,000	2	77	144
PR-1955	1.40	---	---	---	300	---	50	---	---	---	---	6.46	6.40	6.36	4-5	---	13,000	2	75/120	24/4
<u>Castable</u>																				
IBC-101	1.320	---	---	---	484	905	---	---	---	---	2.2/3.0	0.67(2)	0.64(2)	0.64(2)	8-12	---	3,000/6,000	6-8	135	4
IBC-111	1.389	---	---	---	521	1215	69	---	---	---	---	1.50(2)	1.50(2)	1.50(2)	8-12	---	15,000	12	135	8-12
AVOCAT 8021	---	---	0.4	---	2940	---	---	---	---	---	---	2.16	2.16	1.89	---	---	---	---	200	---
40-SA-2	1.327	1.360	0.382	---	1100	5000	---	---	1.20	2.44	5.97	8.25	7.75	6.50	4-6	---	0.5-1	180	4-8	
40-SA-40	1.338	1.930	0.451	---	1126	5261	---	---	1.35	3.56	5.44	8.25	7.75	6.50	4-6	---	0.5-1	180	4-8	
40-SA-80	1.15	---	---	---	800	---	---	---	---	---	---	4.00	4.00	2.80	4-6	---	800/1200	1-2	77/240	24/4
93-073	1.75	4.1	---	---	275	---	65	---	---	---	---	8.00	8.00	6.00	4-6	---	1.1 x 10 <sup>6</sup>	2	77	24
93-104	1.44	2.42	---	---	275	---	65	---	---	---	2.3	8.00	8.00	6.00	4-6	---	1.1 x 10 <sup>6</sup>	---	77	24
RTV-511	1.20	---	---	---	350	---	45	---	---	---	---	5.55	5.55	5.55	4-6	---	200,000	4-8	77	24

Summary of Insulation Material Property Data Received from Suppliers

Figure 5, Sheet 2 of 3

Material	Specific Gravity, G/cc	Thermal Conductivity, Btu-in./hr-ft <sup>2</sup> -°F cal/ft <sup>2</sup> -°C	Specific Heat @ 250°F	Moisture Absorption, %	Tensile Strength, PSI	Elongation at Max. Tensile Strength, %	Modulus, PSI	Shore Hardness	Ablation rate in			Raw Material Cost \$/lb	Del. Time, Weeks	Viscosity @ 77°F, cP	Pot. Life @ 77°F	Curing Conditions Temp., Time, hr	
									Oxy-acetylene Torch Test 100 Bra 25 Sec 100 Bra 25 Sec 100 Bra 25 Sec	Plasma Arc Test, 50 Bra 100 Bra 25 Sec 50 Bra 100 Bra 25 Sec	FT-sec						
<b>Sprayable</b>																	
IES-105	1.30	--	--	0.5	54	143	119	--	--	--	0.76(2)	0.69(2)	8-12	3000-6000	6-8	135	148
IES-107	1.240	1.920	0.34	0.5	770	26	6552	--	--	--	1.62(2)	1.60(2)	8-12	1000-3000	1-3	135	12
IES-108	1.208	--	--	0.5	--	--	--	--	--	--	0.73(2)	0.67(2)	8-12	3000-6000	6-8	135	148
IES-109	1.237	--	--	0.5	--	--	--	--	1.0	2.9	0.72(2)	0.66(2)	8-12	3000-6000	6-8	135	148
AVCOM II	1.02	--	0.34	--	2000	23	--	40 Shore D	--	--	1.65	1.55	12-24	15,000	--	77	16
PR-1933	1.445	1.444	0.29	--	550	250	--	35 Rex	--	--	5.17	5.00	3-4	250,000-800,000	0.5-2	75/120	24/4
Castable Carbon	--	--	--	--	--	--	--	--	--	--	0.20(3)	0.20(3)	4-6	--	--	--	--

Summary of Insulation Material Property Data Received from Suppliers



Pressure-Cured Group	Rocket Motor Applications		Performance Characteristics
	Large Rocket Motors	Smaller Motors	
Gen-Gard V-44 (Control)	Used in the 100-, 120-, 156-, and 260-in.-dia. motors (U.T.C., Lockheed, Thiokol, Aerojet)	Polaris A3 Minuteman Wing II	Excellent performance reliability and reproductibility.
Hitco 6520	Forward dome and low erosion areas of L-71 (156-in.-dia.) motor (Lockheed).		Good performance.
Orco 9250	120-in.-dia. SRM for Titan III-C.		Good performance.
5031-1	Aft dome insulation in L-71 (156-in.-dia.) motor (Lockheed): 120-in.-dia SRM for Titan III-C.		Good performance.
USR-3804		Genie Motors	Low ablation rates.
Gen-Gard 4010		Genie Motors	Low ablation rates.
SRM-81-8		Used in a number of small motors including Sparrow and ZAP	Good performance at low gas velocities.
USR-3800		Polaris A3, Genie Motors	Good performance at high and low gas velocities.
N-356		Genie Motors	Good performance.
Gen-Gard V-62		74-in.-dia Upper Stage motor and Genie Motors	Good performance.

Use History of Supplier Recommended Insulation Materials

Figure 6, Sheet 1 of 4

<u>Pressure-Cured Group</u>	<u>Rocket Motor Applications</u>		<u>Performance Characteristics</u>
	<u>Large Rocket Motors</u>	<u>Smaller Motors</u>	
Carborazole 10			
Carborazole 18			
Carborazole 26			
FM 5272		Evaluated in test motors for use in the 260-in.-dia nozzle (Thiokol) and for use in the Nomad motor.	Low ablation rates.
LPL 4B		Subscale motors (156-in.-dia program).	Good overall performance.
S-2048		Subscale motors	Good ablative properties.
X-30-724			
SE-557		Subscale motors	Good ablative properties.
K-1213			
K-1255			
K-1305W		Subscale motors	Good ablative properties.
Guardian		Subscale motors	Good performance.

Figure 6, Sheet 2 of 4

Use History of Supplier Recommended Insulation Materials

<u>Trowelable Group</u>	<u>Rocket Motor Applications</u>		<u>Performance Characteristics</u>
	<u>Large Rocket Motors</u>	<u>Smaller Motors</u>	
Gen-Gard V-61	Used as a repair and joint sealant material in the 120- and 260-in.-dia motors.		Good performance in high and low gas velocity areas.
IBT-100	Used as nozzle shell insulation in the 260-SL-3 motor.	Polaris test motor Genie motors.	Low ablation rates in high gas velocity areas.
IBT-106		Subscale 44-in.-dia motor (260-in.-dia. rocket motor program) AGC. Self-Eject Launch Technology Program Subscale test motors, AGC	Good performance.
LPL-44	Forward and aft dome insulation in (1-72) (156-in.-dia) motor (Lockheed)		Good performance.
TI-H704B		Subscale 66-SS-2 and 66-SS-3 motors (156-in.-dia program) (Thiokol).	Good performance.
93-083			
TBS-542			
PR-1955			

Use History of Supplier Recommended Insulation Materials

<u>Castable Group</u>	<u>Rocket Motor Applications</u>		<u>Performance Characteristics</u>
	<u>Large Rocket Motors</u>	<u>Smaller Motors</u>	
IBC-101	Used as inert slivers in the 260-SL-3 motor		Good performance.
40SA-2		Genie motors	Good performance.
40SA-40		Hawk and Genie motors	Good performance in low gas velocity regions.
40SD-80			
93-073			
93-104			
RTV-511		Used as base heat insulation in Polaris A3 motor	Good performance.
Castable Carbon		Nomad Test Motors	Low ablation rate in high gas velocity regions.
Avcoat 8021			
<u>Sprayable Group</u>			
IBS-105			
IBS-108		Diameter wall insulation in 2.75 FFAR motor	Good performance.
IBS-109		Aft end insulation in 2.75 FFAR motor	Good performance.
IBS-107		Evaluated in Advanced Sparrow motors	Good performance.
Avcoat II		External insulation of Minuteman motors	Good performance at low heat flux levels.
PR 1933			

Use History of Supplier Recommended Insulation Materials

<u>Material Designation</u>	<u>Supplier</u>	<u>Basic Binder</u>	<u>Basic Filler</u>	<u>Physical Group</u>
Gen-Gard V44 (Control)	General Tire & Rubber Co. Akron, Ohio	Acrylonitrile- butadiene	Asbestos- Silica	Pressure Cure
5031-1	West American Rubber Co.	Acrylonitrile- butadiene	Asbestos	Pressure Cure
6520	H. I. Thompson Co. Gardena, Calif.	Acrylonitrile- butadiene	Silica	Pressure Cure
ORCO 9250	Ohio Rubber Co.	Acrylonitrile- butadiene	Asbestos- Silica	Pressure Cure
USR 3804	U. S. Rubber Co. Mishewaka, Indiana	Ethylene-propy- lene rubber	Asbestos	Pressure Cure
Gen-Gard V4010	General Tire & Rubber Co. Akron, Ohio	Ethylene-propy- lene rubber	Asbestos	Pressure Cure
Gen-Gard V62	General Tire & Rubber Co. Akron, Ohio	Styrene-butadiene rubber	Asbestos	Pressure Cure
LPE-2	Lockheed Company Redlands, Calif.	Polyisoprene- butadiene	Asbestos	Pressure Cure
N-356	B. F. Goodrich Co. Akron, Ohio	Phenolic-Acrylo- nitrile-butadiene	Inorganic Hydrate	Pressure Cure
SE 557	General Electric Co. Waterford, N. Y.	Silicone rubber	Silica	Pressure Cure
S-2048	Dow Corning Corp. Midland, Mich.	Silicone rubber	Silica	Pressure Cure

Intermediate List of 30 Insulation Materials Applicable to Large Rocket Motors

<u>Material Designation</u>	<u>Supplier</u>	<u>Basic Binder</u>	<u>Basic Filler</u>	<u>Physical Group</u>
X-30742	Dow Corning Corp. Midland, Mich.	Silicone rubber	Silica	Pressure Cure
USR 3800	U. S. Rubber Co. Mishewaka, Indiana	Phenolic-Acrylonitrile-butadiene	Boric Acid	Pressure Cure
SMR 81-8	West American Rubber Co. Anaheim, Calif.	Butyl rubber	Asbestos-Silica	Pressure Cure
Gen-Gard V61	General Tire & Rubber Co. Akron, Ohio	Epoxy-Polysulfide Acrylonitrile-butadiene	Asbestos	Troweling
LPC-31	Lockheed Company Redlands, Calif.	Polybutadiene Acrylonitrile-Acrylic Acid Terpolymer	Asbestos	Troweling
TI-H704B	Thiokol Chemical Co. Brigham City, Utah	Polybutadiene Acrylonitrile-Acrylic Acid Terpolymer	Asbestos	Troweling
IBT-100 (SD850-15C)	Aerojet-General Corp. Sacramento, Calif.	Polybutadiene Acrylonitrile-epoxy	Asbestos	Troweling
IBT-106	Aerojet-General Corp. Sacramento, Calif.	Polybutadiene-Acrylonitrile-epoxy	Asbestos	Troweling
93-083	Dow Corning Corp. Midland, Mich.	Silicone rubber	Silica	Troweling

Intermediate List of 30 Insulation Materials Applicable to Large Rocket Motors

<u>Material Designation</u>	<u>Supplier</u>	<u>Basic Binder</u>	<u>Basic Filler</u>	<u>Physical Group</u>
40SA2	American Polytherm Co. Sacramento, Calif.	Polyurethane	Silica	Casting
40SA40	American Polytherm Co. Sacramento, Calif.	Polyurethane	Silica	Casting
IBC-101	Aerojet-General Corp. Sacramento, Calif.	Polybutadiene- Acrylonitrile- epoxy	Asbestos	Casting
93-073	Dow Corning Corp. Midland, Mich.	Silicone rubber	Silica	Casting
SD 878-2	Aerojet-General Corp. Sacramento, Calif.	Polybutadiene- Acrylonitrile & Terpolymer of Polybutadiene, Acrylonitrile & Acrylic Acid	Antimony Oxide Potassium Titanate	Spraying
IBS-108	Aerojet-General Corp. Sacramento, Calif.	Polybutadiene- Acrylonitrile	Asbestos	Spraying
IBS-105	Aerojet-General Corp. Sacramento, Calif.	Polybutadiene- Acrylonitrile- epoxy	Asbestos	Spraying
RTV 511	General Electric Co. Waterford, N. Y.	Silicone rubber	Silica	Spraying
NRL 1126	Insulation Technology, Inc. Sacramento, Calif.	Phenolic	Refractory Powder	Spraying
AVCOAT II	AVCO, Corp. Lowell, Mass.	Epoxy-polyamide	Refractory Powder	Spraying


Intermediate List of 30 Insulation Materials Applicable to Large Rocket Motors

Pressure-Cured Class (4 Materials)




Supplier

Gen-Gard V-44 (Control)	General Tire & Rubber Co.
Orco 9250	Ohio Rubber Co.
USR 3804	Uniroyal, Inc.
USR 3800	Uniroyal, Inc.

Trowelable (6 Materials)

Gen-Gard V-61 (Control)	General Tire & Rubber Co.
IBT-100	Aerojet-General Corp.
IBT-106	Aerojet-General Corp.
LPL-44 	Lockheed Propulsion Co.
TI-H704B	Thiokol Chemical Corp.
Gen-Gard 4011	General Tire & Rubber Co.

Castable (5 Materials)

IBC-101	Aerojet-General Corp.
40 SD-80	American Poly-Therm Co.
Castable Carbon 	Atlantic Research Corp.
RTV-511	General Electric Corp.
Avcoat 8021	AVCO Corp.
93-104 	Dow Corning Corp.
IBC-111 	Aerojet-General Corp.

Sprayable (5 Materials)

IBS-107	Aerojet-General Corp.
IBS-108	Aerojet-General Corp.

List of 20 Insulation Materials Selected  
for Evaluation in Task I



Sprayable Class

Supplier

IBS-109

Aerojet-General Corp.

Avcoat II

AVCO Corp.

PR-1933

Products Research & Chem. Corp.



Material could not be procured at acceptable cost to program; DC-93-104 used in place of LPL-44.



Could not be processed into test motor aft closure; IBC-111 used in place of castable carbon.

List of 20 Insulation Materials Selected  
for Evaluation in Task I

NASA CR-72581

<u>Material</u>	<u>Supplier</u>	<u>Procurement Summary</u>
V-44	GT&R	Available; residual from 260-SL-3 program
Orco 9250	Ohio Rubber	Purchase Order G10352; \$75 for 45 lb or \$1.67/lb
USR 3800	Uniroyal	Free Samples; 35 lb
USR 3804	Uniroyal	Free Sample; 35 lb
V-61	GT&R	Available; residual from 260-SL-3 program
IBT-100	AGC	Raw material; \$0.65/lb
IBT-106	AGC	Raw material; \$0.60/lb
LPL-44	LPC	Procurement cancelled
TI-H704B	TCC	Free Sample; 6 lb
4011	GT&R	Free Sample; 25 lb
IBC-101	AGC	Raw material available; \$0.67/lb
IBC-111	AGC	Raw material available
40SD-80	American Polytherm	Purchase Order G635512; \$135 for 30 lb or \$4.50/lb
Castable Carbon	ATC	Purchase Order G635625; \$115 for 25 lb or \$4.60/lb
RTV-511	GE	Purchase Order G635367; \$144 for 24 lb or \$5.10/lb
Avcoat 8021	AVCO	Purchase Order G 104219; \$170 for 20 lb or \$8.50/lb
93-104	DC	Free Sample; 20 lb
IBS-107	AGC	Raw material available; \$1.62/lb
IBS-108	AGC	Raw material available; \$0.73/lb
IBS-109	AGC	Raw material available; \$0.72/lb
Avcoat II	AVCO	Purchase Order G636021; \$74.50 for 26.5 lb or \$2.79/lb
PR 1933	PR	Purchase Order G103542; \$207.78 for 34 lb or \$6.15/lb

Task I Insulation Material Procurement

Figure 9

Material	Mechanical Properties @ 77°F										Thermal Properties														
	Tensile					Shore A					Heat Capacity, cal/gm-°C					Thermal Diffusivity, cm <sup>2</sup> /sec					Thermal Conductivity, Btu-in/hr-ft <sup>2</sup> -°F				
	Strength, psi	Elongation, %	Modulus, psi	Hardness, psi	Density, gm/cc	100°F	200°F	300°F	150°F	250°F	300°F	70°F	125°F	150°F	200°F	275°F	70°F	150°F	200°F	250°F					
V-144	775	288	315	1580	73	1.296	1.204	1.206	0.407	0.443	0.445	.00115	---	.00115	---	.00135	---	1.955	2.034	---	2.118				
Oreo 9650	789	483	504	2111	67	1.259	1.228	1.207	0.373	0.401	0.408	.00135	---	.0013	---	.0012	---	1.942	1.886	---	1.844				
USR 3800	1096	183	200	26,205	90	1.146	1.090	0.971	0.432	0.511	Melted	.00086	.00089	.00083	---	.00077	---	0.783	1.171	---	1.206				
USR 3804	735	252	276	2424	79	1.199	1.166	1.126	0.375	0.418	0.432	.0016	---	.0015	---	.0015	---	1.686	1.927	---	2.081				
V-61	1333	8.3	8.5	22,951	90	1.308	1.233	1.146	0.382	0.471	0.431	.0010	.00121	.00096	---	.00087	---	1.170	1.352	---	1.413				
IFB-1100	866	59	61	3900	90	1.390	1.351	1.319	0.324	0.367	0.388	.0013	.00118	.0013	---	.0013	---	1.529	1.675	---	1.848				
IFB-1106	8366	36	37	8873	89	1.423	1.374	1.356	0.356	0.403	0.425	.00115	---	.00135	---	.00145	---	1.519	1.945	---	2.310				
93-104	120	26	29	1376	51	1.431	1.373	1.340	0.288	0.328	0.346	.00215	---	.0019	---	.0016	---	2.265	2.216	---	2.321				
TI-H701B	123	165	184	442	31	1.334	1.293	1.251	0.364	0.410	0.428	.0026	---	.0022	---	.00175	---	3.358	3.069	---	2.654				
4011	1405	38	46	5962	81	1.200	1.145	1.112	0.428	0.446	0.450	.00165	---	.00135	---	.0012	---	2.184	1.959	---	1.754				
IFB-1101	942	133	135	3373	81	1.329	1.283	1.111	0.363	0.396	0.414	.0012	---	.00155	---	.00145	---	1.452	2.115	---	2.050				
40SD-80	865	80	83	2364	54	1.312	1.263	1.249	0.337	0.375	0.396	.0012	---	.0013	---	.00145	---	1.520	1.628	---	1.976				
Castable Carbon						1.674	1.625	1.599	0.216	0.234	0.241	.0172	---	.0151	---	.0148	---	16.491	16.110	---	16.086				
RVF-511	82	68	68	167	34	1.169	1.124	1.083	0.346	0.374	0.378	.00145	---	.0016	---	.0012	---	1.486	1.822	---	1.444				
Avcoat 8021	3332	91	91	35,958	90	1.192	1.346	1.300	0.453	0.497	0.512	.0011	---	.00087	---	.00082	---	1.591	1.322	---	1.329				
IBS-107	1112	23	36	13,534	84	1.225	1.190	1.164	0.389	0.439	0.457	.00115	---	.00125	---	.0011	---	1.366	1.698	---	1.617				
IBS-108	118	151	160	193	24	1.253	1.207	1.107	0.389	0.439	0.460	.00145	---	.0021	---	.00213	---	1.825	2.866	---	3.172				
IBS-109	178	95	96	348	35	1.235	1.199	1.175	0.385	0.418	0.436	.0016	---	.00155	---	.00125	---	2.254	2.127	---	1.753				
Avcoat II	2364	30	31	45,490	51	1.102	1.051	1.026	0.507	0.540	0.554	.00084	---	.00083	---	.00083	---	1.263	1.309	---	1.334				
PR1933	291	228	228	132	21	1.416	1.346	1.300	0.320	0.360	0.371	.0017	---	.0019	---	.0030	---	1.864	2.428	---	3.886				

NOTES:  $\Delta$  IBS-108 synonymous with original IBS-105 identification.  
 $\Delta$  Strain at maximum tensile strength.  
 $\Delta$  Strain at break.

Property Measurement Data Summary

Figure 10, Sheet 1 of 4

	Bond Line Tensile and Shear Strength				Type of Bond Failure	Working Consistency	Ambient Pot Life, hrs	Heat of Combustion cal/gm	Heat of Combustion Btu/lb
	Bonding Components	Bonding System Insulation to Steel	Tensile Bond Strength, psi	Shear Strength, psi					
V-44	S/I/L/P	162-Y-22/Epon 948.2	155.1	P 134.4	P	Solid	----	5822	10,480
Orco 9250	S/I/L/P	162-Y-22/Epon 948.2	171.1	P 134.9	P	Solid	----	5897	10,614
USR 3800	S/I/L/P	162-Y-22/Epon 948.2	167.5	P 130.6	P	Solid	----	6474	11,653
USR 3804	S/I/L/P	162-Y-22/Epon 948.2	175.3	P 137.3	P	Solid	----	7053	12,695
V-61	S/I/L/P	162-Y-22	148.0	P 138.5	P	Paste	0.25	5441	9,794
IBT-100	S/I/P	162-Y-22/Epon 948.2	166.8	P 105.0	P	Paste	16-24	6151	11,072
IBT-106	S/I/P	162-Y-22/Epon 948.2	161.4	P 107.7	P	Semi-Viscous Paste	16-24	6931	12,476
93-104	S/I/L/P	162-Y-22/Epon 948.2	No measurable bond attained between insulation and liner			Fluid	2	4182	7,528
TI-H704B	S/I/L/P	162-Y-22/Epon 948.2	159.8	P 122.7	P	Paste	~12	6916	12,449
IBC-101	S/I/P	162-Y-22/Epon 948.2	131.3	P 104.5	P	Fluid	12-16	7724	13,903
4011	S/I/L/P	162-Y-22/Epon 948.2	8	IL 58	IL	Paste	0.5	7199	14,998
40SD-80	S/I/L/P	162-Y-22/Epon 948.2	109.0	P >200	P	Fluid	3	5772	10,390
RTV-511	S/I/L/P	162-Y-22/Epon 948.2	No measurable bond attained between insulation and liner			Fluid	6	5434	9,781
Avcoat 8021	S/I/L/P	162-Y-22/Epon 948.2	169.5	P 130.8	P	Solid	----	8434	15,181
IBS-107	S/I/P	162-Y-22/Epon 948.2	93.3	P 102.1	P	Viscous Liquid	6	8592	15,466
IBS-108	S/I/P	162-Y-22/Epon 948.2	126.6	IP 75.8	IP	Viscous Liquid	12-16	8530	15,354
IBS-109	S/I/P	162-Y-22/Epon 948.2	125.2	IP 82.3	IP	Viscous Liquid	12-16	8267	14,881
Avcoat II	S/I/L/P	162-Y-22/Epon 948.2	93.8	IL 72.6	IL	Fluid	4	9934	17,880
PR 1933	S/I/L/P	162-Y-22/Epon 948.2	No measurable bond attained between insulation and liner			Semi-Viscous Paste	2	4412	7,941

Property Measurement Data Summary

Figure 10, Sheet 2 of 4


Liner	Bond Strength "As Received"			Bond Strength After Drying			Bond Strength After 50% RH Storage			Bond Strength After 90% RH Storage		
	Tensile, Shear, Loss, %		Weight Gain %	Tensile, Shear, Loss, %		Weight Gain %	Tensile, Shear, Loss, %		Weight Gain %	Tensile, Shear, Loss, %		Weight Gain %
	psi	psi	psi	psi	psi	psi	psi	psi	psi	psi	psi	psi
V-44	155	134	96	122	2.25	1.13	138	143	1.13	162	131	2.40
Orco 9250	172	135	173	155	1.92	1.01	100	148	1.01	85	116	1.80
USR 3800	168	131	181	178	10.44	1.51	158	164	1.51	159	116	2.60
USR 3804	175	137	99	159	0.59	0.36	158	164	0.36	159	116	0.77
V-61	158	139	160	130	4.40	1.65	158	157	1.65	152	125	3.12
IBT-100	167	105	53	52	0.16	0.34	55	34	0.34	69	48	0.62
IBT-106	161	108	104	66	0.16	0.39	84	92	0.39	59	80	0.73
93-104	-----Not Tested-----											
TI-F704B	160	122	94	139	0.43	0.30	138	144	0.30	161	101	1.78
4011	-----Not Tested-----											
IBC-101	131	105	64	63	0.14	0.42	61	74	0.42	83	69	0.84
40SD-80	109	262	182	127	0.47	0.49	104	157	0.49	103	210	1.03
RTV-511	-----Not Tested-----											
Avcoat 8021	170	131	55	199	0.60	0.94	150	179	0.94	151	144	1.63
IBS-107	93	102	73	77	0.11	0.32	85	88	0.32	77	62	0.65
IBS-108	127	71	63	38	0.29	0.30	61	42	0.30	56	31	0.60
IBS-109	125	82	86	59	0.44	0.31	46	32	0.31	74	40	0.60
Avcoat II	-----Not Tested-----											
FR 1933	-----Not Tested-----											
IBC-111	96	189	103	109	0.16	0.32	75	89	0.32	84	103	0.68

Property Measurement Data Summary


Figure 10, Sheet 3 of 4

- NOTES: **1** IBS-108 nomenclature synonymous with original IBS-105 identification.  
 (For Sheets **2** and **3**) **2** S/I/L/P: 4130 steel/insulation/SD850-2 liner/ANB-3254 propellant.  
**3** Cured slabs of insulation bonded to steel plates.  
**4** P: failure in propellant.  
 IP: adhesive failure at insulation-propellant-interface.  
 IL: adhesive failure at insulation-liner-interface.  
**5** No liner required.  
**6** 50% IP, 50% P.  
**7** All bond samples failed randomly in the propellant unless otherwise noted.  
**8** Break within 1 mm of the propellant surface.  
**9** Break at the propellant-to-insulation interface, specimens being retested to verify data.  
**10** Use of SD850-2 liner on a residual specimen of IBC-111 which had been exposed to 180°F yielded a tensile value of 108 psi.

Property Measurement Data Summary




Typical Stress-Strain Diagrams for Insulation Materials




Typical Stress-Strain Diagrams for Insulation Materials






Typical Stress-Strain Diagrams for Insulation Materials




Typical Stress-Strain Diagrams for Insulation Materials



Density of Insulation Materials

Figure 12, Sheet 1 of 2



Density of Insulation Materials






Figure 13

Thermal Diffusivity-vs-Temperature



Thermal Conductivity-vs-Temperature

Figure 14



Heat Capacity-vs-Temperature

Figure 15





Figure 16





Viscosity Buildup Characteristics of Castable Insulations

Figure 17






Figure 18


Viscosity Buildup Characteristics of Sprayable Insulations




Thermogravimetric Analysis of Insulation Materials




Thermogravimetric Analysis of Insulation Materials




Thermogravimetric Analysis of Insulation Materials  
 Figure 19, Sheet 3 of 5



Thermogravimetric Analysis of Insulation Materials



Thermogravimetric Analysis of Insulation Materials



LMISD Test Motor Configuration

Figure 20



## M E M O R A N D U M

TO: D. L. Nachbar 10 June 1968  
 FROM: J. M. Kovacs JMK:wjs  
 2019A:3252:807  
 SUBJECT: Preliminary Stress Analysis of LMISD Test Motor  
 DISTRIBUTION: E. P. Eales, R. D. Entz, R. Knapp, File  
 ENCLOSURE: (1) Detailed Stress Calculations

A preliminary structural evaluation of the LMISD test motor primary components has been completed for a design pressure of 720 psi, approximately 115% of MEOP, with results shown in the table below. The small margins of safety should not be of concern, since they are based upon conservative analytical methods used to simplify the stress calculations.

TABLE OF MINIMUM MARGINS OF SAFETY  
 (Design Pressure of 720 psi)

<u>Component</u>	<u>Stress</u>	<u>Allowable</u>	<u>Mode</u>	<u>Margin of Safety</u>
Cover Plate	16,600	36,000	Bending	1.15
Bolt	18,000(1b)	20,800(1b)	Tension	0.165
Chamber	8,136	36,000	Tension	3.20
Nozzle Housing	30,170	36,000	Bending	0.20
Asbestos Phenolic	282	5,400	Shear	Large

$$MS = \frac{\text{Calculated Stress}}{\text{Allowable}} - 1$$

Per your request, no thermal stress analysis of the graphite insert was performed. A simplified heat transfer analysis performed by the Aerophysics Department showed the asbestos phenolic/graphite interface to reach about 800°F, with the steel shell remaining at ambient for the 20 second duration.

A nominal bolt torque will be adequate to prevent leakage of the large diameter chamber joints, maximum separation conservatively estimated at less than 0.012 inches at the O-Ring seal.

Approved by: J. M. Kovacs  
 Engineering Specialist  
 SRO Stress Group  
 Propulsion Division

R. D. Entz, Manager  
 SRO Stress Group  
 Propulsion Division

Stress Analysis of LMISD Test Motor









Figure 23



SECT A-A  
PROCESS SECTIONS 1, 2, 3, 4  
PRIOR TO INITIAL CURE

Aft Closure Insulation Specimen Processing Setup


Figure 24



Scribed Mark on Nozzle  
Standing Fwd Looking Aft


Specimen Location in Nozzle SN I-1

Figure 25



Scribed Mark on Nozzle  
Standing Forward Looking Aft  
Specimen Location in Nozzle S/N I-2

Figure 26



Modified IBT-106  
Added 3% Acetylene Black

Modified IBT-106  
Added 5% 7TF-1  
Asbestos


Scribed Mark on Nozzle  
Standing Fwd-Looking Aft

Specimen Location in Nozzle S/N I-3A

Figure 27

\*Original Identification was  
S/N I-3; Damaged DC93-104  
Removed and Replaced with IBT-100

Figure 24



Pressure-vs-Time Performance

MOTOR S/N I-1


Motor Chamber Pressure, peta		Time, Seconds		Propellant ARB-2254		Port area (left)		Benefits	
1. Motor	17.6 sec	Dr (initial) in	1.613	Weight	207	lb	Linear	lb	lb
2. Motor	17.6 sec	Dr (final) in	1.613	Density	---	lb/in <sup>3</sup>	Linear	lb	lb
3. Motor	17.6 sec	U <sub>2</sub> (OL) in/sec	---	Batch No.	B-473	---	Linear	lb	lb
4. Motor	17.6 sec	U <sub>2</sub> (OL) in/sec	---	Configuration	End Burning	---	Linear	lb	lb
5. Motor	17.6 sec	U <sub>2</sub> (OL) in/sec	---	Grain length	13.75	in	Linear	lb	lb
6. Motor	17.6 sec	U <sub>2</sub> (OL) in/sec	---	Grain O. D.	17.01	in	Linear	lb	lb
7. Motor	17.6 sec	U <sub>2</sub> (OL) in/sec	---	Web thickness	---	in	Linear	lb	lb
8. Motor	17.6 sec	U <sub>2</sub> (OL) in/sec	---	Web thickness	---	in	Linear	lb	lb
9. Motor	17.6 sec	U <sub>2</sub> (OL) in/sec	---	Web thickness	---	in	Linear	lb	lb
10. Motor	17.6 sec	U <sub>2</sub> (OL) in/sec	---	Web thickness	---	in	Linear	lb	lb
11. Motor	17.6 sec	U <sub>2</sub> (OL) in/sec	---	Web thickness	---	in	Linear	lb	lb
12. Motor	17.6 sec	U <sub>2</sub> (OL) in/sec	---	Web thickness	---	in	Linear	lb	lb
13. Motor	17.6 sec	U <sub>2</sub> (OL) in/sec	---	Web thickness	---	in	Linear	lb	lb
14. Motor	17.6 sec	U <sub>2</sub> (OL) in/sec	---	Web thickness	---	in	Linear	lb	lb
15. Motor	17.6 sec	U <sub>2</sub> (OL) in/sec	---	Web thickness	---	in	Linear	lb	lb
16. Motor	17.6 sec	U <sub>2</sub> (OL) in/sec	---	Web thickness	---	in	Linear	lb	lb
17. Motor	17.6 sec	U <sub>2</sub> (OL) in/sec	---	Web thickness	---	in	Linear	lb	lb
18. Motor	17.6 sec	U <sub>2</sub> (OL) in/sec	---	Web thickness	---	in	Linear	lb	lb
19. Motor	17.6 sec	U <sub>2</sub> (OL) in/sec	---	Web thickness	---	in	Linear	lb	lb
20. Motor	17.6 sec	U <sub>2</sub> (OL) in/sec	---	Web thickness	---	in	Linear	lb	lb
21. Motor	17.6 sec	U <sub>2</sub> (OL) in/sec	---	Web thickness	---	in	Linear	lb	lb
22. Motor	17.6 sec	U <sub>2</sub> (OL) in/sec	---	Web thickness	---	in	Linear	lb	lb
23. Motor	17.6 sec	U <sub>2</sub> (OL) in/sec	---	Web thickness	---	in	Linear	lb	lb
24. Motor	17.6 sec	U <sub>2</sub> (OL) in/sec	---	Web thickness	---	in	Linear	lb	lb
25. Motor	17.6 sec	U <sub>2</sub> (OL) in/sec	---	Web thickness	---	in	Linear	lb	lb

Pressure-vs-Time Performance, Motor S/N I-1

Figure 28



Figure 28



Length	lb/ft	Web thickness	17.7	sec	Di (initial)	1.610	in	4	Propellant	AMB-2251	Remarks
l, corr	lb/ft	Web av. pres.	610	psia	Di (final)				Weight	207	lb
l, end	lb/ft	Burning rate	11.35	in/sec	Di				Density		lb/ft <sup>3</sup>
l, sec	lb/ft	Pin di			Av/Ai (initial)	2.57	in <sup>2</sup>		Av/Ai (final)		in <sup>2</sup>
l, sec	lb/ft	Pin Av di			Av/Ai (final)				Configuration	End Burning	
l, sec	lb/ft	Pin Av di			Di (half angle)	15°			Grain length	13.75	in
l, sec	lb/ft	Av			Thrust max	AVJ Graphite			Grain O. D.	17.01	in
l, sec	lb/ft	Av			Kf				Web thickness		in
l, sec	lb/ft	Av			Ign interval				Ign interval		ms
l, sec	lb/ft	Av							Port area (eff)		in <sup>2</sup>
l, sec	lb/ft	Av							Av/Ai (eff)		
l, sec	lb/ft	Av							Total motor wt		lb
l, sec	lb/ft	Av							Length		in
l, sec	lb/ft	Av							In Dia		in
l, sec	lb/ft	Av							Out Dia	70 ± 5	in
l, sec	lb/ft	Av							Ign prim. charge	300	g
l, sec	lb/ft	Av							Main charge	5	g

Large Motor Insulation  
 Program: Space-Optimal  
 Contract: NAS-1-11221  
 Test No.: 1231-JOL-OK-002  
 Assay Dwg No.: 11690149  
 Date Recd.: 10/31/68  
 Prep. By: D. L. Nachbar  
 RESEARCHER GENERAL CORPORATION  
 1400 UNIVERSITY AVENUE  
 ANN ARBOR, MICHIGAN 48106

Pressure-vs-Time Performance, Motor S/N I-2

Figure 29





Figure 30

Pressure-vs-Time Performance, Motor S/N I-3A



Summary of Insulation Specimen Posttest Profiles, Motor S/N I-1

Figure 31




Figure 32

Summary of Insulation Specimen Posttest Profiles, Motor S/N I-2




Figure 33

Summary of Insulation Specimen Posttest Profiles, Motor S/N I-3A

	LOCATIONS														Max.		
	8	9	10	11	12	13	14	15	16	17	18	19	20	21		22	
0°: V-144																	
Initial Mach No.	.57	.38	.26	.21	.16	.14	.11	.10	.09	.08	.06	.05	.01	.01	.08	.08	Stag
Thickness Loss	0.26	0.57	0.57	0.49	0.41	0.34	0.30	0.24	0.22	0.21	0.15	0.08	0.08	0.08	0.08	0.08	0.08
TLR, in/sec/√A	-	.032	.032	.028	.023	.019	.017	.014	.013	.012	.009	.005	.005	.005	.005	.005	.037
45°: IBS-108																	
Initial Mach No.	.49	.31	.24	.17	.14	.11	.10	.09	.08	.06	.05	.02	.01	-	-	-	-
Thickness Loss	0.14	0.84	0.95	0.81	0.74	0.56	0.51	0.41	0.29	0.31	0.23	0.12	0.06	0.07	0.08	1.00	1.00
TLR	-	.048	.054	.046	.042	.032	.029	.023	.016	.018	.013	.007	.004	.004	.005	.057	
90°: V-61																	
Initial Mach No.	.49	.31	.24	.07	.04	.11	.10	.09	.08	.06	.05	.02	.01	-	-	-	-
Thickness Loss	0.31	0.25	0.26	0.19	0.16	0.14	0.09	0	0	0	0.02	0.15	0.08	0.06	0.05	0.31	0.31
TLR	-	.014	.015	.011	.009	.008	.005	-	-	-	.001	.008	.005	.004	.004	.018	
135°: IBS-107																	
Initial Mach No.	.42	.28	.20	.16	.14	.11	.10	.09	.08	.06	.05	.02	.01	-	-	-	-
Thickness Loss	0.17	0.45	0.30	0.20	0.20	0.20	0.18	0.15	0.13	0.14	0.19	0.17	0.08	0.07	0.05	0.45	0.45
TLR	-	.026	.017	.011	.011	.011	.010	.008	.007	.008	.001	.009	.005	.005	.004	.026	
180°: IBT-100																	
Initial Mach No.	.46	.30	.21	.17	.14	.11	.10	.09	.08	.06	.05	.02	.01	-	-	-	-
Thickness Loss	0.25	0.31	0.31	0.32	0.30	0.23	0.21	0.17	0.17	0.22	0.16	0.10	0.08	0.08	0.09	0.31	0.31
TLR	-	.018	.018	.018	.017	.013	.012	.009	.009	.003	.009	.006	.005	.005	.005	.018	
215°: IBC-101																	
Initial Mach No.	.46	.30	.21	.17	.14	.11	.10	.09	.08	.06	.05	.02	.01	-	-	-	-
Thickness Loss	0.18	0.59	0.75	0.60	0.45	0.36	0.34	0.27	0.27	0.25	0.23	0.14	0.13	0.13	0.13	0.77	0.77
TLR	-	.034	.042	.034	.026	.021	.019	.015	.015	.014	.013	.008	.007	.007	.007	.044	
270°: IBT-106																	
Initial Mach No.	.57	.38	.26	.21	.16	.14	.11	.10	.09	.08	.06	.05	.01	-	-	-	-
Thickness Loss	0.21	0.52	0.31	0.30	0.31	0.28	0.28	0.30	0.30	0.28	0.27	0.10	0.12	0.12	0.10	0.52	0.52
TLR	-	.030	.018	.017	.018	.016	.016	.017	.017	.016	.016	.005	.007	.007	.006	.030	
315°: IBS-109																	
Initial Mach No.	.42	.28	.20	.16	.14	.11	.10	.09	.08	.06	.05	.02	.01	-	-	-	-
Thickness Loss	0.18	0.48	0.52	0.48	0.48	0.37	0.30	0.30	0.29	0.27	0.22	0.09	0.09	0.08	0.08	0.55	0.55
TLR	-	.027	.030	.027	.027	.021	.017	.017	.017	.015	.013	.005	.005	.005	.005	.030	

NOTES: 1 TLR, thickness loss rate =  $\frac{\text{Thickness Loss}}{\text{Web Duration}}$ ; web duration was 17.6 sec.

2 Maximum ablation occurred between position 9 and 10.

Summary of Insulation Specimen Erosion Data, Motor S/N I-1

Figure 34

	LOCATIONS													Max.		
	8	9	10	11	12	13	14	15	16	17	18	19	20		21	22
0°: V-44 Initial Mach No. Thickness Loss TLR <sup>1</sup>	.43 0.25 -	.30 0.47 .027	.23 0.37 .021	.19 0.31 .018	.15 0.30 .017	.12 0.24 .014	.11 0.23 .013	.10 0.21 .012	.08 0.20 .011	.05 0.14 .008	.04 0.12 .007	.03 0.12 .007	.01 0.09 .005	.01 0.09 .005	.05 0.05 .003	.027 0.47 .027
45°: 40SD-80 Initial Mach No. Thickness Loss TLR	.43 0.24 -	.30 0.53 .030	.23 0.62 .035	.19 0.61 .035	.15 0.58 .033	.12 0.41 .023	.11 0.46 .026	.10 0.41 .023	.08 0.41 .023	.05 0.41 .023	.04 0.19 .011	.03 0.11 .006	.01 0.11 .006	.01 0.10 .005	.09 0.09 .005	.62 0.62 .035
90°: V-61 Initial Mach No. Thickness Loss TLR	.43 0.40 -	.30 0.29 .016	.23 0.17 .010	.19 0.12 .007	.15 0.12 .007	.12 0.14 .008	.11 0.08 .004	.10 0.05 .003	.08 0.05 .003	.05 0.04 .002	.04 0.04 .002	.03 0.05 .003	.01 0 0	.01 0.04 .002	.05 0.05 .003	.48 0.48 .027
135°: Avcoat II Initial Mach No. Thickness Loss TLR	.43 0.50 -	.30 1.00 .057	.23 1.00 .066	.19 0.93 .062	.15 0.79 .045	.12 0.67 .038	.11 0.58 .033	.10 0.52 .029	.08 0.46 .026	.05 0.39 .022	.04 0.25 .015	.03 0.07 .004	.01 0.10 .006	.01 0.09 .005	.09 0.09 .005	1.00 1.00 .057
180°: RTV-511 Initial Mach No. Thickness Loss TLR	.43 0.55 -	.30 1.43 .081	.23 1.16 .066	.19 1.10 .062	.15 1.06 .060	.12 1.04 .059	.11 1.00 .057	.10 0.94 .054	.08 0.88 .050	.05 0.87 .049	.04 0.95 .055	.03 0.75 .042	.01 0.15 .008	.01 0.12 .007	.10 0.10 .006	1.43 1.43 .081
225°: PR-1933 Initial Mach No. Thickness Loss TLR	.43 0.51 -	.30 1.45 .082	.23 1.33 .075	.19 1.23 .070	.15 1.21 .068	.12 1.19 .067	.11 1.16 .066	.10 1.14 .064	.08 0.70 .063	.05 1.10 .062	.04 1.09 .062	.03 0.90 .050	.01 0.50 .028	.01 0.21 .012	.16 0.16 .009	1.45 1.45 .082
270°: TBS-758 Initial Mach No. Thickness Loss TLR	.43 0.60 -	.30 1.58 .089	.23 1.48 .084	.19 1.28 .072	.15 1.18 .067	.12 0.98 .055	.11 0.80 .045	.10 0.72 .041	.08 0.70 .040	.05 0.58 .033	.04 0.49 .028	.03 0.21 .012	.01 0.10 .006	.01 0.05 .003	.05 0.05 .001	1.58 1.58 .089
315°: IBC-111 Initial Mach No. Thickness Loss TLR	.43 0.52 -	.30 0.70 .040	.23 0.35 .020	.19 0.22 .013	.15 0.18 .010	.12 0.14 .008	.11 0.16 .009	.10 0.18 .010	.08 0.14 .008	.05 0.11 .006	.04 0.20 .012	.03 0.14 .088	.01 0.08 .005	.01 0.05 .003	.02 0.02 .001	1.05 1.05 .059

NOTES: <sup>1</sup> TLR, thickness loss rate = Thickness Loss / Web Duration; web duration was 17.7 sec

<sup>2</sup> Maximum ablation occurred between position 9 and 10.

Figure 35


	LOCATIONS																		Max. <sup>3</sup>
	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22				
0° : V-44																			
Initial Mach No.	.44	.31	.22	.18	.04	.12	.10	.09	.08	.07	.06	.04	.02	-	-	-	-	-	
Thickness Loss	0.36	0.36	0.30	0.26	0.23	0.24	0.24	0.22	0.21	0.21	0.21	0.10	0.09	0.08	0.06	0.06	0.06	0.38	
TLR <sup>1</sup>	0.021	0.021	0.017	0.015	0.013	0.014	0.014	0.012	0.012	0.012	0.012	0.006	0.005	0.005	0.003	0.003	0.003	0.022	
45° : V-61/TI-H704B <sup>2</sup>																			
Initial Mach No.	.37	.25	.18	.14	.12	.10	.09	.08	.07	.06	.05	.04	.02	-	-	-	-	-	
Thickness Loss	0.20	0.70	0.85	0.52	0.46	0.43	0.30	0.31	0.30	0.26	0.20	0.10	0.05	0.08	0.05	0.05	0.05	0.92	
TLR	0.011	0.040	0.049	0.030	0.026	0.024	0.017	0.018	0.017	0.015	0.011	0.006	0.003	0.005	0.003	0.003	0.003	0.052	
90° : USR-3800																			
Initial Mach No.	.41	.28	.21	.17	.14	1.2	.10	.08	.07	0.6	0.5	0.4	.02	-	-	-	-	-	
Thickness Loss	0.11	0.11	0.10	0.10	0.10	0.08	0.08	0.08	0.08	0.07	0.07	0.04	0.04	0.04	0.08	0.08	0.11	0.11	
TLR	0.006	0.006	0.006	0.006	0.006	0.005	0.005	0.005	0.005	0.004	0.004	0.002	0.002	0.002	0.002	0.005	0.005	0.006	
135° : Orco 9250																			
Initial Mach No.	.44	.31	.22	.18	.14	.12	.10	.09	.08	.07	.06	.04	.02	-	-	-	-	-	
Thickness Loss	0.25	0.20	0.12	0.15	0.10	0.06	0.05	0.05	0.05	0.05	0.05	0.05	0.06	0.05	0.05	0.05	0.05	0.25	
TLR	0.011	0.016	0.004	0.011	0.010	0.010	0.009	0.010	0.009	0.009	0.008	0.005	0.005	0.005	0.003	0.003	0.016	0.016	
180° : IBT-100																			
Initial Mach No.	.41	.31	.22	.17	.14	.12	.10	.09	.08	.07	.06	.04	.02	-	-	-	-	-	
Thickness Loss	0.20	0.28	0.25	0.20	0.8	0.17	0.15	0.17	0.16	0.15	0.14	0.09	0.08	0.08	0.05	0.05	0.05	0.28	
TLR	0.011	0.016	0.014	0.011	0.010	0.010	0.009	0.010	0.009	0.009	0.008	0.005	0.005	0.005	0.003	0.003	0.016	0.016	
225° : 4011																			
Initial Mach No.	.41	.28	.21	.17	.14	.12	.10	.08	.07	.06	.05	.04	.02	-	-	-	-	-	
Thickness Loss	0.25	0.42	0.30	0.25	0.24	0.22	0.15	0.16	0.15	0.15	0.13	0.08	0.08	0.10	0.10	0.10	0.42	0.42	
TLR	0.014	0.024	0.017	0.014	0.014	0.013	0.009	0.009	0.009	0.009	0.007	0.005	0.005	0.006	0.006	0.006	0.024	0.024	
270° : Avcoat 8021																			
Initial Mach No.	.44	.31	.22	.18	.14	.12	.10	.09	.08	.07	.06	.04	.02	-	-	-	-	-	
Thickness Loss	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	
TLR	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	

NOTES: <sup>1</sup> TLR, thickness loss rate = Thickness Loss / Web Duration ; web duration was 17.6 sec.  
<sup>2</sup> V-61 from Locations 16 to 22; TI-H704B from Locations 8 to 18.  
<sup>3</sup> Maximum ablation occurred between locations 9 and 10.

Summary of Insulation Specimen Erosion Data, Motor S/N I-3A


Figure 36






Thickness Loss Rate-vs-Initial Mach Number, Motor S/N I-1

Figure 37



Thickness Loss Rate-vs-Initial Mach Number, Motor S/N I-2

Figure 38



Thickness Loss Rate-vs-Initial Mach Number, Motor S/N I-3A

Figure 39

Figure 18




Figure 40

Pressure-vs-Time Performance, Motor S/N I-3

Erosion	Material Cost \$/lb for 25,000 lb	Density gm/cc @ 100° F	THERMAL PROPERTIES			Thermal Conductivity Btu-in./ sq-ft °F @ 74° F	Moisture Absorption Weight Gain @ 50% RH, 90% RH, %				
			Heat of Combustion cal./gm	Heat Capacity cal./gm °C @ 150° F	Heat of Combustion cal./gm						
1. USR-3800	Castable Carbon	0.90	Avcoat II	9934	Avcoat II	0.507	USR-3800	0.783	IBS-108	0.30	0.59
2. Oreo 9250	IBF-106	0.97	USR-3800	8592	Avcoat 8021	0.453	V-61	1.170	TI-H704B	0.30	1.78
3. V-61 (Control)	IBF-100	1.05	RTV-511	8530	USR-3800	0.432	Avcoat II	1.263	IBS-109	0.31	0.60
4. IBF-100	IBC-101	1.05	Avcoat 8021	8267	V-4011	0.428	IBS-107	1.366	IBS-107	0.32	0.65
5. IBS-107	IBS-108	1.10	USR-3804	8134	V-44	0.407	IBS-101	1.452	IBC-111	0.32	0.68
6. IBC-111	IBS-109	1.10	V-4011	7724	IBS-107	0.389	RTV-511	1.886	IBF-100	0.34	0.62
7. IBF-106	USR-3800	1.40	IBS-107	7199	IBS-108	0.389	IBF-106	1.519	USR-3804	0.36	0.77
8. V-44 (Control)	USR-3804	1.40	IBS-109	7053	IBS-109	0.385	40SD-80	1.520	IBF-106	0.39	0.73
9. IBS-109	Oreo 9250	1.46	IBS-108	6931	V-61	0.382	IBF-100	1.529	IBC-101	0.42	0.84
10. V-4011	Avcoat II	1.55	Oreo 9250	6916	TI-H704B	0.375	Avcoat 8021	1.591	40SD-80	0.49	1.03
11. USR-3804	TI-H704B	1.87	V-44	6474	Oreo 9250	0.373	USR-3804	1.686	Avcoat 8021	0.94	1.63
12. 40SD-80	Avcoat 8021	1.89	V-61	6151	TI-H704B	0.364	PR-1933	1.864	Oreo 9250	1.01	1.80
13. IBC-101	IBC-111	1.90	40SD-80	5897	IBC-101	0.363	IBS-108	1.825	V-44	1.13	2.40
14. TI-H704B	IBS-107	2.00	IBC-101	5822	V-44	0.356	Oreo 9250	1.942	USR-3800	1.51	2.60
15. IBS-108	40SD-80	2.80	TI-H704B	5772	40SD-80	0.346	V-44	1.955	V-61	1.65	3.12
16. Avcoat II	V-44	3.19	IBC-111	5441	V-61	0.337	V-4011	2.184	RTV-511, PR-1933, 93-104, Avcoat II, Castable Carbon, TBS-756; not tested.		
17. RTV-511	V-61	3.48	IBF-100	5434	IBF-100	0.374	IBS-109	2.254			
18. PR-1933	PR-1933	5.00	PR-1933	4412	PR-1933	0.320	93-104	2.265			
19. TBS-756	RTV-511	5.55	IBF-106	4182	93-104	0.288	TI-H704B	3.358			
20. Avcoat 8021; no data ob- tained. Cast- able Carbon and 93-104; not tested	93-104	6.00	93-104	Castable Carbon, IBC-111, TBS-756; not tested.	Castable Carbon	0.216	Castable Carbon	16.191			
21.	V-4011	6.25	Castable Carbon	1.674	IBC-111, TBS-756; not tested.	IBC-111, TBS-756; not tested.					

△ Raw material, plus mixing and curing cost.

Relative Listing of Materials with Respect to Erosion, Cost, Physical, Thermal, Chemical, and Adhesive Properties

Figure 41, Sheet 1 of 2

Mechanical Properties		Ambient Pot Life		Bond Line Tensile/Shear		Bond Line Tensile/Shear After Moisture Exposure	
Acceptable	Marginal	Acceptable	Marginal	Acceptable	Marginal	Acceptable	Marginal
V-44	93-104	IBT-100	93-104	V-44	IBS-108	V-44	IPW-100
Orco 9250	IBS-108	IBT-106	40SD-80	Orco 9250	IBS-109	Orco 9250	IBT-106
USR-3800	TBS-758	TI-H70UB	TBS-758	USR-3800	Avcoat II	USR-3800	IBC-101
USR-3804		IBC-101	Avcoat II	USR-3804	IBS-107	USR-3804	IBC-111
V-61		IBC-111	PR-1933	V-61		V-61	IBS-107
IBT-100		RTV-511		IBT-100		40SD-80	IBS-109
IBT-106		TBS-107		IBT-106		Avcoat 8021	IBS-108
TI-H70UB		TBS-108		TI-H70UB			
V-4011		TBS-109		IBT-101			
IBC-101				IBC-101			
IBC-111				IBC-111			
40SD-80				40SD-80			
Avcoat 8021				Avcoat 8021			
IBS-107							
IBS-109							
Avcoat II							
PR-1933							

NOTES: 1 Acceptable: Tensile strength > 120 psi, elongation at maximum tensile strength > 0.75%.  
 Marginal: Tensile strength < 120 psi, but > 90 psi.  
 Unacceptable: Tensile strength < 90 psi.

2 Acceptable: Pot Life > 4 hrs.  
 Marginal: Pot Life < 4 hrs, but > 1 hr.  
 Unacceptable: Pot Life < 1 hr.  
 Not applicable to pressure-cured materials; V-44, Orco 9250, USR-3800, USR-3804, Avcoat 8021.

3 Acceptable: Tensile/Shear > 100 psi; failure in propellant.  
 Marginal: Tensile/Shear < 100 psi; but > 50 psi; failure at insulation-liner-propellant interface.  
 Unacceptable: Tensile/Shear < 50 psi.

4 No SD850-2 liner used with these specimens.

5 Materials which were unacceptable in the original bond line tensile/shear test were not subjected to moisture absorption tests.

Relative Listing of Materials with Respect to Erosion, Cost, Physical, Thermal, Chemical, and Adhesive Properties

Figure 41, Sheet 2 of 2

NASA CR-72581

Department 3800 Propel. Development, Line 5		Department 0720 Material Technology		Project	
Material	Rating <sup>1</sup>	Material	Rating <sup>1</sup>	Material	Rating <sup>2</sup>
IBT-100	970	IBC-101	847	USR 3800	47
IBT-106	955	IBT-100	846	IBS-107	61
IBS-109	908	IBT-106	840	IBS-109	70
IBC-111	885	IBC-111	830	Orco 9250	72
IBS-107	885	IBS-107	732	IBT-100	75
IBC-101	870	4011	704	IBT-106	75
IBS-108	847	IBS-109	703	IBC-111	81
TI-H704B	783	IBS-108	702	IBC-101	83
Orco 9250	700	Avcoat II	692	Avcoat II	90
USR 3800	615	40SD-80	686	TI-H704B	108
40SD-80	585	V-61	664	V-44	108
USR 3804	585	Orco 9250	660	40SD-80	110
Avcoat II	570	USR 3800	649	USR 3804	112
V-44	570	TI-H704B	641	IBS-108	120
V-61	520	USR 3804	593	V-61	130
4011	480	V-44	576	4011	Eliminated

<sup>1</sup> Rating based on 10 points for best material in each category considered multiplied by the weighting factor.


<sup>2</sup> Rating based on relative standing of each material in each category considered.

Summary of Material Ratings

Figure 42

Pressure-Cured Class

Gen-Gard V-44 (Control)

USR 3800 

Supplier


General Tire & Rubber Co.

Uniroyal, Inc.

Trowelable Class

IBT-100

IBT-106

TI-H704B 

Aerojet-General Corp.

Aerojet-General Corp.

Thiokol Chemical Corp.

Castable Class

IBC-101

IBC-111

40SD-80

Aerojet-General Corp.

Aerojet-General Corp.

American Poly-Therm Co.

Sprayable Class

IBS-107

IBS-109


Avcoat II


Aerojet-General Corp.

Aerojet-General Corp.

Avco Corp.

Back-Up Materials


 Orco 9250


 Avcoat 8021

Ohio Rubber Co.

Avco Corp.

---




 Orco 9250 was the back-up material for USR-3800


 Avcoat 8021 was the back-up material for TI-H704B


Recommended Materials for Further  
Evaluation in Tasks II and III


Figure 43



<u>PRESSURE-CURED</u>	<u>TASK II</u>	<u>TASK III</u>
V-44 (Control)	No demonstration	5 motor tests
USR 3800 	No demonstration	1 motor test
<u>TROWELABLE</u>		
IBT-100	1 demonstration forward/aft head insulator	1 motor test
IBT-106	1 demonstration	1 motor test
TI-H704B 	1 demonstration	1 motor test
<u>CASTABLE</u>		
IBC-111	1 demonstration	1 motor test
IBC-101	No demonstration	1 motor test
40SD-80	1 demonstration	1 motor test
<u>SPRAYABLE</u>		
IBS-107	2 demonstrations	1 motor test
IBS-109	2 demonstrations	1 motor test
Avcoat II 	1 demonstration	1 motor test

 Orco 9250 alternate.

 Avcoat 8021 alternate.

 Use of Avcoat II dependent on outcome of bond strength remeasurement.

Recommended Tasks II and III Material  
Selection and Evaluation Plan

Figure 44

**APPENDIX I**

**TEST PROCEDURES FOR  
MATERIAL PROPERTY MEASUREMENTS**

I. COMPOSITE TENSILE STRENGTH AND MODULUS

The mechanical properties of each of the 20 materials to be screened were evaluated using standard JANAF dumbbell specimens tested on an Instron machine according to AGC Method 3431. The specimens were prepared by die-cutting from a nominal 0.5-in.-thick piece of insulation material. In the case of the castable-sprayable-trowelable materials, the specimens were prepared by casting into Instron bar molds or into 0.5-in.-thick slabs from which the bars were cut. Triplicate specimens were tested at a strain rate of 2.0 in./min.

II. DENSITY

The density of insulation materials at 100, 200, and 300°F were measured by the liquid displacement method. A Dow Corning 710 silicone liquid that remains stable at 500°F was used as the displacement fluid. The test apparatus was constructed to permit the heated sample to be weighed in air; then the sample was transferred and immersed in heated Dow Corning 710 fluid where it was weighed again. The volume and weight of the test sample were obtained at the desired test temperature; material density was calculated from this data.

III. POT LIFE AND VISCOSITY

The pot life and viscosity of the highly viscous trowelable materials were determined from time-viscosity curves using the extrusion tube rheometer designed by Aerojet. Samples were loaded into a temperature-controlled reservoir and pressurized to produce vertical flow through a thermostated discharge tube. The available discharge tubes were 20 in. long and their inside diameters varied from 0.131 to 0.683 in. Measurements made by using this equipment and a standard calibrating fluid showed that neither complex operating techniques nor special corrections were required to obtain accuracy and reproducibility.

The pot life and viscosity of the less viscous castable and sprayable materials were determined from time-viscosity curves using a rotational viscometer. This viscometer was used to measure the thixotropic breakdown of a sample, and was able to determine the viscosity of the material over a very wide range of shear stresses.

The viscosity of each sample was determined at intervals of 10 min. to 3 hours (depending on reactivity) until the end of the pot life was indicated by material gelling.

IV. BOND LINE TENSILE STRENGTH

The bond line tensile and shear strength of the 4130 steel, Fuller 162-Y-22 primer, insulation specimen, SD850-2 liner (if required) and ANB-3254 propellant composite were determined using the double-plate sandwich specimen described in Aerojet Method 3421. The specimens were prepared by bonding the insulation to be tested to steel plates approximately 2.375 in. square. The insulation was lined with SD-850-2 liner (if necessary) and propellant was cast between two plates held parallel in a mold. The cross-section of the composite was approximately 1.75 in.-sq. Then the specimens were stressed to failure in either a tensile or a shear mode (duplicate specimens in each mode) and the failure stress was recorded. The type and location of the failure also was noted. Insulation used in these tests were "as received".

V. WATER ABSORPTION

The moisture absorption and regain characteristics of the insulation materials were determined by drying samples for (24 of each material) of the insulation (approximately 0.080 in. thick) in a 180°F circulating air oven. After constant weight was reached, eight of the samples were removed from the oven and used to prepare specimens for evaluation of bond line tensile and shear strength as described previously in test method IV.

Eight of the samples then were exposed to a controlled relative humidity of 50% at 77°F until constant weight again was achieved. These samples were used to evaluate bond line tensile and shear strength as in IV. The weight gain, weight loss, and bond strength measurements provided an overall assessment of the moisture retention characteristics and effect on bonding of the individual insulation materials. The remaining eight samples were exposed to a controlled 90% relative humidity as described above. These specimens were redried and weighed as described above to determine the amount of the moisture evolved at the higher humidity level.

VI. THERMAL DIFFUSIVITY AND THERMAL CONDUCTIVITY

The flash method was used to determine the thermal diffusivity of insulation material specimens. In this method, a very short pulse of radiant energy was directed at the front of a specimen and the resultant history of the rear surface was recorded. This method, which measured diffusivity from ambient temperature in air up to 1400°F used a resistance furnace to heat the specimen and a thermocouple as the rear-surface temperature detector. Thermal conductivity was calculated from the measured density, specific heat, and diffusivity values.

VII. THERMOGRAVIMETRIC ANALYSIS (TGA)

A thermogravimetric (TGA) balance was used to study the weight loss and temperature as a function of time of insulation samples. The apparatus consisted of an automatic recording balance and a heavy duty furnace. A linear heating rate of 20°C/min. was used up to a maximum temperature of 800°C. Testing was conducted in an argon atmosphere.

VIII. HEAT CAPACITY (SPECIFIC HEAT)

A calorimeter was used to determine the heat capacity of insulation materials. The material samples were heated to the desired temperature with an electric, multiple-tube furnace and dropped into distilled water in the calorimeter. The temperature of the system at equilibrium was observed and used to calculate the material enthalpy. Initially, the calorimeter was calibrated using a known weight of copper or zinc. The mean specific heat was obtained from the slope of the enthalpy ( $\Delta H$ ) temperature curve. Instantaneous specific heats were approximated closely by plotting the slopes of  $\Delta H$  vs temperature at small intervals along the curve.


IX. HEAT OF COMBUSTION

The material heat of combustion was determined by the standard bomb calorimeter technique. A known weight of sample was reacted with oxygen in a "bomb" type of calorimeter and the heat balance at equilibrium was used to calculate the heat of combustion for the material.

NASA CR-72581

## APPENDIX II

### ENGINEERING DRAWINGS FOR LMISD TEST MOTOR




- NOTES:
- 1 REMOVE ALL BURRS AND SHARP EDGES.
  - 2 REMOVE ALL FLASH AND LOOSE-HANGING MATERIAL.
  - 3 INTERPRET DRAWING PER MIL-D-1000.
  - 4 MARK PER ASB 5275-H WITH 1146899 AND APPLICABLE DASH NUMBER.
  - 5 PER AGC-1 INSERT TO 1146899-9 CLOSURE AND AGC-34151-1 ADHESIVE.
  - 6 INSULATION SPECIMENS SHALL BE PROCESSED IN ACCORDANCE WITH AN APPROVED AGC PROCEDURE; THE MATERIALS TO BE PROCESSED WILL BE SPECIFIED BY THE PROJECT MANAGER.
  - 7 ACCEPTABLE MATERIALS:
    - FR-5525, VLSI EPOXY RESIN, DGE, DGE BT, DGE 27129.
    - FR-5525, VLSI EPOXY RESIN, DGE, DGE BT, DGE 27129.
    - FR-5525, VLSI EPOXY RESIN, DGE, DGE BT, DGE 27129.
  - 8 PER AGC-1 INSERT TO 1146899-9 CLOSURE AND AGC-34151-1 ADHESIVE ON -3 THROAT AS FOLLOWS:
    - A. APPLY BRUSH COAT OF MIL-R-9239 PHENOLIC RESIN TO INTERFACE SURFACE OF -3 THROAT.
    - B. WRAP ASBESTOS-PHENOLIC ON -3 THROAT TO 3/16" THICKNESS SUFFICIENT TO FILL GAPS BETWEEN -3 THROAT AND -3 THROAT.
    - C. APPLY BRUSH COAT OF MIL-R-9239 PHENOLIC RESIN TO MINIMUM OF 300 TO 325 F, AS DETERMINED BY THERMOUPLE.
    - D. MACHINING TO FINAL DIMENSIONS PERMISSIBLE.

QTY	DESCRIPTION	UNIT	REVISION	DATE	BY	CHKD
1	PHENOLIC INSULATION					
1	ADHESIVE					
1	INSERT					
4	INSERTIONS SPECIMENS					
1	1146899 CLOSURE					
1	-3 THROAT					
1	INSERT					
1	ATJ GRAPHITE					

REV	DATE	DESCRIPTION
1	11/11/69	ISSUED FOR MANUFACTURE
2	11/11/69	ISSUED FOR MANUFACTURE
3	11/11/69	ISSUED FOR MANUFACTURE
4	11/11/69	ISSUED FOR MANUFACTURE
5	11/11/69	ISSUED FOR MANUFACTURE
6	11/11/69	ISSUED FOR MANUFACTURE
7	11/11/69	ISSUED FOR MANUFACTURE
8	11/11/69	ISSUED FOR MANUFACTURE
9	11/11/69	ISSUED FOR MANUFACTURE
10	11/11/69	ISSUED FOR MANUFACTURE
11	11/11/69	ISSUED FOR MANUFACTURE
12	11/11/69	ISSUED FOR MANUFACTURE
13	11/11/69	ISSUED FOR MANUFACTURE
14	11/11/69	ISSUED FOR MANUFACTURE
15	11/11/69	ISSUED FOR MANUFACTURE
16	11/11/69	ISSUED FOR MANUFACTURE
17	11/11/69	ISSUED FOR MANUFACTURE
18	11/11/69	ISSUED FOR MANUFACTURE
19	11/11/69	ISSUED FOR MANUFACTURE
20	11/11/69	ISSUED FOR MANUFACTURE
21	11/11/69	ISSUED FOR MANUFACTURE
22	11/11/69	ISSUED FOR MANUFACTURE
23	11/11/69	ISSUED FOR MANUFACTURE
24	11/11/69	ISSUED FOR MANUFACTURE
25	11/11/69	ISSUED FOR MANUFACTURE
26	11/11/69	ISSUED FOR MANUFACTURE
27	11/11/69	ISSUED FOR MANUFACTURE
28	11/11/69	ISSUED FOR MANUFACTURE
29	11/11/69	ISSUED FOR MANUFACTURE
30	11/11/69	ISSUED FOR MANUFACTURE
31	11/11/69	ISSUED FOR MANUFACTURE
32	11/11/69	ISSUED FOR MANUFACTURE
33	11/11/69	ISSUED FOR MANUFACTURE
34	11/11/69	ISSUED FOR MANUFACTURE
35	11/11/69	ISSUED FOR MANUFACTURE
36	11/11/69	ISSUED FOR MANUFACTURE
37	11/11/69	ISSUED FOR MANUFACTURE
38	11/11/69	ISSUED FOR MANUFACTURE
39	11/11/69	ISSUED FOR MANUFACTURE
40	11/11/69	ISSUED FOR MANUFACTURE
41	11/11/69	ISSUED FOR MANUFACTURE
42	11/11/69	ISSUED FOR MANUFACTURE
43	11/11/69	ISSUED FOR MANUFACTURE
44	11/11/69	ISSUED FOR MANUFACTURE
45	11/11/69	ISSUED FOR MANUFACTURE
46	11/11/69	ISSUED FOR MANUFACTURE
47	11/11/69	ISSUED FOR MANUFACTURE
48	11/11/69	ISSUED FOR MANUFACTURE
49	11/11/69	ISSUED FOR MANUFACTURE
50	11/11/69	ISSUED FOR MANUFACTURE
51	11/11/69	ISSUED FOR MANUFACTURE
52	11/11/69	ISSUED FOR MANUFACTURE
53	11/11/69	ISSUED FOR MANUFACTURE
54	11/11/69	ISSUED FOR MANUFACTURE
55	11/11/69	ISSUED FOR MANUFACTURE
56	11/11/69	ISSUED FOR MANUFACTURE
57	11/11/69	ISSUED FOR MANUFACTURE
58	11/11/69	ISSUED FOR MANUFACTURE
59	11/11/69	ISSUED FOR MANUFACTURE
60	11/11/69	ISSUED FOR MANUFACTURE
61	11/11/69	ISSUED FOR MANUFACTURE
62	11/11/69	ISSUED FOR MANUFACTURE
63	11/11/69	ISSUED FOR MANUFACTURE
64	11/11/69	ISSUED FOR MANUFACTURE
65	11/11/69	ISSUED FOR MANUFACTURE
66	11/11/69	ISSUED FOR MANUFACTURE
67	11/11/69	ISSUED FOR MANUFACTURE
68	11/11/69	ISSUED FOR MANUFACTURE
69	11/11/69	ISSUED FOR MANUFACTURE
70	11/11/69	ISSUED FOR MANUFACTURE
71	11/11/69	ISSUED FOR MANUFACTURE
72	11/11/69	ISSUED FOR MANUFACTURE
73	11/11/69	ISSUED FOR MANUFACTURE
74	11/11/69	ISSUED FOR MANUFACTURE
75	11/11/69	ISSUED FOR MANUFACTURE
76	11/11/69	ISSUED FOR MANUFACTURE
77	11/11/69	ISSUED FOR MANUFACTURE
78	11/11/69	ISSUED FOR MANUFACTURE
79	11/11/69	ISSUED FOR MANUFACTURE
80	11/11/69	ISSUED FOR MANUFACTURE
81	11/11/69	ISSUED FOR MANUFACTURE
82	11/11/69	ISSUED FOR MANUFACTURE
83	11/11/69	ISSUED FOR MANUFACTURE
84	11/11/69	ISSUED FOR MANUFACTURE
85	11/11/69	ISSUED FOR MANUFACTURE
86	11/11/69	ISSUED FOR MANUFACTURE
87	11/11/69	ISSUED FOR MANUFACTURE
88	11/11/69	ISSUED FOR MANUFACTURE
89	11/11/69	ISSUED FOR MANUFACTURE
90	11/11/69	ISSUED FOR MANUFACTURE
91	11/11/69	ISSUED FOR MANUFACTURE
92	11/11/69	ISSUED FOR MANUFACTURE
93	11/11/69	ISSUED FOR MANUFACTURE
94	11/11/69	ISSUED FOR MANUFACTURE
95	11/11/69	ISSUED FOR MANUFACTURE
96	11/11/69	ISSUED FOR MANUFACTURE
97	11/11/69	ISSUED FOR MANUFACTURE
98	11/11/69	ISSUED FOR MANUFACTURE
99	11/11/69	ISSUED FOR MANUFACTURE
100	11/11/69	ISSUED FOR MANUFACTURE



- NOTES:
- 1 REMOVE ALL BURRS AND SHARP EDGES, EQUIVALENT TO Q30.8 MAXIMUM, INSIDE SURFACES, Q30.8 MAXIMUM, UNLESS OTHERWISE NOTED.
  - 2 INTERPLOT DRAWING PER MIL-D-10900.
  - 3 SURFACE FINISH WITH FINISH AND APPLICABLE DASH NO. AND ASSIGNED SERIAL NUMBER.
  - 4 SURFACE ROUGHNESS 250/ UNLESS OTHERWISE NOTED.
  - 5 WELD PER ASME BOILER AND PRESSURE-VESSEL CODE, SECTION VIII AND VESSEL CODE, SECTION III, TYPE MIL-70-16.
  - 6 RADIOGRAPHICALLY INSPECT ALL WELDS PER ASME BOILER AND PRESSURE-VESSEL CODE, SECTION III, PARA 824, USING VACUUM TUBE GENERATED RADIATION.
  - 7 FINISH UNFINISHED SURFACES OF ALL WELDS AND EXTERIOR SURFACES ALL PRESSURE-VESSEL SURFACES AND ALL WELDS PER ASME BOILER AND PRESSURE-VESSEL CODE, SECTION III, PARA 828, USING WET PARTICLE WITH AG-302N.
  - 8 APPLY MIL-P-8558, GRADE 3, CORROSION PREVENTIVE COMPOUND IN ACCORDANCE WITH AG-302N.
  - 9 APPLY MIL-P-855, ZINC CHROMATE PRIMER TO EXTERIOR SURFACES IN ACCORDANCE WITH AG-3027. OMITTING PRETREATMENT REQUIREMENTS AS SPECIFIED IN PARA. 3.1.

APPLIC. BI	PRIMER	MIL-P-8558
AMANI	WELD ROD	WEL-1000/16
AMANI	CORROSION PREVENTIVE COMPOUND	WEL-1000/16 OR WEL-1000/16 MIL-C-10075
11	-3	FLANGE
11	-1	CLOSURE
11		STEEL
11		QQ-S-741

APPLIC. BI	PRIMER	MIL-P-8558
AMANI	WELD ROD	WEL-1000/16
AMANI	CORROSION PREVENTIVE COMPOUND	WEL-1000/16 OR WEL-1000/16 MIL-C-10075
11	-3	FLANGE
11	-1	CLOSURE
11		STEEL
11		QQ-S-741

APPLIC. BI	PRIMER	MIL-P-8558
AMANI	WELD ROD	WEL-1000/16
AMANI	CORROSION PREVENTIVE COMPOUND	WEL-1000/16 OR WEL-1000/16 MIL-C-10075
11	-3	FLANGE
11	-1	CLOSURE
11		STEEL
11		QQ-S-741


APPLIC. BI	PRIMER	MIL-P-8558
AMANI	WELD ROD	WEL-1000/16
AMANI	CORROSION PREVENTIVE COMPOUND	WEL-1000/16 OR WEL-1000/16 MIL-C-10075
11	-3	FLANGE
11	-1	CLOSURE
11		STEEL
11		QQ-S-741











- REVISIONS:
- 1 REMOVE FLASHING.
  - 2 INTERPRET DRAWING PER MIL-D-1000.
  - 3 MARK PER ASS'N 2113-H WITH DIMENSIONAL APPLICABLE DASH NO. AND ASSIGNED SERIAL NUMBER.
  - 4 CLEAN CAP AND RUBBER SHEET BY SOLVENT WIPING PRIOR TO BONDING.
  - 5 INSULATE CAP BY BUILDING UP FIVE PLIES OF 0.20 THICK MS 1138 WITH AGC-34151-1 ADHESIVE PER AGC-36433.


NO.	REV.	DATE	BY	CHKD.	DESCRIPTION
1	E	11/11/68	WJL	WJL	REVISED TO SHOW 1/16 INCH CAP
2	D	11/11/68	WJL	WJL	REVISED TO SHOW 1/16 INCH CAP
3	C	11/11/68	WJL	WJL	REVISED TO SHOW 1/16 INCH CAP
4	B	11/11/68	WJL	WJL	REVISED TO SHOW 1/16 INCH CAP
5	A	11/11/68	WJL	WJL	REVISED TO SHOW 1/16 INCH CAP

ADHESIVE	EPOXY 921	ASC-34151-1
INSULATION	RUBBER	INS/ISS CLASS
INSULATION	SO THICK	
1/16 INCH	CAP	

PART NAME	CAP INSULATED - LM5D TEST MOTOR
DRAWING NO.	1146904
REV.	E
DATE	11/11/68
BY	WJL
CHKD.	WJL
APP'D.	
SCALE	AS SHOWN
SHEET NO.	1 OF 1




- NOT:
- 1 REMOVE ALL BURRS AND SHARP EDGES.
  - 2 INTERPRET DRAWING PER MIL-D-1000.
  - 3 MARK OFF SPECIFICATIONS WITH 1146905, APPLICABLE DASH NO. AND ASSIGNED SERIAL NO.
  - 4 SURFACE ROUGHNESS 250 / UNLESS OTHERWISE NOTED.
  - 5 WELD PER ASME BOILER AND PRESSURE VESSEL CODE, SECTION VIII AND II, TYPE WELDED JOINT PER MIL-E-22200, 'B', TYPE WELDED JOINT PER MIL-E-18038, 'A'.
  - 6 PRESSURE VESSEL CODE, SECTION VIII, PART 5, USING MAGNUM TUBE GENERATED RADIATION.
  - 7 MAGNETIC PARTICLE INSPECT ALL INTERIOR AND EXTERIOR SURFACES. ALL PRESSURE VESSEL CODE, SECTION VIII, PART 5, USING NET PARTICLE PROCESS.
  - 8 CLEAN CHAMBER AND RUBBER SHEETS BY SOLVENT WIPING PRIOR TO BONDING.
- A INSULATE CHAMBER BY BUILDING UP FIVE PILES OF .200 THICK RUBBER AND FIVE PILES OF .200 THICK INSULATION PER MIL-E-22200, 'B', TYPE WELDED JOINT PER MIL-E-18038, 'A'. LONGITUDINAL JOINTS SHALL BE STAGGERED NO LESS THAN 1.0 BETWEEN PILES.
- B APPLY MIL-C-15193, GRADE 3, CORROSION PREVENTIVE COMPOUND IN ACCORDANCE WITH ACC-3424 TO -19 AND -20 ASSY.
- C APPLY MIL-P-2845 ZINC CHROMATE PRIMER TO EXTERIOR SURFACES IN ACCORDANCE WITH ACC-3027, DRIFTING PRETREATMENT REQUIREMENTS AS SPECIFIED IN PARA. 3.11.

ITEM	QTY	DESCRIPTION	REF	UNIT
1	1	CHAMBER INSULATED-UMISO TEST MOTOR		
2	1	CHAMBER INSULATED-UMISO TEST MOTOR		
3	1	CHAMBER INSULATED-UMISO TEST MOTOR		
4	1	CHAMBER INSULATED-UMISO TEST MOTOR		
5	1	CHAMBER INSULATED-UMISO TEST MOTOR		
6	1	CHAMBER INSULATED-UMISO TEST MOTOR		
7	1	CHAMBER INSULATED-UMISO TEST MOTOR		
8	1	CHAMBER INSULATED-UMISO TEST MOTOR		
9	1	CHAMBER INSULATED-UMISO TEST MOTOR		
10	1	CHAMBER INSULATED-UMISO TEST MOTOR		
11	1	CHAMBER INSULATED-UMISO TEST MOTOR		
12	1	CHAMBER INSULATED-UMISO TEST MOTOR		
13	1	CHAMBER INSULATED-UMISO TEST MOTOR		
14	1	CHAMBER INSULATED-UMISO TEST MOTOR		
15	1	CHAMBER INSULATED-UMISO TEST MOTOR		
16	1	CHAMBER INSULATED-UMISO TEST MOTOR		
17	1	CHAMBER INSULATED-UMISO TEST MOTOR		
18	1	CHAMBER INSULATED-UMISO TEST MOTOR		
19	1	CHAMBER INSULATED-UMISO TEST MOTOR		
20	1	CHAMBER INSULATED-UMISO TEST MOTOR		
21	1	CHAMBER INSULATED-UMISO TEST MOTOR		
22	1	CHAMBER INSULATED-UMISO TEST MOTOR		
23	1	CHAMBER INSULATED-UMISO TEST MOTOR		
24	1	CHAMBER INSULATED-UMISO TEST MOTOR		
25	1	CHAMBER INSULATED-UMISO TEST MOTOR		
26	1	CHAMBER INSULATED-UMISO TEST MOTOR		
27	1	CHAMBER INSULATED-UMISO TEST MOTOR		
28	1	CHAMBER INSULATED-UMISO TEST MOTOR		
29	1	CHAMBER INSULATED-UMISO TEST MOTOR		
30	1	CHAMBER INSULATED-UMISO TEST MOTOR		
31	1	CHAMBER INSULATED-UMISO TEST MOTOR		
32	1	CHAMBER INSULATED-UMISO TEST MOTOR		
33	1	CHAMBER INSULATED-UMISO TEST MOTOR		
34	1	CHAMBER INSULATED-UMISO TEST MOTOR		
35	1	CHAMBER INSULATED-UMISO TEST MOTOR		
36	1	CHAMBER INSULATED-UMISO TEST MOTOR		
37	1	CHAMBER INSULATED-UMISO TEST MOTOR		
38	1	CHAMBER INSULATED-UMISO TEST MOTOR		
39	1	CHAMBER INSULATED-UMISO TEST MOTOR		
40	1	CHAMBER INSULATED-UMISO TEST MOTOR		
41	1	CHAMBER INSULATED-UMISO TEST MOTOR		
42	1	CHAMBER INSULATED-UMISO TEST MOTOR		
43	1	CHAMBER INSULATED-UMISO TEST MOTOR		
44	1	CHAMBER INSULATED-UMISO TEST MOTOR		
45	1	CHAMBER INSULATED-UMISO TEST MOTOR		
46	1	CHAMBER INSULATED-UMISO TEST MOTOR		
47	1	CHAMBER INSULATED-UMISO TEST MOTOR		
48	1	CHAMBER INSULATED-UMISO TEST MOTOR		
49	1	CHAMBER INSULATED-UMISO TEST MOTOR		
50	1	CHAMBER INSULATED-UMISO TEST MOTOR		
51	1	CHAMBER INSULATED-UMISO TEST MOTOR		
52	1	CHAMBER INSULATED-UMISO TEST MOTOR		
53	1	CHAMBER INSULATED-UMISO TEST MOTOR		
54	1	CHAMBER INSULATED-UMISO TEST MOTOR		
55	1	CHAMBER INSULATED-UMISO TEST MOTOR		
56	1	CHAMBER INSULATED-UMISO TEST MOTOR		
57	1	CHAMBER INSULATED-UMISO TEST MOTOR		
58	1	CHAMBER INSULATED-UMISO TEST MOTOR		
59	1	CHAMBER INSULATED-UMISO TEST MOTOR		
60	1	CHAMBER INSULATED-UMISO TEST MOTOR		
61	1	CHAMBER INSULATED-UMISO TEST MOTOR		
62	1	CHAMBER INSULATED-UMISO TEST MOTOR		
63	1	CHAMBER INSULATED-UMISO TEST MOTOR		
64	1	CHAMBER INSULATED-UMISO TEST MOTOR		
65	1	CHAMBER INSULATED-UMISO TEST MOTOR		
66	1	CHAMBER INSULATED-UMISO TEST MOTOR		
67	1	CHAMBER INSULATED-UMISO TEST MOTOR		
68	1	CHAMBER INSULATED-UMISO TEST MOTOR		
69	1	CHAMBER INSULATED-UMISO TEST MOTOR		
70	1	CHAMBER INSULATED-UMISO TEST MOTOR		
71	1	CHAMBER INSULATED-UMISO TEST MOTOR		
72	1	CHAMBER INSULATED-UMISO TEST MOTOR		
73	1	CHAMBER INSULATED-UMISO TEST MOTOR		
74	1	CHAMBER INSULATED-UMISO TEST MOTOR		
75	1	CHAMBER INSULATED-UMISO TEST MOTOR		
76	1	CHAMBER INSULATED-UMISO TEST MOTOR		
77	1	CHAMBER INSULATED-UMISO TEST MOTOR		
78	1	CHAMBER INSULATED-UMISO TEST MOTOR		
79	1	CHAMBER INSULATED-UMISO TEST MOTOR		
80	1	CHAMBER INSULATED-UMISO TEST MOTOR		
81	1	CHAMBER INSULATED-UMISO TEST MOTOR		
82	1	CHAMBER INSULATED-UMISO TEST MOTOR		
83	1	CHAMBER INSULATED-UMISO TEST MOTOR		
84	1	CHAMBER INSULATED-UMISO TEST MOTOR		
85	1	CHAMBER INSULATED-UMISO TEST MOTOR		
86	1	CHAMBER INSULATED-UMISO TEST MOTOR		
87	1	CHAMBER INSULATED-UMISO TEST MOTOR		
88	1	CHAMBER INSULATED-UMISO TEST MOTOR		
89	1	CHAMBER INSULATED-UMISO TEST MOTOR		
90	1	CHAMBER INSULATED-UMISO TEST MOTOR		
91	1	CHAMBER INSULATED-UMISO TEST MOTOR		
92	1	CHAMBER INSULATED-UMISO TEST MOTOR		
93	1	CHAMBER INSULATED-UMISO TEST MOTOR		
94	1	CHAMBER INSULATED-UMISO TEST MOTOR		
95	1	CHAMBER INSULATED-UMISO TEST MOTOR		
96	1	CHAMBER INSULATED-UMISO TEST MOTOR		
97	1	CHAMBER INSULATED-UMISO TEST MOTOR		
98	1	CHAMBER INSULATED-UMISO TEST MOTOR		
99	1	CHAMBER INSULATED-UMISO TEST MOTOR		
100	1	CHAMBER INSULATED-UMISO TEST MOTOR		







- NOTE:**
- 1 BOND -5 TUBE TO -11 AFT ENC WITH AGC-34265 WRAP WITH 1.00 INCH WIDE PRESSURE SENSITIVE INDUSTRIAL TAPE WITH THREE CONTINUOUS WRAPS. BOTH ENDS AS SHOWN.
  - 2 BOND WITH AGC-34103 CEMENT.
  - 3 SEAL TUBE WITH WS1076 SEALANT.
  - 4 APPLY AGC-3089-1 PRIMER TO CLEANED SURFACE BY BRUSHING OR DIPPING.
  - 5 MAINTAIN A TEMPERATURE OF 70° ± 30°F ON 114389 ASSEMBLY.
  - 6 BOND STYROFOAM TO PAPERBOARD USING WS-1076 SEALANT.
  - 8 MARK PER ASD5215-N WITH 1143989-8.

REV	DATE	DESCRIPTION	BY	CHKD
1	70272	HERCULES MARK 2		
2	06202	160 MAX DIA		
3	06202	160 MAX DIA		
4		HERCULES MARK 2		
5		160 MAX DIA		
6		160 MAX DIA		
7		160 MAX DIA		
8		160 MAX DIA		
9		160 MAX DIA		
10		160 MAX DIA		
11		160 MAX DIA		

REV	DATE	DESCRIPTION	BY	CHKD
1		SEALANT	WS-1076	
2		PRIMER	AGC-34089-1	
3		CEMENT	AGC-34265	
4		KRAFT WRAPPING PAPER	UU-P-268	
5		CEMENT	AGC-34103	
6		1 INCH WIDE PRESSURE SENSITIVE INDUSTRIAL TAPE	CL-1	
7		PAPERBOARD END AFT	COML GR	
8		STYROFOAM SUPPORT, RIGID		
9		CELLULOSE ACETATE BUTYRATE	TULON T-800	
10		PAPERBOARD END FWD	COML GR	
11		STYROFOAM SUPPORT, RIGID		

REV	DATE	DESCRIPTION	BY	CHKD
1		STYROFOAM SUPPORT, RIGID		
2		CELLULOSE ACETATE BUTYRATE	TULON T-800	
3		PAPERBOARD END FWD	COML GR	
4		STYROFOAM SUPPORT, RIGID		
5		CELLULOSE ACETATE BUTYRATE	TULON T-800	
6		PAPERBOARD END FWD	COML GR	
7		STYROFOAM SUPPORT, RIGID		
8		CELLULOSE ACETATE BUTYRATE	TULON T-800	
9		PAPERBOARD END FWD	COML GR	
10		STYROFOAM SUPPORT, RIGID		
11		CELLULOSE ACETATE BUTYRATE	TULON T-800	
12		PAPERBOARD END FWD	COML GR	

REV	DATE	DESCRIPTION	BY	CHKD
1		CELLULOSE ACETATE BUTYRATE	TULON T-800	
2		PAPERBOARD END FWD	COML GR	
3		STYROFOAM SUPPORT, RIGID		
4		CELLULOSE ACETATE BUTYRATE	TULON T-800	
5		PAPERBOARD END FWD	COML GR	
6		STYROFOAM SUPPORT, RIGID		
7		CELLULOSE ACETATE BUTYRATE	TULON T-800	
8		PAPERBOARD END FWD	COML GR	
9		STYROFOAM SUPPORT, RIGID		
10		CELLULOSE ACETATE BUTYRATE	TULON T-800	
11		PAPERBOARD END FWD	COML GR	
12		STYROFOAM SUPPORT, RIGID		
13		CELLULOSE ACETATE BUTYRATE	TULON T-800	
14		PAPERBOARD END FWD	COML GR	
15		STYROFOAM SUPPORT, RIGID		
16		CELLULOSE ACETATE BUTYRATE	TULON T-800	
17		PAPERBOARD END FWD	COML GR	
18		STYROFOAM SUPPORT, RIGID		
19		CELLULOSE ACETATE BUTYRATE	TULON T-800	
20		PAPERBOARD END FWD	COML GR	
21		STYROFOAM SUPPORT, RIGID		
22		CELLULOSE ACETATE BUTYRATE	TULON T-800	
23		PAPERBOARD END FWD	COML GR	
24		STYROFOAM SUPPORT, RIGID		
25		CELLULOSE ACETATE BUTYRATE	TULON T-800	
26		PAPERBOARD END FWD	COML GR	
27		STYROFOAM SUPPORT, RIGID		
28		CELLULOSE ACETATE BUTYRATE	TULON T-800	
29		PAPERBOARD END FWD	COML GR	
30		STYROFOAM SUPPORT, RIGID		
31		CELLULOSE ACETATE BUTYRATE	TULON T-800	
32		PAPERBOARD END FWD	COML GR	
33		STYROFOAM SUPPORT, RIGID		
34		CELLULOSE ACETATE BUTYRATE	TULON T-800	
35		PAPERBOARD END FWD	COML GR	
36		STYROFOAM SUPPORT, RIGID		
37		CELLULOSE ACETATE BUTYRATE	TULON T-800	
38		PAPERBOARD END FWD	COML GR	
39		STYROFOAM SUPPORT, RIGID		
40		CELLULOSE ACETATE BUTYRATE	TULON T-800	
41		PAPERBOARD END FWD	COML GR	
42		STYROFOAM SUPPORT, RIGID		
43		CELLULOSE ACETATE BUTYRATE	TULON T-800	
44		PAPERBOARD END FWD	COML GR	
45		STYROFOAM SUPPORT, RIGID		
46		CELLULOSE ACETATE BUTYRATE	TULON T-800	
47		PAPERBOARD END FWD	COML GR	
48		STYROFOAM SUPPORT, RIGID		
49		CELLULOSE ACETATE BUTYRATE	TULON T-800	
50		PAPERBOARD END FWD	COML GR	
51		STYROFOAM SUPPORT, RIGID		
52		CELLULOSE ACETATE BUTYRATE	TULON T-800	
53		PAPERBOARD END FWD	COML GR	
54		STYROFOAM SUPPORT, RIGID		
55		CELLULOSE ACETATE BUTYRATE	TULON T-800	
56		PAPERBOARD END FWD	COML GR	
57		STYROFOAM SUPPORT, RIGID		
58		CELLULOSE ACETATE BUTYRATE	TULON T-800	
59		PAPERBOARD END FWD	COML GR	
60		STYROFOAM SUPPORT, RIGID		
61		CELLULOSE ACETATE BUTYRATE	TULON T-800	
62		PAPERBOARD END FWD	COML GR	
63		STYROFOAM SUPPORT, RIGID		
64		CELLULOSE ACETATE BUTYRATE	TULON T-800	
65		PAPERBOARD END FWD	COML GR	
66		STYROFOAM SUPPORT, RIGID		
67		CELLULOSE ACETATE BUTYRATE	TULON T-800	
68		PAPERBOARD END FWD	COML GR	
69		STYROFOAM SUPPORT, RIGID		
70		CELLULOSE ACETATE BUTYRATE	TULON T-800	
71		PAPERBOARD END FWD	COML GR	
72		STYROFOAM SUPPORT, RIGID		
73		CELLULOSE ACETATE BUTYRATE	TULON T-800	
74		PAPERBOARD END FWD	COML GR	
75		STYROFOAM SUPPORT, RIGID		
76		CELLULOSE ACETATE BUTYRATE	TULON T-800	
77		PAPERBOARD END FWD	COML GR	
78		STYROFOAM SUPPORT, RIGID		
79		CELLULOSE ACETATE BUTYRATE	TULON T-800	
80		PAPERBOARD END FWD	COML GR	
81		STYROFOAM SUPPORT, RIGID		
82		CELLULOSE ACETATE BUTYRATE	TULON T-800	
83		PAPERBOARD END FWD	COML GR	
84		STYROFOAM SUPPORT, RIGID		
85		CELLULOSE ACETATE BUTYRATE	TULON T-800	
86		PAPERBOARD END FWD	COML GR	
87		STYROFOAM SUPPORT, RIGID		
88		CELLULOSE ACETATE BUTYRATE	TULON T-800	
89		PAPERBOARD END FWD	COML GR	
90		STYROFOAM SUPPORT, RIGID		
91		CELLULOSE ACETATE BUTYRATE	TULON T-800	
92		PAPERBOARD END FWD	COML GR	
93		STYROFOAM SUPPORT, RIGID		
94		CELLULOSE ACETATE BUTYRATE	TULON T-800	
95		PAPERBOARD END FWD	COML GR	
96		STYROFOAM SUPPORT, RIGID		
97		CELLULOSE ACETATE BUTYRATE	TULON T-800	
98		PAPERBOARD END FWD	COML GR	
99		STYROFOAM SUPPORT, RIGID		
100		CELLULOSE ACETATE BUTYRATE	TULON T-800	

1143989-8  
 MOTOR IGNITER  
 ASSY  
 1143989  
 SCALE: 1:1  
 RELEASE DATE: 11/27/57  
 SHEET NO. 2

PC 399 CC #4  
 231-1-1  
 DRAWING LEVEL  
 PART NEXT FINAL NEXT ASSEMBLY USED ON  
 NO. 1143989 APPLICATION  
 WTS. USED

1143989-8  
 MOTOR IGNITER  
 ASSY  
 1143989  
 SCALE: 1:1  
 RELEASE DATE: 11/27/57  
 SHEET NO. 2



APPENDIX III

INDIVIDUAL INSULATION MATERIAL  
SPECIMEN PRE- AND POSTTEST PROFILES  
FOR MOTORS S/N I-1, I-2, AND I-3A

FIGURE LIST

	<u>Figure</u>
Motor S/N I-1, 0° - V-44 Specimen Profile	1
Motor S/N I-1, 45° - IBS-108 Specimen Profile	2
Motor S/N I-1, 90° - V-61 Specimen Profile	3
Motor S/N I-1, 135° - IBS-107 Specimen Profile	4
Motor S/N I-1, 180° - IBT-100 Specimen Profile	5
Motor S/N I-1, 225° - IBC-101 Specimen Profile	6
Motor S/N I-1, 270° - IBT-106 Specimen Profile	7
Motor S/N I-1, 315° - IBS-109 Specimen Profile	8
Motor S/N I-2, 0° - V-44 Specimen Profile	9
Motor S/N I-2, 45° - 40SD-80 Specimen Profile	10
Motor S/N I-2, 90° - V-61 Specimen Profile	11
Motor S/N I-2, 135° - Avcoat II Specimen Profile	12
Motor S/N I-2, 180° - RTV-511 Specimen Profile	13
Motor S/N I-2, 225° - PR1933-2 Specimen Profile	14
Motor S/N I-2, 270° - TBS-758 Specimen Profile	15
Motor S/N I-2, 315° - IBC-111 Specimen Profile	16
Motor S/N I-3A, 0° - V-44 Specimen Profile	17
Motor S/N I-3A, 45° - V-61/II-H704B Specimen Profile	18
Motor S/N I-3A, 90° - USR-3800 Specimen Profile	19
Motor S/N I-3A, 135° - ORCO-9250 Specimen Profile	20
Motor S/N I-3A, 180° - IBT-100 Specimen Profile	21
Motor S/N I-3A, 225° - Gen Gard 4011 Specimen Profile	22
Motor S/N I-3A, 270° - Avcoat 8021 Specimen Profile	23
Motor S/N I-3A, 315° - USR-3804 Specimen Profile	24






Figure 1

Motor S/N I-1, 0° - V-44 Specimen Profile




Motor S/N I-1, 45° - IBS-108 Specimen Profile

Figure 2




Motor S/N I-1, 90° - V-61 Specimen Profile

Figure 3




Motor S/N I-1, 135° - IBS-107 Specimen Profile

Figure 4



Motor S/N I-1, 180° - IBT-100 Specimen Profile


Figure 5



Motor S/N I-1, 225° - IBC-101 Specimen Profile


Figure 6






Motor S/N I-1, 270° - IBT-106 Specimen Profile

Figure 7




Motor S/N I-1, 315 ° - IBS-109 Specimen Profile

Figure 8




Motor S/N I-2, 0° - V-44 Specimen Profile

Figure 9




Motor S/N I-2, 45° - 40SD-80 Specimen Profile

Figure 10




Motor S/N I-2, 90° - V-61 Specimen Profile

Figure 11




Motor S/N I-2, 135° - Avcoat III Specimen Profile

Figure 12



Motor S/N I-2, 180° - RTV-511 Specimen Profile


Figure 13



Motor S/N I-2, 225° - PR1933-2 Specimen Profile


Figure 14






Motor S/N I-2, 270° - TBS-758 Specimen Profile

Figure 15




Motor S/N I-2, 315° - IBC-111 Specimen Profile

Figure 16




Motor S/N I-3A, 0° - V-44 Specimen Profile

Figure 17




Motor S/N I-3A, 45° - V-61/TI-H704B Specimen Profile

Figure 18




Motor S/N I-3A, 90° - USR-3800 Specimen Profile

Figure 19




Motor S/N I-3A, 135° - ORCO-9250 Specimen Profile

Figure 20



Motor S/N I-3A, 180° - IBT-100 Specimen Profile


Figure 21



Motor S/N I-3A, 225° - Gen Gard 4011 Specimen Profile


Figure 22





Motor S/N I-3A, 270° - Avcoat 8021 Specimen Profile

Figure 23



Motor S/N I-3A, 315° - USR 3804 Specimen Profile

Figure 24

## FINAL REPORT DISTRIBUTION LIST

NASA Lewis Research Center 21000 Brookpark Road Cleveland, Ohio 44135 Attn: Contracting Officer Mail Stop 500-313 (1) Solid Rocket Technology Branch Mail Stop 500-205 (8) Technical Library Mail Stop 60-3 (2) Tech. Report Control Office Mail Stop 5-5 (1) J. Kennard Mail Stop 3-17 (1) Tech. Utilization Office Mail Stop 3-19 (1) Patent Counsel Mail Stop 500-311 (1)	NASA George C. Marshall Space Flight Center Redstone Arsenal Huntsville, Alabama, 35812 Attn: Technical Library (1) R-P&VE-PA/K, Chandler (1)
National Aeronautics and Space Administration Washington, D.C. 20546 Attn: RPM/William Cohen (3) RPS/Robert W. Ziem (1) ATSS-AL/Technical Library (2)	Jet Propulsion Laboratory Calif. Institute of Technology 4800 Oak Grove Drive Pasadena, California 91103 Attn: Richard Bailey (1) Technical Library (1)
NASA Ames Research Center Moffett Field, California 94035 Attn: Technical Library (1)	Scientific & Technical Information Facility NASA Representative P.O. Box 33 College Park, Maryland 20740 Attn: CRT (6)
NASA Langley Research Center Langley Station Hampton, Virginia 23365 Attn: Robert L. Swain (1) Technical Library (1)	<u>GOVERNMENT INSTALLATIONS</u>
NASA Goddard Space Flight Center Greenbelt, Maryland 20771 Attn: Technical Library (1)	AF Space Systems Division Air Force Unit Post Office Los Angeles, California 90045 Attn: Col. E. Fink (1)
NASA Manned Spacecraft Center 2101 Webster Seabrook Road Houston, Texas 77058 Attn: (1)	AF Research and Technology Division Bolling AFB, D.C., 20332 Attn: Dr. Leon Green, Jr. (1)
	AF Rocket Propulsion Laboratory Edwards AFB, California 93523 Attn: RPM/Mr. C. Cook (2)
	AF Materials Laboratory Wright-Patterson AFB, Ohio 45433 Attn: MANC/D. Schmidt (1) MAAE (1)

AF Ballistic Missile Division P.O. Box 262 San Bernadino, California Attn: WDSOT	(1)	Chemical Propulsion Information Agency Applied Physics Laboratory 8621 Georgia Avenue Silver Spring, Maryland 20910	(1)
Structures Division Wright Patterson AFB, Ohio 45433 Attn: FDT/R. F. Hoener	(1)	Defense Documentation Center Cameron Station 5010 Duke Street Alexandria, Virginia 22314	(1)
Army Missile Command Redstone Scientific Information Center Redstone Arsenal, Alabama 35809 Attn: Chief, Document Section	(1)	Defense Materials Information Center Battelle Memorial Institute 505 King Avenue Columbus, Ohio 43201	(1)
Ballistic Research Laboratory Aberdeen Proving Ground, Maryland 21005 Attn: Technical Library	(1)	Materials Advisory Board National Academy of Science 2101 Constitution Ave., N.W. Washington, D.C., 20418 Attn: Capt. A. M. Blamphin	(1)
Picatinny Arsenal Dover, New Jersey, 07801 Attn: Technical Library	(1)	Institute for Defense Analysis 1666 Connecticut Ave., N.W. Washington, D.C. Attn: Technical Library	(1)
Navy Special Projects Office Washington, D.C., 20360 Attn: H. Bernstein	(1)	Advanced Research Projects Agency Pentagon, Room 3D154 Washington, D.C., 20301 Attn: Tech. Information Office	(1)
Naval Air Systems Command Washington, D.C. 20360 Attn: AIR-330/Dr. O. H. Johnson	(1)		
Naval Propellant Plant Indian Head, Maryland 20640 Attn: Technical Library	(1)	<u>INDUSTRY CONTRACTORS</u>	
Naval Ordnance Laboratory White Oak Silver Spring, Maryland 20910 Attn: Technical Library	(1)	Aerojet-General Corporation P.O. Box 1168 Solid Rocket Division Sacramento, California 94086 Attn: Dr. B. Simmons Tech. Information Ctr. Space Booster Dept.	(1) (1) (8)
Naval Ordnance Test Station China Lake, California 93557 Attn: Technical Library C. J. Thelen	(1) (1)	Aerojet-General Corporation P.O. Box 296 Azusa, California 91702 Attn: Technical Library	(1)
Naval Research Laboratory Washington, D.C., 20390 Attn: Technical Library	(1)		

Aerospace Corporation 2400 East El Segundo Boulevard El Segundo, California 90245 Attn: Technical Library Solid Motor Dev. Office	(1) (1)	Lockheed Missiles & Space Company P.O. Box 504 Sunnyvale, California Attn: Technical Library	(1)
Aerospace Corporation P.O. Box 95085 Los Angeles, California 90045 Attn: Technical Library	(1)	Lockheed Propulsion Company P.O. Box 111 Redlands, California 93273 Attn: Bud White	(1)
Atlantic Research Corporation Shirley Highway at Edsall Road Alexandria, Virginia 22314 Attn: Technical Library	(1)	Martin Marietta Corporation Baltimore Division Baltimore, Maryland 21203 Attn: Technical Library	(1)
Battelle Memorial Library 505 King Avenue Columbus, Ohio 43201 Attn: Edward Unger	(1)	Mathematical Sciences Corporation 278 Renook Way Arcadia, California 91107 Attn: M. Fourney	(1)
Boeing Company P. O. Box 3999 Seattle, Washington 98124 Attn: Technical Library	(1)	Philco Corporation Aeronutronics Division Ford Road Newport Beach, California 92660 Attn: Technical Library	(1)
Chrysler Corporation Space Division Michoud Operations New Orleans, Louisiana Attn: Technical Library	(1)	Rocketdyne Solid Propulsion Operations P.O. Box 548 McGregor, Texas Attn: Technical Library	(1)
Douglas Missiles & Space Systems Huntington Beach, California Attn: T. J. Gordon	(1)	Rocketdyne 6633 Canoga Avenue Canoga Park, California 91304 Attn: Technical Library	(1)
Hercules, Inc. Allegany Ballistics Laboratory P.O. Box 210 Cumberland, Maryland 21502 Attn: Technical Library	(1)	Rohm and Haas Redstone Arsenal Research Division Huntsville, Alabama 35807 Attn: Technical Library	(1)
Hercules Company Bacchus Works P.O. Box 98 Magna, Utah 84044 Attn: Technical Library	(1)	Rohr Corporation Space Products Division 8200 Arlington Boulevard Riverside, California	(1)
Thiokol Chemical Corporation Wasatch Division Brigham City, Utah 94302 Attn: Dan Hess Technical Library	(1) (1)	TRW Inc. Structures Division 23444 Euclid Avenue Cleveland, Ohio 44117 Attn: L. Russell	(1)

Thiokol Chemical Corporation Elkton Division Elkton, Maryland 21921 Attn: Technical Library	(1)	TRW Systems One Space Park Redondo Beach, California 90278 Attn: M. Lipow	(1)
Thiokol Chemical Corporation Huntsville Division Huntsville, Alabama 35807 Attn: Technical Library	(1)	United Technology Center P.O. Box 358 Sunnyvale, California 94088 Attn: Technical Library	(1)
Uniroyal, Inc. Mishawaka, Indiana 46544 Attn: Mr. D. O. Trok		The B. F. Goodrich Co. Aerospace and Defense Products Div. 1499 Bayshore Highway Burlingame, California Attn: Mr. R. S. Moore, District Manager	
Insulation Technology, Inc.; U.S. Polymeric, Inc. P.O. Box A.D. 3601 Orangerie Way Carmichael, California Attn: Mr. J. C. Boswell		The American Poly-Therm Co. 3574 Western Ave. P.O. Box 38619 Sacramento, California 95838	
AVCO Corp. Space Systems Div. 201 Lowell St. Wilmington, Mass. 01887 Attn: Mr. K. M. Jacobs		AVCO Corp. Lycoming Div. 550 S. Main St. Stratford, Conn. 06497 Attn: Sales Dept.	
Union Carbide Corp. Silicone Div. 2770 Leonis Blvd. Los Angeles (Vernon), Calif. 90058 Attn: Elastomer Materials Dept.		Arrowhead Products 4411 Katella Ave. Los Alamitos, Calif. 90720 Attn: Mr. J. L. E'berly, Chief Engineer	
Narmco Materials Div. 600 Victoria St. Costa Mesa, Calif. Attn: Mr. W. Chester		Kirkhill Rubber Co. Aerospace Div. Brea, Calif. Attn: R. M. Rhoads	
The Goodyear Tire and Rubber Co. Aviation Product Div. 1144 E. Market St. Akron, Ohio Attn: Mr. J. T. Reynolds		West American Rubber Co. 2703 New Jersey Ave. San Jose, Calif. 95124 Attn: Mr. D. E. Ulery	
H. I. Thompson Fiberglass Co. Defense Product Div. 1600 W. 135th St. Gardena, Calif. Attn: Mr. R. I. Cox		Ferro Corp., Cordo Div. 3512-20 Helms Ave. Culver City, Calif 90230 Attn: Mr. M. Scott, Technical Sales	
Raybestos Manhattan, Inc. 168 S. Beaker St. S. San Francisco, Calif. Attn: Mr. N. J. Cox		Fiberite West Coast Corp. 690 No. Lemon St. P.O. Box 738 Orange, Calif. Attn: Mr. H. Christensen	

Dow Corning Corp.  
1299 Bayshore Blvd.  
Burlingame, Calif.  
Attn: Mr. L. C. Diebler

General Electric Co.  
401 Lesser St.  
Oakland, Calif. 94601  
Attn: Mr. F. E. Stanko

Atlantic Research Corp.  
Henry G. Shirley Memorial Highway at  
Edsall Rd.  
Alexandria, Virginia 22314  
Attn: Mr. E. L. Olcott,  
Director Materials Dept.

Garlock, Inc.  
220 E. Grand Ave.  
San Francisco, Calif. 94080  
Attn: Mr. J. W. Wright, Manager

Products Research and Chemical Corp.  
2919 Empire Ave.  
Burbank, Calif 91504  
Attn: Mr. D. Corkill, Manager,  
Engineering Service Dept.

Ohio Rubber Co.  
Ben Hur Ave.  
Willoughby, Ohio 44094  
Attn: Mr. G. S. Hackel,  
Product Sales Manager

Minnesota Mining and Manufacturing Co.  
1210 University Ave.  
St. Paul, Minnesota 55104  
Attn: Mr. J. W. Davis, Plastics Div.

The DeVilbiss Co.  
1335 No. Tenth St.  
San Jose, Calif 95112  
Attn: Mr. W. T. Jacobs