

NATIONAL AERONAUTICS AND SPACE ADMINISTRATION

Technical Memorandum 33-356

*Review of Beryllium Technology
for Spacecraft Applications*

R. G. Moss

GPO PRICE \$ _____

CFSTI PRICE(S) \$ _____

Hard copy (HC) _____ -

Microfiche (MF) _____ -

ff 653 July 65



N 68-33018

(ACCESSION NUMBER)

35 (PAGES)

ck-96319 (NASA CR OR TMX OR AD NUMBER)

(THRU) _____

1 (CODE)

17 (CATEGORY)

FACILITY FORM 602

JET PROPULSION LABORATORY
CALIFORNIA INSTITUTE OF TECHNOLOGY
PASADENA, CALIFORNIA

November 1, 1967

807-53396

NATIONAL AERONAUTICS AND SPACE ADMINISTRATION

Technical Memorandum 33-356

*Review of Beryllium Technology
for Spacecraft Applications*

R. G. Moss

Approved by:

A handwritten signature in cursive script, reading "H. Martens", is written over a horizontal line.

H. Martens, Manager
Materials Section

**JET PROPULSION LABORATORY
CALIFORNIA INSTITUTE OF TECHNOLOGY
PASADENA, CALIFORNIA**

November 1, 1967

TECHNICAL MEMORANDUM 33-356

Copyright © 1967

Jet Propulsion Laboratory
California Institute of Technology

Prepared Under Contract No. NAS 7-100
National Aeronautics & Space Administration

Contents

I. Introduction	1
II. State-of-the-Art	2
A. Fabrication	3
B. Joining	4
C. Beryllium Alloys	5
D. Present Materials Availability	5
E. Anticipated Future Progress	5
III. Recent Programs	6
A. Applications	6
B. Joining	7
C. Fabrication	8
D. Properties of Beryllium	8
E. Beryllium Alloys	8
IV. Conclusions	9
References	10
Bibliography	16

Table

1. Comparative properties of Be and alloys of Ti, Al, and Mg	9
--	---

Abstract

The present status and anticipated future developments in beryllium and beryllium alloys are described. Properties of beryllium together with its advantages and disadvantages are discussed. Current technology and projected progress in fabrication, forming, joining, testing, and applications of beryllium are noted, as are a number of the more important programs in these areas.

Review of Beryllium Technology for Spacecraft Applications

I. Introduction

The purpose of this report is to describe the present status and anticipated future developments in applications of beryllium (Be) and beryllium alloys. The report represents the results of the literature survey portion of a research program being carried out by the Materials Section of the Jet Propulsion Laboratory.

Information reported herein was obtained by surveying pertinent published reports, attendance at meetings and symposia, personal discussions with other workers in these fields, and visits to some of the organizations which are particularly active in the use or development of these materials.

As a result of this extensive survey, it has been possible to draw several conclusions as to the present status, and most likely future progress, in Be and Be alloys. Areas of uncertainty or ambiguity have been identified as well as areas where work remains to be done.

The advantages and disadvantages of Be and Be alloys are discussed, and a brief summary of the present state of the material properties and availability is given. Pitfalls, problems and peculiarities in the testing, forming,

joining and usage of Be are noted together with the developmental status of primary and secondary fabrication techniques. Some of the more important current programs are described, and a projection is made of probable advances in the state-of-the-art. A bibliography of reports on Be is presented herein.

Designers have been reluctant to use Be because of its high cost, variability of product, low ductility, and toxicity. Experience with Be as a structural material was also lacking. This situation is beginning to change. In many cases, cost is not a vital factor; in fact, use of Be may lower overall system costs when weight can be saved. Product reproducibility and reliability have improved significantly in recent years. Toxicity has been controlled successfully by careful attention to proper handling procedures such as collecting dust and chips at the tool bit, filtering air and coolant fluids, and careful maintenance of high standards of cleanliness and housekeeping (Refs. 1 and 2).

The present major disadvantage in the use of Be and Be alloys is poor resistance to crack growth. Careful reading of the literature reveals that there is considerable uncertainty and disagreement as to the true sensitivity of Be to cracks, particularly as affected by material

properties (Refs. 3-7). Resolution of this uncertainty will provide designers with more accurate data on the fracture sensitivity and allowable flaw size in structural applications, and should increase confidence in Be.

A vital point in the successful application of Be is the need for a cooperative effort between materials, design and structures discipline in order to utilize the material in a way which takes maximum advantage of the material's high modulus, strength, and lightness while minimizing its lack of ductility and its poor resistance to crack propagation. This is the only approach which will permit maximum material utilization and minimum design problems without an extensive iterative process. This interdisciplinary cooperation will permit increased design flexibility and greater materials efficiency at minimum cost.

II. State-of-the-Art

The application of Be to designs which are limited to compression loading is practical at this time without additional development (Refs. 8-10). It is also possible to use Be in simple tension, but biaxial tensile applications require caution in design and material selection. Designs utilizing Be should emphasize applications where resistance to gross buckling, crippling, or flutter is required rather than tensile or biaxial strength (Refs. 8 and 11). The various advantages and disadvantages of Be should be considered carefully during the spacecraft design phase in order to achieve the most effective usage and to prevent problems in fabrication and assembly.

The physical properties of Be, even more than those of most other materials, are affected by the form of the starting material and subsequent processing operations (Refs. 12-15). The best bidirectional properties are obtained from cross-rolled sheet, either from ingot stock or hot-pressed powder compacts. Maximum longitudinal tensile strength is obtained from wire and extrusions; hot-pressed block has lower strength but better bidirectional properties and is less costly. Surface roughness, which may present problems in some applications, is greater in ingot sheet products than in powder sheet.

The major factors which affect physical properties are grain size, grain orientation, and purity, particularly with respect to oxygen (O), silicon (Si), iron (Fe), and aluminum (Al). Highest strength, greatest ductility and greatest resistance to crack propagation occur when grain size is fine (10 μ or less) and equiaxed. Several per-

cent of beryllium oxide (BeO) has been found to improve strength and retard recrystallization and grain growth during hot working. Excessive amounts of Al cause hot shortness during forging or hot working. Reduced Al content gives improved high-temperature strength and ductility (Ref. 16). Iron acts to tie up the Al and improves forgeability. Silicon appears to react with the Al, forming a low-melting grain boundary phase which also causes hot-shortness. Grain boundary segregation of Al, Fe, and Si has been observed, with Fe and Al tending to cosegregate (Ref. 14). The balance between Al, Fe, and Si thus appears to affect fabrication and materials properties (Ref. 17). There are indications that Cu may improve ductility, possibly by blunting the ends of microcracks (Refs. 14, 17). Processing history of the material is also of great importance, largely because of the effect process history has on grain size, orientation, and purity (Refs. 12, 14).

In order to properly characterize Be, it is necessary to know what the starting material was, how it was processed, the final grain size, the chemical composition, and the mechanical properties (Ref. 18). Different combinations of properties are desirable for different applications. The designer and metallurgist should be aware of the process history and properties in order to make the most effective use of all of the attractive properties of Be.

Production of Be mill products is low, and this is a major cause of the high prices, long lead times, and uneven quality. Capital investment in forging, rolling, and surface conditioning equipment cannot be justified by the producers until output and sales increase (Ref. 19). Generally, users have found it easier and cheaper to perform such operations as flattening and final edge milling rather than having the producers do it (Ref. 20).

The importance of uniformity and reliability increases as the design requirements approach the guaranteed minimum strength and elongation values. Most present applications do not utilize a large proportion (i.e., 70% or more) of the tensile strength of Be, so the problem of material uniformity has been avoided. Should a specific application require using almost all of the guaranteed minimum tensile strength available, careful control of incoming materials will be required.

There is little hope that some major breakthrough in ductility improvement will occur (Ref. 13). The brittle behavior appears to be inherent in the material, and

neither alloying nor purification seems to hold much promise of significant improvements. The inherent brittleness is caused by a lack of room temperature slip systems. In order to deform plastically, the crystal must have five independent slip systems; Be possesses only four such systems in tension, and none in compression. Therefore, cracks occur when Be is overloaded, acting as a sort of additional slip system and permitting the material to deform (Ref. 13). Knowledgeable personnel at the Air Force Materials Laboratory (AFML) feel that a better understanding of the basic behavior of Be is needed, and that learning how to activate additional slip systems at room temperature is one field which needs more effort (Refs. 9, 21). It is recognized that it may prove impossible to activate such additional slip systems at normal temperatures.

It has been reported that the presence of microcracks sometimes reduces the brittle failure tendency of Be, possibly by allowing deformation without catastrophic failure or by retarding growth of larger cracks (Refs. 6, 22). This phenomenon warrants further study. It may be possible to develop a material which is less sensitive to surface defects, notches, edge cracks, etc., or at least to determine accurately the true sensitivity of Be mechanical properties to the presence of cracks or notches.

The fatigue strength of Be is excellent, exceeding that of Al or Ti for 10^5 cycles or more (Refs. 4, 5, 23).

A. Fabrication

Most Be mill products are available as 36- × 96-in. sheets which have been formed from hot-pressed -200-mesh powder, jacketed in steel and hot cross-rolled. After rolling, the steel jacket is removed and the beryllium surface is ground and then etched to remove grinding marks, cracks, and twins. Another form is hot-pressed block, which is also formed from powder, but is either not reduced by further working, or is reduced very slightly to increase density or obtain a desired size or shape. A newer product is ingot sheet, which is formed by vacuum induction casting followed by forging, upset forging, extruding, and cross-rolling either separately or in combination. Preliminary working operations aid in breaking up the as-cast structure and refining the grain size; normally only one of the primary forming operations is used before rolling. Ingot sheet typically is of higher purity, but has somewhat poorer surface finish and mechanical properties than powder sheet. The lower properties are believed to be caused by the relatively coarse grain size. Ingots prepared from -325-mesh

powder have given improved yield and tensile strengths owing to the finer final grain size (Ref. 14).

Each of these mill products possesses certain advantages and disadvantages. Use of one or another of them will be dictated by design, application, and cost factors.

Final fabrication into components may be done by machining, hot-forming, forging, or extrusion (if the shape is relatively simple) or combinations of these. Machining can be done with normal shop tools and procedures providing that due care is exercised in the control and containment of the toxic dusts. For example, rough sawing is done with a fine-toothed blade in a band saw at 500 ft/min. Shaping and milling are performed with standard carbide tools. Tool wear is about 5 times as great as for Al. Drilling is generally done using a special drill¹ which senses drilling pressures and maintains constant torque. Backup plates are recommended for sawing or drilling thin, unsupported stock to avoid applying bending moments to the Be which might cause cracking or delamination.

After final machining, at least 2 mils is removed from the surface by etching to remove twins and microcracks (Refs. 12, 24-27). Selection of an etching solution seems to be a matter of balancing off final surface finish, metal removal rate, and ease of solution control. Etchant composition and temperature usually are the most critical factors. Typical etchants are given in Refs. 26 and 28. In general, users of Be agree that fabrication is not difficult or unreasonably expensive, providing that proper care is taken during machining and handling to prevent surface scratches, cracks or other handling damage (Refs. 29, 30).

Fairly complex sheet metal components may be made by hot-forming at about 1350°F (Refs. 30, 31). Beryllium may be hot-worked successfully because additional prism slip becomes possible above 940°F. Below this temperature the critical resolved shear stress for basal slip is lower, and the prism slip cannot occur (Ref. 13). To form Be, the stock, usually sheet, is placed into a heated die and the part is formed as pressure slowly is applied to the die (Refs. 5, 12, 31, 32). Normally, forming is done in ceramic dies, but some workers have had limited success forming smaller parts in stainless steel or Inconel dies (Refs. 29-35). Relatively simple shapes such as angles, channels, and spacers have been formed in this

¹Tornetic controlled torque drill, manufactured by Dyna Systems, Inc., Torrance, Calif.

way (Refs. 23, 36-38). Channel sections almost 8 ft long have been produced using specially designed stainless steel punches and dies. A few more complex parts such as domes, double convex sheets, and cylindrical sections also have been made successfully (Refs. 39-41). Bends with a $5T-6T$ radius ($T =$ thickness) are possible with powder sheet, and $3T-4T$ can be obtained with ingot sheet. The quoted results are for parts formed at $1300-1350^{\circ}\text{F}$. Bending processes usually result in a higher scrap loss than machining, but in neither type of operation are losses considered to be a serious problem by those who have been performing the work.

Both open and closed die forgings have been formed successfully. Usually it is necessary to jacket the Be billet with steel or stainless steel before forging; if this precaution is taken, relatively complex parts may be forged successfully (Refs. 42-44). More recently, aircraft components, such as brackets, have been forged bare, both in open and closed dies. An important limitation of this process is the quality and forgeability of the input stock (Ref. 45).

Extrusion of Be has been demonstrated for a number of different shapes (Refs. 46-48). Although common shapes, such as tubes can be formed, they are not readily available; long lead times may be required for delivery, even for relatively standard sizes. The major problems encountered during extrusion are the need for higher ram pressures (relative to aluminum), die design at the inlet, and the tendency for the Be to seize and gall. Galling can be eliminated by jacketing the Be billet in stainless steel, but this increases material costs and requires expensive operations in both the cladding of the Be and removal of the cladding after extrusion. Various die lubricants have been tried, but without complete success. The approaches used for forming Be wire seem to have provided the best answers to the lubrication problem. One organization sheaths the Be in Ni before drawing, and etches away the Ni surface after drawing (Ref. 49). Another dips the Be into a graphite type of lubricant before extruding and drawing (Ref. 50). Both methods can result in embedding the lubricant in the surface of the Be, reducing mechanical properties appreciably.

B. Joining

Presently used joining techniques are rather limited; mechanical fastening and adhesive bonding are most often used, while welding, braze welding, and brazing and diffusion bonding are employed where loss of

strength due to recrystallization and grain growth either can be retarded by proper joint and fixture design or is not important for the particular application involved.

Mechanical fastening is well developed and has proven very successful. The major problems are preventing joint rotation and avoiding cracking or delaminating the sheets while drilling the holes and installing rivets. If threaded holes are tapped and drilled, the threads must be etched before use to remove surface damage. Investigations also have been made of joint design, the effect of using different types of fasteners, and the usefulness of compound joints, i.e., mechanical fastener plus adhesive (Ref. 51).

If a lower level of shear strength is acceptable, adhesive bonding can be used successfully. A number of sizable structures have been adhesively joined with satisfactory results (Refs. 12, 35, 51-55). In fact, it is planned to adhesively bond all of the structural components of a solar panel array having individual panel sections as large as 13×8.5 ft (Ref. 52). When application of pressure and heat during bonding is impractical, either because of joint design or the effects on adjacent materials, adhesive bonding is less effective. Room temperature curing adhesives normally have lower shear and peel strengths, and are less desirable where high strength is required.

Both spot welding and electron beam welding are being investigated as joining techniques, but neither appears to hold much promise because of the high thermal conductivity of Be and the extensive grain growth which results in brittle joints (Ref. 56). Battelle has reported recently that they have successfully joined Be sheets ranging from 0.020 to 0.250 in. thick by electron beam welding. High oxide content seems to inhibit good wetting and joining (Ref. 57), while sheets of low oxide content are more prone to weld cracking. Addition of preplaced Al shims aids welding of 0.25-in. sheets as does the addition of filler wire (Ref. 58).

The most common braze alloys at present are Ag-base and AlSi, although some Zn alloys are also used (Refs. 5, 12, 51). Development of improved and lower-temperature braze alloys is being conducted to improve wetting and bonding, increase joint strength and remelt temperatures, widen process tolerances, and lower brazing temperatures to $1200-1400^{\circ}\text{F}$. Brazing at this temperature avoids the $1500-1600^{\circ}\text{F}$ recrystallization range. Indications are that most of these objectives can be met within

the next few years; brazing in argon rather than vacuum, use of beryl formers in the braze alloy, and control of the oxide content of the Be all will aid in obtaining better and more reliable braze joints (Ref. 59).

Diffusion bonding of Be is in an early stage of development. So far results have been spotty, both with and without bonding aids (Refs. 51, 60, 61). The process seems to be adversely affected by a number of variables, not all of which have been identified; they are thought to include oxide content, surface preparation, time, temperature, pressure, atmosphere, and nature of bonding aids, if any.

C. Beryllium Alloys

The only successful family of Be alloys developed to date are the Be-Al series, commonly known as Lockalloys. Aluminum contents of from 24 to 43% have been prepared and tested, but the standard commercial grade is the 38% Al alloy. Actually this is a dispersion of Al in Be rather than a true alloy. The advantages are greater ductility, lower cost, and elimination of the requirement for etching after machining. Lockalloy can be cold-formed and punched in the annealed condition. It may be spot-, seam-, and projection-welded successfully, and is generally easier to join and fabricate than commercially pure beryllium. The penalty is a reduction in modulus to about that of steel, and appreciably lower strength, with a density about 25% less than that of Al (Refs. 17, 62-69). Reproducibility of physical properties from heat to heat appears to be satisfactory (Ref. 62). Not much Lockalloy is being used at present, and it is not as widely available as commercially pure Be. There is a lack of experience in the design and use of Lockalloy components which seems to inhibit many designers from using it.

Attempts to develop other alloys by adding elements such as Fe have resulted in further embrittling the Be (Refs. 17, 70). However, additions of Cu to Be in an attempt to prepare usable solid solution alloys are promising. Ingots have been extruded which extrude much like unalloyed Be. More studies of these alloys are continuing (Ref. 71).

D. Present Materials Availability

Beryllium suppliers have stated they can fill orders for 10 to 12 3- × 8-ft hot cross-rolled sheets within 8 weeks. Similar quantities of Be ingot sheet and hot pressed block are said to be available in slightly longer

times. However, some users have had difficulty obtaining material on these delivery schedules (Ref. 16). Recently, sheets as long as 180 in. were rolled successfully from powder-derived material.

Several users have complained about the quality of the sheet as received from the mill. Most common complaints are lack of sheet flatness and the presence of edge cracks; these problems reportedly are not serious in more recent production (Refs. 20, 36). Inability to meet specifications on physical properties is occasionally mentioned, but apparently 100% mill testing has kept low yield and tensile properties from becoming a serious problem. Since many applications require relatively low strengths, almost all of the production can be sold without major difficulty (Ref. 16).

Small quantities of 0.001-0.005 in. foil have been produced, but it is very expensive and the uniformity and reproducibility of this form of Be is not established. The minimum standard thickness obtainable is 0.020 in. However, some 0.010 in. material is available in small sizes. Rolling below 0.020 in. often results in excessive grain orientation; bidirectional properties are reduced; poor surface finish results; thickness varies; and lack of flatness becomes troublesome. Thin gauges are usually formed by etching heavier gauge stock (Ref. 30), which is expensive.

E. Anticipated Future Progress

Both Berylco² and Brush Beryllium³ are working to improve material quality and reliability. A major requirement is more and better in-house processing capability, longer mill runs, and better process controls (Refs. 19, 70). The need for these changes is recognized, and they will be made eventually; exactly how soon will depend to a large degree on the future usage of Be products.

A definite improvement in material quality and uniformity already has occurred and has been acknowledged by several Be users (Refs. 24, 29). Further improvements are certain, but the exact timing is not. In addition to improved hot-pressed and rolled sheet, increasing quantities of ingot sheet are becoming available. It is likely that alloying will improve the mechanical properties,

²The Beryllium Corp., Reading, Pa.

³The Brush Beryllium Co., Cleveland, Ohio.

and better rolling equipment will permit reductions to thinner gauges without excessive loss of properties. Thinner sheet in larger sizes also should become available as a standard item within the next several years. Production quantities of foils are not envisioned in the near future, but are a strong possibility within several years — or sooner if a definite requirement for significant amounts can be demonstrated.

It will be some time, perhaps as much as 3 to 5 years, before Be sheet can be ordered from the mill in the same way that Ti or some of the refractory metals are at this time. Just when it will become a standard material will depend largely upon the success of designers and engineers in applying it and the size of the market.

The first major improvements in fabrication and assembly will be related directly to material quality and uniformity. Selection of individual sheets for physical and mechanical properties will become less of a necessity. Additional straightening and flattening operations will not be required for most applications. Machining and handling will become standard operations, routinely performed by even more organizations than at present. This will occur partly through normal movement of personnel (and techniques) throughout industry and partly through increased demand for these services, which will make it more attractive and profitable for additional companies to develop Be capabilities.

Assembly will be easier as more people become experienced with the techniques, as fit-up problems are reduced by better flatness of as-received stock, and as more assembly techniques become available. These new methods will encompass Be fasteners (both blind and threaded), improved rivets and riveting procedures, a wider range of braze alloys, and diffusion bonding, electron beam welding, or braze welding. More attention to design will permit better joint configurations and reduce the complexity of assembly. In some instances, combinations of Be, Be-Al, and Al may be used to improve fabrication and assembly of particularly difficult shapes or joints.

III. Recent Programs

Many organizations are conducting Be development programs. Some are sponsored by industrial organizations, some by the AEC, some by other NASA installations;

many are Air Force supported.⁴ A brief summary of a number of the more pertinent programs is given below.

A. Applications

McDonnell Aircraft has fabricated and successfully tested wing boxes and a rudder section made of a Be skin and stiffeners, joined with bolts and mechanical blind rivets. Failure occurred at 150–160% of design stress, and no primary failures through fastener holes were observed (Refs. 72–73). The material used had a design yield strength of 50,000 psi and design ultimate of 70,000 psi (Ref. 74). Republic Aviation made a box beam section from sheet for Marshall Space Flight Center; fastening was by mechanical blind rivets. They reported little difficulty in working with the material (Ref. 36). This section is now being tested. Another box beam fabricated for MSFC has been assembled using Be fasteners which are being made by Standard Pressed Steel.⁵ The beam should be tested shortly.

Boeing recently completed a program for the Air Force on the fabrication and testing of a solar panel spar 76 in. long, formed from sheet. It failed at about 2½ times design load. Failure was initiated at a defect about 0.040 in. in diameter (Ref. 37). Boeing is in the early stages of another solar panel development program for JPL, the ultimate object of which is to fabricate and test a 20 W/lb array with over 1200 sq ft of surface area. In order to satisfy this requirement, a Be structure is required. Beryllium spars up to 13 ft long must be fabricated, formed, and adhesively joined to other members (Refs. 52, 74). Lockheed is fabricating a number of *Agena* components from Be as a production operation without any significant difficulties. Machining, forming, and etching are performed routinely with little scrap loss (Refs. 29, 38). Most applications seem to be in non-critical or lightly loaded areas.

At Langley Research Center, NASA is fabricating a Be truss structure based upon the *Mariner II* design. Extruded Be, Al, and Lockalloy tubing 0.25 to 0.75 in. in diameter with 0.020–0.040 in. walls is being used in the structural members. Major problems are joint design and

⁴The Air Force has been and is continuing to be the major sponsor of programs ranging from basic studies of single and polycrystalline Be fabrication of components for structural test such as wing boxes, rudder sections and solar panel spars.

⁵Standard Pressed Steel, Philadelphia, Pa.

adequate stress transfer from strut to strut at the joints. Use of aluminum joints imposes a heavy weight penalty, while Be "spider" joints are costly and difficult to fabricate and assemble. Present design is a compromise in which the "spider" is Al, with short Al tubes adhesively bonded to the Be with a slip collar (Ref. 75).

Solar⁶ is producing a similar truss structure to be used as a gimbal support for *Saturn* guidance engines. Extruded Be tubing 11 ft long, having a 5-in. diameter with a 0.125-in. wall will be connected at the ends by forged and machined Be caps. Joining will be by adhesives. Only 3-ft lengths have been extruded so far, but no trouble is anticipated with longer lengths. Surface finish, uniformity, and tensile strength are considered to be very good (Ref. 60).

North American is using hot-pressed block for instruments, containers, and other noncritical and nonstructural applications. They have had some problems with cracks in the as-received materials but claim no problems in machining and brazing parts (Refs. 76, 77). The shroud nose dome which encloses *Lunar Orbiter* during launch was fabricated by Boeing by machining from hot pressed block (Ref. 78). Rocketdyne is developing and fabricating Be rocket nozzles for use in small rocket motors. Some test data is available (Ref. 79).

B. Joining

Several programs are underway to develop diffusion bonding techniques for Be. Solar, Lockheed, and North American had tried to spot diffusion bond Be sheets with rather erratic results (Refs. 51, 60, 61). Lockheed has diffusion-bonded sheets successfully by adding Al or Cu to the interface (Ref. 80). Boeing also reports having some success diffusion-bonding Be on a small scale (Ref. 81). Cleaning procedures and the time lag between cleaning and bonding seem to be very important. The variation in oxide content of the sheet also affects bond quality and reproducibility (Refs. 19, 82). Battelle⁷ has gas-pressure-bonded Be successfully, but the process is expensive and not fully developed; it is not applicable to some shapes and joint configurations which would be of interest for spacecraft applications, although some very complex shapes have been formed at relatively high tooling costs (Refs. 83-85).

⁶Division of International Harvester Co., San Diego, Calif.

⁷Battelle Memorial Institute, Columbus, Ohio.

Solar is conducting a study of braze alloys and brazing techniques (Ref. 59). Low oxide content is essential for optimum braze flow and joint strength. Several Ag-base alloys have been developed which appear to wet and flow well and have good lap shear strength. The best of these are being selected for additional development under a follow-on Air Force program. Several promising Ti-base alloys also are under development. Earlier work by Aeronca⁸ and Lockheed (Refs. 40, 41, 51, 56) resulted in braze alloys and techniques which gave good results but had limitations, particularly because of high brazing temperature, low remelt temperature, low joint strength, and uncertain reproducibility. Other organizations conducting Be brazing programs include Bi-Braze Corporation,⁹ Union Carbide,¹⁰ and MIT.

Battelle has electron-beam-welded Be sheets successfully. Although good welds have been obtained with little porosity or undercutting and essentially no microcracks, joint efficiencies have been low. Best results were obtained with 0.020- and 0.062-in. sheets; welds in 0.250-in. sheet were much more difficult to prepare without undercutting, cracks, or porosity.

The oxide content must be less than 0.7% for best results; this finding agrees with the brazing and diffusion bonding studies cited above (Ref. 57). Autonetics¹¹ and Lawrence Radiation Laboratory¹² also have joined Be by electron beam welding (Ref. 56). Lawrence Radiation Laboratory employed a prebuttering technique (precoating the joint with braze or weld metal) in the joint areas. In studying electron beam welding of Lockalloy, LRL found that although there was incomplete penetration, welds in 0.010-in. sheet were stronger than the base metal.

Several organizations have welded Be successfully by tungsten inert gas (TIG) welding both with and without prebuttered joints (Refs. 41, 56, 86, 87). LRL listed welding parameters in Ref. 56. Berylco is studying both butt and projection welding.

Adhesive bonding is well developed as a Be joining technique (Refs. 23, 41, 55, 88); little new work is being

⁸Aeronca Manufacturing Corp., Middletown, Ohio.

⁹Bi-Braze Corp., Glen Cove, New York.

¹⁰Union Carbide Y-12 Plant, Oak Ridge, Tenn.

¹¹Autonetics Division of North American Aviation, Inc., Anaheim, Calif.

¹²Lawrence Radiation Laboratory, Livermore, Calif.

conducted except that Boeing is examining several 3M Company¹³ structural adhesives for use in the large area solar panel program (Ref. 89).

C. Fabrication

Forging development is being done primarily by Ladish,¹⁴ Brush, and TRW.¹⁵ Successful cylinders up to 13 in. high by 31 in. in diameter have been formed by ring rolling; cylinders up to 16 in. high by 13 in. in diameter have been forged bare. Other shapes such as discs, rectangular beams, hemispheres and hollow shafts also have been forged (Refs. 12, 17, 42-46, 89). Autonetics Division of North American has studied the effects of forging variables on directionality of properties (Ref. 43).

Nuclear Metals¹⁶ and Berylco have done extensive development of Be extrusion, succeeding in extruding shapes up to 41 ft long. Sections have included tubing, rods, finned tubes, rectangles, I's H's, hat sections, and squares. Uniformity of properties from end to end along the extrusion is reported to be good, but transverse mechanical strengths were low (Refs. 12, 17, 46-48).

Formability studies are being conducted by Hughes, Lockheed, and Boeing. The effects of bend radius, forming temperature, and material source (powder or ingot) were studied. Ingot sheet may be formed successfully at lower temperatures than powder sheet, or, if formed at the same temperature, ingot sheet can be formed more severely without cracking (Refs. 5, 30, 39, 40, 53).

D. Properties of Beryllium

The Air Force is sponsoring studies of the properties and behavior of polycrystalline beryllium to better understand the ductility problem and attempt to find a solution (or establish with certainty that no solution exists). Some of the work is being done at Wright-Patterson AFB, and some is being done at Nuclear Metals and Franklin Institute¹⁷ (Refs. 9, 90).

The fracture behavior, crack growth, and sensitivity to notches and cracks of Be recently came under study by

¹³Minnesota Mining and Manufacturing Company, Rochester, Minn.

¹⁴Ladish Co., Cudahy, Wis.

¹⁵TRW, Cleveland, Ohio.

¹⁶Nuclear Metals Division of Textron, Concord, Mass.

¹⁷The Franklin Institute, Philadelphia, Pa.

several organizations. Previous data in this field is scattered, incomplete, and contradictory. In an attempt to resolve this uncertainty, various aspects of the fracture behavior of Be with induced sharp-edged defects are being examined by Westinghouse,¹⁸ Battelle, Sandia,¹⁹ Boeing, and the Flight Dynamics Laboratory of the Air Force at Wright Field (Refs. 6, 21, 22, 33, 52, 91, 92). Notch sensitivity of Be has been studied briefly by Lockheed, Boeing, Douglas, and Brush Beryllium at room temperature, cryogenic temperatures, and elevated temperatures (Refs. 3, 5, 33, 52, 93, 94). Battelle has compiled the information available in 1958 in an extensive bibliography (Ref. 95). The data at elevated temperatures indicated that for a stress concentration factor (K_t) of 4 there is actually some strengthening of the Be; at room temperature or below there is some lowering of the Be strength, but it is not severe. This is true both for powder and ingot sheet. For $K_t = 2.5$, at -320°F , notched strength of ingot sheet actually exceeded unnotched strengths (Ref. 3). Preliminary data reported by Westinghouse indicated that crack growth may stop when the crack enters a low stress region (Ref. 22).

The Air Force Flight Dynamics Laboratory recently awarded a contract to develop techniques to minimize crack propagation in Be aircraft structures by improved design and fabrication techniques. A JPL program to determine the effects of material and composition variations on notch strength was begun recently, and should further help to clarify the fracture behavior of Be.

E. Beryllium Alloys

Both Hughes and Lockheed are enthusiastic about the potential of Lockalloy (Refs. 29, 30, 53). A range of Al contents of from 24 to 43% has been studied; the 38% Al alloy is presently most widely used (Refs. 53, 65-69). The major advantages are ease of fabrication, handling, and assembly. Lockalloy in the annealed condition is easily formed (it can be bent cold to a 6T to 8T radius), drilled, and machined; it also can be joined successfully by welding (both spot and seam) and brazing. This permits more complex and extensive forming and machining operations, without the need for a final etch to remove surface microcracks or twins. The physical and mechanical properties of Lockalloy are tabulated and compared with Be, Al, and Mg in Table 1 (Refs. 17, 49, 50, 53, 96, 97).

¹⁸Westinghouse Electric Corp., Astronuclear Division, Large, Pa.

¹⁹Sandia Corp., Albuquerque, N.M.

**Table 1. Comparative properties of Be and alloys of Ti, Al, and Mg
(all properties at room temperature)**

	Cross rolled Be sheet ^a	Cross rolled Be sheet ^b	Hot pressed Be block ^c	62 Be-38 Al sheet	Mg alloy HM21A-T8	Al alloy 7075T6	Ti alloy sheet Ti-6V-4 Al
Tensile yield strength, psi	75,000	53,800	48,400	50,400	37,000	72,200	147,000
Tensile ultimate strength, psi	55,400	40,300	40,700	36,600	30,000	63,200	137,000
Tensile modulus $\times 10^6$, psi	43.1		42.4	29.2	6.50	10.3	16.0
Tensile elongation, %	8	3.2	1	8.1	4	7	10
Compressive yield strength, psi	58.3		27,000	34,200	22,000	68,000	126,000
Compressive modulus $\times 10^6$, psi	42.6		42.6	29.1	6.5	10.0	16.4
Density, lb/in. ³	0.066	0.066	0.066	0.0756	0.064	0.101	0.160
Coefficient of thermal expansion, in./in./°F (77-212°F)	6.4×10^6			9.0×10^6	21.8	12.9	4.8
Thermal conductivity, Btu/(hr ft ² °F/ft)	104		104	123	80 (est)	76	3.8

^aPowder-derived; all values in longitudinal direction.
^bIngot-derived; all values in longitudinal direction.
^cSR-200 powder.

Hughes is sponsoring development of Be and Be-Al alloy components to replace Al and Mg in satellite applications. Analytical studies indicate that considerable weight savings are possible. Some of these weight savings are obtained by use of thin sheet material, which is not normally supplied by the producers; it is chemically milled to 0.005 or 0.010 in. from 0.020- or 0.025-in. sheet (Refs. 30, 53), which imposes a severe cost penalty. However, if a large market for this sheet develops, both Hughes and Brush Beryllium are confident that thin gauges can be produced successfully in quantity (Refs. 16, 30).

A substantial order recently was placed for Lockalloy to be used on *Minuteman*. This may be the beginning of an appreciable use of Be alloys. Berylco is in the early stages of a program to develop Be-Cu alloys by casting and extrusion. So far the progress is encouraging (Ref. 71).

The above programs do not include all of the current beryllium effort. However, they are the more important and extensive programs, and include those most directly applicable to spacecraft requirements. A list of current government-sponsored Be programs is contained in Ref. 98.

IV. Conclusions

Beryllium possesses significant advantages in strength-to-weight ratio and modulus-to-weight ratio as compared with presently used spacecraft structural materials.

Beryllium is presently usable for compression-limited applications without further development. It can be used in simple tension successfully; but in biaxial tension care must be exercised in design, fabrication, and assembly.

Joining of beryllium with mechanical fasteners, solder, braze welding, and adhesives is well developed, and can be considered acceptable for spacecraft use without further development. Joining by brazing, welding, diffusion bonding and electron beam welding has been demonstrated successfully, and can be considered to be in the advanced development stage. All of these latter joining methods require at least some refinement.

Forming and machining beryllium is essentially fully developed.

Problems still exist in the areas of material quality and uniformity, but improvements are being made. Further improvements are expected in the future.

The fracture behavior and effect of sharp-edged defects on different types of beryllium material are not well known or understood. Present data is incomplete and conflicting. Programs presently underway should clarify this problem.

Procedures have been developed for containing the toxic beryllium dusts formed during machining. If proper care is observed, the hazards involved in handling and fabricating beryllium can be minimized so that toxicity is not a problem.

References

1. "Health Hazards of Beryllium Can Be Controlled," *Safety Maintenance*, Vol. 1, No. 1, pp. 32-36, July 1958.
2. *Beryllium: Its Metallurgy and Properties*, edited by H. H. Hausner, University of California Press, Berkeley and Los Angeles, 1965.
3. Campbell, J. E., "Review of Recent Developments - Beryllium," DMIC Technical Note, Defense Metals Information Center, Battelle Memorial Institute, Columbus, Ohio, November 5, 1965.
4. Darwin, G. E., and Buddery, J. H., *Metallurgy of the Rarer Elements - Beryllium*, Academic Press, New York, 1960.
5. Crawford, R. F., and Burns, A. B., "Design Data for Beryllium," ASD-TR-61-692, Air Force Systems Division, Air Force Materials Laboratory, Wright-Patterson AFB, Ohio.
6. *Beryllium Fracture Mechanics*, preliminary report to NASA Research Advisory Committee, Westinghouse Astronuclear Laboratory, Large, Pa., January 1967.
7. *Mechanical Properties of Beryllium at Cryogenic Temperatures Including Notch Specimen Data*, DMIC Technical Note, Defense Metals Information Center, Battelle Memorial Institute, Columbus, Ohio, November 5, 1965.
8. Darwin, G. E., Article (Chapter 5) in *Materials in Space Technology*, edited by G. V. Thompson, Gordon and Breach, New York, 1963.
9. Perlmutter, I., Air Force Materials Laboratory, Wright-Patterson AFB, Ohio, personal communication, October 1966.
10. Gumnich, K. F., "Aerospace Industry Beryllium Materials Utilization," paper presented at SAE Aeronautics and Space Engineering and Manufacturing Meeting, Los Angeles, Calif., October 3-7, 1966.
11. Armstrong, H. H., Burns, A. B., and Crawford, R. G., "Structural Weight and Cost Comparisons of Large Space Structures Employing Beryllium-Aluminum Alloys," reported under Contract NAS 8-11298, Marshall Space Flight Center, Ala.
12. Williams, R. F., and Ingels, S. W., *Fabrication of Beryllium - A Survey of Current Technology*, NASA-TMX-53453, Vol. I, Marshall Space Flight Center, Huntsville, Ala., July 1966.

References (contd)

13. Conrad, H., and Perlmutter, I., *Beryllium as a Technological Material*, AFML-TR-65-310, Air Force Materials Laboratory, Wright-Patterson AFB, Ohio, November 1965.
14. Hanes, H. D., et al., *Physical Investigation of Beryllium*, DMIC Report 230, Defense Metals Information Center, Battelle Memorial Institute, Columbus, Ohio, June 24, 1966.
15. Porembka, S. W., and Hanes, H. D., *Beryllium Ingot Sheet*, DMIC Memo 206, Defense Metals Information Center, Battelle Memorial Institute, Cleveland, Ohio, August 10, 1965.
16. King, Bryce, The Brush Beryllium Co., Cleveland, Ohio, personal communications, October 1966, April 1967.
17. "Beryllium Technology," *Metallurgical Society Conferences*, Vol. 33, edited by A. M. S. Schethy and H. A. Johnson, AIME, Gordon and Breach, New York, 1966.
18. *Characterization of Beryllium*, MAB-226-M, Materials Advisory Board, National Academy of Sciences, Washington, D. C., August 1966.
19. King, Bryce, "Beryllium Sheet – Today, Tomorrow, the Future," paper presented at SAE Aeronautics and Space Engineering and Manufacturing Meeting, Los Angeles, Calif., October 3–7, 1966.
20. Bohman, G., "Tooling and Fabrication Technology Development for Beryllium Sheet Metal Structure," paper presented at SAE Aeronautics and Space Engineering and Manufacturing Meeting, Los Angeles, Calif., October 3–7, 1966.
21. Burte, H. M., "Beryllium Materials – Trends in Research, Development and Potential Use," paper presented at SAE Aeronautics and Space Engineering and Manufacturing Meeting, Los Angeles, Calif., October 3–7, 1966.
22. *Beryllium Thermal Shock Testing*, preliminary report to NASA Research and Advisory Committee, Westinghouse Astronuclear Laboratory, Large, Pa., January 1967.
23. Barnett, F. E., Fimm, J. M., and Koch, L. C., "Beryllium Structures for Aircraft," Paper 660666, presented at SAE Aeronautics and Space Engineering and Manufacturing Meeting, Los Angeles, Calif., October 3–7, 1966.
24. Snider, R. E., and Kahles, J. F., *Machining Data for Be*, AFMDC-66-3, Air Force Machinability Data Center, Manufacturing Technology Division, Air Force Materials Laboratory, Wright-Patterson AFB, Ohio, June 1966.
25. *Evaluation Test Methods for Beryllium*, MAB-205-M, Materials Advisory Board, NAS-NRC, Washington, D. C., March 1966.
26. Williams, R. F., and Ingels, S. E., *Fabrication of Beryllium – Vol. 3, Metal Removal Techniques*, NASA TMX-53453, Marshall Space Flight Center, Huntsville, Ala., August 1966.

References (contd)

27. Porembka, S. W., and Hanes, H. D., *Surface Damage in Machined Beryllium*, DMIC Memo 198, Defense Metals Information Center, Battelle Memorial Institute, Columbus, Ohio, January 4, 1965.
28. Missel, L., and Shaheen, M. E., "Chemical Milling of Beryllium," *Metal Finishing*, Vol. 63, pp. 69-71, November 1965.
29. Ingels, S. E., Lockheed Missiles and Space Co., Sunnyvale, Calif., personal communication.
30. Van Hammersveldt, J., Hughes Aircraft Corp., Culver City, Calif., personal communication.
31. Williams, R. F., and Ingels, S. E., *Forming Techniques for Beryllium Alloys*, NASA TMX-53453, Vol. 2, Marshall Space Flight Center, Huntsville, Alabama, July 1966.
32. Van Hammersveldt, J., Svendensen, T. S., and Hayes, W. C., "Making Satellite Structures from Beryllium Lockalloy," *Metal Progr.*, Vol. 91, pp. 91-95, February 1967.
33. Tiffany, C., Boeing Co., Space Division, Kent, Wash., personal communication, January 1967.
34. Dickason, R. C., *Beryllium Forming, Preliminary Hot Draw Forming Tests*, Report CMRI 1351, Lockheed Aircraft Co., Burbank, Calif., January 7, 1967.
35. Second Quarterly Report, D2-113355-2, JPL Contract 951653, Boeing Co., Space Division, Kent, Wash., April 1967.
36. Bohmann, G., and Fuchs, W. A., *Beryllium Box Beam Development Program*, Fairchild Hiller Report FHR-3249, X66-19531, Marshall Space Flight Center, Huntsville, Ala., March 1966.
37. Oken, S., and Dilks, B. H., *Structural Evaluation of Beryllium Solar Panel Spars*, AFFDL-TR-65-45, Air Force Flight Dynamics Laboratory, Wright-Patterson AFB, Ohio, August 1966.
38. Rebholz, M. J., "Application of Beryllium on the Agena," *J. Spacecraft*, Vol. 3, No. 5, pp. 715-722, May 1965.
39. Ingels, S. E., *Ductility of Cross-Rolled Beryllium Sheet - Barrier or Challenge*, Report LMSC-A-820503, Lockheed Missiles and Space Co., Sunnyvale, Calif., March 15, 1966.
40. Krusos, J. N., et al., *Beryllium Composite Structures*, ASD-TR-61-706, Vol. 2, Manufacturing Technology Laboratory, Air Force Materials Laboratory, Wright-Patterson AFB, Ohio, June 1962.
41. Krusos, J. N., et al., *Sheet Beryllium Composite Structures*, ASD-TR-7-845 (II), AD 276815, Manufacturing Technology Division, Air Force Materials Laboratory, Wright-Patterson AFB, Ohio, April 1962.

References (contd)

42. Hayes, A. F., and Noel, R., *Development and Evaluation of Forging Parameters in the Manufacture of Conical Beryllium Structural Shapes*, IR 8-247 (V), Manufacturing Technology Division, Air Force Materials Laboratory, Wright-Patterson AFB, Ohio, February 1, 1966.
43. Gross, A. G., and Colteryahn, L. E., "Effects of Thermal-Mechanical Variables on the Anisotropy of Forged Beryllium," AFML-TR-66-333, Air Force Materials Laboratory, Wright-Patterson AFB, Ohio, December 1966.
44. Kosinski, E. J., and Hayes, A. F., "Recent Advances in Forging Beryllium," Paper 66034, presented at SAE Aeronautics and Space Engineering and Manufacturing Meeting, Los Angeles, Calif., October 3-7, 1966.
45. Murphy, E. A., Hornak, M. B., and O'Rourke, R. G., *Developing Technology to Forge Unclad Beryllium*, AFML-TR-65-30, Manufacturing Technology Division, Wright-Patterson AFB, Ohio, January 1965.
46. Siergiez, J. M., "Extrusion of Beryllium Structural Shapes," in *Newer Structural Materials for Aerospace Vehicles*, ASTM Special Technical Publication No. 379, ASTM, Philadelphia, Pa., 1964, pp. 106-118.
47. *The Metal Beryllium*, edited by D. W. White, Jr., and J. E. Burke, American Society for Metals, Cleveland, Ohio, 1955.
48. Loewenstein, P., "Production of Structural Shapes and Tubing of Beryllium and Beryllium Alloys," paper presented at SAE Aeronautics and Space Engineering and Manufacturing Meeting, Los Angeles, Calif., October 3-7, 1966.
49. Denny, J. P., and Stitzlein, C. F., "Beryllium Fine Wire," paper presented at 96th Annual AIME Meeting, Los Angeles, Calif., February 23, 1967.
50. Klien, J. G., "Fabrication and Properties of Beryllium Wire," paper presented at 96th Annual AIME Meeting, Los Angeles, Calif., February 23, 1967.
51. Williams, R. F., and Ingels, S. E., *Joining Beryllium*, NASA-TMX-53453, Vol. 6, Marshall Space Flight Center, Huntsville, Ala., July 1966.
52. *First Quarterly Report*, The Boeing Co., Space Division, Kent, Wash., Report D2-113355-2 on Contract JPL 951653, January 1967.
53. Van Hammersveldt, J., "Satellite Structural Parts, Beryllium Lockalloy," Paper SSD60355B, presented at Aeronautics and Space Engineering and Manufacturing Meeting, Los Angeles, Calif., October 3-7, 1966.
54. Dastin, S. J., "Bonded Be Structures," Republic Aviation Corporation Paper V-3, presented at Society of Aerospace Materials and Process Engineers, 9th National Symposium, Joining Materials for Aerospace Systems, Dayton, Ohio, November 14-16, 1966 (published by Western Periodicals Co., No. Hollywood, Calif., 1965).
55. Dastin, S. J., "Bonded Beryllium Structures," *Adhesives Age*, Vol. 9, pp. 24-27, May 1966.
56. *Sixth Progress Report by the Committee on Beryllium Metallurgy of the Materials Advisory Board*, MAB 199M(6), National Academy of Sciences, Washington, D. C., April 1966.

References (contd)

57. Hauser, D., et al., *Electron-Beam Welding of Beryllium*, AFML-TR-66-215, Systems Engineering Group (RTD), Air Force Systems Command, Wright-Patterson AFB, Ohio, July 1966.
58. Hauser, D., Monroe, R. E., and Martin, D. C., *Electron-Beam Welding of Beryllium*, Systems Engineering Group (RTD), Air Force Systems Command, Wright-Patterson AFB, Ohio, March 1967.
59. Bogowitz, R. G., and Metcalf, A. G., *Brazing Beryllium by Capillary Flow*, Solar Report RDR 1502-4 Fourth Progress Report, Air Force Materials Laboratory, Wright-Patterson AFB, Ohio, July 19, 1966.
60. Creamer, G., Solar Division, International Harvester Co., San Diego, Calif., personal communication, September 1966.
61. King, J. P., Jr., Robelotto, R. P., and Dillingham, A. C., Jr., *Diffusion Bonding of Titanium and Beryllium*, Interim Engineering Progress Report, IR 8-318(IV), Manufacturing Technology Division, Air Force Materials Laboratory, Wright-Patterson AFB, Ohio, August 1966.
62. Fenn, R. W., et al., "A Mechanical Property Evaluation of Be-38% Al Alloy from -320 to 800°F ," *Metals Engineering Quarterly*, Vol. 5, pp. 37-47, November 1965.
63. Armstrong, H. H., *Weight Saving Through the Use of Be-Al Alloys for Saturn-Type Vehicle Structures*, HREC/1298-1, Lockheed Missiles and Space Co., Huntsville, Ala., December 1965.
64. Fenn, R. W., et al., "Comparison of Lightweight Structural Materials: Be and Alloys of Be, Mg, Al and Ti," Paper 660652, presented at Aeronautics and Space Engineering and Manufacturing Meeting, Los Angeles, Calif., October 3-7, 1966.
65. *Mechanical Property Data 62 Be-38 Al Alloy, Annealed Sheet*, Air Force Materials Laboratory, Wright-Patterson AFB, Ohio, March 1967.
66. Fenn, R. W., Crooks, D. D., and Pasternak, R. C., "New Ductile Be-Al Wrought Alloys," *ASTM Symposium on Newer Structural Materials for Aerospace Vehicles*, ASTM Special Publication No. 379, 67th Annual Meeting, American Society for Testing Materials, Philadelphia, Pa., June 1964.
67. Fredlyander, I. N., et al., "Al-Be Base Alloys," *Metallovedeniye i Termicheskaya Obrabotka Metallov*, No. 3, pp. 2-5, March 1965.
68. Sibert, M. E., and Hulquist, A. E., "Production of Be Alloys," *J. of Metals*, Vol. 18, No. 11, pp. 1215-1222, November 1966.
69. Dedrick, J. H., Clayton, H. R., and Fisher, P. A., "Recent Developments in Light Alloys for Engineering Applications," *Proc. Inst. of Mech. Eng.*, Vol. 180, Part 3D, pp. 142-144, 1965-66.
70. Ranzetta, G. V. T., and Scott, V. D., "The Effect of Thermal Treatment on the Metallographic Structure of Be and Dilute Be Alloys," *J. Nucl. Materials*, Vol. 10, No. 2, pp. 113-126, 1963.

References (contd)

71. Meyers, G. E., "Development of Solid Solution Strengthened High Purity Beryllium Alloy Sheet," AD 639838, The Beryllium Corp., Reading, Pa., August 1966.
72. Mainhardt, J. H., "Manufacturing Concepts and Assembly of a Beryllium Wing and Rudder Structure," paper presented at SAE Aeronautics and Space Engineering and Manufacturing Meeting, Los Angeles, Calif., October 3-7, 1966.
73. Finn, J. M., Koch, L. C., and Muehlberger, D. E., *Design, Fabrication and Test of an Aerospace Plane Beryllium Wing Box*, AFFDL-TR-67-38, Air Force Flight Dynamics Laboratory, Wright-Patterson AFB, Ohio, March 1967.
74. *Sixth Monthly Progress Report*, The Boeing Co., Space Division, Kent, Wash., on Contract JPL 951653, April 1, 1967.
75. Rummler, D., Langley Research Center, Langley Field, Virginia, personal communication.
76. Gross, A., Autonetics Division, North American Aviation, Inc., Anaheim, Calif., personal communication.
77. Leischer, K. A., and Green, R. J., *Minuteman Producibility No. 7*, Report C5-1514/32, AD 469658, Navigation Systems, Autonetics Division, North American Aviation, Inc., Anaheim, Calif., July 1965.
78. Langston, M. E., "Materials in an Atlas-Agena Shroud," *Metal Progr.*, Vol. 91, No. 2, pp. 125-130, February 1967.
79. Campagna, F. E., *Development and Demonstration of a Be Rocket Engine*, Vol. 2, AFRPL-TR-66-251, Air Force Rocket Propulsion Laboratory, Edwards AFB, Calif., November 1966.
80. D'Annessa, A. T., "Diffusion Bonding Be, Mo and W," *Metal Progr.*, Vol. 91, No. 2, pp. 71-74, February 1967.
81. Bauer, E. E., Boeing Co., Space Division, Kent, Wash., personal communication, March 1967.
82. Sinizer, D., North American Aviation, Inc., Los Angeles Division, personal communication, March 1967.
83. Paprocki, S. J., Hodge, E. S., and Gripshover, P. J., *Gas-Pressure Bonding*, DMIC Report 159, Defense Metals Information Center, Battelle Memorial Institute, Columbus, Ohio, September 1961.
84. Gripshover, P. J., Battelle Memorial Institute, Columbus, Ohio, personal communication, October 1966.
85. Hodge, E. S., Gripshover, P. J., and Hanes, H. D., *Solid State Bonding of Beryllium*, Battelle Report CONF-729-2 AEC Contract W-7405-eng-92, Battelle Memorial Institute, Columbus, Ohio, October 1964.
86. Weik, H., "Brazeing and Welding of Beryllium," *Metallwiss und Tech.*, Vol. 18, No. 3, pp. 235-243, 1964.

References (contd)

87. Brundige, E. L., et al., "Welding of Be," *Welding J.*, Supp. Vol. 38, pp. 4105-4135, October 1959.
88. Nadler, M. A., and Epstein, G., "Bonding Components in Rocket Motors," *Aerospace Eng.*, Vol. 21, pp. 70, 71, 86, 88, 89, May 1962.
89. Snyder, F., The Boeing Co. Space Division, Kent, Wash., personal communication, February 1967.
90. Cronin, L. R., Kaufman, D. F., and Pickett, J. J., *Beryllium BiCrystal Studies*, AFML-TR-65-242, Vol. II, Air Force Materials Laboratory, Wright-Patterson Air Force Base, Ohio, June 1966.
91. Adolphson, D., Sandia Corp., Albuquerque, New Mexico, personal communication, November 1966.
92. Campbell, J. E., Battelle Memorial Institute, Columbus, Ohio, personal communication, October 1966.
93. Christensen, R. H., *Fatigue Cracking and Residual Strength of Beryllium Panels*, Douglas Report SM47625, Douglas Aircraft Co., Santa Monica, Calif., 1964.
94. Grala, E. M., "Tensile and Notched Strength of QMV Wrought I-400 Beryllium at Cryogenic Temperatures," Brush Beryllium Technical Information Sheet TIS-109, Revision A, The Brush Beryllium Co., Cleveland, Ohio, February 1965.
95. Hodge, W., *Beryllium for Structural Applications — a Review of the Unclassified Literature, 1958-1960*, DMIC Report 168, Defense Metals Information Center, Battelle Memorial Institute, Columbus, Ohio, May 18, 1962.
96. *Be-Al Alloys*, Lockheed Missiles and Space Co., Sunnyvale, Calif., August 16, 1963.
97. Fenn, R. W., Jr., et al., *Evaluation of Be-38% Al Alloy*, Final Report, DCN1-4-50-01262-01851(1F), on Contract NAS 8-11448, Marshall Space Flight Center, Huntsville, Ala., February 28, 1965.
98. Denny, J. P., "Be Ingots and Be Lockalloy Wrought Products," Paper 660633, presented at Aeronautics and Space Engineering and Manufacturing Meeting, Los Angeles, Calif., October 3-7, 1966.

Bibliography

- Advancement of Structural Beryllium Technology*, McDonnell Corp., Contract AF33(615)-1521, Air Force Flight Dynamics Laboratory, Air Force Materials Laboratory, Wright-Patterson AFB, Ohio, 1966.
- Amico, M., *Brazing Type 303 Stainless Steel Fittings to Beryllium*, Report MR1-159, AD 459112, Lockheed Missiles and Space Co., Sunnyvale, Calif., February 1961.

Bibliography (contd)

- Amonenko, V. M., et al., *Study of Beryllium and Chromium Whiskers*, FTD-TT-65-339, AD 618630, Foreign Technology Division, Wright-Patterson Air Force Base, Ohio, July 12, 1965.
- Andrews, C. W., "Effects of Hydrostatic Pressure on Terminal Structure and Mechanical Behavior of Beryllium," *Acta Met.*, Vol. 15, pp. 623-637, April 1967.
- An Investigation of Be and W Altered by High-Pressure Deformation*, AD 613969, Pressure Technology Corp., Woodbridge, New Jersey, November 7, 1964.
- An Investigation of Be and W Altered by High Pressure Deformation*, Engineering Progress Report 4, AD 614086, Pressure Technology Corp., Woodbridge, New Jersey, September 1964.
- An Investigation of Be and W Altered by High Pressure Deformation*, Engineering Progress Report 3, AD 614128, Pressure Technology Corp., Woodbridge, New Jersey, July 1964.
- An Investigation of Be and W Altered by High Pressure Deformation*, Engineering Progress Report 2, AD 614124, Pressure Technology Corp., Woodbridge, New Jersey, May 1964.
- An Investigation of Be and W Altered by High Pressure Deformation*, Engineering Progress Report 1, AD 614236, Pressure Technology Corp., Woodbridge, New Jersey, March 1964.
- Armstrong, H. H., *Weight-Saving Through the Use of Be-Al Alloys for Saturn-Type Vehicle Structures*, HREC/1298-1, Lockheed Missiles and Space Co., Huntsville, Ala., December 1965.
- Armstrong, H. H., Burns, A. B., and Crawford, R. G., "Structural Weight and Cost Comparisons of Large Space Structures Employing Beryllium-Aluminum Alloys," paper published under Contract NAS 8-11298, Marshall Space Flight Center, Huntsville, Ala.
- Armstrong, H. H., and Burns, A. B., "Large Stiffened Cylinder Weight-Cost Comparisons Between Be-38% AP and Other Materials," *J. Spacecraft*, Vol. 4, No. 3, pp. 370-374, April 1967.
- Aronin, L. R., Kaufman, D. F., and Pickett, J. J., *Beryllium BiCrystal Studies*, AFML-TR-65-252, Vol. II, Research and Technical Division, Air Force Materials Laboratory, Wright-Patterson AFB, Ohio, June 1966.
- Barnett, F. E., Finn, J. M., and Koch, L. C., "Beryllium Structures for Aircraft," Paper 660666, paper presented at SAE Aeronautics and Space Engineering and Manufacturing Meeting, Los Angeles, Calif., October 3-7, 1966.
- Beach, J. G., *Electrodeposited, Electroless and Anodized Coatings on Beryllium*, DMIC Memo 197, Defense Metals Information Center, Battelle Memorial Institute, Columbus, Ohio, September 1, 1964.
- Be-Al-Alloys*, Lockheed Missiles and Space Co., Sunnyvale, California, August 16, 1963.
- Bear, W. R., *Beryllium Sheet Fabricability Program*, Report ERR-FW-064, Engineering Dept., General Dynamics, Ft. Worth, Texas, December 30, 1960.

Bibliography (contd)

- Beaver, W. W., and Wikle, K. G., "Mechanical Properties of Be Fabricated by Powder Metallurgy," *J. of Metals*, Vol. 16, May 1964.
- Beryllium Fracture Mechanics*, preliminary report to NASA Research Advisory Committee, Westinghouse Astronuclear Laboratory, Large, Pa.
- Beryllium Research and Development Program*, Quarterly Progress Report, AD 432452, Nuclear Metals Corp., Concord, Mass., August 1963.
- Billman, G. C., *Electromechanical Machining of Beryllium*, Report C5-1190/32, AD 467847, North American Aviation, Autonetics Division, Anaheim, Calif., June 29, 1965.
- Billman, G. C., *Minuteman Producibility Study No. 2B, Beryllium Forgings for Gimbal Rings*, Report C502248/32, AD 477517, North American Aviation, Autonetics Division, Anaheim, Calif., December 1965.
- Bogowitz, R. G., and Metcalf, A. G., *Brazing Beryllium by Capillary Flow*, Solar Report RDR 1502-4, Fourth Progress Report, Air Force Materials Laboratory, Wright-Patterson AFB, Ohio, July 19, 1966.
- Bogowitz, R. G., and Metcalf, A. G., *Brazing Beryllium by Capillary Flow*, Solar Report RD4 1504-7, Interim Progress Report 1, April 1-June 30, 1967.
- Bohmann, G., and Fuchs, W. A., *Beryllium Box Beam Development Program*, Fairchild Hiller Report FHR-3249, Marshall Space Flight Center, Huntsville, Ala., March 1966.
- Bohman, G., "Tooling and Fabrication Technology Development for Beryllium Sheet Metal Structure," paper presented at SAE Aeronautics and Space Engineering and Manufacturing Meeting, Los Angeles, Calif., October 3-7, 1966.
- Boulger, F. W., Rosenfeld, A. R., and Strohecker, D. E., *Survey of the Current Knowledge of the Deformation Characteristics of Beryllium and the Refractory Metals*, Quarterly Progress Report 3, AD 600363, Battelle Memorial Institute, Columbus, Ohio, April 22, 1964.
- Brown, A. R. G., and Jepson, K. S., "Titanium, Beryllium, and the Refractory Metals in the Aircraft Industry," *Proc. Inst. Mech. Eng.*, Vol. 180, Pt. 3D, pp. 75-89, 1965-1966.
- Brundige, E. L., et al., "Welding of Be," *Welding J.*, Supp. Vol. 38, pp. 4105-4135, October 1959.
- Burte, H. M., "Beryllium Materials - Trends in Research, Development, and Potential Use," paper presented at SAE Aeronautics and Space Engineering and Manufacturing Meeting, Los Angeles, Calif., October 3-7, 1966.
- Campagna, F. E., *Development and Demonstration of a Be Rocket Engine, Vol. II*, AFRPL-TR-66-251, Air Force Rocket Propulsion Laboratory, Edwards AFB, Calif.
- Campagna, F. E., *High Energy Propellant Beryllium Thrust Chamber Program*, Phase I Report, AFRPL-TR-67-150, Air Force Rocket Propulsion Laboratory, Edwards AFB, Calif., May 1967.

Bibliography (contd)

- Campbell, J. E., *Review of Recent Developments – Beryllium*, DMIC Technical Note, Defense Metals Information Center, Battelle Memorial Institute, Columbus, Ohio, November 5, 1965.
- Characterization of Beryllium*, MAB 226-M, Materials Advisory Board, National Academy of Sciences, Washington, D. C., August 1966.
- Charest, J. A., and Warnica, R. L., *Spallation Thresholds of I-400 Beryllium*, General Motors Defense Research Laboratories, Santa Barbara, Calif., Sandia Corp. Contract 16-5210, July 1966.
- Christensen, R. H., *Fatigue Cracking and Residual Strength of Beryllium Panels*, Douglas Report SM47625, Douglas Aircraft Co., Santa Monica, Calif.
- Conrad, H., and Perlmutter, I., *Beryllium as a Technological Material*, AFML-TR-65-310, Air Force Materials Laboratory, Wright-Patterson AFB, Ohio, November 1965.
- Cramp, E. E., Hoffpanir, C. R., and Musil, F. J., *Beryllium Sandwich Structure Design Procedures and Test Plan – December 1965*, Report D5-13237, AD 480785L, The Boeing Co., Launch Systems Branch, Huntsville, Ala., March 15, 1966.
- Crawford, R. F., and Burns, A. B., *Design Data for Beryllium*, ASD-TR-61-692, Flight Dynamics Laboratory, Aeronautical Systems Division, Wright-Patterson AFB, Ohio (available from Dept. of Commerce, O.T.S., Washington, D. C.), February 1962.
- Cronin, L. R., Kaufman, D. F., and Pickett, J. J., *Beryllium Bi-crystal Studies*, AFML-TR-65-242, Vol. II, Air Force Materials Laboratory, Wright-Patterson AFB, Ohio, June 1966.
- Croutzeiller, M., et al., *Beryllium Research and Development Program. Identification of Inclusions and Precipitates in Beryllium of Different Origins*, Final Report ASD TDR-62-509, Vol. 7, AD 464834, Nuclear Metals Division, Textron, Concord, Mass., February 1965.
- Czechanski, W. B., and Goodman, E., *Surface Finishing of Fine Beryllium Wire*, RTD IR-9-148, Vol. 1, AD 801482, Value Engineering Co., Alexandria, Va., October 1966.
- Danforth, A. L., and Krashes, D., "Polishing Beryllium by Vibration," *Metal Progr.*, Vol. 91, No. 2, p. 115, February 1967.
- D'Annessa, A. T., "Diffusion Bonding Be, Mo, and W," *Metal Progr.*, Vol. 91, No. 2, pp. 71-74, February 1967.
- Dastin, S. J., "Bonded Be Structures," Republic Aviation Corporation Paper V-3, presented at the Ninth National Society of Aerospace Materials and Process Engineers, Dayton, Ohio, November 14-16, 1966.
- Dastin, S. J., "Bonded Beryllium Structures," *Adhesives Age*, Vol. 9, pp. 24-27, May 1966.
- Darwin, G. E., and Buddery, J. H., *Metallurgy of the Rarer Elements—Beryllium*, Academic Press, New York, 1960.

Bibliography (contd)

- Darwin, G. E., and Taylor, P. G., Chapter 5 in *Materials in Space Technology*. Edited by G. V. Thompson. Gordon and Breach, New York, 1963.
- Dedrick, J. H., Clayton, H. R., and Fisher, P. A., "Recent Developments in Light Alloys for Engineering Applications," *Proc. Inst. Mech. Eng.*, Vol. 180, Pt. 3D, pp. 142-144, 1965-1966.
- Deesing, E. F., *Electron Beam Brazing of Beryllium*, NAEC-AML-1997, AD-603192, Naval Air Engineering Center, Aeronautical Materials Laboratory, Philadelphia, Pa., July 27, 1964.
- De Haven, J. C., *Why Beryllium?*, AD 606850, Rand Corp., Santa Monica, Calif., March 14, 1958.
- Denny, J. P., *Development of an Economic Process for the Production of .005 Inch Diameter Beryllium Wire*, Interim Progress Report, AD 434819, The Beryllium Corp., Reading, Pa., January 31, 1964.
- Denny, J. P., *Development of a Manufacturing Process for the Production of .005 Inch Diameter Beryllium Wire*, Interim Technical Document on Contract AF 33(657)-11271, AD 444108, The Beryllium Corp., Reading, Pa., June 1, 1964.
- Denny, J. P., and Stitzlein, C. F., "Beryllium Fine Wire," paper presented at the 96th Annual Meeting of the AIME, Los Angeles, Calif., February 23, 1967.
- Denny, J. P., "Beryllium Ingots and Beryllium Lockalloy Wrought Products," Paper 660633, presented at SAE Aeronautics and Space Engineering and Manufacturing Meeting, Los Angeles, Calif., October 3-7, 1966.
- Dickason, R. C., *Beryllium Forming, Preliminary Hot Drawing Tests*, CMRI 1351, Lockheed Aircraft Corp., Burbank, Calif., January 9, 1967.
- Effects of Thermo-Mechanical Variables on the Texture and Bend Ductility of High Purity Beryllium Sheet*, Report I-B2106-1, AD 426848, The Franklin Institute, Philadelphia, Pa., December 15, 1963.
- Eighth Progress Report by the Committee on Beryllium Metallurgy, Production of Fine Beryllium Wire*, MAB 199-M(8), Metals Advisory Board, National Academy of Sciences, Washington, D. C., August 1966.
- Ells, C. E., and Weir, J. R., "Effect of Neutron Irradiation on the Plastic Deformation and Fracture of Beryllium," *J. of Nucl. Mat.*, Vol. 13, No. 1, pp. 49-56, 1966.
- Evaluation Test Methods for Beryllium*, MAB-205-M, Materials Advisory Board, NAS-NRC, Washington, D. C., March 1966.
- Evaluation of Fine, Anodized Beryllium Wire*, NAEC AML 1943, AD 439085, Aeronautical Materials Laboratory, Naval Air Material Center, Philadelphia, Pa., May 7, 1964.

Bibliography (contd)

- Evans, R. M., "Review of Recent Developments – Metal Joining," DMIC Letter, Battelle Memorial Institute, Columbus, Ohio, December 22, 1966.
- Evans, R. E., and Lowe, J. N., *Development of Beryllium Sheet with High Yield Strength and Ductility*, AFML-TR-65-327, AD 474605, Atomic Weapons Research Establishment, Aldermaston, England, September 1965.
- Evans, G. R., *Beryllium Fabrication: A Compilation of LSMC-Generated Reports*, Report LSMC-LS-63, AD 479787L, Lockheed Missiles and Space Co., September 1964.
- Evans, G. R., *Beryllium Fabrication Methods: An Annotated Bibliography*, Report LSMC-LS-58, AD 479798L, Lockheed Missiles and Space Co., Sunnyvale, Calif., August 1964.
- Farthing, T. W., and Leech, J. R., "Beryllium Technology," *Proc. Inst. Mech. Eng.*, Vol. 180, Pt. 3D, pp. 16–23, 1965–1966.
- Feasibility of Fabricating Structural Components from Beryllium Tubing*, Report MDR 2-20535, AD 457044, The Boeing Co., Seattle, Wash., August 31, 1964.
- Fenn, R. W., Jr., Crooks, D. C., Brodie, R. W., and Chinowsky, S., "Comparison of Lightweight Structural Materials: Be and Alloys of Be, Mg, Al and Ti," Paper 660652, presented at SAE Aeronautics and Space Engineering and Manufacturing Meeting, Los Angeles, Calif., October 3–7, 1966.
- Fenn, R. W., Jr., et al., *Evaluation of Be-38% Al Alloys*, Final Report DCN1-4-50-01262-01262-01851(1F), on Contract NAS 8-11448, Marshall Space Flight Center, Huntsville, Ala., February 28, 1965.
- Fenn, R. W., et al., "A Mechanical Property Evaluation of Be-38% Al Alloy from –320 to 800°F," *Metals Eng. Quarterly*, Vol. 5, pp. 37–47, November 1965.
- Fenn, R. W., Jr., Crooks, D. D., and Pasternak, R. C., "New Ductile Be-Al Wrought Alloys," *ASTM Symposium on Newer Structural Materials for Aerospace Vehicles*, ASTM Special Publication No. 379, 67th Annual Meeting, American Society for Testing Materials, Philadelphia, Pa., 1964.
- Fiber-Reinforced Metals and Alloys*, Bimonthly Report 6, AD 405939, Armour Research Foundation (now IITRI), May 3, 1963.
- Finn, J. M., Koch, L. C., and Muehlberger, D. E., *Design, Fabrication and Test of an Aerospace Plane Beryllium Box Beam*, AFFDL-TR-67-38, Air Force Flight Dynamics Laboratory, Wright-Patterson AFB, Ohio, March 1967.
- Finn, J. M., Koch, L. C., Muehlberger, D. E., *Design, Fabrication and Ground Testing of the F-4 Beryllium Rudder*, AFFDL-TR-67-68, Air Force Materials Laboratory, Wright-Patterson Air Force Base, Ohio, April 1967.
- First Quarterly Report*, Contract AF33(615) 1521, McDonnell Aircraft Corp., Air Force Materials Laboratory, Wright-Patterson AFB, Ohio.
- First Quarterly Report*, Report D2-113355-1, Contract JPL 951653, The Boeing Co., Space Division, Kent, Washington, January 1967.

Bibliography (contd)

- FitzGerald, A. F., *Electrodeposition of Beryllium Metal: An Annotated Bibliography*, Report LSMC-LS-66-30, AD 805359L, Lockheed Missiles and Space Co., Sunnyvale, Calif., December 1966.
- Frazier, V. L., *Defense Metals Information Center Selected Acquisitions*, AD 272087, Battelle Memorial Institute, Cleveland, Ohio, January 1962.
- Fredlyander, I. N., et al., "Al-Be Base Alloys," translation from *Metallovedeniye i Termicheskaya, Obratolka Metallov*, No. 3, pp. 2-5, March 1965.
- Gelles, S. H., Nerses, V., and Siergiej, J., "Beryllium as a Structural Material," *J. of Metals*, Vol. 15, No. 11, pp. 843-48, November 1963.
- Gelles, S. H., *Beryllium Research and Development Programs*, ASD-TDR-62-509, Vol. 2, AD 406872, Nuclear Metals Corp., Concord, Mass., April 1963.
- Gelles, S. H., *Beryllium Research and Development Program*, Report NMI-9522, AD 294323, Nuclear Metals Corp., Concord, Mass., November 5, 1962.
- Goldmann, J. B., *Beryllium: An Annotated Bibliography, July-September 1962 Supplement II Special Bibliography SB-62-22*, 3-80-62-30, Lockheed Missiles and Space Co., Sunnyvale, Calif. (available from ASTIA or Office of Technical Services, Dept. of Commerce, Wash., D. C.), April 1963.
- Goldmann, J. B., *Beryllium: A Survey of the Literature January-June 1963: An Annotated Bibliography*, Report No. 3-80-63-5, 5363-54, AD 439444, Lockheed Missiles and Space Co., Sunnyvale, Calif., July 1963.
- Goldmann, J. B., *Beryllium: An Annotated Bibliography, April-June 1962*, AD 296346, Lockheed Missiles and Space Co., Sunnyvale, Calif., October 1962.
- Goldmann, J. B., *Beryllium: A Survey of the Literature, April-July 1961*, Report 3-80-61-6, AD 271 939, Lockheed Missiles and Space Co., Sunnyvale, Calif., October 1961.
- Grala, E. M., *Tensile and Notched Strength of QMV Wrought I-400 Beryllium at Cryogenic Temperatures*, Brush Beryllium Technical Information Sheet TIS-109, Revision A, Brush Beryllium Co., Cleveland, Ohio, February 1965.
- Greenspan, J., and Kaufman, A. R., *Beryllium Research and Development in the Area of Composite Materials*, Quarterly Progress Report 1, NMI 9402, AD 604584, Nuclear Metals Corp., Concord, Mass., December 1, 1958.
- Gross, A. H., Jr., "Primary Recrystallization in Commercially Pure Beryllium," *J. of Nucl. Materials*, Vol. 13, No. 1, pp. 1-12, 1964.
- Gross, A. G., and Colteryahn, L. E., *Effects of Thermal-Mechanical Variables on the Anisotropy of Forged Beryllium*, AFML-TR-66-333, Air Force Materials Laboratory, Wright-Patterson AFB, Ohio, December 1966.
- Gumnick, K. F., "Aerospace Industry Be Materials Utilization," paper presented at SAE Aeronautics and Space Engineering and Manufacturing Meeting, Los Angeles, Calif., October 3-7, 1966.
- Gurev, H. S., "Review of Recent Developments - High Energy Rate Processes," DMIC Letter, Battelle Memorial Institute, Columbus, Ohio, February 17, 1967.
- Hanes, H. D., "Review of Recent Developments - Beryllium," DMIC Letter, Battelle Memorial Institute, Columbus, Ohio, February 4, 1966.

Bibliography (contd)

- Hanes, H. D., "Review of Recent Developments—Beryllium," DMIC Letter, Battelle Memorial Institute, Columbus, Ohio, May 5, 1966.
- Hanes, H. D., and Zurney, F. T., "Review of Recent Developments—Beryllium," DMIC Letter, Battelle Memorial Institute, Columbus, Ohio, September 23, 1966.
- Hanes, H. D., and Zurney, F. T., "Review of Recent Developments—Beryllium," DMIC Letter, Battelle Memorial Institute, Columbus, Ohio, December 30, 1966.
- Hanes, H. D., et al., *Physical Investigation of Beryllium*, DMIC Report 230, Defense Metals Information Center, Battelle Memorial Institute, Columbus, Ohio, June 24, 1966.
- Hauser, D., et al., *Electron-Beam Welding of Beryllium*, AFML-TR-66-215, Systems Engineering Group (RTD), Air Force Systems Command, Wright-Patterson AFB, Ohio, July 1966.
- Hauser, D., Monroe, R. E., and Martin, D. C., *Electron-Beam Welding of Beryllium*, Systems Engineering Group (RTD), Air Force Systems Command, Wright-Patterson AFB, Ohio, March 1, 1967.
- Hausner, H. H., *Beryllium: Its Metallurgy and Properties*, University of California Press, Berkeley and Los Angeles, 1965.
- Hayes, A. F., and Noel, R., *Development and Evaluation of Forging Parameters in the Manufacture of Conical Beryllium Structural Shapes*, IR 8-247(V), Manufacturing Technology Division, Air Force Materials Laboratory, Wright-Patterson AFB, Ohio, February 1966.
- Hayes, A. F., and Yoblin, A., *Development of Manufacturing Process for Forging Engine Parts Made of Beryllium*, Interim Engineering Progress Report, RTD IR-8-247/Vol. 3, AD 460361, Ladish Co., Cudahy, Wis., March 1, 1965.
- Hayes, A. F., and Yoblin, J. A., *Development of Manufacturing Process for Forging Engine Parts Made of Beryllium*, Interim Engineering Progress Report, ASD IR-8-247/Vol. 2, AD 459615, Ladish Co., Cudahy, Wis., December 1, 1964.
- "Health Hazards of Beryllium Can be Controlled," *Safety Maintenance*, Vol. 1, No. 1, pp. 32-36, 1 July 1958.
- Herman, M., et al., *Flow and Fracture Studies of High Purity and Alloyed Beryllium*, Quarterly Report, AD 620241, Franklin Institute, Philadelphia, Pa., October 6, 1964.
- Herman, M., et al., *Flow and Fracture Studies of High Purity and Alloyed Beryllium*, AD 620589, Franklin Institute, Philadelphia Pa., January 6, 1965.
- Herman, M., et al., *Flow and Fracture Studies of High Purity and Alloyed Beryllium*, Final Report, AD 620188, Franklin Institute, Philadelphia, Pa., August 1965.
- Hessler, R. H., "Rolling of Beryllium Sheet Takes Special Care," *Iron Age*, Vol. 186, No. 22, pp. 136-138, December 1, 1960.
- Hill, N. A., "Variation of Tensile and Bend Properties in a Beryllium Sheet," *J. of Nucl. Materials*, Vol. 5, No. 2, pp. 193-199, 1962.

Bibliography (contd)

- Hodge, W., *Beryllium for Structural Application – A Review of the Unclassified Literature 1958–1960*, DMIC Report 168, Defense Metals Information Center, Battelle Memorial Institute, Columbus, Ohio, May 18, 1962.
- Hodge, E. S., Gripshover, P. J., and Hanes, H. D., *Solid State Bonding of Beryllium*, Battelle Report CONF-729-2 on AEC Contract W-7405-eng-92, Battelle Memorial Institute, Columbus, Ohio, October 1964.
- Hodge, W., *Review of Recent Developments in the Technology of Beryllium*, DMIC Memo 123, Defense Metals Information Center, Battelle Memorial Institute, Columbus, Ohio, August 18, 1961.
- Hoffman, G. A., *Beryllium as an Aircraft Structural Material*, P-871, Rand Corp., Santa Monica, Calif., May 28, 1956.
- Hoffmanner, A. L., *Study of Methods to Produce Composite Beryllium Blades*, First Bimonthly Report on Contract No. W65-0281-F, Bureau of Naval Weapons, Washington, D. C., May 28, 1965.
- Hoffmanner, A. L., *Study of Methods to Produce Composite Beryllium Blades*, Report ER-65-45-7, AD 488053, TRW, Cleveland, Ohio, August 12, 1966.
- Holden, F. C., and Bolger, F. W., *U. S. Government Metalworking Processes and Equipment Program*, DMIC Report 201, Defense Metals Information Center, Battelle Memorial Institute, Columbus, Ohio, March 18, 1964.
- Holden, F. C., and Bolger, F. W., *Second Status Report of the U. S. Government Metalworking Processes and Equipment Program*, DMIC Report 209, Defense Metals Information Center, Battelle Memorial Institute, Columbus, Ohio, November 23, 1964.
- Holden, F. C., and Bolger, F. W., *Third Status Report of the U. S. Government Metalworking Processes and Equipment Program*, DMIC Report 218, Defense Metals Information Center, Battelle Memorial Institute, Columbus, Ohio, June 16, 1965.
- Holden, F. C., and Bolger, F. W., *Fifth Status Report of the U. S. Government Metalworking Processes and Equipment Program*, DMIC Report 225, Defense Metals Information Center, Battelle Memorial Institute, Columbus, Ohio, June 10, 1966.
- Holden, F. C., and Bolger, F. W., *Sixth Status Report of the U. S. Government Metalworking Processes and Equipment Program*, DMIC Report 233, Defense Metals Information Center, Battelle Memorial Institute, Columbus, Ohio, November 21, 1966.
- Hornak, M. B., et al., *Rolling Improved Beryllium Sheet*, Final Report, ML TDR 64-193, AD 451646, The Brush Beryllium Co., Cleveland, Ohio, April 1964.
- Ingels, S. E., "Ductility of Cross-Rolled Beryllium Sheet – Barrier or Challenge," Report LMSC-A-820503, Lockheed Missiles and Space Co., Sunnyvale, Calif., March 15, 1966.
- Inoue, N., et al., *Effects of Prestraining Under Hydrostatic Pressure on the Mechanical Behavior of Polycrystalline Beryllium*, AFML-TR-67-64, Air Force Materials Laboratory, Wright-Patterson AFB, Ohio, January 1967.

Bibliography (contd)

- International Conference on the Metallurgy of Beryllium, Grenoble, France, May 17-20, 1965*, Presses Universitaires de France, Paris, 1966.
- Jacobson, M. I., *Beryllium Research and Development Program. Metallurgical Factors Affecting the Ductile-Brittle Transition in Beryllium*, ASD TDR 62-509, Vol. 5, AD 604599, Textron, Nuclear Metals Division, July 1964.
- Jenkins, R. G., and Siergie, J. M., *Development of Improved Fabrication Methods, Process and Techniques for Producing Typical Aircraft Shapes from Beryllium*, Report NMI-9701.3, AD 294006, Nuclear Metals Corp., Concord, Mass., December 28, 1962.
- Kassowsky, R., "Twinning in Beryllium Binary Alloys During Pressurization in a Solid Medium," *Trans. AIME*, Vol. 239, pp. 828-834, June 1967.
- Kaufman, D. F., *Beryllium Bi-Crystal Studies*, Interim Engineering Report, AD 461371, Textron, Nuclear Metals Division, September 30, 1964.
- Kaufmann, A. R., *Beryllium Research and Development Program*, ASD TDR 62-509, Vol. 3, AD 606666, Nuclear Metals, Concord, Mass., July 1964.
- Keller, J. A., Natwick, J. W., and Majeske, F. J., *Manufacturing Research Investigation, Chemical Conversion Coating for Blackening Beryllium*, AD 292351, Lockheed Missiles and Space Co., Sunnyvale, Calif., February 6, 1961.
- Kennon, J. L., *Beryllium to Magnesium Adhesive Qualification Test Program*, Report LMSC-849726, AD 487909, Lockheed Missiles and Space Co., Sunnyvale, Calif., October 16, 1963.
- Kennon, J. L., *Beryllium Joint Evaluation Stress Relief vs. Non-stress Relief*, Report LSMC-847992, AD 487910, Lockheed Missiles and Space Co., Sunnyvale, Calif., August 30, 1963.
- Khorenko, V. K., Kornienko, L. A., and Matvienko, B. V., "Study of the Oxidation of Thin Films of Beryllium," *Russian J. of Phys. Chem.*, Vol. 40, No. 8, pp. 1020-1023 (in English), August 1966.
- King, B., "The Mechanical Properties of Beryllium," "Beryllium, Its Properties and Applications," UCLA short course, April 4-8, 1963.
- King, B., *Performance of Cross-Rolled Sheet in Structural Applications*, The Brush Beryllium Co., Cleveland, Ohio, March 1965.
- King, Bryce, "Beryllium Sheet - Today, Tomorrow, the Future," paper presented at SAE Aeronautics and Space Engineering and Manufacturing Meeting, Los Angeles, Calif., October 3-7, 1966.
- King, J. P., Jr., Robelotto, R. P., and Dillingham, A. C., Jr., *Diffusion Bonding of Titanium and Beryllium*, Interim Engineering Progress Report, IR 8-318(IV), Manufacturing Technology Division, Air Force Materials Laboratory, Wright-Patterson AFB, Ohio, August 1966.
- King, J. P., Jr., Robelotto, R. P., and Dillingham, A. C., Jr., *Diffusion Bonding Ti and Be*, IR-8-318(V), North American Aviation, Report No. NA 65-840-4, Manufacturing Technology Division, Air Force Materials Laboratory, Wright-Patterson AFB, Ohio, November 1966.

Bibliography (contd)

- King, J. P., Jr., Robelotto, R. P., and Dillingham, A. C., Jr., *Diffusion of Titanium and Beryllium*, IR-8-318(VI), North American Aviation, Report No. NA 65-850-5, Manufacturing Technology Division, Air Force Materials Laboratory, Wright-Patterson AFB, Ohio, February 1967.
- Klein, J. G., "Fabrication and Properties of Beryllium Wire," paper presented at 96th Annual Meeting of the AIME, Los Angeles, Calif., February 23, 1967.
- Kojola, K. L., "Metallurgical Aspects of Beryllium Joining Technology," Ninth National Symposium of Society of Aerospace Materials and Process Engineers, Joining of Materials for Aerospace Systems, Dayton, Ohio, November 14-16, 1965 (published by Western Periodicals Co., North Hollywood, Calif., 1965).
- Kosinski, E. J., and Hayes, A. F., "Recent Advances in Forging Beryllium," Paper 660634, paper presented at SAE Aeronautics and Space Engineering and Manufacturing Meeting, Los Angeles, Calif., October 3-7, 1966.
- Kurson, J. L., Kyelby, A. S., Borosic, J., and Eck, F. B., "Beryllium-Faced Sandwich Structures," *Materials Research and Standards*, Vol. 3, pp. 825-831, October 1963.
- Krusos, J. N., et al., *Beryllium Composite Structures, Vol. I. Design and Application*, ASD-TR-61-706, Manufacturing Technology Division, Air Force Materials Laboratory, Wright-Patterson AFB, Ohio, May 1962.
- Krusos, J. N., et al., *Beryllium Composite Structures, Vol. II*, ASD-TR-61-706, Vol. II, Manufacturing Technology Division, Air Force Materials Laboratory, Wright-Patterson AFB, Ohio, June 1962.
- Krusos, J. N., et al., *Sheet Be Composite Structures*, ASD-TR-7-845(II), AD 276815, Manufacturing Technology Division, Air Force Materials Laboratory, Wright-Patterson AFB, Ohio, April 1962.
- Laboratory and Flight Evaluation of Aircraft Aircooled Wheel Brakes with Beryllium Heat Sink*, Report LB-31550, AD 603758, Douglas Aircraft Co., Santa Monica, Calif., December 20, 1963.
- Landusky, C. A., *Mechanical Properties of Beryllium Wire*, Report M-2109, AD 297684, Aerojet-General Corp., Azusa, Calif., November 20, 1961.
- Langston, M. E., "Materials in an Atlas-Agena Shroud," *Metal Progr.*, Vol. 91, No. 2, pp. 125-130, February 1967.
- Lawley, A., Breedis, J. F., and Meakin, J. D., "Microstain Behavior of Be Single Crystals," *Acta Met.*, Vol. 14, pp. 1339-1347, October 1966.
- Lawley, A., and Meakin, J. D., "Friction and Micro-yielding of Beryllium," *Acta Met.*, Vol. 14, pp. 236-240, 1966.
- Leadbetter, C. J., "Beryllium," *J. Royal Aeronautical Soc.*, Vol. 70, pp. 781-787, August 1966.
- Leischer, K. A., and Green, R. J., *Minuteman Producibility No. 7*, Report C5-1514/32, AD 469658, Navigation Systems, Autonetics Division, North American Aviation, Anaheim, Calif., July 1965.

Bibliography (contd)

- Loewenstein, P., "Production of Structural Shapes and Tubing of Beryllium and Beryllium Alloys," paper presented at SAE Aeronautics and Space Engineering and Manufacturing Meeting, Los Angeles, Calif., October 3-7, 1966.
- Loucks, T. L., *Further Results on the Fermi Surface of Beryllium*, AFSOR 64 2107, AD 451734, Pennsylvania State University, University Park, Pa., January 3, 1964.
- LMSD Beryllium Evaluation Program*, Report LMSD-800-257, AD 465201, Lockheed Missiles and Space Co., Sunnyvale, Calif., October 15, 1960.
- "Lunar Module Will Carry Beryllium Radio Antenna," *Materials in Design Engineering*, Vol. 65, No. 2, p. 46, February 1967.
- Mainhardt, J. H., "Manufacturing Concepts and Assembly of a Beryllium Wing and Rudder Structure," paper presented at SAE Aeronautics and Space Engineering and Manufacturing Meeting, Los Angeles, Calif., October 3-7, 1966.
- Maltsev, M. V., Morozov, L. N., Zverev, K. P., and Efremov, Yu N., "Oxidation of Be When Heated in Air," *Izv. VUZ Tsvetnaya Met.*, No. 1, pp. 116-118, 1966 (in Russian).
- Mechanical Evaluation of the First Production Primary Beryllium Spacer*, Report R210-8-64-53, AD 457626, AVCO, Research and Advanced Development Division, Wilmington, Mass., November 24, 1964.
- Mechanical Property Data 62 Be-38 Al Alloy Annealed Sheet*, AD 278723, Air Force Materials Laboratory, Wright-Patterson AFB, Ohio, March 1967.
- Meyers, G. E., *Development of Solid Solution Strengthened High Purity Be Alloy Sheet*, AD 639838, The Beryllium Corp., Reading, Pa., August 1966.
- Meyers, G. E., Denny, J. P., *Casting and Hot-Working of Sound, Large Diameter Beryllium Ingots, Phase III*, RTD-IR8-120, Vol. 4, AD 455764, The Beryllium Corp., Reading, Pa., September 1, 1964.
- Meyers, G. E., *Casting and Hot-Working of Sound, Large Diameter Beryllium Ingots*, Final Report AFML-TR-65-361, AD 475603, The Beryllium Corp., Reading, Pa., September 1965.
- Missel, L., and Shaheen, M. E., "Chemical Milling of Be," *Metal Finishing*, Vol. 63, pp. 69-71, November 1965.
- Moment, R. L., "Elastic Anisotropy of Rolled Beryllium," *Trans. AIME*, Vol. 239, pp. 542-546, April 1967.
- Morrow, F., White, J. S., Williams, A. H., *Machining Damage Studies in Beryllium*, AD 464769, Ministry of Aviation, London, April 1965.
- Muller, W. C., Wolff, A. K., and Kaufmann, A. R., *Study of Methods to Control Grain Size, Purity and Texture in Beryllium and Beryllium Alloys*, Report NMI-8001.6, AD 478594, Textron, Nuclear Metals Division, Concord, Mass., March 1, 1966.

Bibliography (contd)

- Murphy, E. A., Hornak, M. B., and O'Rourke, R. G., *Developing Technology to Forge Unclad Beryllium*, Final Report AFML-TR-65-30, Manufacturing Technology Division, Air Force Materials Laboratory, Wright-Patterson AFB, Ohio, January 1965.
- Murphy, E. A., and O'Rourke, R. G., *Fabrication of Ultrafine Beryllium Wire*, Final Report on Contract NOw 63-0137, AD 419008, The Brush Beryllium Co., Cleveland, Ohio, August 1, 1963.
- Murphy, E. A., and O'Rourke, R. G., *Fabrication of Ultrafine Beryllium Wire*, Final Report on Contract NOw 64-0162, AD 610316, The Brush Beryllium Co., Cleveland, Ohio, December 7, 1964.
- Nadler, M. A., and Epstein, G., "Bonding Components in Rocket Motors," *Aerospace Eng.*, Vol. 21, pp. 70, 71, 86, 88, 89, May 1962.
- Oken, S., and Dilks, B. H., *Structural Evaluation of Beryllium Solar Panel Spars*, AFFDL-TR-65-45, Air Force Flight Dynamics Laboratory, Wright-Patterson AFB, Ohio, August 1966.
- Orrell, N. G., *The Fabrication of Beryllium Powder Forging*, Report RD-63-105, AD 430386, Wyman Gordon Co., Worcester, Mass., 1963.
- Paine, R. M., et al., *High Strength, High Modulus, Low Density Continuous Filaments of Beryllium*, AFML-TR-65-318, AD 474754L, The Brush Beryllium Co., Cleveland, Ohio, September 1965.
- Paprocki, S. J., Hodge, E. S., and Gripshover, P. J., *Gas-Pressure Bonding*, DMIC Report 159, Defense Metals Information Center, Battelle Memorial Institute, Columbus, Ohio, September 1961.
- Paragraph on Be Brittleness, *Materials Engineering*, Vol. 65, No. 4, p. 6, April 1967.
- Perlstein, F., Wick, R. W., and Galloccio, A., *Protection of Beryllium Against High Temperature Oxidation*, Report FA A66-6, AD 632835, Pitman-Dunn Research Laboratories, Frankford Arsenal, Philadelphia, Pa., January 1966.
- Pinto, N. P., and Denny, J. P., "Beryllium Wire: A New Engineering Material," *Metal Progr.*, Vol. 91, No. 6, pp. 107, 108, 110, 112, 114, June 1967.
- Poirier, J. P., Antolin, J., and Dupoy, J. M., "Investigations on Some Deformation Modes of Beryllium," *Canadian J. of Phys.*, Vol. 45, No. 2, pp. 1221-1224, February 1967.
- Porembka, S. W., and Hanes, H. D., *Surface Damage in Machined Be*, DMIC Memo 198, Defense Metals Information Center, Battelle Memorial Institute, Columbus, Ohio, January 4, 1965.
- Porembka, S. W., and Hanes, H. D., *Beryllium Ingot Sheet*, DMIC Memo 206, Defense Metals Information Center, Battelle Memorial Institute, Columbus, Ohio, August 10, 1965.
- Preliminary Evaluation of Beryllium Sheet*, Report A068, AD 417310, McDonnell Aircraft Co., St. Louis, Mo., September 10, 1963.

Bibliography (contd)

- Prochko, R. J., Myers, J. R., and Saper, R. K., "Corrosion of Beryllium by Salt Water," *Materials Protection*, Vol. 5, pp. 39-42, December 1966.
- Properties of Beryllium*, General Astrometals Corp., Yonkers, New York, 1961.
- Ranzetta, G. V. T., and Scott, V. D., "The Effect of Thermal Treatment on the Metallographic Structure of Be and Dilute Be Alloys," *J. Nucl. Materials*, Vol. 10, No. 2, pp. 113-126, October 1963.
- Rebholz, M. J., "Application of Beryllium on the Agena," *J. Spacecraft*, Vol. 3, No. 5, pp. 715-722, May 1965.
- Rebholz, M. J., and Wolff, G. E., *Beryllium Design and Development*, Report LMSC/A701583, AD 471000, Lockheed Missiles and Space Co., Sunnyvale, Calif., September 25, 1964.
- Rebholz, M. J., *Buckling Strength of Curved Beryllium Panels*, AD 624644, Lockheed Missiles and Space Co., 1964, presented at International Symposium on Beryllium Metallurgy, Philadelphia, Pa., October 15-17, 1964.
- Riedinger, L. A., and Foster, R. E., *Beryllium Applications in Structural Design*, Report No. LMSD-2643, AD 615599, Lockheed Missiles and Space Co., Sunnyvale, Calif., January 1958.
- Seventh Progress Report by the Committee on Beryllium Metallurgy of the Materials Advisory Board*, MAB-199(M7), National Academy of Sciences, Washington, D. C., June 1966.
- Sibert, M. E., and Hulquist, A. E., "Production of Be Alloys," *J. Metals*, Vol. 18, No. 11, pp. 1215-1222, November 1966.
- Siergiez, J. M., "Extrusion of Beryllium Structural Shapes," *ASTM Special Technical Publication No. 379, Newer Structural Materials for Aerospace Vehicles*, American Society for Testing Metals, Philadelphia, Pa., pp. 106-118, 1964.
- Singletary, J. B., and Rittenhouse, J. B., "The Effects of Space Environment on Structural Materials," Paper 660675, presented at SAE Aeronautics and Space Engineering and Manufacturing Meeting, Los Angeles, Calif., October 3-7, 1966.
- Sixth Progress Report by the Committee on Beryllium Metallurgy of the Materials Advisory Board*, MAB 199M(6), National Academy of Sciences, Washington, D. C., April 1966.
- Smallwood, W. R., *Beryllium Erosion Corrosion Investigation for Solid Rocket Nozzles*, AFRPL-TR-66-71, AD 372384, Philco Corp., Aeronutronic Division, Newport Beach, Calif., May 1966.
- Snider, R. E., and Kahles, J. F., *Machining Data for Be*, AFMDL 66-3, Air Force Machinability Data Center, Manufacturing Technology Division, Air Force Materials Laboratory, Wright-Patterson AFB, Ohio, June 1966.
- Sofa, L. L., and Basl, G. J., *High Strength Forged Beryllium for Structural Application*, Report REK-D-H-005, AD 468107, Rocketdyne Division, North American Aviation, Canoga Park, Calif., October 15, 1964.

Bibliography (contd)

- Soltis, P. J., *Study of the Size Effect in Fine Beryllium Wire, Phase II*, NAEC AML 1909, AD 438478, Naval Air Engineering Center, Philadelphia, Pa., March 27, 1964.
- Soltis, P. J., Golding, W. H., *Elevated Temperature Strength of Fine Beryllium Wire, Phase II*, NAEC-AML-2256, Naval Air Engineering Center, Philadelphia, Pa., August 4, 1965.
- Spangler, G. E., et al., *Preparation and Evaluation of High Purity Beryllium*, AD 620264, Franklin Institute, Philadelphia, Pa., November 14, 1964.
- Spangler, G. E., et al., *Preparation and Evaluation of High Purity Beryllium*, Final Report, Contract N0w 62-0536, AD 418422, The Franklin Institute, Philadelphia, Pa.
- Stack, E., "Forming Exotic Materials by Use of High Pressure Hydraulics," ASTME Special Publication SP 65-127, ASTME, Dearborn, Mich., 1965.
- Steinberg, M. A., and Kerfoot, H. P., "Design of High Temperature Structural Systems," paper from *High Temperature Technology*, Butterworth and Company, London, 1964.
- Straka, K., *Beryllium and Its Alloys in the Aviation Industry*, TT-64-1027, AD 470330, Foreign Technology Division, Wright-Patterson AFB, Ohio, June 9, 1965.
- Sumner, G., "Brittle Behavior in Extruded Beryllium Tubes," *International J. Fracture Mech.*, Vol. 2, No. 2, pp. 448-459, June 1966.
- Terry, E. L., and King, B., *Static and Repeated Loading Characteristics of Joints in Beryllium Structures*, The Brush Beryllium Co., Cleveland, Ohio, March 1965.
- The Metal Beryllium*, edited by D. W. White, Jr., and J. E. Burke, American Society for Metals, Cleveland, Ohio, 1955.
- "Typical Questions Re: Beryllium Aircraft/Aerospace Applications," Lockheed Missiles and Space Co., Sunnyvale, Calif., Special Products Services, September 1, 1966.
- Van Hammersveldt, J., "Satellite Structural Parts, Beryllium Lockalloy," Paper SSD60355B, presented at SAE Aeronautics and Space Engineering and Manufacturing Meeting, Los Angeles, Calif., October 3-7, 1966.
- Van Hammersveldt, J., Svendsen, T. S., and Hayes, W. C., "Making Satellite Structures from Beryllium Lockalloy," *Metal Progr.*, Vol. 91, No. 2, pp. 91-95, February 1967.
- Van Torne, L. I., "Point Defect Scattering in Beryllium," *Phys. Status Solidi*, Vol. 18, pp. 737-742, 1966.
- Veltri, R. D., and Cox, J. E., *Investigation of a Process for the Production of Metallic Filaments*, Report E9 10342-5, AD 633527, United Aircraft Corp., E. Hartford, Conn., June 8, 1966.

Bibliography (contd)

- Weik, H., "Brazing and Welding of Beryllium," *Metallwiss und Tech.*, Vol. 18, No. 3, pp. 235-243, 1964.
- Westlund, E. F., and Lohmann, H. G., "Vapor-Plating Aluminum on Beryllium," *Welding J.*, Vol. 46, No. 3, pp. 207-210, March 1967.
- Wilhelm, F., and Wilsdorf, H. G. F., *Beryllium Research and Development Program. A Study of the Brittle Behavior of Beryllium by Means of Transmission Electron Microscopy*, ASD TDR 62-509, Vol. 4, AD 606667, Nuclear Metals, Concord, Mass., July 1964.
- Williams, R. F., and Ingels, S. E., *Forming Techniques for Beryllium Alloys*, NASA TMX-53453, Marshall Space Flight Center, Huntsville, Ala., July 1966.
- Williams, R. F., and Ingels, S. E., *Joining Beryllium*, NASA TMX-53453, Vol. 6, Marshall Space Flight Center, Huntsville, Ala., July 1966.
- Williams, R. F., and Ingels, S. E., *Fabrication of Beryllium - A Survey of Current Technology*, NASA-TMX-53453, Vol. 1, Marshall Space Flight Center, Huntsville, Ala., July 1966.
- Williams, R. F., and Ingels, S. E., *Fabrication of Beryllium, Metal Removal Techniques*, NASA TMX-53453, Marshall Space Flight Center, Huntsville, Ala., August 1966.
- Wilson, D. V., "Plastic Anisotropy in Sheet Metals," *J. Inst. of Metals*, Vol. 94, pp. 84-93, 1966.
- Wyatt, W. H., *Evaluation of Wyman-Gordon Press-Forged Beryllium Cone*, Report TM 60, AD 453427, AVCO Research and Advanced Development Division, Wilmington, Mass., April 11, 1960.
- Yaffee, M. L., "Structural Application of Beryllium Grow," *Aviation Week and Space Technology*, Vol. 81, No. 19, pp. 64, 65, 68, 70, 71, 75, 77, 78, November 9, 1964.