

WANL-PR-(Q)-015
NASA-CR-72326

FACILITY FORM 602

N 68-18131 (THRU) _____
 (ACCESSION NUMBER)

27 (PAGES) _____ (CODE) _____
 Cf-72326 (NASA CR OR TMX OR AD NUMBER) _____ (CATEGORY) _____

DEVELOPMENT OF DISPERSION STRENGTHENED TANTALUM BASE ALLOY

GPO PRICE \$ _____

CFSTI PRICE(S) \$ _____



Hard copy (HC) 3.00

Microfiche (MF) 65

ff 653 July 65

Fourteenth Quarterly Report
 by
 R. W. Buckman and R. C. Goodspeed

prepared for
 National Aeronautics and Space Administration
 Lewis Research Center
 Space Power Systems Division
 Under Contract (NAS 3-2542)



ASTRONUCLEAR LABORATORY
WESTINGHOUSE ELECTRIC CORPORATION

NOTICE

This report was prepared as an account of Government-sponsored work. Neither the United States nor the National Aeronautics and Space Administration (NASA), nor any person acting on behalf of NASA:

- A) Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately-owned rights; or
- B) Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method or process disclosed in this report.

As used above, "person acting on behalf of NASA" includes any employee or contractor of NASA, or employee of such contractor, to the extent that such employee or contractor of NASA or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with NASA, or his employment with such contractor.

Copies of this report can be obtained from:

National Aeronautics & Space Administration
Office of Scientific and Technical Information
Washington 25, D. C.
Attention: AFSS-A

DEVELOPMENT OF DISPERSION STRENGTHENED
TANTALUM BASE ALLOY

by

R. W. Buckman, Jr.

and

R. C. Goodspeed

FOURTEENTH QUARTERLY PROGRESS REPORT

Covering the Period

February 20, 1967 to May 20, 1967

Prepared for

NATIONAL AERONAUTICS AND SPACE ADMINISTRATION
Contract NAS 3-2542

Technical Management
Paul E. Moorhead
NASA-Lewis Research Center
Space Power Systems Division

Astronuclear Laboratory
Westinghouse Electric Corporation
Pittsburgh, 36, Pa.



PRECEDING PAGE BLANK NOT FILMED.

ABSTRACT

Development of dispersion strengthened tantalum base alloys for use in advanced space power systems continued as the evaluation of 0.04 inch thick Ta-7W-1Re-1Hf-0.012C-0.012N (ASTAR-811CN; Heat NASV-23) sheet was essentially completed. Ductile-brittle transition temperatures of tungsten inert gas welded ASTAR-811CN were determined as a function of longer post-weld annealing times than previously studied. The results were related to microstructure, phase morphology, and hardness data. Investigation of the effects of grain size on the creep properties of Ta-8W-1Re-1Hf (ASTAR-811; Heat NASV-22) and Ta-8W-1Re-0.7Hf-0.025C (ASTAR-811C; Heat NASV-20) was continued. Initial results show that the creep properties of ASTAR-811C when recrystallized to 0.03mm grain size were independent of the final annealing temperature.

TABLE OF CONTENTS

	<u>Page No.</u>
I. INTRODUCTION	1
II. PROGRAM STATUS	2
A. WELDABILITY	2
B. EFFECT OF THERMAL TREATMENT ON CREEP BEHAVIOR	9
C. PHASE IDENTIFICATION AND MORPHOLOGY	10
III. FUTURE WORK	13
IV. REFERENCES	16

LIST OF FIGURES

	<u>Page No.</u>
1. Effect of Post Weld Annealing on the Ductile-Brittle Transition Temperature of TIG Welded ASTAR-811CN	4
2. Microstructure of TIG Welded ASTAR-811CN Specimens After Sixteen Hour Post Weld Anneal at 980°C	6
3. Microstructures of TIG Welded ASTAR-811CN Specimens After Sixteen and 500 Hour Post Weld Anneals at 1200°C	7
4. Effect of Annealing Time at 2200°F on the Hardness and Ductile-Brittle Transition Temperature of TIG Welded ASTAR-811CN	8
5. Microstructure of ASTAR-811C as a Function of Pre-Test Annealing Time and Temperature	11
6. Microstructures Representative of Specimens of ASTAR-811C Annealed 1 Hr./1650°C, 5 Minutes/1900°C, and 30 Seconds/2000°C and Strained 2 to 2-1/2% in Creep under Stress of 15,000 psi at 1315°C	12
7. Microstructures of ASTAR-811CN Specimens Annealed for 1 Hour at 1650°C and Aged in Ultra High Vacuum	14

LIST OF TABLES

	<u>Page No.</u>
1. Ductile-Brittle Transition Temperature of Post (TIG) Weld Annealed ASTAR-811CN	3
2. Hardness of Post Weld Annealed ASTAR-811CN TIG Weldments	5
3. Creep Behavior of ASTAR-811C Sheet Tested at 2400°F and 15,000 psi	10
4. Chemistry and X-ray Diffraction Analyses of Aged ASTAR-811CN Specimens	15

I. INTRODUCTION

This, the fourteenth and final quarterly progress report on the NASA-sponsored program, "Development of Dispersion Strengthened Tantalum Base Alloys" describes the work accomplished during the period February 20, 1967 to May 20, 1967. The work was performed under Contract NAS 3-2542.

The primary objective of the current phase of this program is the processing and evaluation of 0.04 inch sheet of three compositions which were melted as 60 pound, 4 inch diameter ingots. The compositions were selected for potential sheet and tubing applications on the basis of weldability, creep resistance, and fabricability characteristics.

Prior to this quarterly period, several promising tantalum alloy compositions have been developed which exhibited a good combination of creep resistance, weldability, and fabricability.⁽¹⁾ Three compositions, Ta-8W-1Re-1Hf-0.025C (ASTAR-811C), Ta-8W-1Re-1Hf (ASTAR-811) and Ta-7W-1Re-1Hf-0.012C-0.012N (ASTAR-811CN), were selected for scale up. These compositions were double vacuum, consumable electrode arc melted as 60 pound, 4 inch diameter ingots, which were subsequently processed to 0.04 inch sheet by a combination of forging and rolling. Evaluation of all three compositions has been essentially completed.

During this quarterly period, the evaluation of ASTAR-811 and ASTAR-811CN was completed with the exception of a few remaining creep tests. The effect of post weld annealing for times out to 500 hours at 1800-2600°F on the ductile-brittle transition temperature of ASTAR-811CN was determined. The investigation of the effect of annealing time and annealing temperature on the creep behavior of all three compositions was redirected to study only ASTAR-811C and ASTAR-811.

II. PROGRAM STATUS

A. WELDABILITY

Tungsten inert gas (TIG) welded 0.04 inch thick sheet specimens of ASTAR-811CN were annealed for 16 hours at 1800, 2200, and 2600°F (980, 1200, and 1425°C) and for 500 hours at 2200°F (1200°C). The post weld annealed specimens were tested in bending over a 1t bend radius with the weld bead transverse to the bend axis and the ductile-to-brittle behavior was determined. The data are summarized in Table 1 along with 1 hour post weld annealing data reported previously.⁽²⁾ The effect of post weld annealing temperature and time on the ductile-brittle behavior of ASTAR-811CN is summarized in the data plotted in Figure 1. As-TIG welded, ASTAR-811CN exhibited a DBTT* of -225°F. Post weld annealing for 1 hour at 1800-3000°F resulted in an increase in the DBTT with the peak increase observed after heating for 1 hour at 2600°F. Increasing the annealing time to 16 hours shifted the aging peak down to 2200°F. This behavior is indicative of an aging-overaging reaction and has been observed previously in tantalum alloys containing a reactive metal and nitrogen addition.^(3,4,5) At 2200°F, an aging peak as evidenced by the ductility minima was observed after heating for 16 hours. However after heating at 2200°F for 500 hours, the bend ductility was the same as for as-welded material.

Transverse sections from the post weld annealed specimens were mounted and studied metallographically. A hardness traverse was also made on the metallographically prepared specimens. Again as reported earlier,⁽²⁾ very little hardness variation was observed over the fusion and heat affected zone and base metal. The hardness as affected by annealing time and temperature is summarized in Table 2. Generally there was a decrease in hardness level of about 15 DPH units for specimens post weld annealed for 1 hour irrespective of the annealing temperature. However, as noted previously there was an increase in the DBTT as the post weld annealing temperature was increased to 2600°F. As has been discussed in the 10th Quarterly Report⁽³⁾ there is a strengthening reaction associated with the nitride precipita-

*DBTT - Ductile-Brittle Transition Temperature

**TABLE 1 - Ductile-Brittle Transition Temperature of Post (TIG) Weld Annealed
ASTAR-811CN^(a) (Ta-7W-1Re-1Hf-0.012C-0.012N; Heat No.
NASV-23)**

Post Weld Anneal	Test Temperature		No Load Bend Angle (Degrees)	Remarks	DBTT	
	^o F	^o C			^o F	^o C
As-TIG Welded	-250	-157	90	Failure Bend	-225	-143
	-225	-143	91			
1 Hr. at 980 ^o C (1800 ^o F)	-100	-73	92	Bend Bend Brittle failure in weld Brittle failure in weld and HAZ	-200	-129
	-200	-129	92			
	-225	-143	77			
	-250	-157	44			
	-320	-196	30			
16 Hrs. at 980 ^o C (1800 ^o F)	-100	-73	92	Bend Bend Brittle failure in weld and HAZ	-200	-129
	-200	-129	92			
	-250	-157	25			
	-320	-196	12			
1 Hr. at 1200 ^o C (2200 ^o F)	-100	-73	91	Bend Brittle failure in weld Brittle failure in weld and HAZ	-100	-73
	-125	-87	77			
	-150	-101	26			
	-200	-129	37			
16 Hrs. at 1200 ^o C (2200 ^o F)	+175	+79	88	Bend Bend Brittle failure in weld and HAZ Brittle failure in weld	+125	+52
	+125	+52	100			
	+75	+23	51			
	0	-18	90			
500 Hrs. at 1200 ^o C (2200 ^o F)	-100	-73	92	Bend Bend Very slight brittle failure in weld	-225	-143
	-200	-129	92			
	-250	-157	90			
	-320	-196	90			
1 Hr. at 1425 ^o C (2600 ^o F)	+75	+23	92	Bend Very slight ductile failure in weld Brittle failure in weld and HAZ	0	-18
	+50	+10	90			
	+25	-4	90			
	0	-18	90			
	-100	-73	52			
16 Hrs. at 1425 ^o C (2600 ^o F)	+75	+23	92	Bend Bend Bend Brittle failure in weld and HAZ	-175	-115
	-25	-31	90			
	-125	-87	91			
	-225	-143	47			
1 Hr. at 1650 ^o C (3000 ^o F)	-50	-46	103	Bend Brittle failure in weld Brittle failure in weld and HAZ	-100	-73
	-150	-101	84			
	-200	-129	9			
	-250	-157	21			

(a) Sheet specimens, 0.04 inch thick, were all annealed for 1 hr. at 1650^oC (3000^oF) prior to welding.




FIGURE 1 - Effect of Post Weld Annealing on the Ductile-Brittle Transition Temperature of TIG Welded ASTAR-811CN

tion and a hardness decrease associated with the carbide precipitation. Both reactions are occurring simultaneously, thus making it difficult to separate the effects of each. Microstructural changes associated with the annealing temperature may explain the ductile-brittle transition behavior,⁽²⁾ since there does not appear to be a correlation between the room temperature hardness and the ductile-brittle transition temperature.

TABLE 2 - Hardness of Post Weld Annealed ASTAR-811CN TIG Weldments

Annealing Time (hrs.)	DPH After Annealing at Indicated Temperature (°F)				
	As-Welded	1800	2200	2600	3000
1	275	260	260	260	260
16	275	245	245	250	---
500	275	---	220	---	---

Microstructures of post weld annealed specimens are shown in Figures 2 and 3. The microstructure after post weld annealing for sixteen hours at 1800°F (980°C) (Figure 1) is very similar to that after annealing for one hour at 1800°F. The hardness was also similar and the same ductile-brittle behavior was exhibited after a one and sixteen hour post weld anneal.

The microstructure of specimens annealed for 16 and 500 hours at 2200°F (1200°C) are shown in Figure 3a and 3b respectively. Although there was little observable difference in the microstructure between the specimens annealed 1 hour and 16 hours at 2200°F, there was a significant increase in the ductile-brittle transition temperature, along with a hardness decrease. This behavior for ASTAR-811CN post weld annealed at 2200°F is summarized in Figure 4. Increasing the post weld annealing time to 500 hours resulted in a DBTT of -225°F, (the same as measured for as-welded material) and a resultant room temperature hardness of 220 DPH. As will be discussed under the phase identification section of this report, the precipitate after 500 hours at 2200°F is a Hf(CN) while the Ta₂C (dimetal carbide) is observed after 1 and 16 hours at 2200°F.






FIGURE 2 - Microstructure of TIG Welded ASTAR-811CN (Ta-7W-1Re-1Hf-0.012C-0.012N) Specimens After Sixteen Hour Post Weld Anneal at 980°C



(a) Post Weld Annealed for 16 Hours at 1200°C



(b) Post Weld Annealed for 500 Hours at 1200°C

FIGURE 3 - Microstructures of TIG Welded ASTAR-811CN (Ta-7W-1Re-1Hf-0.012C-0.012N) Specimens After 16 and 500 Hour Post Weld Anneals at 1200°C




FIGURE 4 - Effect of Annealing Time at 2200°F on the Hardness and Ductile-Brittle Transition Temperature of TIG Welded ASTAR-811CN

The very preliminary results obtained on the influence of post weld annealing time and temperature on the ductile brittle behavior of TIG welded ASTAR-811CN show that the reactions occurring are complex. More detailed study would be required to completely define the specific reactions responsible for the changes in ductility that were observed.

B. EFFECT OF THERMAL TREATMENT ON CREEP BEHAVIOR

Evaluation of the effect of annealing temperature and annealing time on the creep behavior of ASTAR-811C and ASTAR-811 was initiated this period. During the previous quarter, annealing studies had been made on as-rolled 0.04 inch sheet of each composition to determine the grain growth behavior. ⁽²⁾ From these data specimens of ASTAR-811C were annealed for the following times at the indicated temperature to give a recrystallized grain size of 0.03 mm.

<u>Annealing Time (minutes)</u>	<u>Annealing Temperature (°C/°F)</u>
60	1650/3000
10	1800/3270
5	1900/3450
0.5	2000/3630

This is the grain size achieved after heating for 1 hour at 3000°F, and has been the final heat treatment standardized on for creep testing of all the experimental tantalum base alloys. The specimens of ASTAR-811C were then tested in creep at 2400°F and 15,000 psi under ultra high vacuum. The data obtained are listed in Table 3. Also included in Table 3 are the previously reported data obtained on ASTAR-811C which had been annealed for 1 hour at 3000, 3270, and 3630°F (1650, 1800, and 2000°C) prior to testing. These data would tend to indicate that the creep rate is insensitive to the prior annealing temperature if the grain diameter is maintained at a constant size. However, preliminary results indicate that if material is annealed to give a grain size of 0.06 mm the final annealing temperature does appear to be critical.

TABLE 3 - Creep Behavior of ASTAR-811C, Ta-8W-1Re-1Hf-0.025C
(Heat NASV-20), Sheet (0.04 Inch Thick) Tested at 2400°F
and 15,000 psi

Heat Treatment	Average Grain Diameter ^(a) (mm)	Test Duration (hrs.)	Total Elongation (%)	Time to 1% Elongation (hrs.)
1 hour at 3000°F/1650°C	0.03	555	2.53	262
10 minutes at 3270°F/1800°C	0.03	472	2.58	241
5 minutes at 3450°F/1900°C	0.03	497	2.12	275
30 seconds at 3630°F/2000°C	0.03	503	2.18	294
1 hour at 3270°F/1800°C	0.06	507	2.00	290
1 hour at 3630°F/2000°C	0.18	1003	2.10	474

(a) Determined by line intercept method.

The behavior exhibited by ASTAR-811C annealed to give a 0.03 mm grain size was unexpected since the as annealed pre-test microstructures were significantly altered by the annealing temperature (see Figure 5). As the annealing temperature was increased from 3000°F to 3630°F, the amount of precipitate visible was significantly decreased indicating that carbon had been taken into solution. The only apparent microstructural difference between material annealed 30 seconds and 60 minutes at 2000°C (3630°F) is the grain size. Otherwise all of the carbon appears to be in solution. However, after testing for 500 hours at 2400°F, the post test microstructures were very similar irrespective of the pretest annealing treatment (see Figure 6). Additional tests are underway on the carbon free analog of ASTAR-811C, ASTAR-811 as well as on specimens which have been annealed to give a recrystallized grain size of approximately 0.06-0.07 mm.


C. PHASE IDENTIFICATION AND MORPHOLOGY

Results reported in the previous quarterly report⁽²⁾ showed that two precipitation reactions were occurring in ASTAR-811CN. Sheet (0.04 inch thick) which had been given



(a)


500X



(b)


1500X

1 Hour at 3270°F (1800°C)



(c)


500X



(d)


1500X

5 Minutes at 3450°F (1900°C)



(e)

500X




(f)

1500X


30 Seconds at 3630°F (2000°C)

FIGURE 5 - Microstructure of ASTAR-811C (Ta-8W-1Re-0.7Hf-0.025C) as a Function of Pre-Test Annealing Time and Temperature




(a)

500X




(b)

500X



(c)

1500X



(d)


1500X

FIGURE 6 - Microstructures Representative of Specimens of ASTAR-811C (Ta-8W-1Re-1Hf-0.025C) Annealed 1 Hr./1650°C, 5 Minutes/1900°C, and 30 Seconds/2000°C and Strained 2 to 2-1/2% in Creep Under Stress of 15,000 psi at 1315°C


a 1 hour anneal at 3000°F (1650°C) followed by low temperature annealing treatments at 1800–2600°F for 1 hour resulted in the formation of only a Ta₂C phase. As the annealing time was increased to 16 hours, Ta₂C was still the only phase observed at 1800–2400°F but at 2600°F a Hf(CN) phase was detected.⁽²⁾ During this period, sheet specimens which had annealed 1 hour at 3000°F (1650°C) were exposed for times up to 907 hours at 2200 and 2400°F. The data obtained are listed in Table 4. Microstructures of the annealed specimens are shown in Figure 7. The microstructure of all four specimens was essentially identical. A fine precipitate existed throughout the matrix and along the grain boundaries. This precipitate was chemically extracted and identified by x-ray diffraction as a FCC phase with a lattice parameter of 4.58 Å. The phase was identified as Hf_{.75}Ta_{.25}(CN)_{1-x}. The specimens were also analyzed for carbon, oxygen, and nitrogen and the results are also included in Table 4. There appeared to be a slight decrease in carbon and nitrogen content but more analyses will be required to verify this. The precipitation of the carbonitride phase proceeds in two steps. At 2200 and 2400°F, only the Ta₂C was observed after aging solution annealed specimen for 1 and 16 hours. However, the equilibrium phase apparently is the carbonitride and it will form if the exposure time is sufficiently long. The implications of this precipitation reaction are that the sluggishness of this reaction should improve creep behavior and improved creep resistance has indeed been observed for compositions strengthened with carbonitride phases.⁽³⁾

III. FUTURE WORK


During the next period, the remaining experimental work on the effect of annealing time and annealing temperature on creep behavior of ASTAR-811C and ASTAR-811 will be completed. Also a few remaining creep tests will be conducted on ASTAR-811 and ASTAR-811CN. This will complete the experimental work to be done in this investigation. Work will then commence on the writing of a final technical report which is scheduled for publication during the early part of 1968.




(a) Aged 839 Hrs. at 1200°C



(b) Aged 165 Hrs. at 1315°C



(c) Aged 426 Hrs. at 1315°C



(d) Aged 907 Hrs. at 1315°C

FIGURE 7 - Microstructures of ASTAR-811CN (Ta-7W-1Re-1Hf-0.012C-0.012N)
Specimens Annealed for 1 Hour at 1650°C and Aged in Ultra High Vacuum

**TABLE 4 - Chemistry and X-ray Diffraction Analyses of Aged ASTAR-811CN
(Ta-7W-1Re-1Hf-0.012C-0.012N) Specimens^(a)**

Aging Treatment	Chemical Analyses ^(b) (in ppm)			Bulk Extractions	Diamond Pyramid Hardness ^(c)
	Carbon	Nitrogen	Oxygen		
839 Hours at 2200°F	110	80	16	FCC; $a_0 = 4.58\text{\AA}$	218
165 Hours at 2400°F	140	100	--	FCC; $a_0 = 4.58\text{\AA}$	229
426 Hours at 2400°F	100	110	--	FCC; $a_0 = 4.58\text{\AA}$	223
907 Hours at 2400°F	94	110	18	FCC; $a_0 = 4.58\text{\AA}$	224

(a) All specimens were annealed for 1 hour at 1650°C (3000°F) prior to aging.

(b) Pre-test analysis C 123 ppm
 O 18 ppm
 N 125 ppm

(c) Pre-test hardness - 294 DPH

IV. REFERENCES

1. R. W. Buckman, Jr. and R. T. Begley, "Development of Dispersion Strengthened Tantalum Base Alloy", Final Technical Report, Phase I, WANL-PR-(Q)-004.
2. R. W. Buckman, Jr. and R. C. Goodspeed, "Development of Dispersion Strengthened Tantalum Base Alloy", 13th Quarterly Progress Report, WANL-PR(Q)-014, NASA-CR-72306.
3. R. W. Buckman, Jr. and R. C. Goodspeed, "Development of Dispersion Strengthened Tantalum Base Alloy", 10th Quarterly Progress Report, WANL-PR(Q)-011, NASA-CR-72093.
4. R. W. Buckman, Jr. , "Development of Dispersion Strengthened Tantalum Base Alloy" 4th Quarterly Report , WANL-PR-(Q)-005, NASA-CR-54288.
5. R. W. Buckman, Jr. , "Development of Dispersion Strengthened Tantalum Base Alloy" 5th Quarterly Report, WANL-PR-(Q)-006, NASA-CR-54462.

DISTRIBUTION LIST

TRW
Caldwell Research Center
23555 Euclid Avenue
Cleveland, Ohio 44117
Attn: Librarian
Attn: G. J. Guarnieri

TRW
New Devices Laboratories
7209 Platt Avenue
Cleveland, Ohio 44104
Attn: Librarian

National Aeronautics & Space Adm.
Washington, D. C. 20546
Attn: Walter C. Scott
Attn: James J. Lynch (RN)
Attn: George C. Deutsch (RR)
Attn: S. V. Manson

National Aeronautics & Space Adm.
Scientific and Technical Inf. Facility
Box 5700
Bethesda, Maryland 21811

NASA-Ames Research Center
Moffet Field, California 94035
Attn: Librarian

NASA-Goddard Space Flight Center
Greenbelt, Maryland 20771
Attn: Librarian

NASA-Langley Research Center
Hampton, Virginia 23365
Attn: Librarian

NASA-Manned Spacecraft Center
Houston, Texas 77001
Attn: Librarian

NASA-Jet Propulsion Laboratory
4800 Oak Grove Drive
Pasadena, California 91103
Attn: Librarian

NASA-Lewis Research Center
21000 Brookpark Road
Cleveland, Ohio 44135
Attn: Librarian
Attn: Dr. Bernard Lubarsky
Attn: Mr. R. L. Cummings
Attn: Mr. G. M. Ault
Attn: Mr. J. Joyce
Attn: Mr. P. E. Moorhead
Attn: Mr. N. T. Musial
Attn: Mr. T. Strom
Attn: Mr. T. A. Moss
Attn: Dr. Louis Rosenblum
Attn: J. Creagh
Attn: Mr. J. Dilley
Attn: Mr. J. J. Fackler
Attn: Mr. I. I. Pinkel
Attn: Mr. G. Tulsiaak
Attn: Mr. W. D. Klopp
Attn: Mr. C. Hoffman
Attn: NASA-Lewis Lab. Report Central
Section

NASA- Western Operations Office
150 Pico Boulevard
Santa Monica, California 90406
Attn: Mr. John Keeler

National Bureau of Standards
Washington 25, D. C.
Attn: Librarian

NASA-George C. Marshall Space Flight Center
Huntsville, Alabama 35812
Attn: Librarian
Attn: Wm. A. Wilson



**Astronuclear
Laboratory**

Aeronautical Systems Division
Wright-Patterson Air Force Base, Ohio
Attn: Charles Armbruster
Attn: T. Cooper
Attn: Librarian
Attn: John L. Morris
Attn: H. J. Middendorp
Attn: G. Thompson
Attn: G. Sherman

Army Ordnance Frankford Arsenal
Bridesburg Station
Philadelphia 37, Pennsylvania
Attn: Librarian

Bureau of Ships
Dept. of the Navy
Washington 25, D. C.
Attn: Librarian

Bureau of Weapons
Research and Engineering
Material Division
Washington 25, D. C.
Attn: Librarian

U. S. Atomic Energy Commission
Technical Reports Library
Washington 25, D. C.
Attn: J. M. O'Leary

U. S. Atomic Energy Commission
Germantown, Maryland
Attn: Col. E. L. Douthett
Attn: H. Rothen
Attn: Major Gordon Dicker

U. S. Atomic Energy Commission
Technical Information Service Extension
P. O. Box 62
Oak Ridge, Tennessee

U. S. Atomic Energy Commission
Washington 25, D. C.
Attn: M. J. Whitman

Argonne National Laboratory
9700 South Cross Avenue
Argonne, Illinois
Attn: Librarian

Brookhaven National Laboratory
Upton, Long Island, New York
Attn: Librarian

Oak Ridge National Laboratory
Oak Ridge, Tennessee
Attn: W. O. Harms
Attn: Dr. A. J. Miller
Attn: Librarian
Attn: N. T. Bray

Office of Naval Research
Power Division
Washington 25, D. C.
Attn: Librarian

U. S. Naval Research Laboratory
Washington 25, D. C.
Attn: Librarian

Advanced Technology Laboratories
Division of American Standard
369 Whisman Road
Mountain View, California
Attn: Librarian

Aerojet General Corporation
P. O. Box 296
Azusa, California
Attn: Librarian

Aerojet General Nucleonics
P. O. Box 77
San Ramon, California
Attn: Librarian

AiResearch Manufacturing Company
Sky Harbor Airport
402 South 36th Street
Phoenix, Arizona
Attn: Librarian
Attn: E. A. Kovacevich

AiResearch Manufacturing Company
9851-9951 Sepulveda Boulevard
Los Angeles 45, California
Attn: Librarian

I. I. T. Research Institute
10 W. 35th Street
Chicago, Illinois 60616

Atomics International
8900 DeSoto Avenue
Canoga Park, California 91304
Attn: W. Botts

Avco
Research & Advanced Development Dept.
201 Lowell Street
Wilmington, Massachusetts
Attn: Librarian

Babcock and Wilcox Company
Research Center
Alliance, Ohio
Attn: Librarian

Battelle Memorial Institute
505 King Avenue
Columbus, Ohio
Attn: C. M. Allen
Attn: Librarian
Attn: Defense Metals Inf. Center

The Bendix Corporation
Research Laboratories Division
Southfield, Detroit 1, Michigan
Attn: Librarian

Bell Aerosystems Co.
P. O. Box 1
Buffalo 5, New York
Attn: E. J. King

The Boeing Company
Seattle, Washington
Attn: Librarian

Brush Beryllium Company
17876 St. Clair Avenue
Cleveland, Ohio 44110
Attn: Librarian

Carborundum Company
Niagara Falls, New York
Attn: Librarian

Chance Vought Aircraft Inc.
P. O. Box 5907
Dallas 22, Texas
Attn: Librarian

Clevite Corporation
Mechanical Research Division
540 East 105th Street
Cleveland 8, Ohio
Attn: Mr. N. C. Beerli

Climax Molybdenum Company of Michigan
1600 Huron Parkway
Ann Arbor, Michigan
Attn: Librarian

Convair Astronautics
50001 Kerry Villa Road
San Diego 11, California
Attn: Librarian

E. I. duPont deNemours and Co., Inc.
Wilmington 98, Delaware
Attn: Librarian

Electro-Optical Systems, Inc.
Advanced Power Systems Division
Pasadena, California
Attn: Librarian

Fansteel Metallurgical, Corp.
North Chicago, Illinois
Attn: Librarian



Ford Motor Company
Aeronutronics
Newport Beach, California
Attn: Librarian

General Dynamics/General Atomic
P. O. Box 608
San Diego, California 92112
Attn: Librarian

General Electric Company
Atomic Power Equipment Div.
P. O. Box 1131
San Jose, California

General Electric Company
Flight Propulsion Laboratory Dept.
Cincinnati 15, Ohio
Attn: Librarian
Attn: Dr. J. W. Semmel

General Electric Company
Missile and Space Vehicle Dept.
3198 Chestnut Street
Philadelphia 4, Pennsylvania
Attn: Librarian

General Electric Company
Vallecitos
Vallecitos Atomic Lab.
Pleasanton, California
Attn: Librarian

Herring Corp.
7356 Greenback Drive
Hollywood, California 91605
Attn: Don Adams

General Dynamics/Fort Worth
P. O. Box 748
Fort Worth, Texas
Attn: Librarian

General Motors Corporation
Allison Division
Indianapolis 6, Indiana
Attn: Librarian

Hamilton Standard
Div. of United Aircraft Corp.
Windsor Locks, Connecticut
Attn: Librarian

Hughes Aircraft Company
Engineering Division
Culver City, California
Attn: Librarian

Lockheed Missiles and Space Div.
Lockheed Aircraft Corp.
Sunnyvale, California
Attn: Librarian

Marquardt Aircraft Co.
P. O. Box 2013
Van Nuys, California
Attn: Librarian

The Martin Company
Baltimore 3, Maryland
Attn: Librarian

The Martin Company
Nuclear Division
P. O. Box 5042
Baltimore 20, Maryland
Attn: Librarian

Martin Marietta Corp.
Metals Technology Laboratory
Wheeling, Illinois

Massachusetts Institute of Technology
Cambridge 39, Massachusetts
Attn: Librarian

Materials Research and Development
Manlabs Inc.
21 Erie Street
Cambridge 39, Massachusetts

Materials Research Corporation
Orangeburg, New York
Attn: Librarian

McDonnell Aircraft
St. Louis, Missouri
Attn: Librarian

MSA Research Corporation
Callery, Pennsylvania
Attn: Librarian

North American Aviation
Los Angeles Division
Los Angeles 9, California
Attn: Librarian

National Research Corp.
Metals Division
45 Industrial Place
Newton, Massachusetts 02164
Attn: Dr. M. L. Torte
Director of Metallurgical Research

Lawrence Radiation Laboratory
Livermore, California
Attn: Dr. James Hadley
Head, Reactor Division

Pratt & Whitney Aircraft
400 Main Street
East Hartford 8, Connecticut
Attn: Librarian

Republic Aviation Corporation
Farmingdale, Long Island, New York
Attn: Librarian

Solar
2200 Pacific Highway
San Diego 12, California

Southwest Research Institute
8500 Culebra Road
San Antonio 6, Texas
Attn: Librarian

Rocketdyne
Canoga Park, California
Attn: Librarian

Superior Tube Co.
Norristown, Pennsylvania
Attn: Mr. A. Bound

Sylvania Electric Products, Inc.
Chem. & Metallurgical
Towanda, Pennsylvania
Attn: Librarian

Temescal Metallurgical
Berkeley, California
Attn: Librarian

Union Carbide Stellite Corp.
Kokomo, Indiana
Attn: Librarian

Union Carbide Metals
Niagara Falls, New York
Attn: Librarian

Union Carbide Nuclear Company
P. O. Box X
Oak Ridge, Tennessee
Attn: X-10 Laboratory Records Department

United Nuclear Corporation
Research & Engineering Center
Grassland Road
Elmsford, New York 10523
Attn: Librarian
Attn: Mr. Albert Weinstein



**Astronuclear
Laboratory**

Universal Cyclops Steel Corp.
Refractomet Division
Bridgeville, Pennsylvania
Attn: C. P. Mueller

TRW Space Technology Laboratories
One Space Park
Redondo Beach, California
Attn: Librarian

University of California
Lawrence Radiation Lab.
P. O. Box 808
Livermore, California
Attn: Librarian

University of Michigan
Department of Chemical & Metallurgical Eng.
Ann Arbor, Michigan
Attn: Librarian

Vought Astronautics
P. O. Box 5907
Dallas 22, Texas
Attn: Librarian

Wolverine Tube Division
Calumet & Hecla, Inc.
17200 Southfield Road
Allen Park, Michigan
Attn: R. C. Cash

Wyman-Gordon Co.
North Grafton, Massachusetts
Attn: Librarian

Wah Chang Corporation
Albany, Oregon
Attn: Librarian

Lawrence Radiation Laboratory
P. O. Box 808
Livermore, California 94551
Attn: Richard R. Vandervoort

WANL-PR-(Q)-015
NASA-CR-72326

March 1968

NG8-18131

ERRATA

Please attach the enclosed strip to identify the photomicrographs shown on Page 6 of the Fourteenth Quarterly Report entitled "Development of Dispersion Strengthened Tantalum Base Alloy".

Astronuclear Laboratory
Westinghouse Electric Corporation
Pittsburgh, Pa.