https://ntrs.nasa.gov/search.jsp?R=19680004167 2020-03-12T11:41:43+00:00Z

NASA CR-72349



# ELECTROCHEMICAL CHARACTERIZATION OF NONAQUEOUS SYSTEMS FOR SECONDARY BATTERY APPLICATION

M. Shaw, O. A. Paez, A. H. Remanick

by

prepared for

# NATIONAL AERONAUTICS AND SPACE ADMINISTRATION

CONTRACT NO. NAS 3-8509

CESTI PRICE(S) \$ \_\_\_\_\_

5

SIXTH QUARTERLY REPORT

Hard copy (HC) \_\_\_\_\_ AUGUST - OCTOBER 1967

Microfiche (MF)

# 583 Miy 65

GFO PRICE

WHITTAKER CORPORATION NARMCO RESEARCH & DEVELOPMENT DIVISION 3540 Aero Court San Diego, California 92123



CATEGORY)

(CODE)

THRU)

# NOTIC E

This report was prepared as an account of Government sponsored work. Neither the United States, nor the National Aeronautics and Space Administration (NASA), nor any person acting on behalf of NASA:

A.) Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or

B.) Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method or process disclosed in this report.

As used above, "person acting on behalf of NASA" includes any employee or contractor of NASA, or employee of such contractor, to the extent that such employee or contractor of NASA, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with NASA, or his employment with such contractor.

Requests for copies of this report should be referred to

National Aeronautics and Space Administration Scientific and Technical Information Division Attention: USS-A Woshington, D. C. 20546

# SIXTH QUARTERLY REPORT

# ELECTROCHEMICAL CHARACTERIZATION OF NONAQUEOUS SYSTEMS FOR SECONDARY BATTERY APPLICATION

August, 1967 - October, 1967

by

M. Shaw, O. A. Paez, A. H. Remanick

prepared for

# NATIONAL AERONAUTICS AND SPACE ADMINISTRATION

November 17, 1967

# CONTRACT NAS 3-8509

Technical Management Space Power Systems Division National Aeronautics and Space Administration Lewis Research Center, Cleveland, Ohio Mr. Robert B. King

# NARMCO RESEARCH AND DEVELOPMENT DIVISION

 $\mathbf{OF}$ 

WHITTAKER CORPORATION 3540 Aero Court San Diego, California 92123

# TABLE OF CONTENTS

				Page
ABSTR	RACT			i
SUMM	ARY			ii
INTRO	DUCTIO	ON		iii
I.	RESUL	JTS		
	Α.	Analys	is of Cyclic Voltammograms	1
		1.	Systems Involving Chloride and Perchlorate Electrolytes	7
		2.	Systems Involving Fluoride Electrolytes	12
	В,	Tables	of Cyclic Voltammetric Data	42
II.	REFEF	RENCES	5	58

# CYCLIC VOLTAMMOGRAMS

F	i	ø	u	r	e
_	-	ъ	~	•	~

.

T

Page

1.	Cd in Dimethylformamide - CaCl <sub>2</sub>	20
2.	Cd in Propylene carbonate - $LiClO_4$ + AlCl <sub>3</sub>	21
3.	In in Dimethylformamide - AlCl <sub>3</sub> + LiCl	22
4.	In in Propylene carbonate - AlCl <sub>3</sub> + LiCl	23
5.	In in Propylene carbonate - MgCl	24
6.	V in Dimethylformamide - $Mg(ClO_4)_2$	25
7.	Cr in Dimethylformamide - Mg(ClO <sub>4</sub> ) <sub>2</sub>	26
8.	Mn in Dimethylformamide - LiCl	27
9.	Zn in Dimethylformamide - LiBF <sub>4</sub>	28
10.	Zn in Propylene carbonate - $Mg(PF_6)_2$	29
11.	Cd in Dimethylformamide - LiBF <sub>4</sub>	30
12.	Cd in Propylene carbonate - PF5	31
13.	In in Dimethylformamide - LiPF	32
14.	In in Dimethylformamide - LiBF <sub>4</sub>	33
15.	In in Propylene carbonate - LiBF <sub>4</sub>	34
16.	Fe in Dimethylformamide - $Mg(BF_4)_2$	35
17.	Fe in Propylene carbonate - LiPF <sub>6</sub>	36
18.	Fe in Propylene carbonate – $LiBF_4$	37
19.	V in Dimethylformamide - LiPF <sub>6</sub>	38
20.	V in Propylene carbonate - $Mg(BF_4)_2$	39
21.	Mn in Dimethylformamide - LiPF <sub>6</sub>	40
22.	Mn in Dimethylformamide - KPF <sub>6</sub>	41
	N N N N N N N N N N N N N N N N N N N	

# LIST OF TABLES

Table		Page
I.	Electrolyte Conductivity	3
II.	Electrochemical Systems Screened - Chloride and Perchlorate Electrolytes	5
III.	Electrochemical Systems Screened - Fluoride Electrolytes	6
IV.	Systems Causing Voltage Overload of Instrumentation - Chloride and Perchlorate Electrolytes	43
<b>v.</b>	Systems Causing Voltage Overload of Instrumentation - Fluoride Electrolytes	44
VI.	Systems Causing Current Overload of Instrumentation	47
VII.	Peak Current Density Range - Chloride and Perchlorate Electrolytes	48
VIII.	Peak Current Density Range - Fluoride Electrolytes	49
IX.	Sweep Index	51
х.	$\Delta V_{p}$ , Coulombic Ratio, and Discharge Capacity	52
XI.	Systems Exhibiting Anodic Peak Only	53
XII.	Systems Exhibiting Cathodic Peak Only	55
XIII.	Systems Exhibiting No Peaks	56

# ELECTROCHEMICAL CHARACTERIZATION OF NONAQUEOUS SYSTEMS FOR SECONDARY BATTERY APPLICATION

by

M. Shaw, O. A. Paez, A. H. Remanick

#### ABSTRACT

Multisweep cyclic voltammograms have been obtained for an additional 161 systems comprising zinc, cadmium, molybdenum, indium, iron, vanadium, chromium, and manganese electrodes in dimethylformamide, and propylene carbonate solutions of chlorides, perchlorates, and fluorides.

Voltammograms are presented for twenty-two of these systems. Tabular data includes peak current density, sweep index, anodic-to-cathodic peak displacement, coulombic ratio, and discharge capacity. Systems exhibiting neither anodic nor cathodic peaks are listed, as well as those causing instrument overload due to a combination of high current and relatively low conductance.

#### SUMMARY

The electrochemical characterization of nonaqueous battery systems by nultisweep cyclic voltammetry has been continued. Cyclic voltammograms are now available on over nine hundred systems comprising silver, copper, nickel, cobalt, zinc, cadmium, molybdenum, indium, iron, vanadium, chromium, and manganese in chloride, perchlorate, and fluoride solutions of acetonitrile, butyrolactone, dimethylformamide, and propylene carbonate. Solutes consist primarily of AlCl<sub>3</sub>, LiCl, MgCl<sub>2</sub>, CaCl<sub>2</sub>, Mg(ClO<sub>4</sub>)<sub>2</sub>, LiClO<sub>4</sub>, MgF<sub>2</sub>, LiPF<sub>6</sub>, KPF<sub>6</sub>, Mg(PF<sub>6</sub>)<sub>2</sub>, Ca(PF<sub>6</sub>)<sub>2</sub>, LiBF<sub>4</sub>, Mg(BF<sub>4</sub>)<sub>2</sub>, and Ca(BF<sub>4</sub>)<sub>2</sub>. The voltammograms of twenty-two systems are included in this report.

During this reporting period cyclic voltammetry was initiated on vanadium, chromium, and manganese electrodes. In general, vanadium and chromium electrodes exhibit low or negligible cathodic electrochemical activity due possible to dissolution of the anodic product. Manganese electrodes show anodic and cathodic electrochemical activity with large peak-to-peak voltage separation.

Tables are presented listing system parameters derived from the cyclic voltammograms. These tables include data on peak current densities, sweep index, anodic-to-cathodic peak displacement, coulombic ratio, and discharge capacity. Listed also are those systems exhibiting neither anodic nor cathodic peaks, as well as those systems causing instrument overload.

-ii-

## INTRODUCTION

The purpose of this program is to conduct a molecular level screening by the cyclic voltammetric method on a large number of electrochemical systems in nonaqueous electrolytes, and to characterize them as to their suitability for use in high energy density secondary batteries.

Since the release and storage of energy in a battery is initiated at the molecular level of the reaction, and therefore dependent on the charge and mass transfer processes, it is essential that screening be conducted at this level, in order to eliminate those systems whose electrode processes are inadequate for secondary battery operation.

#### I. RESULTS

# A. ANALYSIS OF CYCLIC VOLTAMMOGRAMS

Table I lists the conductivities of the solutions used in preparing the electrochemical systems screened during this quarter. The systems screened are shown in Tables II and III, representing a total of 161 systems. To date, cyclic voltammograms have been obtained for over 900 different positiveelectrolyte combinations.

Curve analysis was accomplished by dividing all systems into two major groups:

- 1. Systems involving chloride and perchlorate electrolytes.
- 2. Systems involving fluoride electrolytes.

Each main group was then subdivided according to the identity of the working electrode. Each of these subgroups was further broken down according to the identity of the solvent portion of the solution. The cyclic voltammograms are then discussed in terms of the total solution. This classification facilitates data analysis, and has permitted a more significant correlation among the electrochemical systems.

Except in those cases where the metal is converted to a cathodic material prior to assembly in the measuring cell, the working electrode is the base metal itself. During the voltage sweep, the metal is oxidized to some anodic product which serves as the cathode subsequently reduced during the cathodic portion of the sweep. Each sweep cycle thus corresponds to a charge-discharge cycle. In the absence of complicating factors, it is assumed that chloride cathodes would be formed in chloride electrolytes, and fluoride cathodes in fluoride electrolytes.

-1-

Each cyclic voltammogram is identified by a CV number and labelled according to the electrochemical system, sweep rate, temperature, and zero reference representing the open circuit voltage (ocv) of the working electrode with respect to the indicated reference electrode. The current axis is in units of ma/cm<sup>2</sup>, each unit being of variable scale depending on the X-Y recorder sensitivity setting. A maximum sensitivity of 0.1 ma/cm<sup>2</sup>/cm division has been established to avoid exaggerating the current background of poor systems. The sweep is always in a clockwise direction, the potential becoming more positive to the right. Positive currents represent anodic (charge) reactions, and negative currents represent cathodic (discharge) reactions. The voltage axis units are relative to the ocv so that voltage units are in terms of electrode polarization.

For comparative purposes, current density magnitude is classified according to very high (more than 300 ma/cm<sup>2</sup>), <u>high (100-300 ma/cm<sup>2</sup>), medium high (50-100 ma/cm<sup>2</sup>), medium low (10-50 ma/cm<sup>2</sup>), low (1-10 ma/cm<sup>2</sup>), and very low (less than  $1 \text{ ma/cm}^2$ ).</u>

Analysis is based on the cyclic voltammograms obtained at the lowest sweep rate, 40 mv/sec, except where additional information is required from the higher sweep rate curves to aid in the analysis.

# TABLE I

# ELECTROLYTE CONDUCTIVITY \*

Electrolyte	Molality	Conductivity
	m	$ohm^{-1}cm^{-1}$
Dimethylformamide-KPF <sub>6</sub>	0.75	2. 1 x 10 <sup>-2</sup>
Dimethylformamide-Mg(ClO <sub>4</sub> ) <sub>2</sub>	0.75	$1.9 \times 10^{-2}$
Dimethylformamide-LiClO <sub>4</sub>	0.5	$1.8 \times 10^{-2}$
Dimethylformamide-LiPF 6	0.5	9.9 x $10^{-3}$
Dimethylformamide-AlCl <sub>3</sub> + LiCl	(1)	$7.8 \times 10^{-3}$
Dimethylformamide - LiCl	0.5	7.7 x $10^{-3}$
$Dimethylformamide-LiBF_4$	0.5	7.3 x $10^{-3}$
Propylene carbonate-KPF	1.0	$7.0 \times 10^{-3}$
Propylene carbonate-LiPF <sub>6</sub>	0.5	5.8 x $10^{-3}$
Propylene carbonate-LiClO4	1.0	5.8 x $10^{-3}$
Dimethylformamide-Ca( $PF_6$ ) <sub>2</sub>	<0.5 (s)	5.8 x $10^{-3}$
Propylene carbonate-LiClO <sub>4</sub> + AlCl <sub>3</sub>	0.5 (2)	5.6 x $10^{-3}$
Propylene carbonate-AlCl <sub>3</sub> + LiCl	(3)	5.3 x $10^{-3}$
Propylene carbonate-CaCl <sub>2</sub>	<0.5 (s)	5.3 x $10^{-3}$
Propylene carbonate-LiBF <sub>4</sub>	0.5	2.9 x $10^{-3}$
Dimethylformamide-Mg( $PF_{6}^{-}$ )	<0.5 (s)	$2.8 \times 10^{-3}$
Propylene carbonate-Ca( $PF_6$ ) <sub>2</sub>	<b>≪0.5 (s)</b>	$2.8 \times 10^{-3}$
Propylene carbonate-Ca( $PF_6$ ) <sub>2</sub>	<0.25 (s)	$2.8 \times 10^{-3}$

≭ In order of decreasing conductivity

Saturated (s)

1

0.5 m LiCl, saturated at less than 0.25 m AlCl Concentration with respect to each salt 0.5 m AlCl<sub>3</sub>, saturated at less than 0.10 m LiCl (1)

- (2)
- (3)

# TABLE I (Cont'd.) \*

Electrolyte	Molality	Conductivity
	m	$ohm^{-1}cm^{-1}$
Dimethylformamide-Mg(BF $_4$ ) <sub>2</sub>	<0.5 (s)	2.4 x $10^{-3}$
Propylene carbonate-Mg(PF <sub>6</sub> )	<0.25 (s)	2.4 x $10^{-3}$
Dimethylformamide-PF <sub>5</sub>	0.25	$2.2 \times 10^{-3}$
Propylene carbonate-MgCl <sub>2</sub>	<0.25	$2.0 \times 10^{-3}$
Dimethylformamide-Ca( $BF_4$ ) <sub>2</sub>	<0.5 (s)	$1.9 \times 10^{-3}$
Propylene carbonate-LiCl + LiClO	(4)	$1.3 \times 10^{-3}$
Propylene carbonate-PF5	<b>0.</b> 5	1.3 x 10 <sup>-3</sup>
Propylene carbonate-Ca $(BF_4)_2$	<b>√0.25 (s)</b>	$8.2 \times 10^{-4}$
Propylene carbonate-Mg(PF <sub>6</sub> ) <sub>2</sub>	<0.25 (s)	7.3 x 10 <sup>-4</sup>
Dimethylformamide-BF <sub>3</sub>	0.5	$7.0 \times 10^{-4}$
Propylene carbonate-CaCl <sub>2</sub>	<0.10 (s)	6.9 x $10^{-4}$

\* In order of decreasing conductivity

(s) Saturated

- ,4 57 ÷.

0.05 m in  $LiClO_4$ , saturated with LiCl(4)

# TABLE II

# ELECTROCHEMICAL SYSTEMS SCREENED CHLORIDE AND PERCHLORATE ELECTROLYTES

Solvent	Dimethylformamide	Propylene carbonate
Li Cl	V, Cr, Mn	
LiClO <sub>4</sub>	V, Cr, Mn	V, Cr, Mn
$LiCl + LiClO_4$		Zn, Cd, Mo, In, Fe, V
$LiClO_4 + AlCl_3$		Zn, Cd, Mo, In, Fe, V
MgCl <sub>2</sub>		Mo, In, Fe
Mg(ClO <sub>4</sub> ) <sub>2</sub>	V, Cr, Mn	
CaCl <sub>2</sub>	Zn, Cd, Mo, In, Fe, V	Zn, Cd, Mo, In, Fe, V
AlCl <sub>3</sub> + LiCl	In, V, Cr, Mn	Mo, In, Fe, V, Cr, Mn

# TABLE III

Solvent	Dimethylformamide	Propylene carbonate
LiPF <sub>6</sub>	Mo, In, Fe, V, Cr, Mn	Mo, In, Fe, V
крғ <sub>6</sub>	V, Cr, Mn	V, Cr, Mn
Mg(PF <sub>6</sub> ) <sub>2</sub>	Zn, Cd, Mo, In, Fe, V	Zn, Cd, Mo, In, Fe, V
Ca(PF <sub>6</sub> ) <sub>2</sub>	Zn, Cd, Mo, In, Fe, V, Cr, Mn	Zn, Cd, Mo, In, Fe, V, Cr, Mn
PF <sub>5</sub>	Zn, Cd, Mo, In, Fe, V, Cr, Mn	Zn, Cd, Mo, In, Fe, V, Cr, Mn
LiBF <sub>4</sub>	Zn, Cd, Mo, In, Fe, V, Cr, Mn	Zn, Cd, Mo, In, Fe, V
Mg(BF <sub>4</sub> ) <sub>2</sub>	Zn, Cd, Mo, In, Fe, V, Cr, Mn	Zn, Cd, Mo, In, Fe, V
$Ca(BF_4)_2$	Zn, Cd, Mo, In, Fe, V, Cr, Mn	Zn, Cd, Mo, In, Fe, V, Cr, Mn
BF <sub>3</sub>	Zn, Cd, Mo, In Fe, V, Cr, Mn	

# ELECTROCHEMICAL SYSTEMS SCREENED FLUORIDE ELECTROLYTES

-6-

#### 1.

#### Systems Involving Chloride and Perchlorate Electrolytes

## a. Zinc Electrode

#### (1) <u>Dimethylformamide solution</u>

Zinc in CaCl<sub>2</sub> solution results in voltage overload on the anodic sweep. The overload results from the high current and low conductivity of this system.

# (2) <u>Propylene carbonate solutions</u>

The cyclic voltammogram for zinc in  $LiCl + LiClO_4$  solution shows low anodic and cathodic currents, but no well-defined peaks. Excessive concentration polarization is indicated.

The cyclic voltammogram for zinc in  $\text{LiClO}_4 + \text{AlCl}_3$  solution shows a single anodic peak and no cathodic peak within the 2 volt scan. Expansion of the sweep range shows a cathodic peak at more negative potentials. Large peakto-peak voltage separations have occurred for zinc with  $\text{LiClO}_4$  alone in propylene carbonate (Ref. 1, Fig. 16), similar to that observed for this system. Zinc in CaCl<sub>2</sub> solution exhibits voltage overload for both anodic and cathodic processes at very low current densities, probably due to low solution conductivity.

#### b. Cadmium Electrode

#### (1) Dimethylformamide solution

The cyclic voltammogram for cadmium in  $CaCl_2$  solution is shown in Figure 1 (CV-2963). The curve shows multiple anodic peaks and a single cathodic peak. The cathodic peak occurs 100 mv more positive than the first anodic peak. Similar results were obtained earlier in LiCl solution.

#### (2) Propylene carbonate solutions

Cadmium in LiCl + LiClO<sub>4</sub> solution shows only slight electrochemical activity, with no peak formation, similar to that observed earlier for zinc in this electrolyte.

-7-

The curve for cadmium in  $\text{LiClO}_4 + \text{AlCl}_3$  solution is shown in Figure 2 (CV-3236). The curve shows a sharp anodic peak and two smaller cathodic peaks. Current densities are in the medium range. At faster scan rates only a single anodic and cathodic peak are observed. Further study would be required to interpret these results. The results in CaCl<sub>2</sub> solution are similar to those for the zinc electrode.

# c. Molybdenum Electrode

#### (1) Dimethylformamide solution

Molybdenum is essentially inactive in  $CaCl_2$  solution, as was observed earlier in LiCl solution.

# (2) Propylene carbonate solutions

The CV curve for molybdenum in  $LiClO_4 + AlCl_3$  solution shows a single broad anodic peak of medium high current density, and no cathodic activity. In  $LiCl + LiClO_4$  solution, the curve for molybdenum shows low anodic activity and no cathodic activity. Molybdenum in  $LiCl + AlCl_3$  solution results in voltage overload with high anodic and no cathodic current. In  $MgCl_2$  and  $CaCl_2$  solutions, anodic voltage overload results and no cathodic activity is indicated.

# d. Indium Electrode

#### (1) Dimethylformamide solutions

The cyclic voltammogram for indium in LiCl + AlCl<sub>3</sub> solution is shown in Figure 3 (CV-3392). A complex anodic reaction is indicated by the multipeak positive current. Poor charge-discharge efficiency is predicted based on the low coulombic ratio (cathodic-to-anodic peak areas). Comparison of current peak height ratios at faster sweep rates indicates a soluble anodic product.

-8-

Anodic voltage overload results for indium in CaCl<sub>2</sub> solution.

# (2) <u>Propylene carbonate solutions</u>

The cyclic voltammogram for indium in  $\text{LiCl} + \text{LiClO}_4$  solution shows a low, broad anodic peak in the low current density range, and virtually no cathodic current.

Indium in  $\text{LiClO}_4 + \text{AlCl}_3$  solution shows a sharp anodic peak in the medium high current density range, and broad multiple cathodic peaks. A similar curve for indium in  $\text{LiCl} + \text{AlCl}_3$  solution is shown in Figure 4 (CV-3382). The curve for indium in  $\text{MgCl}_2$  solution is shown in Figure 5 (CV-2971) indicating a single anodic, and a double cathodic peak both in the high current density range. Indium in  $\text{CaCl}_2$  solution shows voltage overload for both the anodic and cathodic sweeps.

#### e. Iron Electrode

#### (1) Dimethylformamide solution

Iron electrodes in CaCl<sub>2</sub> solution result in anodic voltage overload.

#### (2) Propylene carbonate solutions

Iron shows negligible activity in  $LiCl + LiClO_4$  solution. In the case of  $MgCl_2$  solution, iron shows a well formed anodic peak in the medium low range, followed by a lower broad peak. No cathodic reaction is evident, however. Very low anodic and cathodic activity occurs for iron in CaCl\_2 solution, and no peaks are observed.

Iron electrodes in  $\text{LiCl} + \text{AlCl}_3$  solution exhibit complex anodic peaks in the medium high current density range, with low cathodic activity. Similar complex anodic peaks occur for iron in  $\text{LiClO}_4 + \text{AlCl}_3$  solution. Cathodic activity is indicated at the extreme negative end of the cathodic scan resulting in more than 1 volt peak-to-peak separation.

#### f. Vanadium Electrode

#### (1) Dimethylformamide solutions

Vanadium electrodes indicate very high anodic activity in LiCl solution causing anodic current overload of the instrumentation. The solution turns a dark red color indicating anodic dissolution of the electrode. Cathodic current is nil. Vanadium in CaCl<sub>2</sub> solution results in anodic voltage overload. A red discoloration of the solution was noted, as well as the formation of a black reaction product on the working electrode. Anodic voltage overload results for vanadium in LiClO<sub>4</sub> and LiCl + AlCl<sub>3</sub> solutions. Again, cathodic current is negligible. The sweep curve for vanadium in Mg(ClO<sub>4</sub>)<sub>2</sub> solution shows a sharp, very high current density anodic peak and virtually no cathodic activity. This is shown in Figure 6 (CV-3444).

# (2) Propylene carbonate solutions

No electrochemical activity is observed for vanadium in LiCl + LiClO<sub>4</sub> solution. The curve for vanadium in LiClO<sub>4</sub> solution shows a single sharp anodic high current density peak and only low cathodic activity. Vanadium in LiClO<sub>4</sub> + AlCl<sub>3</sub> solution shows a single, sharp anodic peak in the high current density range and relatively no cathodic activity. In LiCl + AlCl<sub>3</sub> solution, vanadium electrodes exhibit anodic voltage overload due to high current. Red discoloration of the solution, with negligible cathodic reaction, indicates excessive anodic dissolution. Vanadium in CaCl<sub>2</sub> solution shows very low anodic and no cathodic activity.

#### g. Chromium Electrode

# (1) Dimethylformamide solutions

The curve for chromium in  $Mg(ClO_4)_2$  solution is shown in Figure 7 (CV-3449). A single anodic peak of high current density with virtually no reduction current is evident. Chromium electrodes in  $LiClO_4$ , LiCl, and  $LiCl + AlCl_3$ solutions result in anodic voltage overload with no cathodic activity.

-10-

# (2) Propylene carbonate solutions

Chromium in LiCl + AlCl<sub>3</sub> solution show multipeak anodic activity in the medium high range and low cathodic activity. Low anodic and very low cathodic activity is indicated in LiClO<sub>4</sub> solution.

## h. Manganese Electrode

## (1) Dimethylformamide solutions

Manganese electrodes in chloride and perchlorate solutions show a large voltage spread between anodic and cathodic peaks indicating high activation polarization. In the case of LiCl + AlCl<sub>3</sub> solution, the curves show a broad, high anodic peak, with low cathodic activity at the negative extreme of the voltage range. Very low anodic and cathodic activity at the scan limits is observed also for  $Mg(ClO_4)_2$ . Curves for LiClO<sub>4</sub> solution show a single, very high anodic peak at the positive extreme, but no cathodic activity within the total scan. The curve for manganese in LiCl solution shows a single, anodic peak and multiple broad cathodic peaks. Peak current densities fall in the low range, and peak-to-peak voltage separation is greater than 0.5 v. The curve is shown in Figure 8 (CV-3315).

# (2) Propylene carbonate solutions

Manganese in LiCl + AlCl<sub>3</sub> solution shows a medium low, current density anodic peak and no cathodic activity. Low anodic currents and no cathodic activity is indicated in  $LiClO_4$  solution.

-11-

#### 2.

#### Systems Involving Fluoride Electrolytes

#### a. Zinc Electrode

#### (1) Dimethylformamide solutions

Zinc electrodes in  $PF_5$  solution give voltage overload caused by a combination of very high anodic current and low solution conductivity. Cathodic voltage overload is obtained in  $Mg(PF_6)_2$  solution. The cyclic voltammogram for zinc in Ca(PF<sub>6</sub>)<sub>2</sub> solution shows a single broad, high current density anodic peak. The reduction reaction is initiated at the same potential as the oxidation reaction, forming a well-defined cathodic peak. 200 mv negative to this peak, however, erratic peak behavior is obtained, which may be related to the observed continuous dislodging of reaction product from the electrode.

The curve for zinc in  $\text{LiBF}_4$  solution is shown in Figure 9 (CV-3272). A secondary oxidation process is indicated. The cathodic peak occurring 0.4 v cathodic to the major anodic peak appears clean, although, a second cathodic reaction is indicated at the extreme end of the negative range. Peak current densities fall in the medium high range. Measurements in BF<sub>3</sub>, Mg(BF<sub>4</sub>)<sub>2</sub>, and Ca(BF<sub>4</sub>)<sub>2</sub> solutions result in anodic and cathodic voltage overload with very high cathodic current densities.

## (2) Propylene carbonate solutions

Zinc in  $PF_5$  solution shows a broad, low current density cathodic peak, and a medium low anodic with no tendency towards peaking. The curve for zinc in Mg(PF<sub>6</sub>)<sub>2</sub> solution is shown in Figure 10 (CV-3134). The single anodic and cathodic peaks fall in the medium high current density range, and are seen to be broad and highly polarized as evidenced by a peak-to-peak separation greater than 1 volt.

Zinc electrodes in  $\text{LiBF}_4$  solution show a sharp anodic peak followed by very erratic non-reproducible cathodic activity. The erratic behavior may be due to sudden changes, such as cracking of the electrode surface layer, exposing

-12-

new electroactive surface. A black reaction product forms on the working electrode. Peak current densities are in the medium low range.

Zinc in  $Ca(BF_4)_2$  solution shows broad, single anodic and cathodic peaks separated by 0.8 v. Peak current densities are in the high and medium high range respectively. In  $Ca(PF_6)_2$  solution, the curve shows a medium low anodic and a medium high cathodic peak. Small random oscillations are exhibited, possibly caused by erratic surface changes. Voltage overload occurs in  $Mg(BF_4)_2$  solutions as a result of very high current densities.

# b. Cadmium Electrode

# (1) Dimethylformamide solutions

The cyclic voltammogram for cadmium in  $PF_5$  solution shows a broad, poorly defined irreproducible anodic peak of very high current density, and a medium low current density cathodic peak. Anodic-to-cathodic peak voltage separation is greater than 1 volt. Voltage overload results in Mg(PF<sub>6</sub>)<sub>2</sub> and Ca(PF<sub>6</sub>)<sub>2</sub> solutions, as a result of a combination of very high anodic and cathodic activity and low solution conductivity.

Measurements on cadmium in  $\text{LiBF}_4$  solutions caused instrumental oscillation and voltage overload near the extremes of the voltage range. These oscillations are no doubt set off by sudden changes in electrode geometry, in combination with high current densities, resulting in impedance mismatch and affecting the response of the potentiostat. A cyclic voltammogram was recorded for this system by setting voltage limits at only ±0.3 v relative to the o.c.v. The curve is a good example of a high current density reversible system, and is shown in Figure 11 (CV-3273). Cadmium in BF<sub>3</sub>, Mg(BF<sub>4</sub>)<sub>2</sub>, and Ca(BF<sub>4</sub>)<sub>2</sub> solutions result in voltage overload for both anodic and cathodic sweeps.

# (2) Propylene carbonate solutions

Cadmium electrodes in  $PF_5$  solution yield results similar to those observed for zinc in this electrolyte. A medium high cathodic peak is obtained, with

-13-

no tendency for anodic peak formation. The curve is shown in Figure 12 (CV-3006). Cadmium in  $Mg(PF_6)_2$  solution results in voltage overload.

Voltage overload resulted for cadmium in  $Ca(PF_6)_2$ ,  $Mg(BF_4)_2$  and  $Ca(BF_4)_2$  solutions. In  $Mg(BF_4)_2$  solution, overload results for both anodic and cathodic sweeps. In  $Ca(PF_6)_2$  and  $Ca(BF_4)_2$  solutions the overload condition is encountered only on the anodic sweep.

Cadmium in  $\text{LiBF}_4$  solution exhibits voltage overload caused by system oscillations similar to that described above for the Cd/DMF-LiBF<sub>4</sub> system. Very high anodic and cathodic currents were recorded. Additional measurements are warranted for this system.

## c. Molybdenum Electrode

#### (1) Dimethylformamide solutions

Curves for molybdenum electrodes in  $PF_5$  solution show two very low but distinct anodic peaks, and no cathodic activity. In LiPF<sub>6</sub> solution, two anodic peaks are again formed, but closer together than in  $PF_5$  solution. Low cathodic activity is indicated in LiPF<sub>6</sub> solution, with two peaks again evident. Charge-to-discharge voltage separation is excessively large however. Voltage overload occurs in both Mg(PF<sub>6</sub>)<sub>2</sub> and Ca(PF<sub>6</sub>)<sub>2</sub> solutions.

The results for molybdenum electrodes in  $\text{LiBF}_4$  solution indicate anodic activity in the medium high current density range, but no cathodic activity. Voltage overload results in BF<sub>3</sub>, Mg(BF<sub>4</sub>)<sub>2</sub> and Ca(BF<sub>4</sub>)<sub>2</sub> solutions with high currents on the anodic sweep, but with no current on the cathodic sweep.

# (2) Propylene carbonate solutions

Molybdenum shows no activity in  $PF_5$  solution, within the normal scanning range (+1.0 to -1.0v), but in the range 0 to +2.0 v, anodic voltage overload occurs. A medium high anodic peak is obtained in  $LiPF_6$  solution, and the cathodic peak is of low current density and separated by more than 1.0 v

-14-

from the anodic reaction. Anodic voltage overload results for molybdenum in  $Mg(PF_6)_2$  solution. Molybdenum in LiBF<sub>4</sub> solution shows results similar to those observed in dimethylformamide solution. Medium high anodic current is obtained with no tendency towards peak formation. A low cathodic current occurs at -1.0 v. Similar results with lower current densities are observed for molybdenum in Ca(BF<sub>4</sub>)<sub>2</sub>, but with lower current densities.

Voltage overload caused by very high anodic currents results for molybdenum in  $Mg(BF_4)_2$  and  $Ca(PF_6)_2$  solutions. The cathodic current for both of these systems is nil.

d. Indium Electrode

i

#### (1) Dimethylformamide solutions

The cyclic voltammogram for indium in  $PF_5$  solution shows a high anodic current with no tendency for peak formation. No reduction reaction is evident. The solution becomes dark brown during cycling. Indium in LiPF<sub>6</sub> solution s hows very high anodic activity as indicated in Figure 13 (CV-3036). The cathodic current is in the very low range, and is limited by the anodic dissolution of the indium working electrode as evidenced by darkening of the solution and plating out of a metal (presumably indium) on the counterelectrode. Sweep rate behavior also indicates a soluble cathode. Voltage overload results in Mg(PF<sub>6</sub>)<sub>2</sub> and Ca(PF<sub>6</sub>)<sub>2</sub> solutions, again due to very high anodic activity and low solution conductance.

The curve for indium in  $\text{LiBF}_4$  solution shows very high anodic and medium low cathodic activity. As seen in Figure 14 (CV-3282) the anodic peak area is much larger than the cathodic peak area (by roughly a factor of a hundred) indicating poor charge-discharge efficiency. Voltage overload results for both anodic and cathodic sweeps due to very high currents and low conductivity in BF<sub>3</sub>, Mg(BF<sub>4</sub>)<sub>2</sub>, and Ca(BF<sub>4</sub>)<sub>2</sub> solutions.

-15-

## (2) Propylene carbonate solutions

The electrochemical behavior of indium electrodes in  $PF_5$  solution is similar to that observed for  $PF_5$  in dimethylformamide. Indium in LiPF<sub>6</sub> solution shows high anodic and medium high cathodic activity, accompanied by excessive dissolution of the cathodic material. Metal deposition, presumably indium, is observed on the counterelectrode. Anodic voltage overload results for indium electrodes in Mg(PF<sub>6</sub>)<sub>2</sub> solution.

The cyclic voltammogram for indium in  $\text{LiBF}_4$  solution is shown in Figure 15 (CV-3179). The electrode characteristics indicated in this curve are an improvement over that in Figure 14 (CV-3282) for dimethylformamide solution. Still, the large peak-to-peak voltage separation (0.9v), and low cathodic-to-anodic coulombic ratio, are not favorable from the standpoint of secondary battery operation.

Indium in  $Ca(PF_6)_2$ ,  $Ca(BF_4)_2$  and  $Mg(BF_4)_2$  all results in voltage overload caused by very high anodic and cathodic currents and low solution conductivity.

# e. Iron Electrode

#### (1) Dimethylformamide solutions

Iron in  $PF_5$  solution causes voltage overload as a result of high anodic activity and low solution conductance. High anodic and cathodic activity occurs in LiPF<sub>6</sub>, Mg(PF<sub>6</sub>)<sub>2</sub> and Ca(PF<sub>6</sub>)<sub>2</sub> solutions. The broad multiple peaks and large voltage separation between anodic and cathodic reactions in all three systems make them unsatisfactory for secondary battery application.

Iron electrodes in  $\text{LiBF}_4$  solution show a sharp anodic peak of medium high current density and very low cathodic activity. In  $Mg(BF_4)_2$  and  $Ca(BF_4)_2$  solutions, iron electrodes show sharp anodic peaks of very high current density and low cathodic activity. Voltage separation is greater than 1 volt. The cyclic voltammogram for iron in  $Mg(BF_4)_2$  solution is shown in Figure 16

-16-

(CV-3328). Voltage overload results in BF solution on the anodic sweep, with high anodic and cathodic currents.

## (2) Propylene carbonate solutions

The cyclic voltammogram for iron in  $PF_5$  solution indicates low anodic and cathodic activity with no peak formation. The curve for iron in  $LiPF_6$  solution is shown in Figure 17 (CV-3061) and is the best of the iron systems examined to date. Peak currents are in the medium low range, peak-to-peak separation is 0.5 v, and the charge-discharge efficiency is 86%. Iron in  $Mg(PF_6)_2$  solution shows broad, low anodic peak and very low cathodic activity with no peak formation.

The cyclic voltammogram for iron in  $\text{LiBF}_4$  solutions is shown in Figure 18 (CV-3189). The curve shows single anodic and cathodic peaks of medium low current densities, and 1.4 v peak-to-peak separation. The large voltage separation indicates high activation polarization. Similar results are obtained for iron in Mg(BF<sub>4</sub>)<sub>2</sub>, Ca(BF<sub>4</sub>)<sub>2</sub> and Ca(PF<sub>6</sub>)<sub>2</sub> solutions.

#### f. Vanadium Electrode

#### (1) Dimethylformamide solutions

Vanadium in  $PF_5$  solution results in voltage overload. Sharp anodic peaks in the medium low current density range, with repeat peaks at the same potential on the reverse sweep, occur in LiPF<sub>6</sub>, Mg(PF<sub>6</sub>)<sub>2</sub>, and Ca(PF<sub>6</sub>)<sub>2</sub> solutions. In each case, a low cathodic peak is observed, separated by greater than 1 volt from the anodic peak. The curve for LiPF<sub>6</sub> is shown in Figure 19 (CV-3046). The results for vanadium in KPF<sub>6</sub> solution are similar except that no cathodic activity or repeat peaks are observed.

The voltammograms for vanadium electrodes in  $\text{LiBF}_4$ ,  $\text{Mg(BF}_4)_2$ ,  $\text{Ca(BF}_4)_2$ , and in BF<sub>3</sub> solutions show low to very low anodic and cathodic activity. In

general, results for vanadium, in fluoride electrolyte, show anodic activity decreasing after the first cycle. Continued cycling yields reproducibility only at low or very low current density levels.

## (2) Propylene carbonate solutions

Vanadium after a few cycles exhibits very low electrochemical activity in  $PF_5$ ,  $LiPF_6$ ,  $KPF_6$ , or  $Mg(PF_6)_2$  and  $Ca(PF_6)_2$  solutions of propylene carbonate.

In the case of  $\text{LiBF}_4$ ,  $Mg(\text{BF}_4)_2$ , and  $Ca(\text{BF}_4)_2$  solutions, vanadium exhibits low or very low anodic and cathodic activity following the first few cycles. A typical curve obtained after several cycles is shown in Figure 20 (CV-3171).

# g. Chromium Electrode

# (1) Dimethylformamide solutions

The curve for chromium in  $\text{LiPF}_6$  solution shows a single sharp anodic peak of medium low current density range, and no cathodic peak. Cathodic activity of less than 2 ma/cm<sup>2</sup> is indicated at the extreme negative voltage range. Similar results are obtained for KPF<sub>6</sub> solutions. Chromium electrodes in  $\text{LiBF}_4$  and in BF<sub>3</sub> solutions result in anodic voltage overload accompanied by high currents. Cathodic currents are negligible in both cases.

# (2) <u>Propylene carbonate solutions</u>

The curve for chromium in  $\text{KPF}_6$  solution shows low anodic and very low cathodic activity with no current peaks. Similar results occur in  $\text{Ca}(\text{PF}_6)_2$  solution. Chromium electrodes in  $\text{PF}_5$  and  $\text{Ca}(\text{BF}_4)_2$  solutions result in voltage overload with high anodic currents. No reduction reaction is evidenced.

### h. Managese Electrode

#### (1) Dimethylformamide solutions

The curve for manganese in LiPF solution shows single anodic and cathodic peaks of high current density. High activation polarization is indicated by

-18-

0.9 v peak-to-peak voltage separation as seen in Figure 21 (CV-3303). Plating of a metal on the counterelectrode indicates that some anodic dissolution is occurring. The curve obtained in KPF<sub>6</sub> solution is shown in Figure 22 (CV-3439).

Manganese in LiBF<sub>4</sub> solution shows single anodic and cathodic peaks. The sweep rate dependence of the anodic and cathodic peaks indicates a soluble anodic product. Peak-to-peak voltage separation is 0.7 v. Voltage over-load results on both anodic and cathodic sweeps for manganese in BF<sub>3</sub>,  $Mg(BF_4)_2$ ,  $Ca(BF_4)_2$ , and PF<sub>5</sub> solutions.

# (2) Propylene carbonate solutions

Manganese in  $\text{KPF}_6$  and  $\text{Ca}(\text{PF}_6)_2$  solutions shows low cathodic activity. The anodic current in the case of  $\text{KPF}_6$  is in the medium low range, although no peak results. In  $\text{Ca}(\text{PF}_6)_2$  solution a broad anodic peak in the low current density range is observed.



Ì

--20-



-21-



-22-



-23-



1

- 24 -



-25-



-26-



Figure 8


- 28 -







T

1

- 30 -



- 31 -



- 32 -



-33-



-34-





1



ł

- 3,7 -



- 38 -





-40-



-41-

Figure 22

в.

#### TABLES OF CYCLIC VOLTAMMETRIC DATA

Included in this section are tables listing parameters derived from the cyclic voltammograms. These parameters are as follows:

1. Sweep index - This is a relative figure of merit taking into account peak height, sweep rate, and discharge capacity. This parameter is described in more detail in an earlier report (Ref. 2, p. 80).

2. Peak current density range - Relative magnitude of peak currents classified according to page 2.

3.  $\Delta V_p$  - Peak-to-peak displacement in volts of charge and discharge reactions giving a measure of overall electrode reversibility, or in more practical terms, a measure of suitability of the electrochemical system for second battery application.

4. Coulombic ratio - Ratio of cathodic to anodic peak area. Values significantly in excess of unity for the pre-formed electrodes (chlorinated and fluorinated metals) are indicative of the contribution of the original cathodic material to the discharge reaction independent of the material formed by the preceding charge sweep.

5. Discharge capacity - Measure of discharge utilization per unit area of electrode surface, when compared with the coulombic ratio except for values of the latter greater than unity.

Also included are tables listing the systems causing voltage and current overload of the instrumentation preventing recordable voltammograms as well as those systems failing to exhibit either anodic or cathodic peaks. In cases of solutions having varying molality, the concentrations are included with the designated system. The concentration of all solutions are listed in Table I.

#### TABLE IV

## SYSTEMS CAUSING VOLTAGE OVERLOAD OF INSTRUMENTATION CHLORIDE AND PERCHLORATE ELECTROLYTES

•		Max. Anod.	Max. Cath.
System	CV	<u> </u>	<u> </u>
		ma/cm <sup>2</sup>	ma/cm <sup>2</sup>
Zn/DMF-CaCl <sub>2</sub>	2958	400	100
Zn/PC-CaCl <sub>2</sub>	3195	nil	nil
Cd/PC-CaCl <sub>2</sub>	3196	nil	nil
Mo/PC-MgCl <sub>2</sub>	2970	80	20
Mo/PC-CaCl	3198	40	nil
$Mo/PC-AlCl_3 + LiCl$	3366	2400	nil
In/DMF-CaCl <sub>2</sub>	2978	200	nil
In/PC-CaCl <sub>2</sub>	3197	nil	nil
Fe/DMF-CaCl <sub>2</sub>	2969	200	20
$V/DMF-LiClO_4$	3316	2400	nil
V/DMF-CaCl <sub>2</sub>	2977	1600	nil
$V/DMF-AlCl_3 + LiCl$	3393	2400	nil
$V/PC-AlCl_3 + LiCl$	3372	2400	nil
Cr/DMF-LiCl	3310	2400	nil
Cr/DMF-LiClO <sub>4</sub>	3317	2800	nil
$Cr/DMF-AlCl_3 + LiCl$	3394	2800	nil
$Mn/PC-LiClO_4$	3414	400	4

DMF -	-	Dimethylformamide
-------	---	-------------------

#### TABLE V

#### SYSTEMS CAUSING VOLTAGE OVERLOAD OF INSTRUMENTATION FLUORIDE ELECTROLYTES

System	CV	Max. Anod.	Max. Cath.
<u>System</u>	<u> </u>	$\frac{1}{ma/cm^2}$	$\frac{1}{ma/cm^2}$
$Z_n/DMF-Mg(PF_6)_2$	3089	400	600
Zn/DMF-PF <sub>5</sub>	2985	1600	600
$Z_n/DMF-Mg(BF_4)_2$	3323	1200	800
$Z_n/DMF-Ca(BF_4)_2$	3353	1600	1600
Zn/DMF-BF <sub>3</sub>	3265	1200	450
$Z_n/PC-Mg(BF_4)_2$	3162	1200	800
$Cd/DMF-Mg(PF_6)_2$	3090	1600	1200
Cd/DMF-Ca(PF <sub>6</sub> ) <sub>2</sub>	3078	1600	800
$Cd/DMF-Mg(BF_4)_2$	3324	1200	1200
$Cd/DMF-Ca(BF_4)_2$	3354	1600	1600
Cd/DMF-BF <sub>3</sub>	3264	1200	450
$Cd/PC-Mg(PF_6)_2$	31 35	1200	1200
$Cd/PC-Ca(PF_6)_2$	3153	400	300
Cd/PC-LiBF <sub>4</sub>	3174	400	1200
$Cd/PC-Mg(BF_4)_2$	3163	1200	800
$Cd/PC-Ca(BF_4)_2$	3210	400	200
$Mo/DMF-Mg(PF_6)_2$	3091	1600	nil
$Mo/DMF-Ca(PF_6)_2$	3079	1200	100

DMF - Dimethylformamide PC - Propylene carbonate

ł

System	CV	Max. Anod.	Max. Cath.
Dystem		$ma/cm^2$	$\frac{1}{ma/cm^2}$
$Mo/DMF-Mg(BF_4)_2$	3325	1600	nil
$Mo/DMF-Ca(BF_4)_2$	3355	1600	nil
Mo/DMF-BF <sub>3</sub>	3263	1200	nil
$Mo/PC-Mg(PF_6)_2$	3136	800	nil
Mo/PC-Ca(PF <sub>6</sub> ) <sub>2</sub>	3154	1200	nil
$Mo/PC-Mg(BF_4)_2$	3164	1200	nil
$\ln/DMF-Mg(PF_6)_2$	3092	1600	400
$\ln/DMF-Ca(PF_6)_2$	3080	1600	800
$\ln/DMF - Mg(BF_4)_2$	3326	1200	1200
$\ln/DMF-Ca(BF_4)_2$	3356	1600	1600
In/DMF-BF <sub>3</sub>	3262	1200	800
$\ln/PC - Mg(PF_6)_2$	3142	800	480
$\ln/PC-Ca(PF_6)_2$	3155	1200	800
$\ln/PC - Mg(BF_4)_2$	3165	1200	1200
$\ln/PC-Ca(BF_4)_2$	3216	400	400
Fe/DMF-PF5	2991	800	nil
Fe/DMF-BF3	3261	1200	200
V/DMF-PF5	2984	200	200

DMF - Dimethylformamide

l

ι.

## TABLE V (Cont'd.)

i.

Ţ.

System_	CV	Max. Anod. C.D.	Max. Cath. C.D.
		ma/cm <sup>2</sup>	ma/cm <sup>2</sup>
Cr/DMF-Ca(PF <sub>6</sub> ) <sub>2</sub>	3336	800	nil
Cr/DMF-PF5	3351	800	nil
Cr/DMF-LiBF <sub>4</sub>	3289	1600	nil
$Cr/DMF-Mg(BF_4)_2$	3334	1600	nil
$Cr/DMF-Ca(BF_4)_2$	3364	1200	nil
Cr/DMF-BF <sub>3</sub>	3266	1200	2
Cr/PC-PF5	3349	800	nil
$Cr/PC-Ca(BF_4)_2$	3348	1200	nil
$Mn/DMF-Ca(PF_6)_2$	3088	1600	400
Mn/DMF-PF <sub>5</sub>	3352	800	800
$Mn/DMF-Mg(BF_4)_2$	3335	1600	1600
$Mn/DMF-Ca(BF_4)_2$	3365	1200	1200
Mn/DMF-BF3	3267	1200	400
Mn/PC-PF5	3350	800	800
$Mn/PC-Ca(BF_4)_2$	3347	1200	1200

DMF - Dimethylformamide

I.

### TABLE VI

#### SYSTEMS CAUSING CURRENT OVERLOAD \*\* OF INSTRUMENTATION

System	CV	Max. Anod. <u> </u>	Max. Cath. C. D.
		ma/cm <sup>2</sup>	ma/cm <sup>2</sup>
V/DMF-LiCl	3309	ov	nil

\*\* ov-maximum current greater than 4.8 amp/cm<sup>2</sup>

DMF - Dimethylformamide

## TABLE VII

#### PEAK CURRENT DENSITY RANGE CHLORIDE AND PERCHLORATE ELECTROLYTES

System	CV	Anodic	Cathodic
Cd/DMF-CaCl <sub>2</sub>	2963	high	high
$Cd/PC-LiClO_4 + AlCl_3$	3236	medium high	medium high
$\ln/DMF-AlCl_3 + LiCl$	3392	high	medium high
In/PC-LiClO <sub>4</sub>	3246	medium low	low
In/PC-MgCl	2971	high	high
In/PC-AlCl <sub>3</sub> + LiCl	3382	medium high	medium low
$Fe/PC-AlCl_3 + LiCl$	3371	medium low	low
Mn/DMF-LiCl	3315	low	low

DMF - Dimethylformamide

i

#### TABLE VIII

\_ \_ \_ \_ \_ \_

## PEAK CURRENT DENSITY RANGE FLUORIDE ELECTROLYTES

System	CV	Anodic	Cathodic
$Z_n/DMF-Ca(PF_6)_2$	3077	high	high
Zn/DMF-LiBF <sub>4</sub>	3272	high	medium high
$Z_n/DMF - Mg(BF_4)_2$	3323	very high	very high
$Z_n/PC-Mg(PF_6)_2$	3134	medium high	medium high
$Zn/PC-Ca(PF_6)_2$	3152	medium low	medium high
$Z_n/PC-LiBF_4$	3173	medium low	medium low
$Zn/PC-Ca(BF_4)_2$	3209	medium low	medium low
Cd/DMF-PF5	2990	very high	medium low
Cd/DMF-LiBF <sub>4</sub>	3273	very high	very high
Mo/DMF-LiPF <sub>6</sub>	3031	low	low
Mo/PC-LiPF <sub>6</sub>	3051	medium high	low
$\ln/DMF-LiBF_4$	3282	very high	medium low
In/PC-LiPF <sub>6</sub>	3056	high	medium high
$\ln/PC-LiBF_4$	3179	high	medium high
$Fe/DMF-Mg(PF_6)_2$	3041	very high	high
$Fe/DMF-Mg(PF_6)_2$	3094	medium high	high
$Fe/DMF-Ca(PF_6)_2$	3082	high	high
$Fe/DMF-Ca(BF_4)_2$	3358	very high	medium high
Fe/PC-LiPF <sub>6</sub>	3061	medium low	medium low
Fe/PC-LiBF <sub>4</sub>	3189	medium low	medium low
$Fe/PC-Mg(BF_4)_2$	3166	high	high
V/DMF-LiPF <sub>6</sub>	3046	medium low	low
$V/DMF-Mg(PF_6)_2$	3099	medium low	low

DMF - Dimethylformamide

ī.

#### TABLE VIII (Cont'd.)

<u>cv</u>

3087

3072

3303

3439

3290

System	
--------	--

 $V/DMF-Ca(PF_6)_2$ 

Mn/DMF-LiPF<sub>6</sub>

Mn/DMF-LiPF<sub>6</sub>

Mn/DMF-KPF<sub>6</sub>

 $Mn/DMF-LiBF_4$ 

Anodic

high

high

high

very high

medium low

# <u>Cathodic</u> low medium high high

medium high

high

DMF - Dimethylformamide

## TABLE IX

## SWEEP INDEX \*

System	<u>CV</u>	$\frac{\text{Anodic}}{\text{ohm}^{-1}\text{cm}^{-2}}$	$\frac{\text{Cathodic}}{\text{ohm}^{-1}\text{cm}^{-2}}$
$Zn/PC-Mg(PF_6)_2$	3134	12.0	2.9
Cd/DMF-LiBF4	3273	320.0	750.0
Fe/PC-LiPF <sub>6</sub>	3061	2.4	3. 2
Mn/DMF-LiPF	3072	-	14.1
Mn/DMF-KPF	3439	29.5	37.0

DMF - Dimethylformamide

PC - Propylene carbonate

\*  $(peak c.d.)^2 \times 100$ sweep rate x coul/cm<sup>2</sup>

#### TABLE X

# $\Delta V$ , coulombic ratio, and discharge capacity

System	CV	<u> </u>	Coul. ** <u>Ratio</u>	Disch. <u>Capac.</u> coul/cm <sup>2</sup>
$Z_n/DMF-Ca(PF_6)_2$	3077	0.3	-	-
$Z_n/DMF-LiBF_4$	3272	0.41	-	-
$Z_n/PC-Mg(PF_6)_2$	3134	1.2	1.30	. 2. 11
$Z_n/PC_Ca(BF_4)_2$	3209	0.75	-	-
Cd/DMF-CaCl	2963	-	-	0.31
Cd/DMF-LiBF <sub>4</sub>	3273	0.057	0.39	4.8
In/DMF-LiBF	3282	0.56	-	-
In/PC-MgCl	2971	-	0.25	0.73
In/PC-LiPF	3056	0.70	-	-
In/PC-LiBF	3179	0.9	-	-
Fe/PC-LiPF	3061	0.52	0.86	0.48
Fe/PC-LiBF	3189	1.4	-	-
Mn/DMF-LiPF	3072	l. 0	0.27	1.37
Mn/DMF-LiPF	3303	0.9	-	-
Mn/DMF-KPF	3439	0.7	0.37	1.16
$Mn/DMF-LiBF_{A}$	3290	0.7	-	-

\* Voltage separating anodic to cathodic peaks

\*\* Ratio of cathodic to anodic peak areas

DMF - Dimethylformamide

#### TABLE XI

#### SYSTEMS EXHIBITING ANODIC PEAK ONLY\*

	CN	Peak Current Density
System		Kange
$Zn/PC-LiClO_4 + AlCl_3$	3231	medium low
Mo/DMF-CaCl <sub>2</sub>	2968	very low
Mo/DMF-PF <sub>5</sub>	2996	low (a)
$Mo/PC-LiClO_4 + AlCl_3$	3241	medium high
In/DMF-LiPF <sub>6</sub>	3036	very high (a)
$\ln/PC-LiCl + LiClO_4$	3119	low
$Fe/DMF-LiBF_4$	3284	medium high
$Fe/DMF-Mg(BF_4)_2$	3328	very high (b)
$Fe/PC-LiClO_4 + AlCl_3$	3251	low (a)
Fe/PC-MgCl <sub>2</sub>	2976	medium low (a)
$Fe/PC-Mg(PF_6)_2$	3141	low
$Fe/PC-Ca(PF_6)_2$	3156	medium low (b)
$V/DMF-Mg(ClO_4)_2$	3444	high (a)
V/DMF-KPF <sub>6</sub>	3429	medium low
$V/DMF-Mg(BF_4)_2$	3333	very low
V/PC-LiClO <sub>4</sub>	3408	medium high
$V/PC-LiClO_4 + AlCl_3$	3256	high
V/PC-CaCl <sub>2</sub>	3202	very low

\* Maximum cathodic current density in very low range (<1 ma/cm<sup>2</sup>) unless otherwise noted.

- (a) Low range cathodic (<10 ma/cm<sup>2</sup>)
- (b) Medium low range cathodic ( $10-50 \text{ ma/cm}^2$ )

DMF - Dimethylformamide

## TABLE XI (Cont'd.)

System	CV	Peak Current Density Range
Cr/DMF-Mg(ClO <sub>4</sub> ) <sub>2</sub>	3449	high
Cr/DMF-LiPF	3308	medium low
Cr/PC-LiClO <sub>4</sub>	3413	low
$Cr/PC-AlCl_3 + LiCl$	3377	medium high (a)
Mn/DMF-LiClO <sub>4</sub>	3322	high
$Mn/DMF-AlCl_3 + LiCl$	3399	high
$Mn/PC-AlCl_3 + LiCl$	3387	medium low
$Mn/PC-Ca(PF_6)_2$	3346	low

- \* Maximum cathodic current density in very low range (<1 ma/cm<sup>2</sup>) unless otherwise noted.
- (a) Low range cathodic (<10 ma/cm<sup>2</sup>)
- (b) Medium low range cathodic ( $10-50 \text{ ma/cm}^2$ )
- DMF Dimethylformamide
- PC Propylene carbonate

#### TABLE XII

#### SYSTEMS EXHIBITING CATHODIC PEAK ONLY

System

<u>CV</u> 3221 Peak Current Density Range

medium low (a)

 $Fe/PC-Ca(BF_4)_2$ 

(a) Maximum anodic current density in medium high range
 (50-100 ma/cm<sup>2</sup>)

#### TABLE XIII

## SYSTEMS EXHIBITING NO PEAKS \*

System	CV	
$Zn/PC-LiCl + LiClO_4$	3104	(d)
Zn/PC-PF5	3001	(c)
$Cd/PC-LiCl + LiClO_4$	3109	(d)
Cd/PC-PF5	3006	(b)
Mo/DMF-LiBF <sub>4</sub>	3278	(b)
$Mo/PC-LiCl + LiClO_4$	3114	(d)
Mo/PC-PF5	3011	(c)
Mo/PC-LiBF4	3184	(b)
$Mo/PC-Ca(BF_4)_2$	3215	(c)
In/DMF-PF5	2983	(a)
In/PC-PF5	3016	(c)
$Fe/PC-LiCl + LiClO_4$	3124	
Fe/PC-CaCl <sub>2</sub>	3199	
Fe/PC-PF <sub>5</sub>	3021	(d)
V/DMF-LiBF4	3294	(d)
$V/DMF-Ca(BF_4)_2$	3359	(d)
V/DMF-BF <sub>3</sub>	3257	

\* Maximum current density in very low range (<1 ma/cm<sup>2</sup>) unless otherwise noted.

- (a) High range  $(100-300 \text{ ma/cm}^2)$
- (b) Medium high range  $(50-100 \text{ ma/cm}^2)$
- (c) Medium low range  $(10-50 \text{ ma/cm}^2)$
- (d) Low range  $(1-10 \text{ ma/cm}^2)$

DMF - Dimethylformamide

System	CV
$V/PC-LiCl + LiClO_{A}$	3129
V/PC-LiPF <sub>6</sub>	3066
V/PC-KPF	3402 (d)
$V/PC-Mg(PF_6)_2$	3147
$V/PC-Ca(PF_6)_2$	3161
V/PC-PF <sub>5</sub>	3026
V/PC-LiBF <sub>4</sub>	3194
$V/PC - Mg(BF_4)_2$	3171
$V/PC-Ca(BF_4)_2$	3226
Cr/DMF-KPF <sub>6</sub>	3434 (d)
Cr/PC-KPF	3419 (d)
$Cr/PC-Ca(PF_6)_2$	3341
$Mn/DMF-Mg(ClO_4)_2$	3454
Mn/PC-KPF <sub>6</sub>	3424 (a)

 Maximum current density in very low range ( 1 ma/cm<sup>2</sup>) unless otherwise noted.

- (a) High range  $(100-300 \text{ ma/cm}^2)$
- (b) Medium high range  $(50-100 \text{ ma/cm}^2)$
- (c) Medium low range  $(10-50 \text{ ma/cm}^2)$
- (d) Low range  $(1-10 \text{ ma/cm}^2)$

DMF - Dimethylformamide

#### II. REFERENCES

 Whittaker Corporation, Narmco Research and Development Division, Fifth Quarterly Report, NASA Contract NAS 3-8509, NASA Report CR-72293, August 1967.

i

2. Whittaker Corporation, Narmco Research and Development Division, First Quarterly Report, NASA Contract NAS 3-8509, NASA Report CR-72069, August 1966.

#### DISTRIBUTION LIST

National Aeronautics and Space Admin. Washington, D.C. 20546 E. M. Cohn/RNW Attn: A. M. Greg Andrus/PC National Aeronautics and Space Admin. Goddard Space Flight Center Greenbelt, Maryland 20771 T. Hennigan, Code 716.2 Attn: J. Sherfey, Code 735 P. Donnelly, Code 636.2 E. R. Stroup, Code 636.2 National Aeronautics and Space Admin. Langley Research Center Instrument Research Division Hampton, Virginia 23365 Attn: J. L. Patterson, MS 234 M. B. Seyffert, MS 112 National Aeronautics and Space Admin. Langley Research Center Hampton, Virginia 23365 Attn: S. T. Peterson Harry Ricker National Aeronautics and Space Admin. Lewis Research Center 2100 Brookpark Road Cleveland, Ohio 44135 Attn: Library, MS 60-3 N. D. Sanders, MS 302-1 John E. Dilley, MS 500-309 B. Lubarsky, MS 500-201 H, J. Schwartz, MS 500-201 R. B. King, MS 500-202 (2cys.) V. F. Hlavin, MS 3-14 (Final only) M. J. Saari, MS-500-202 J. J. Weber, MS 3-19 Report Control, MS 5-5 Dr. J. S. Fordyce, MS 6-1

National Aeronautics and Space Admin. Scientific and Tech. Information Facility P. O. Box 33 College Park, Maryland 20740 Attn: Acquisitions Branch (SQT-34054) (2 cys. + 1 repro.)

National Aeronautics and Space Admin. George C. Marshall Space Flight Center Huntsville, Alabama 35812 Attn: Philip Youngblood R. Boehme, Bldg. 4487.BB,

M-ASTR-EC

National Aeronautics and Space Admin.
Manned Spacecraft Center
Houston, Texas 77058
Attn: W. R. Dusenbury, Propulsion

and Energy Systems
R. Cohen, Gemini Project Office
R. Ferguson (EP-5)
J. T. Kennedy (EE-5)
F. E. Eastman (EE-4)

National Aeronautics and Space Admin.

Ames Research Center Pioneer Project Moffett Field, California 94035 Attn: J. R. Swain A. S. Hertzog J. Rubenzer, Biosatellite Project Jet Propulsion Laboratory 4800 Oak Grove Drive Pasadena, California 91103 Attn: A. Uchiyama

U. S. Army Engineer R and D Labs. Fort Belvoir, Virginia 22060 Attn: Electrical Power Branch SMOFB-EP

Commanding Officer U. S. Army Electronics R and D Labs. Fort Monmouth, New Jersey 07703 Power Sources Div., Code SELRA/PS Attn: Research Office R and D Directorate Army Weapons Command Rock Island, Illinois 61201 Attn: G. Riensmith, Chief U. S. Army Research Office Box CM, Duke Station Durham, North Carolina 27706 Attn: Dr. W. Jorgensen U. S. Army Research Office Chief, R and D Department of the Army 3 D 442, The Pentagon Washington, D. C. 20546 Harry Diamond Laboratories Room 300, Bldg, 92 Conn. Ave and Van Ness St., NW Washington, D. C. 20438 Attn: N. Kaplan Army Materiel Command Research Division AMCRD-RSCM-T-7 Washington, D. C. 20315 J. W. Crellin Attn: Army Materiel Command Development Division AMCRO-DE-MO-P Washington, D. C. 20315 Attn: M. D. Aiken U. S. Army TRECOM Fort Eustis, Virginia 23604

Attn: Dr. R. L. Echols (SMOFE-PSG) L. M. Bartone (SMOFE-ASE) U. S. Army Mobility Command Research Division Watten, Michigan 48090 Attn: O. Renius (AMSMO-RR) U. S. Army R and L Liaison Group (9851 DV) APO 757 New York, New York 10004 Attn: B. R. Stein Office of Naval Research Department of the Navy Washington, D.C. 20360 Attn: Head, Power Branch, Code 429 H. W. Fox, Code 425 Naval Research Laboratory Washington, D. C. 20390 Attn: Dr. J. C. White, Code 6160 U. S. Navy Marine Engineering Laboratory Annapolis, Maryland 21402 Attn: J. H. Harrison Bureau of Naval Weapons Department of the Navy Washington, D. C. 20360 Attn: W. T. Beatson, Code RAAE-52 M. Knight, Code RAAE-50 Naval Ammunition Depot Crane, Indiana 47522 Attn: E. Bruess H. Schultz Naval Ordnance Laboratory Department of the Navy Corona, California 91720 Attn: W. C. Spindler, Code 441 Army Reactors, DRD U. S. Atomic Energy Commission Washington, D. C. 20545 Attn: D. B. Hoatson

D-2

Naval Ordnance Laboratory Department of the Navy Silver Springs, Maryland 20900 Attn: P. B. Cole, Code WB

Bureau of Ships Department of the Navy Washington, D. C. 20360 Attn: B. B. Rosenbaum, Code 340 C. F. Viglotti, Code 660

Space Systems Division Los Angeles AF Station Los Angeles, California 90045 Attn: SSSD

Air Force Cambridge Research Lab. (CRFE)Washington, D. C. 20545L. G. Hanscom FieldAttn: Lt. Col. J. H. AnBedford, Massachusetts 01731Office of Technical Servic

Flight Vehicle Power Branch Aero Propulsion Laboratory Wright-Patterson AFB, Ohio 45433 Attn: J. E. Cooper

Headquarters, USAF (AFRDR-AS) Washington, D. C. 20546 Attn: Maj. G. Starkey Lt. Col. W. G. Alexander

Rome Air Development Center, ESD Griffis AF Base, New York 13442 Attn: F. J. Mollura (RASSM)

National Bureau of Standards Washington, D. C. 20234 Attn: Dr. W. J. Hamer

Office DDR and E, USE and BSS The Pentagon Washington, D. C. 20310 Attn: G. B. Wareham Institute for Defense Analyses R and E Support Division 400 Army-Navy Drive Arlington, Virginia 22022 Att: R. Hamilton Dr. G. C. Szego

U. S. Atomic Energy Commission Auxiliary Power Branch (SNAP) Division of Reactor Development Washington, D. C. 20545 Attn: Lt. Col. G. H. Ogburn, Jr.

U. S. Atomic Energy Commission Advanced Space Reactor Branch Division of Reactor Development Washington, D. C. 20545 Attn: Lt. Col. J. H. Anderson

Office of Technical Services Department of Commerce Washington, D. C. 20009

Aerojet-General Corporation Von Karman Center Building 312/Dept. 3111 Azusa, California 91703

Aeronutronic Division Philco Corporation Ford Road Newport Beach, California 92660

Aerospace Corporation P. O. Box 95085 Los Angeles, California 90045 Attn: Library

Burgess Battery Company Foot of Exchange Street Freeport, Illinois 61032 Attn: Dr. Howard J. Strauss Aerospace Corporation Systems Design Division 2350 East El Segundo Boulevard El Segundo, California 90246 Attn: John G. Krisilas

Allis-Chalmers Manufacturing Company 1100 South 70th Street Milwaukee, Wisconsin 53201 Attn: Dr. P. Joyner

American University Massachusetts and Nebraska Avenues NW Washington, D. C. 20016 Attn: Dr. R. T. Foley, Chemistry Dept.

Arthur D. Little, Incorporated Acorn Park Cambridge, Massachusetts 02140 Attn: Dr. Ellery W. Stone

Atomics International Division North American Aviation, Incorporated 8900 DeSoto Avenue Canoga Park, California 91304 Attn: Dr. H. L. Recht

Battelle Memorial Institute 505 King Avenue Columbus, Ohio 43201 Attn: Dr. C. L. Faust

Bell Laboratories Murray Hill, New Jersey 07971 Attn: U. B. Thomas

The Boeing Company P. O. Box 3707 Seattle, Washington 98124

Borden Chemical Company Central Research Laboratory P. O. Box 9524 Philadelphia, Pennsylvania 19124 C and D Batteries Division of Electric Autolite Company Conshohocken, Pennsylvania 19428 Attn: Dr. Eugene Willihnganz

Calvin College Grand Rapids, Michigan 49506 Attn: Prof. T. P. Dirkse

Catalyst Research Corporation 6101 Falls Road Baltimore, Maryland 21209 Attn: J. P. Wooley

ChemCell, Incorporated 3 Central Avenue East Newark, New Jersey 07029 Attn: Peter D. Richman

Delco Remy Division General Motors Corporation 2401 Columbus Avenue Anderson, Indiana 46011 Attn: Dr. J. J. Lander

Douglas Aircraft Company, Incorporated Astropower Laboratory 2121 Campus Drive Newport Beach, California 92663

Dynatech Corporation 17 Tudor Street Cambridge, Massachusetts 02138 Attn: R. L. Wentworth

Eagle-Pitcher Company P. O. Box 47 Joplin, Missouri 64802 Attn: E. M. Morse

General Electric Company Battery Products Section P. O. Box 114 Gainesville, Florida 32601 Attn: Dr. R. L. Hadley Elgin National Watch Company 107 National Street Elgin, Illinois 60120 Attn: T. Boswell

Electric Storage Battery Company Missile Battery Division 2510 Louisburg Road Raleigh, North Carolina 27604 Attn: A. Chreitzberg

Electric Storage Battery Company Carl F. Norberg Research Center Wardley, Pennsylvania 19068 Attn: Dr. R. A. Schaefer

Electrochimica Corporation 1140 O'Brien Drive Menlo Park, California 94025 Attn: Dr. Morris Eisenberg

Electro-Optical Systems, Incorporated 300 North Halstead Pasadena, California 91107 Attn: E. Findl

Emhart Manufacturing Company Box 1620 Hartford, Connecticut 06101 Attn: Dr. W. P. Cadogan

Englehard Industries, Incorporated 497 Delancy Street Newark, New Jersey 07105 Attn: Dr. J. G. Cohn

Dr. Arthur Fleischer 466 South Center Street Orange, New Jersey 07050

Grumman Aircraft CPGS Plant 35 Beth Page, Long Island, New York 11101 Attn: Bruce Clark General Electric Company Research and Development Center Schenectady, New York 12301 Attn: Dr. H. Liebhafsky Dr. R. C. Osthoff, Bldg. 37,

General Motors-Defense Research Labs. 6767 Hollister Street Santa Barbara, California 93105 Attn: Dr. J. S. Smatko Dr. C. R. Russell

General Telephone and Electronics Labs. Bayside, New York 11352 Attn: Dr. Paul Goldberg

Globe-Union, Incorporated 900 East Keefe Avenue Milwaukee, Wisconsin 53201 Attn: Dr. Warren Towle

Gould-National Batteries, Incorporated Engineering and Research Center 2630 University Avenue, SE Minneapolis, Minnesota 55418 Attn: D. L. Douglas

Gulton Industries Alkaline Battery Division 212 Durham Avenue Metuchen, New Jersey 08840 Attn: Dr. Robert Shair

Leesona Moos Laboratories Lake Success Park, Community Drive Great Neck, New York 11021 Attn: Dr. H. Oswin

Livingston Electronic Corporation Route 309 Montgomeryville, Pennsylvania 18936 Attn: William F. Meyers
Hughes Aircraft Corporation Centinela Avenue and Teale Street Culver City, California 90230 Attn: T. V. Carvey

Hughes Aircraft Corporation Building 366, MS 524 El Segundo, California 90245 Attn: R. B. Robinson

Hughes Research Labs. Corp. 2011 Malibu Canyon Road Malibu, California 90265 Attn: T. M. Hahn

ITT Federal Laboratories 500 Washington Avenue Nutley, New Jersey 07110 Attn: Dr. P. E. Lightly

IIT Research Institute
10 West 35 Street
Chicago, Illinois 60616
Attn: Dr. H. T. Francis

Idaho State University Department of Chemistry Pocatello, Idaho 83201 Attn: Dr. G. Myron Arcand

Institute of Gas Technology State and 34 Street Chicago, Illinois 60616 Attn: B. S. Baker

John Hopkins University Applied Physics Laboratory 8621 Georgia Avenue Silver Springs, Maryland 20910

Lockheed Missiles and Space Co., 3251 Hanover Street Palo Alto, California 94304 Attn: Library Dr. G. B. Adams Lockheed Missiles and Space Co. Department 52-30 Palo Alto, California 94304 Attn: J. E. Chilton

Lockheed Missiles and Space Co. Department 65-82 Palo Alto, California 94304 Attn: Larry E. Nelson

Magna Corporation Division of TRW, Inc. 101 South East Avenue Anaheim, California Attn: Dr. G. Rohrback

P. R. Mallory and Co., Inc. Technical Services Laboratory Indianapolis, Indiana 46206 Attn: A. S. Doty

P. R. Mallory and Co., Inc. 3029 East Washington Street Indianapolis, Indiana 46206 Attn: Library

Marquardt Corporation 16555 Saticoy Street Van Nuys, California 91406 Attn: Dr. H. G. Krull

Philco Corporation Division of Ford Motor Company Blue Bell, Pennsylvania 19422 Attn: Dr. Phillip Cholet

Radiation Applications, Inc., 36-40 37th Street Long Island City, New York 11101

Material Research Corporation Orangeburg, New York 10962 Attn: V. E. Adler

Melpar Technical Information Center 3000 Arlington Boulevard Falls Church, Virginia 22046 Metals and Control Division Texas Instruments, Inc. 34 Forest Street Attleboro, Massachusetts 02703 Attn: Dr. E. M. Jost

Midwest Research Institute 425 Volker Boulevard Kansas City, Missouri 64110 Attn: Dr. B. W. Beadle

Monsanto Research Corporation Everett, Massachusetts 02149 Attn: Dr. J. O. Smith

North American Aviation, Inc. Rocketdyne Division 6633 Canoga Avenue Canoga Park, California 91303 Attn: Library

North American Aviation, Inc. 2214 Lakewood Boulevard Downey, California 90241 Attn: Burden M. Otzinger

Ozark Mahoning Company 1870 S. Boulder Avenue Tulso, Oklahoma 74119 Attn: Dr. James Beal

Power Information Center University of Pennsylvania 3401 Market Street, Room 2107 Philadelphia, Pennsylvania 19104

Tyco Laboratories, Inc. Bear Hill Hickory Drive Waltham, Massachusetts 02154 Attn: W. W. Burnett

Radio Corporation of America Astro Division Highstown, New Jersey 08520 Attn: Seymour Winkler Radio Corporation of America P. O. Box 800 Princeton, New Jersey 08540 Attn: L. Schulman

Sandia Corporation Box 5800 Albuquerque, New Mexico 87115 Attn: Technical Library (2 copies)

Sonotone Corporation Saw Mill River Road Elmsford, New York 10523 Attn: A. Mundel

Texas Instruments, Inc. 13500 North Central Expressway Dallas, Texas 75222 Attn: Dr. Isaac Trachtenberg

Thomas A. Edison Research Lab. McGraw Edison Company Watchung Avenue West Orange, New Jersey 07052 Attn: Dr. P. F. Grieger

TRW Incorporated TRW Systems Group One Space Park Redondo Beach, California 90278 Attn: Dr. A. Krausz, Bldg. 60, Rm 1470

TRW Incorporated 23555 Euclid Aven ue Cleveland, Ohio 44117 Attn: Librarian

Union Carbide Corporation Development Laboratory Library P. O. Box 6056 Cleveland, Ohio 44101

Union Carbide Corporation Parma Research Center P. O. Box 6116 Cleveland, Ohio 44101 Attn: Library University of California Space Science Laboratory Berkeley, California 94720 Attn: Dr. C. W. Tobias

i

University of Pennsylvania Electrochemistry Laboratory Philadelphia, Pennsylvania 19104 Attn: Prof. J. O'M Brockris

University of Toledo Toledo, Ohio 43606 Attn: Dr. Albertine Krohn

Western Electric Company Suite 802, RCA Building Washington, D.C. 20006 Attn: R. T. Fiske

Westinghouse Electric Corporation Research and Development Center Churchill Borough Pittsburgh, Pennsylvania 15235 Attn: Dr. A. Langer Whittaker Corporation Power Sources Division 3850 Olive Street Denver, Colorado 80237 Attn: J. W. Reiter

Whittaker Corporation Narmco R and D Division 12032 Vose Street North Hollywood, California 91605 Attn: Dr. M. Shaw

Yardney Electric Corporation 40-50 Leonard Street New York, New York 10013 Attn: Dr. George Dalin